Behavior of Fe Powder During High-Energy Ball Milling Cooperated with Dielectric Barrier Discharge Plasma

Leyang DAI[†]

Marine Engineering Institute, Jimei University, Xiamen 361021, China

[Manuscript received 22 May 2012, in revised form 30 September 2012]

© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg

In this study, nanostructured Fe powders were synthesized following 10 hours of high-energy ball milling with a superimposed dielectric barrier discharge plasma (DBDP). The mean size of the milled powder was approximately 100 nm with an average grain size of 16.2 nm. The influence of DBDP on the underlying grain refinement mechanisms during ball milling was investigated by scanning electron microscopy (SEM), transmission electron microscopy (TEM), X-ray diffraction (XRD) and BET methods. Our results show that the Fe particles displayed an extraordinary plasticity during the early milling stages under the action of DBDP, and that the plastic deformation experienced by the Fe particles during this stage was more severe than that present in normal milling. A high concentration of spherical Fe particles, approximately 50–100 nm in diameter, was documented via TEM. We propose that these spherical particles were generated via high temperature disintegration as a result of DBDP electron bombardment during ball milling. Our results suggest that it may be possible to significantly refine metallic powders during milling *via* the superimposition of DBDP.

KEY WORDS: Dielectric barrier discharge plasma (DBDP); High-energy ball milling; Nano-Fe powder; Plastic deformation; Elevated temperature disintegration

1. Introduction

High-energy ball milling has been widely used for the synthesis of nanometric (*e.g.*, size < 100 nm) powder; however, the milling times required for the powder to attain a steady-state particle size ($D_{\min}$) are generally long^[1]. Moreover, high-energy ball milling of the metallic systems can result in severe cold welding, which limits the extent of refinement achieved. Inspection of the published literature shows that it is possible to increase efficiency during high-energy mechanical milling via the superimposition of external fields, such as ultrasonic, electric and plasma environments^[2–4].

Dielectric barrier discharge (DBD) represents a type of non-localized, thermodynamic equilibrium plasma that is discharged under atmospheric pressure. As an excellent source of ideal energetic electrons with 10–30 eV and high density, DBD is used to generate

excited atomic and molecular species, free radicals and excimers which have significant plasma heating and impulse impact effects^[5,6].

In our previous study^[7], pure Al, Fe and W powders were prepared by high-energy ball milling cooperated with superimposed dielectric barrier discharge plasma (DBDP). Our results showed that nano-Fe powders with a mean size of 100 nm were obtained after only 10 h DBDP-assisted milling, whereas 128 nm nano-Al and 100 nm nano-W powders were obtained after 15 h and 3 h, respectively, using this approach. These results suggest that the presence of a DBDP field accelerates the kinetics of particle refinement, although the precise mechanisms responsible for this phenomena are not presently understood. Accordingly, the present study was undertaken in an effort to provide insight into the mechanisms that govern the morphology and size evolution during DBDP-assisted milling of Fe powder.

2. Experimental

A detailed description of the installation drawing for the DBDP-assisted ball milling was given in our

[†] Corresponding author. Assoc. Prof., Ph.D.; Tel: +86 592 6182805; Fax: +86 592 6183318; E-mail address: dai-leyang@jmu.edu.cn (Leyang DAI)

previous work^[7]. Fe powders with a purity of 98% and an average particle size of 10 μm were milled in conventional mode (referred to as C-milling hereafter) and DBDP-assisted mode (referred to as P-milling hereafter) for times of up to 30 h in a stainless steel cylinder under protection of high-purity argon atmosphere (0.1 MPa). The stainless balls were vibrated within the cylinder at a double amplitude of 10 mm and a frequency of 25 Hz. The ball to powder weight ratio was 50:1. The power supply used in the P-milling generates 24 kV of high-voltage alternating current of high frequency of 14 kHz. An amount of 15 mL ethanol and 3% carrageenan (straight-chain polysaccharide sulfat which was combined of 1, 3- β -D-pyran galactose and 1, 4- β -D-pyran galactose) were added as process control agent into the Fe powders prior to milling.

The milling process was interrupted after different milling times in order to remove a small amount of as-milled powders for analysis. The as-milled powders were characterized using a scanning electron microscopy (SEM, LEO 1530VP), a transmission electron microscope (TEM, JEOL 2010), a X-ray diffraction (XRD, Philips X'Pert MPD) and a BET analysis (BET, ASAP 2010 Micromeritics).

3. Results

The morphologies of Fe powders before and after milling were observed by SEM. The results show that the as-received Fe powder exhibited an irregular morphology, with an approximate average particle size of 10 μm (Fig. 1). For comparison, Fig. 2 shows the SEM micrographs of Fe powders milled for 1, 3, 5, 10 and 30 h by C-milling and P-milling respectively. These results show that the Fe powders are deformed from an equiaxed into a plate morphology after 1 h of milling, and that the P-milled material attains a thickness of 100 nm which is significantly smaller than that attained during C-milling for the same process parameters (compare Fig. 2(a) and (b)) (the magnification in Fig. 2(a) and (b) is not high enough for the reader to agree with this statement). Following 3 and 5 h of C-milling, as shown in Fig. 2(c) and (e), the plates are cold welded to each other to form heterogeneous morphologies. An increase in particle

Fig. 1 Morphology of the as-received Fe powders

size is also observed at this stage in the C-milled material where the particle sizes are 20–50 μm . The morphology of the P-milled powders clearly differs from that of the C-milled powders. For example, following 3 h of P-milling, the plate morphology is still evident, although the plate sizes have increased in diameter and thickness. (see Fig. 2(d)). The material P-milled to 5 h retains the thick plate morphology, although the corresponding size is approximately 10 μm (see Fig. 2(f)).

With further increases in milling time, the layered powder particles are increasingly work hardened, until brittle fracture yields more equiaxed particles, consistent with mechanism described in the literature^[8]. As shown in Fig. 2(g), after 10 h of C-milling, the Fe powders are refined to an average size of about 6 μm with a spherical morphology and a high extent of agglomeration. In the case of the P-milled material, however, different behavior is observed. After 10 h of P-milling, very fine primitive particles are evident, with interdispersed larger agglomerates, and a broad size range, generally smaller than about 10 μm (see Fig. 2(h)). It is shown in the insert in Fig. 2(h), that these primitive particles in the agglomerates are nearly equiaxed and approximately 100 nm in size. Increasing the milling time up to 30 h fails to generate significant changes in the morphology of Fe powders for both C-milled and P-milled materials (see Fig. 2(i) and (j)). Moreover, the inserts in Fig. 2(i) and (j), show that the primary particle size is maintained around 100 nm during P-milling whereas the particle size continues to decrease to 3 μm during C-milling. This result suggests that the Fe powders reached a steady-state particle size (D_{min}) of approximately 100 nm after only 10 h P-milling, as compared, for example to published results which suggest that 60 h are needed for Fe powders to reach a D_{min} of 1 μm by C-milling^[9].

The specific surface areas SSA of the C-milled and P-milled Fe powders were measured by BET method, and the average particle sizes of different samples were calculated by the following formula^[10]:

$$d_{\text{BET}} = \frac{6}{\rho \cdot s_w} \quad (1)$$

where d_{BET} is the average particle size, ρ is the density of iron (7.86 g/cm³) and s_w is the SSA value. Consistent with the SEM observations, the s_w corresponding to the P-milled powders are significantly smaller than those of the C-milled powders, and the d_{BET} corresponding to the P-milled powders are significantly smaller than those of the C-milled powders, as summarized in Table 1. The data in table 1 indicate that d_{BET} of P-milling after 60 h is larger than of after 30 h. The main reason might be attributed to the more pronounced heating effect of DBDP for fine Fe particles of ~ 100 nm size after 60 h P-milling. Welding of tiny particles can occur, which would result in the decreasing of SSA while a larger d_{BET} .

To provide fundamental insight into the mech-

Fig. 2 Morphologies of Fe powders milled by C-milling for 1 h (a), 3 h (c), 5 h (e), 10 h (g) and 30 h (i), and by P-milling for 1 h (b), 3 h (d), 5 h (f), 10 h (h) and 30 h (j) (The inserts in the Fig. 2(g)–(j) are the enlarged images of the places indicated by arrows)

anisms that govern particle refinement, Fe powders P-milled for 10 h were studied by TEM. TEM micrographs show that there is a high concentration of particles with a spherical (approximately 50 nm) and dumbbell (approximately 100 nm) morphologies and very smooth surfaces. These two characteristics (*e.g.*, spheroidal morphology and smooth surface) provide strong support to the suggestion that they were formed via some type of liquid droplet breakup mechanism (see Fig. 3(a) and (b)). Electron diffraction was used to index the particles as the bcc structure of the Fe phase, as shown in the insert in Fig. 3(c). Moreover, the diffraction pattern of the Fe powder and the corresponding dark field image confirm the presence of a polycrystalline phase with an average grain size of 15 nm (see Fig. 3(c) and (d)).

The XRD patterns for the as-received and milled Fe powders are shown in Fig. 4. Following 10 h of milling the Fe peaks become broader, and no significant changes in lattice parameter are observed,

Table 1 BET surface area and average particle size of Fe powders after C-milled and P-milled for different times

Milling time /h	C-milled		P-milled	
	$s_w /(\text{m}^2/\text{g})$	d_{BET}/nm	$s_w /(\text{m}^2/\text{g})$	d_{BET}/nm
10 h	—	—	12.3623	61.7
30 h	1.0545	723.9	14.7005	51.9
60 h	1.3683	557.9	13.0576	58.5

regardless of the type of milling environment used. The broadening of the XRD peaks is attributed to the refinement of crystallite size and the concomitant increase of heterogeneous strain in the powders/phases during milling^[11,12]. As estimated on the basis of diffraction peak broadening by the Voigt method^[13,14], the mean grain size of the C-milled Fe powder is 68.4 nm, however, that corresponding to the P-milled powder is 16.2 nm, consistent with the TEM results discussed earlier.

4. Discussion

The investigations described in the present work reveal two critical findings. First, in the case of bcc Fe, the time required to attain a final steady-state particle size (D_{min}) is significantly decreased for the P-milling experiments relative to results obtained with C-milling. Second, the evolution of microstructures during milling of bcc Fe is influenced by the presence of a superimposed DBD plasma.

The first stage during high-energy milling is well documented^[8] and involves powder mixing, concurrent deformation, fracture and welding of prior powder particles. Welding and deformation lead to the formation of large particles with a flake morphology, as shown in Fig. 2(a) and (b). Following this initial stage, welding dominates deformation, leading to an increase in particle size and an accompanying decrease in the number of particles, as documented for the C-milled material studied herein (see Fig. 2(c))

Fig. 3 Bright field (a–c) and dark field (d) TEM images of Fe powders after P-milled for 10 h (The insert in Fig. 3(c) shows the selected area diffraction patterns of Fe phase)

Fig. 4 XRD patterns of Fe powders un-milled (a) and milled for 10 h under C-milled mode (b) and P-milled mode (c)

and (f)). However, in the case of the P-milled material, a different behavior is observed. After 10 h of P-milling, very fine primitive particles are evident, with interdispersed larger agglomerates, and a broad size range, generally smaller than about 10 μm (see Fig. 2(h)). This behavior is attributed to the influence of the DBDP field. During P-milling, when the milling atmosphere is 0.1 MPa argon and the supplied tension is higher than 22 kV ($f \geq 13$ kHz, where f is frequency), a stable glow discharge state^[15] will be maintained in the milling chamber. This will cause the Fe powders to be irradiated by the DBDP, while simultaneously being deformed by the milling media. Because Fe powder, milling balls and milling vial are conductors, the P-milling equipment is a single dielectric layer reactor in which high density electric pulses flow through the powders with high frequency. Theoretically, electroplasticity would be induced by the combined physical effects stimulation of high density electric pulses, which basically including the Joule heating and an active electron push on moving dislocations during plastic flow^[16–19]. For examples, Refs.[16–18], thermal activated plastic flow of metals and ceramics with an electric field or current were observed, and the electric field ($E=2.5$ kV/cm) produced a 20%–25% decrease in the flow stress of the electrodeposited Cu, the yield, flow and fracture stresses and the strain hardening coefficient of polycrystalline NaCl decreased approximately 50% with electric field ($E=1.0$ kV/cm). The researchers suggested that the influence of an electron pulse (electron wind) on the metals thermally-activated motion of dislocations was determined, and the substantial effect of an applied electric field on the oxides flow stress was its influence on the electrochemical potential of vacancies in the space-charge cloud adjacent to the grain boundaries. So the plasma field in our milling chamber will effectively increase the temperature and plastic flow of the Fe particles resulting in an electroplasticity phenomena as the material is exposed to a high density of electric field pulses^[17,19]. Thus, during the P-milling, Fe powders were smashed to thin slabs by milling balls, and this process was accelerated and enhanced in DBDP.

In addition, during the P-milling, when the electron flow and ion beam pulse impact on the surface of Fe powders with very high speed and energy, it will cause a quasistatic thermal stress and a dynamic thermal stress^[20]. Most of the energy carried by those electron flow and ion beam pulse would transfer to Fe particles in the form of heat and resulted in very rapid temperature rising of Fe powder and even causes the melting of Fe particles or even vaporizing. Actually, it was confirmed that the Fe particles had partially melted by DBDP treating alone, *i.e.*, by DBDP milling without balls in the vial, because large Fe particles around 30 μm with smooth surface were observed after 20 min of DBDP treating, which were much bigger than the as-received Fe powder as shown in Fig. 5. As the heat and stress field applied on the powders divert quickly with high frequency, an instantaneous local hot explosion occurs to release the thermal stress and expansion. The bombardment results in Fe liquids splash out and solidify to tiny balls with smooth surface or form distorted dumbbell-shaped particles when the liquid drops encountered, which is shown in Fig. 3(a) and Fig. 3(b). Certainly, these tiny particles accounted for a significant proportion of the nano-powder obtained finally. Of course, the instantaneous melting and solidifying contributed to the fine crystalline grain. In fact, local nanostructures could be produced by current electropulsing too. In Zhang *et al.*^[21,22] researches, nanostructures formed in several conventional materials under high current density electropulsing, such as nanophases of α -Cu (Zn) and β' -(CuZn) in a cold-worked α -Cu (Zn) alloy, nanosized γ -Fe in a low-carbon steel. The mechanisms responsible for the above nanostructured transitions were attributed to the competition of many factors induced by electropulsing, including high-rate heating, thermal stress, reduced thermodynamics barrier and large electron impacting^[23,24].

Commonly, the subsequent stage in ball milling is those of exquiated particle formation and welding of layered particles producing random particle orientations, a steady-state processing constitutes the final milling stage. For P-milling, it just spent 10 h to reach a reasonable balance between the frequencies of particle fracturing and welding, and the steady-state particle size (D_{min}) is around 100 nm (Fig. 2(h))

Fig. 5 Morphology of Fe powders after DBDP treating for 20 min

with the average grain size about 16.2 nm. In comparison, the C-milling time reported by the other authors to reach this grain size was 40 h^[14], 25 h^[25] and 24 h^[26], respectively, while the steady-state particle sizes ($D_{\min}$) of Fe powder milled were not reported definitely. The Fe powder prepared by P-milling has a lump-like morphology. In fact, the lump-like powders are agglomerate of fine primitive particles, and this unique morphological feature of powder makes it very high specific surface area, as shown in Table 1.

5. Conclusions

Since the extensive deformation is advantageous to the refining process, it takes P-milling at 14 kHz (24 kV) only 10 h to prepare nano-Fe powders with a mean particle size of about 100 nm and average grain size of about 16.2 nm. Fe particle/grain size decreased in C-milling and P-milling as milling time increased, however, faster reduction and finer particle/grain size was observed in P-milling due to the combination of DBDP energy with mechanical energy. As a result of the DBDP heating effect and electroplasticity effect, Fe particles displayed an extraordinary plasticity in the early P-milling stages and the plastic deformation of Fe particles was much more severe than that in C-milling. The Fe powders prepared by P-milling are agglomerate of fine primitive particles which have very high specific surface area. Numerous ball-shaped or distorted dumbbell-shaped tiny particles obtained by DBDP hot explosion accounted for a significant proportion of the ultimate nano-powder.

Acknowledgements

The author is grateful to Prof. Min Zhu of South China University of Technology. This work was supported by the National Natural Science Foundation of China (No. 51177008), Natural Science Foundation of Fujian Province (No. 2012J01228), the Program for New Century Excellent Talents in Fujian Province University (No. NCETFJ-Z80136) and Fujian Provincial Department of Science & Technology (Nos. 2011J01324 and JK2010030).

REFERENCES

- [1] C. Suryanarayana, Prog. Mater. Sci. **46** (1–2) (2011) 1.
- [2] D. Chen and H.Y. Liu, Mater. Lett. **72** (2012) 95.
- [3] A. Calka and D. Wexler, Nature **419** (2002) 147.
- [4] M. Zhu, X.Y. Bao, X.P. Yang, N.S. Gu, H. Wang, M.Q. Zeng and L.Y. Dai, Metall. Mater. Trans. A **42** (2011) 2930.
- [5] U. Kogelschatz, Plasma Chem. Plasma Process. **23** (1) (2003) 41.
- [6] U. Giichiro, U. Satoshi, K. Hiroshi and S. Tsutae, J. Appl. Phys. **107** (2010) 023305.
- [7] M. Zhu, L.Y. Dai, N.S. Gu, B. Cao and L.Z. Ouyang, J. Alloys Compd. **478** (2009) 624.
- [8] J.S. Benjamin, Sci. Am. **234** (5) (1976) 40.
- [9] L.Y. Dai, B. Cao and M. Zhu, Acta Metall. Sin. (Engl. Lett.) **19** (2006) 411.
- [10] J. Chaudhuri, M.L. Ram and B.K. Sarkar, J. Mater. Sci. **29** (1994) 3484.
- [11] H.J. Fecht, Nanostruct. Mater. **6** (1995) 33.
- [12] M.H. Enayati, G.R. Aryanpour and A. Ebnonnasir, Int. J. Refract. Met. Hard Mater. **27** (1) (2009) 159.
- [13] T.H. Dekeijser, J.I. Langford, E.J. Mittemeijer and A.B.P. Vogels, J. Appl. Crystallogr. **15** (3) (1982) 308.
- [14] Y.H. Zhao, H.W. Sheng and K. Lu, Acta. Mater. **49** (2) (2001) 365.
- [15] S. Kanazawa, M. Kogoma, T. Moriwaki and S. Okazaki, J. Phys. D **21** (1988) 838.
- [16] D. Yang and H. Conrad, Scr. Mater. **37** (1997) 767.
- [17] H. Conrad and D. Yang, Acta Mater. **50** (2002) 2851.
- [18] H. Conrad, D. Yang and P. Becher, Mater. Sci. Eng. A **477** (2008) 358.
- [19] J.X. Zou, K.M. Zhang, T. Grosdidier, C. Dong, Y. Qin, S.Z. Hao and D.Z. Yang, Mater. Sci. Eng. A **483–484** (2008) 302.
- [20] Y. Qin, J.X. Zou, C. Dong, X.G. Wang, A.M. Wu, S.Z. Hao and Q.F. Guan, Nucl. Instrum. Meth. Phys. Res. B **225** (2004) 544.
- [21] W. Zhang, M.L. Sui, X.N. Guo, G.H. He, K.Y. Hu, B.L. Zhou and D.X. Li, Chin. J. Mater. Res. **14** (2000) 239 (in Chinese).
- [22] W. Zhang, Y.Z. Zhou, M.L. Sui, G.H. He, J.D. Guo and D.X. Li, J. Mater. Sci. Lett. **21** (2002) 1923.
- [23] W. Zhang, M.L. Sui, Y.Z. Zhou, G.H. He, J.D. Guo and D.X. Li, Acta Metall. Sin. **39** (2003) 1009 (in Chinese).
- [24] G.L. Hu, G.Y. Tang, Y.H. Zhu and C.H. Shek, Metall. Mater. Trans. A **42** (2011) 3484.
- [25] C.H. Moelle and H.J. Fecht, Nanostruct. Mater. **6** (1995) 421.
- [26] T.R. Malow and C.C. Koch, Acta Mater. **45** (1997) 2177.