Effect of Ablation Casting on Microstructure and Casting Properties of A356 Aluminium Casting Alloy

V. Bohlooli^{1)†}, M. Shabani Mahalli¹⁾ and S. M. A. Boutorabi²⁾

1) Casting Research Center, School of Metallurgy and Materials Engineering, Iran University of Science and Technology (IUST), Narmak, Tehran, P.O. Box: 16846, Iran

2) Center of Excellence for High Strength Alloys Technology (CEHSAT), School of Metallurgy and Materials Engineering, Iran University of Science and Technology (IUST), Narmak, Tehran, P.O. Box: 16846, Iran

[Manuscript received 25 May 2012, in revised form 15 October 2012]

© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg

Recently the Ablation Casting Technology was invented as a new casting process to improve foundry products quality. In this study, the effects of processing variables on the porosity content, microstructure and feedability of A356 casting alloy were investigated. Secondary dendrite arm spacing (SDAS) and eutectic silicon morphologies were studied to evaluate the influence of Ablation Casting on the microstructure. Casting density was measured in order to identify porosity content and feedability of ablated and non-ablated specimens. In addition, solidification behavior of the samples was investigated by using thermal analysis technique. The cooling curves and the first derivative curves were plotted and compared with each other. Results showed the ablation process could increase solidification rate significantly. In addition, the microstructural evidences revealed that Ablation Casting process results in more fine and homogeneous structure compared to the non-ablated casting. The feedability improved, SDAS reduced to 35% and porosity content decreased to 3.84 vol.% by implementing this process. It concluded the Ablation Casting is an effective process to gain higher quality in aluminum foundry.

KEY WORDS: Ablation Casting; A356 aluminium alloy; Microstructure; Porosity; Cooling curve

1. Introduction

A356 is one of the most important aluminium casting alloys, because of good castability and high strength to density ratio and has caused many researchers to study properties of this alloy. Porosity content and microstructure control mechanical properties of A356 aluminium casting alloy were investigated widely^[1–12].

Cooling rate and solidification behavior of A356 aluminium castings were studied by many researchers in order to obtain desired properties. Application of high solidification rates^[1–3] and ultra high solidification rate^[4,5] show that increment of the cooling rate improves mechanical strength of the alloy. In addition, the high solidification rate causes more homogenous and finer microstructures. Thermal analysis technique is an exact and feasible method to

investigate the solidification behavior of the metals. Lee *et al.*^[6] used this method to study the solidification of A356 aluminium casting alloy.

Porosities are considered to be an important imperfection in aluminium alloy casting. Many researches were focused on how to reduce porosity content^[7,8], mechanism of porosity formation^[9,13] and the effect of porosity on the mechanical properties of aluminium alloys^[10,11,14]. It was shown that the increment of the solidification rate decreases the porosity content and improves casting product properties.

Campbell *et al.*^[12] invented Ablation Casting Technology with a low cost, and it is an effective process to gain higher quality of castings. By using the Ablation Casting, the solidification rate was increased, primary dendrite arm spacing (PDAS) and secondary dendrite arm spacing (SDAS) were decreased, more homogenous microstructure was obtained and therefore casting properties were improved. In the process, melt was poured in a sand mold, the solidifying shell started to growth from wall to the center of the mold. An air gap will be created between the mold and the solid shell by solidification

† Corresponding author. Tel: +98 21 77240540; Fax: +98 21 77240480; E-mail address: vhd.bhl@gmail.com (V. Bohlooli)

contraction. This extremely will reduce the cooling rate that generally would accompany undesired effects on the properties of the aluminum castings. In Ablation Casting process, when the solid shell with sufficient thickness was obtained (this solid shell contains liquid pool in the inner regions), process would started and the sand will be eliminated by water spray system that placed in near position to the far end of the sand mold. The water will remove the air gap and will impinge the solid shell directly. This will increase the solidification rate and mechanical properties of the casting.

In this study, the effect of Ablation Casting process on solidification behavior, feedability, porosity content, microstructure and SDAS of A356 aluminium casting alloy were investigated. Thermal analysis results showed the process increased solidification rate significantly. The Ablation Casting improved feedability, reduced porosity content and decreased SDAS. In addition, the ablated specimens had finer and more homogenous microstructure as compared with non-ablated ones.

2. Experimental Procedure

The experiment was setup by four silica-sand molds without flask. In order to investigate the effect of process on an L-shape aluminium casting properties, the procedure was designed by two molds which were ablated and two other not. The L-shape part and dimensions are shown in Fig. 1. In order to facilitate identification, the ablated molds were named as AF-Mold (with feeder) and A-Mold (without feeder), and the non-ablated ones were named as SF-Mold and S-Mold (with and without feeder respectively). The arrangement of the mold components is illustrated in Fig. 2. For AF-Mold and SF-Mold the riser was a cylinder with 80 mm diameter and 120 mm height which was joined to the L-shape part in the region between positions 2 and 3.

As molding materials 2.0 wt.% bentonite and 15.0 wt.% clay were added to silica-sand. Neither coating material nor chill was used in the silica-sand molds. The melt was prepared in air and at 750 °C. No degasser, nucleant or melt coveral material was used. In order to make same level of gas solubility in the melt, all of the castings were poured in 710 °C.

Three pairs of K-type thermocouple were placed in each mold at the positions 1, 2 and 3 as illustrated in Fig. 1 and Fig. 2. The 30 mm edge cubic specimens were provided from upper regions of these positions for measuring porosity content and microstructural investigations. In order to facilitate identification, specimens were named with referring to the mold and the sampling position as represented in Table 1.

The Ablation Casting process was established by using of a water spray system. The water spray system was placed in near region to the position 1 of ablated molds, as shown in Fig. 2 schematically. When the thermocouple placed in the position 1 of A-Mold

Fig. 1 The L-Shape casting part (a) and the schematic of the L-Shape part (b) (labelled points represent the thermocouple positions 1, 2 and 3).

Fig. 2 Schematic of the mold with feeder, the water spray system was used for Ablation Casting process.

Table 1 Name of the specimens with referring to the mold and the sampling position

	Position 1	Position 2	Position 3
A-Mold	A1	A2	A3
AF-Mold	AF1	AF2	AF3
S-Mold	S1	S2	S3
SF-Mold	SF1	SF2	SF3

and AF-Mold showed temperature of 580 °C, the Ablation Casting process was started. The water spray system turned on and water started to remove sand and air gap in the mold. The water impinged to the solid shell (surface of the L-shape part) directly and increased solidification rate. The spray system supplied water flow rate of 20 L/min, approximately.

Solidification behavior of each position was studied by the use of data received from thermocouples. Cooling curves and first derivative curves were plotted, solidification time for each specimen was calculated by thermal analysis technique. The solidification range was considered from start of nucleation until end of growth.

Casting densities of the samples were measured by Archimedes' law. Mass of the specimens in air and specimens immersing in the water were measured. Afterward, the casting density (ρ_{casting}) of each case was calculated by Eq. (1).

$$\rho_{\text{casting}} = m_a / (m_a - m_w) \quad (1)$$

where m_a and m_w are the masses measured in air and water, respectively. Then the porosity (P , vol.%) of each specimen was calculated by Eq. (2).

$$P = 100\% \times (\rho_{\text{alloy}} - \rho_{\text{casting}}) / \rho_{\text{alloy}} \quad (2)$$

where ρ_{alloy} and ρ_{casting} are the theoretical density of A356 alloy and the density of casting specimen, respectively.

Microstructure was investigated by optical microscopy (OM). Morphology and homogeneity of eutectic silicon in matrix (Al- α) was studied. SDAS was measured by Clemex image analyzer software. SDAS was obtained from averaging five measurements at least.

3. Results and Discussion

3.1 Cooling curve

The cooling curves for the cases of A1, A2, A3, S1, S2 and S3 have been drawn in Fig. 3. Also Fig. 4 shows cooling curves for the cases of AF1, AF2, AF3, SF1, SF2 and SF3. It is obvious that there is significant difference between the cooling curves of the ablated and non-ablated specimens. Comparison of Fig. 3 and Fig. 4 shows that all positions in A-Mold have similar negative slope in their cooling ranges, while in the case of AF1, curve has more negative slope than cases AF2 and AF3 in this range. This difference can relate to feeder existence in the AF-Mold that affected cooling rate of its vicinity (positions 2 and 3). All specimens in non-ablated mold (S1–3 and SF1–3) have near equilibrium cooling condition.

3.2 Solidification time

By the use of data received from thermocouples, the solidification time (t_s) for each specimen was calculated by thermal analysis technique as illustrated in Fig. 5 for case SF1 and in Fig. 6 for case AF1. Variation of first derivative curve investigated in each stage to compute solidification time. Nucleation and eutectic transformation both are exothermal transformations and shift first derivative curve to the positive

Fig. 3 Cooling curves of the specimens in A-Mold and S-Mold

Fig. 4 Cooling curves of the specimens in AF-Mold and SF-Mold

Fig. 5 Cooling curve and first derivative curve for the case of SF1

Fig. 6 Cooling curve and first derivative curve for the case of AF1

values. The solidification time was considered to be from nucleation of the primary phases to end of

growth. In Fig. 5, the specimen SF1 had near equilibrium solidification condition. Therefore it had typical cooling curve and first derivative curve. According to this figure, nucleation of the primary phases (α -Al) started in 16 s at 612 °C where the first derivative curve shifted to positive values instantly. The solidification continue with growing primary phases, till 101 s while the temperature was 575 °C and eutectic transformation arose. In this temperature a large volume of melt solidified instantly and the first derivative curve increased again. Diffusive transformation continued until the first derivative curve passed a minimum in negative values (312 s at 554 °C) and melt solidified completely. After this stage, the first derivative shifted to zero slowly while solid alloy cooled at equilibrium. In Fig. 6, for the case of AF1, likely, nucleation started in 21 s at 617 °C where the values of first derivative curve increased suddenly. The difference between the temperatures of nucleation can relate to use of non-calibrated thermocouples. But this did not affect the results because the variation of first derivative curve indicated the solidification range. While temperature decreased to 580 °C, primary phases were growing and first derivative were oscillating slightly. In this temperature it was assumed the solid shell had sufficient thickness and process was started. The water spray system turned on and removed sand. The water contacted solid shell and increased solidification rate. In this stage the first derivative curve tended to negative values, but in 197 s the eutectic transformation started, this was an exothermal transformation which made resistance to rapid cooling. In this condition, negative slope of the first derivative curve reduced as shown in Fig. 6. This resistance was stronger at the beginning of eutectic transformation and would be weaker with time so the negative slope of first derivative curve increased again. This phenomenon arised because large volume of the melt solidified at the start of eutectic transformation. The solidification ended in 207 s at 552 °C when there was no exothermal transformation so the first derivative curve could shift to more negative values. After this point, the solid cooled at an unsteady condition while the sand removed more and more by water. There are some oscillations at the first derivative curve in this stage which can relate to this unsteady cooling condition. More sand removed by water then more surface contacted water, therefore cooling rate increased and the first derivative curve shifted to minimum. After the minimum the thermal gradient between solid and water decreased so the cooling rate decreased and the first derivative curve returned to smaller values persistently. The solidification times for all samples were calculated by this method and the results are gathered in Table 2.

In Fig.7, solidification times of all specimens were compared. The comparison shows there is significant difference between solidification time of each ablated and non-ablated position. According to these results in the non-Ablated specimens, position 1 has

Table 2 Solidification time (t_s), casting density (ρ_{casting}), porosity (P) and SDAS of the specimens

Specimen	t_s /s	ρ_{casting} /(g·cm ⁻³)	P /vol.%	SDAS / μ m
S1	441	2.57	4.01	52
S2	670	2.55	4.71	60
S3	668	2.55	4.71	60
A1	180	2.65	1.22	39
A2	191	2.64	1.57	39
A3	197	2.62	2.27	42
SF1	296	2.58	3.66	50
SF2	603	2.56	4.36	55
SF3	588	2.56	4.36	55
AF1	186	2.66	0.87	39
AF2	206	2.65	1.22	44
AF3	258	2.62	2.27	44

Fig. 7 Solidification times for ablated and non-ablated specimens

a minimum solidification time and position 2 has the maximum. This variation can relate to different casting modulus of different positions in the L-shape part (volume to surface ratio of the casting). Position 1 had the minimum casting modulus so it has the maximum cooling rate, while position 2 had the maximum casting modulus consequently it has the minimum cooling rate.

In general, each sample in S-Mold has longer solidification time than SF-Mold one, this phenomenon may be caused by the more sand humidity in SF-Mold. The sand molds did not preheat before pouring. Therefore, it might be the silica-sand molds contained different degree of humidity. However, in this study it must consider that researchers did not compare non-ablated specimens. As the scope of present paper, the ablated samples will compare with non-ablated ones. The effect of the sand humidity on the solidification rate was negligible against extreme cooling effect of Ablation Casting process.

In the case of ablated specimens, position 1 has minimum solidification time and position 3 has the maximum. It means that the cooling effect of ablation process was more effective than the cooling effect of casting modulus (volume to surface ratio of the casting). Position 1 was the nearest point to the water

spray system so has maximum cooling rate, in the other hand position 3 is the farthest point to the water spray system, therefore it has the minimum solidification rate.

In general, AF-Mold has longer solidification time than A-Mold. The feeder existence caused to reduce the cooling effect of Ablation Casting process. This effect was more obvious in vicinity of connecting place of feeder to the L-shape (*i.e.* position 2 and 3).

Fig. 7 shows solidification times of ablated specimens are much lower than non-ablated ones. It is visible Ablation Casting cooling effect increased solidification rate for A-Mold and AF-Mold. This increment caused to change casting properties as discussed in next sections.

3.3 Casting density and porosity content

The results obtained by casting density measurements, are represented in Table 2. Porosity of each specimen was calculated by using of Eq.(2) and the results are shown in Table 2. In order to facilitate comparison, variation of the porosities of all samples was plotted in Fig. 8. In the both non-ablated molds, position 2 has the most porosity content. This refers to its lowest solidification rate caused by their highest casting modulus explained in section 3.2 (case S2 and SF2 had the highest ratio of volume to surface in the S-Mold and SF-Mold respectively). Case S1 and SF1 had minimum porosity content in their molds because of their higher solidification rate (case S1 and SF1 had the lowest ratio of volume to surface in the S-Mold and SF-Mold respectively).

In general, the samples of SF-Mold have lower porosity content in comparing to their equal positions in S-Mold. This phenomenon may be related to the feeding and lower solidification time in SF-Mold. The higher solidification rate caused to reduce gas porosity formation during solidification. When the melt cools and solidifies the solubility of hydrogen in molten aluminum decrease extensively. Therefore hydrogen atoms dissolved in aluminum melt, tend to form hydrogen gas molecules or gas porosities during solidification. This is a time-dependent or diffusive transformation. Decrement of the solidification time prevents to take enough time for gas porosity formation. Therefore, lower amount of porosities can form and hydrogen atoms remain as super saturated condition in the solid aluminum.

Fig. 8 Porosity content of ablated and non-ablated specimens

For all of ablated specimens, the porosity content increase with moving from position 1 to 3. In the other word, with referring to Fig. 7 and Fig. 8, it can conclude that position 1 in these molds has minimum solidification time and the minimum porosity content while position 3 has the maximum for both. The effect of the solidification rate on gas porosity formation was explained in later paragraph. In addition to gas porosities, shrinkage porosities result in failure of interdendritic feeding. Because position 1 solidified sooner than position 2, so position 2 acts as feeder for interdendritic regions in the vicinity of position 1. Similarly, position 3 acted as feeder for position 2. Position 3 is the last point solidified in the L-Shape part and has the maximum porosity content.

In comparing of case A1 and AF1, also A2 and AF2, it shows a decrement of the porosity content caused by using feeder in AF-Mold. Case A1 and A2 had higher solidification rate than case AF1 and AF2, but in both latters, coupled effect of the feeding and solidification rate was more effective than just high solidification rate in both formers. In the other hand, the porosity contents of both cases A3 and AF3 are equal. This equality can relate to special solidification condition of case AF3. Solidification time for this specimen can be divided into two ranges. At the first range, the riser fed solidifying alloy (position 3) and decreased porosity content, but in the second range (*i.e.* when ablation process starts), because solidifying front moved from position 1 to 2 and then 3, the region between position 2 and position 3 solidified before position 3. Therefore, position 3 acted as feeder for sooner solidified regions. This means that Ablation Casting had disordered feedability in the case of AF3. In addition, as discussed in section 3.2, case AF3 has longer solidification range than case A3. The higher solidification rate effect in case A3 and special feeding effect in case AF3 caused both specimens have equal porosity content.

Comparison of porosity content between same positions in ablated and non-ablated molds showed 2.79 vol.%, 3.14 vol.% and 2.44 vol.% decrement for case S1 with A1, S2 with A2, and S3 with A3 respectively. In addition to this, it was seen for the case of SF1 with AF1, SF2 with AF2, and SF3 with AF3, the porosity decreased 2.79 vol.%, 3.14 vol.% and 2.09 vol.% respectively. These reductions achieved by Ablation Casting cooling effect. The results are more interesting because the decrement for positions 1 and 2 is constant and independent of feeder existence, but for position 3 is not. It can conclude that unsuitable design of feeder place was applied. This incorrect design made weaker cooling effect or efficiency of Ablation Casting process.

Case S2 or S3 is the most porous specimen as shown in Fig. 8, compared with the case AF1 as the least porous one, it can understand the coupled effect of cooling and improvement of feedability can decrease porosity content to 3.84 vol.%. In other word, by implementing Ablation Casting

process system, which used in this study, the porosity content in A356 aluminium casting alloy can decrease to 3.84 vol.%.

3.4. Microstructure and SDAS

The microstructural evidences obtained by optical microscopy, are represented in Fig. 9(a) to (d). It is visible the microstructure of A356 contains silicon eutectic phases surrounded by aluminum primary phases (α -Al). These figures compare microstructure of the same positions in ablated and non-ablated specimens. There is a significant difference between these cases. It is clear that solidification of ablated specimens are directional (Fig.9(b) and (d)) while non-ablated specimens have not similar condition. The case of A2 and AF1 have finer and more homogenous microstructure than the case of S2 and SF1. The silicon eutectic phases in formers are more distributed than those of latters. This homogeneity arisen by Ablation Casting process can relate to SDAS variation.

The results of SDAS measurements are given in Table 2 and are illustrated in Fig. 10. The figure shows, in the case of S-Mold and SF-Mold, position 1 has less SDAS than position 2 and 3. Fig. 7 showed position 1 had higher solidification rate than position 2 and 3. In addition, position 3 had a little higher solidification rate than position 2. Increment of solidification rate decreased SDAS as classical theories. For this reason position 1 has less SDAS in comparison to same SDAS of position 2 and 3.

Fig. 7 showed SF-Mold had higher solidification

rate than S-Mold so it is visible in Fig. 10 which the specimens of SF-Mold have less SDAS than specimens of S-Mold.

It can be seen in Fig. 10 that all positions in ablated molds (A-mold and AF-Mold) have similar SDAS and there is a relative tendency for SDAS increment from position 1 to 3. Fig. 7 showed solidification rate decreased from position 1 to position 3 for ablated molds.

In Fig. 7, it was clear that A-Mold and AF-Mold had similar solidification rates. It can be seen in Fig. 10 that A1, A2 and AF1 have similar SDAS because of similar solidification condition. In addition, solidification time for case A3 was bigger, so has higher SDAS than A1, A2 and AF1. SDAS for case AF2 is bigger than A3 and the increment is reasonable according to Fig. 7 (AF2 had less solidification rate than A3). In the other hand, the case AF2 had higher solidification rate than case AF3 according to Fig. 7, but the SDAS is the same for both. This result is not reasonable and can relate to measurements errors. Case AF3 has the lowest solidification rate between all ablated specimens, therefore had higher SDAS as shown in Fig. 10.

Evaluation of the Ablated and non-Ablated specimens shows there is significant decrement in SDAS of ablated ones. This accompanied by high solidification rate of ablation process. Decrement of SDAS affected silicon morphologies and made finer silicon eutectic phases. The finer silicon phases, the more homogenous properties. The coarse eutectic silicon phases can act as crack initiation zones and

Fig. 9 Microstructures of Ablated and Non-Ablated specimens: (a) case S2; (b) case A2; (c) case SF1 and (d) case AF1

Fig. 10 SDAS of ablated and non-ablated specimens

reduce mechanical properties of aluminum castings as reported by other researchers^[3]. The maximum decrement of SDAS was observed in comparison between cases S2 and A2. Therefore, it can conclude that by the use of present Ablation Casting system, SDAS of A356 aluminium casting alloy could be reduced to 35%. Consequently, the process is an effective and low cost method to obtain desired mechanical properties in aluminum casting industry.

4. Conclusions

The effect the of Ablation Casting process on properties of A356 aluminium casting alloy was investigated in detailed system at present study. The results showed:

(1) By implementing of the Ablation process, the porosity content of A 356 castings can be reduced to 3.14 vol.% and by using of the correct couple of the riser and the process, this decrement can increase to 3.84 vol.%.

(2) The process can disorder feedability of risers, if unsuitable location for feeding considered in casting design.

(3) Microstructure of the Ablated samples was more homogenous than non-ablated ones. In addition, the process made eutectic silicon phases finer. The finer silicon phases, the more homogenous properties.

(4) Secondary dendrite arm spacing (SDAS) of the specimens reduced to 35% by the use of ablation process. Therefore, this is a feasible and low cost casting process in order to produce A356 aluminium casting alloy with desired mechanical properties.

Acknowledgements

Special thanks to Mr. R. Gholizadeh for kindly cooperation in thermal analysis investigations of this study.

REFERENCES

- [1] M. Tash, F.H. Samuel, F. Mucciardi and H.W. Doty, *Mater. Sci. Eng. A* **443** (2007) 185.
- [2] O. El Sebaie, A.M. Samuel, F.H. Samuel and H.W. Doty, *Mater. Sci. Eng. A* **486** (2008) 241.
- [3] S.G. Shabestari and H. Moemeni, *J. Mater. Process. Technol.* **153–154** (2004) 193.
- [4] L.Y. Zhang, Y.H. Jiang, Z. Ma, S.F. Shan, Y.Z. Jia, C.Z. Fan and W.K. Wang, *J. Mater. Process. Technol.* **207** (2008) 107.
- [5] L.Y. Zhang, B.D. Zhou, Z.J. Zhan, Y.Z. Jia, S.F. Shan, B.Q. Zhang and W.K. Wang, *Mater. Sci. Eng. A* **448** (2007) 361.
- [6] Z.H. Lee and S. Shin, *Met. Mater. Int.*, **10**(1) (2004), 89.
- [7] H. Xu, X. Jiana, T.T. Meeka and Q. Han, *Mater. Lett.* **58** (2004) 3669.
- [8] H. Ni, B. Suna, H. Jianga and W. Ding, *Mater. Sci. Eng. A* **352** (2003) 40.
- [9] J.G. Conley, J. Huang, J. Asada and K. Akiba, *Mater. Sci. Eng. A* **285** (2000) 49.
- [10] C.D. Lee, *Mater. Sci. Eng. A* **464** (2007) 249.
- [11] Z. Ma, A.M. Samuel, F.H. Samuel, H.W. Doty and S. Valtierra, *Mater. Sci. Eng. A* **490** (2008) 36.
- [12] J. Grassi, J. Campbell, M. Hartlieb and F. Major, *Mater. Sci. Forum*, **618–619** (2009) 591.
- [13] O. Saves and R. Kayikci, *Mater. Des.*, **28** (2007) 2224.
- [14] H.R. Ammar, A. Samuel and F. Samuel, *Int. J. Fatigue*, **30** (2008) 1024.