*M*CrAlY/TaC Metal Matrix Composite Coatings Produced by Electrospark Deposition

Yujiang XIE^{1)†}, Yanhong YANG¹⁾, Mingsheng WANG¹⁾ and Jian HOU²⁾

1) State Key Laboratory for Corrosion and Protection, Institute of Metal Research, Chinese Academy of Sciences, Shenyang 110016, China

2) Shenyang Liaohai Equipment Co., Ltd., Shenyang 110003, China

[Manuscript received 6 December 2012, in revised form 10 January 2013]

© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg

*M*CrAlY/TaC metal matrix composite coatings with 10, 20 and 30 wt.% TaC have been successfully produced by electrospark deposition (ESD). The effects of TaC content on microstructure, hardness and oxidation behavior of the composite coatings were studied. The results showed that the composite coatings were composed of superfine γ columnar dendrite and large TaC particles dispersedly distributed. The hardness was enhanced but oxidation resistance of the composite coatings was reduced with increasing TaC contents.

KEY WORDS: *M*CrAlY; Metal matrix composite; Coating; Electrospark deposition

1. Introduction

Turbine blade experiences harsh conditions, often suffered from oxidation and wear at its tip. To meet these new challenges and operate the turbine components at much higher temperature, metal-matrix composite (MMC) coatings are being considered to obtain better wear- and oxidation-resistant properties. These coatings may be developed by adding wear-resistant ceramic particles (such as Al₂O₃, HfC and SiC, etc.) into the oxidation-resistant *M*CrAlY matrix^[1]. The composite coatings have been prepared by laser cladding or thermal spraying^[2,3]. In the laser cladding process, a strong metallurgical bond can be obtained, but often in the risk of thermal damage to blade substrate due to its high susceptibility to hot cracking. In the thermal spraying process, no thermal damage is caused, but the composite coating weakly adheres to the substrate. In contrast, it is possible to produce a metallurgical bonded coating in virtue of minimum thermal damage to substrate materials by using electrospark

deposition process^[4].

Electrospark deposition is a very versatile process and different kinds of coatings have been produced by this process^[5–9]. However, to the best knowledge of the authors, MMC coatings are seldom been reported so far. Our previous work has attempted to prepare a wear- and oxidation-resistant MMC coating by electrospark deposition of *M*CrAlY/BN^[10]. However, it failed due to the decomposition of BN. TaC has a high melting point of 3880 °C and excellent properties such as high hardness and high resistance to chemical reagents. Even at higher temperature, its hardness is not lower than that of diamond. TaC particles reinforced NiCrBSi composite coating has been successfully produced by laser cladding^[11]. The current work shows the feasibility to obtain *M*CrAlY/TaC MMC coating by electrospark deposition and investigates the effects of TaC content on microstructure, hardness and oxidation resistance of the composite coatings. It is expected that the preliminary results can be beneficial to the development of wear- and oxidation-resistant composite coatings.

2. Experimental Details

A 3H-ES-6 ESD machine with a rapidly rotating electrode, high spark energy and high frequency, was

† Corresponding author. Assoc. Prof., Ph.D.; +86 24 23915863; Fax: +86 24 23890049; E-mail address: yjxie@imr.ac.cn (Yujiang XIE)

used to prepare the coatings. The deposition was carried out under the condition of 540 W and 300 Hz. During deposition the electrode was oriented preferentially at an angle of 30° – 45° to the work-piece and rotated at a speed of 3000 r/min, the shielding argon gas was delivered through a side cover and flowed at a rate of 25 mL/min. The revolving electrode was in traveling contact with the work-piece surface and the electrode material was transferred through the arc of every miniature lightning strike. With a succession of pulsed spark discharge deposition, the coating with a desirable thickness was obtained.

A Ni-base superalloy with the composition (wt.%) of Ni-11.5Cr-8.5Co-3.3Al-3.35Ti-1.85Mo-3.7W-3.9Ta-0.05Zr, was cut into the specimens with dimensions of 10 mm $\times$ 15 mm $\times$ 2 mm as the substrate material. The surface was ground to 600 grit SiC, cleaned ultrasonically in alcohol, and then blown dry. The composites of MCrAlY powder with addition of 10, 20 and 30 wt.% TaC were used to make the electrode materials. The MCrAlY powder had a composition (wt.%) of Ni-23Co-20Cr-8Al-4Ta-0.6Y. The electrode materials used for ESD were formed by laser casting wire techniques. The microstructure of the composite electrode materials with 10, 20 and 30 wt.% TaC are shown in Fig. 1. As it is shown in Fig. 1, with an increasing addition of TaC, the amount of TaC (white particles) in the composite obviously increased.

The phase compositions of the composite coatings were identified by means of X-ray diffractometry (XRD). The microstructural morphologies were observed by scanning electron microscopy (SEM). The hardness distribution of the coatings was investigated by microhardness tester. Isothermal oxidation tests were carried out in ambient air in a muffle furnace at 1000 $^{\circ}$ C for 100 h.

3. Results and Discussion

Fig. 2 shows the XRD patterns of MCrAlY/TaC composite coatings with 10, 20 and 30 wt.% TaC, respectively. It can be clearly seen that the more strong TaC peaks can be identified in the composite coatings with the increase of TaC contents and the final products of the three composite coatings contain both TaC and γ .

Fig. 3 shows the cross-sectional morphologies of

MCrAlY/TaC composite coatings with 10, 20 and 30 wt.% TaC, respectively. The composite coatings are fully dense, and there are no cracks to be observed between the coating layer and the substrate. The white particles visible in the composite coatings are TaC phase. The amount of TaC particles in the coatings increased with increasing TaC content in the electrode materials. Between the coatings and substrate, there are clearly visible fusion layers as shown in Fig.4, indicating that the coatings strongly bonded with the substrate.

Fig. 5 shows microstructure morphologies of MCrAlY/TaC composite coatings with 10, 20 and 30 wt.% TaC respectively. It's very interesting to notice that all of the composite coatings were composed of superfine γ columnar dendrite and large TaC particles dispersedly distributed. Furthermore, the presence and increase of TaC particles didn't effect the directionally solidified structure of the composite coatings. The shape of TaC particles was not spherical, and the size of TaC particles is close to that in electrode materials. The results suggest that TaC particles in the electrode were not melted or fully melted and were directly transferred to substrate with molten MCrAlY from electrode during electrospray deposition. It was quite different from previous reports^[12,13] on electrospray coatings containing ceramic particles such as TiC and Y_2O_3 , in which the ceramic particles would melt and solidify preferentially as nuclei after melting and

Fig. 2 XRD patterns of MCrAlY/TaC composite coatings with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) TaC

Fig. 1 Microstructure of the MCrAlY/TaC composite rods with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) TaC

Fig. 3 Cross-sectional morphologies of *MCrAlY*/TaC composite coatings with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) TaC

Fig. 4 Interface morphologies of *MCrAlY*/TaC composite coatings with 10 wt.% (a) and 30 wt.% (b) TaC

Fig. 5 Microstructure morphologies of *MCrAlY*/TaC composite coatings with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) TaC

solidification of electrode. This could be mainly attributed to higher melting point for TaC.

Fig. 6 shows the microhardness profiles of *MCrAlY*/TaC composite coatings with 10, 20 and 30 wt.% TaC. The microhardnesses of the coating and the substrate are shown on the left and right sides, respectively. The curves (a), (b) and (c) indicated that the hardnesses of the composite coatings gradually increased with increasing TaC content. The average hardness of the composite coating with the least TaC addition was about 530 HV_{0.1}. The hardness would increase to 640 HV_{0.1} when the TaC content reached to 30 wt.%.

Fig. 7 shows oxidation kinetics of *MCrAlY*/TaC composite coatings with 10, 20 and 30 wt.% TaC at 1000 °C for 100 h. The curves were characterized by steeply increasing at initial stage and then leveling off

regardless of the TaC content in the deposited coating. In addition, it could be seen that the coating with higher TaC content had a greater mass gain. The oxidation behavior of the coating with 30 wt.% TaC was far inferior to those of other two coatings, and after exposed at 1000 °C for 100 h its weight gain was more than twice those of the others. The results indicated that the oxidation resistance of *MCrAlY*/TaC composite coatings was obviously reduced with increasing TaC contents.

Fig. 8 shows the cross-section morphologies of oxidized *MCrAlY*/TaC composite coatings prepared by ESD with 10, 20 and 30 wt.% TaC when exposed at 1000 °C for 100 h. For the composite coating with 10 wt.% TaC addition, a continuous but less adherent layer assumed to α -Al₂O₃ was formed. When it comes to the other two composite coatings, discontinuous

Fig. 6 Microhardness profiles of *MCrAlY*/*TaC* composite coatings with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) *TaC*

Fig. 7 Oxidation kinetics curves of *MCrAlY*/*TaC* composite coatings with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) *TaC* when exposed at 1000 °C for 100 h

Fig. 8 Cross-section of oxidized *MCrAlY*/*TaC* composite coatings with 10 wt.% (a), 20 wt.% (b) and 30 wt.% (c) *TaC* when exposed at 1000 °C for 100 h

oxide scales were formed. It can be clearly seen that the oxidation-resistance of the composite coatings dramatically deteriorated with increasing *TaC* content. It is well known that *TaC* begins to be oxidized into Ta_2O_3 over 500 °C, then form porous Ta_2O_5 particles over 700 °C^[14]. The increasing amount of Ta_2O_5 in the oxide scale will be harmful for the formation of a dense and continuous alumina layer, which may be the main reason for reduced oxidation resistance of the composite coatings.

4. Conclusion

MCrAlY/*TaC* composite coatings can be successfully produced by electrospray deposition. The composite coatings consisted of superfine γ columnar dendrite matrix and large dispersedly distributed *TaC* particles. The existence and increase of *TaC* particles didn't effect the directionally solidified structure of the composite coatings. The hardness was enhanced but oxidation resistance of the composite coatings was reduced with increasing *TaC* content.

Acknowledgement

The work was supported by the National Natural Science Foundation of China (No.50901081).

REFERENCES

- [1] M. Ohara and M. Mega, US Patent, No.6811898, 2004.
- [2] D. Wolfe and J. Singh, *J. Mater. Sci.* **33** (1998) 3677.
- [3] L.D Zhao, M. Parco and E. Lugscheider, *Surf. Coat. Technol.* **184** (2004) 298.
- [4] Y.J. Xie, M.C. Wang and D.W. Huang, *Appl. Surf. Sci.* **253** (2007) 6149.
- [5] R.J. Wang, Y.Y. Qian and J. Liu, *Appl. Surf. Sci.* **240** (2005) 42.
- [6] Y.J. Xie and M.C. Wang, *Surf. Coat. Technol.* **201** (2006) 3564.
- [7] S. Cadney and M. Brochu, *Intermetallics* **16** (2008) 518.
- [8] Z.J. Feng and C.L. Zeng, *J. Power Sources* **195** (2010) 4242.
- [9] B. Zhang, L. Ma, Z.J. Liang and J.J. Zhao, *Acta Metall. Sin. (Eng. Lett.)* **24** (2011) 309.
- [10] Y.J. Xie, M.C. Wang, *J. Alloys Compd.* **484** (2009) 21.
- [11] M.J. Chao, W.L. Wang, E.J. Liang and D.X. Ouyang, *Surf. Coat. Technol.* **202** (2008) 1918.
- [12] Y. He, H. Pang, H. Qi, D. Wang, Z. Li and W. Gao, *Mater. Sci. Eng. A* **334** (2002) 179.
- [13] S.K. Tang, T.C. Nguyen and Y. Zhou, *Weld J.* **89** (2010) 172.
- [14] G.D. Li, X. Xiong and K.L. Huang, *Trans. Nonferrous Met. Soc. China* **19** (2009) S689.