Phase Homogeneity and Crystal Structure of $\text{Sb}_{88}\text{Te}_{12}$ Synthesized by Melt-quench Method

C. Rangasami[†]

Department of Physics, Erode Sengunthar Engineering College, Erode-57, India

[Manuscript received 5 January 2013, in revised form 28 March 2013]

© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg

Phase homogeneity and crystal structure of $\text{Sb}_{88}\text{Te}_{12}$ alloy synthesized by melt-quench method have been analyzed using X-ray diffraction (XRD) and Raman spectroscopy. Rietveld refinement of crystal structure of $\text{Sb}_{88}\text{Te}_{12}$ has revealed the formation of Sb_8Te_3 and Sb phases respectively with 11R and A7 structures (space group is $R\bar{3}m$). Phase fractions of the phases Sb_8Te_3 and Sb have been determined to be 44.44% and 55.56% respectively. Raman spectrum of $\text{Sb}_{88}\text{Te}_{12}$ has showed a highest intensity peak at 156 cm^{-1} and another peak at 151.1 cm^{-1} , which correspond to A_{1g} modes of Sb_8Te_3 and element Sb, respectively. Analysis of Raman spectrum has substantiated the results obtained from structure refinement regarding the presence of two different phases.

KEY WORDS: $\text{Sb}_{88}\text{Te}_{12}$ alloy; Melt-quench method; XRD; Rietveld refinement; Raman spectroscopy; Multiphase formation

1. Introduction

At room temperature, some materials exhibit amorphous phase even though they can have thermodynamically stable crystalline phase. This kind materials with a capability of fast switching between amorphous and crystalline phases with unique optical and electrical properties are called phase change memory materials (PCMMs).

These are excellent active layer materials in rewritable optical data storage media such as digital versatile disks, blue-ray disks and in phase change random access memory (PCRAM)^[1–7]. PCRAM is a promising non-volatile data storage technology for next generation memory owing to potential characteristics such as fast operation and higher scalability^[5–7].

Ovshinsky^[8] demonstrated firstly that the chalcogenide based alloys of TeAsSiGe system such as $\text{Te}_{48}\text{As}_{30}\text{Si}_{12}\text{Ge}_{10}$ can be switched reversibly between

low and high resistivity states. Following this, Feinleib *et al.*^[9] performed firstly laser-induced phase change in $\text{Te}_{81}\text{Ge}_{15}\text{Sb}_2\text{S}_2$ alloy. But, the crystallization time of this alloy is found to be high (microsecond range). Later on, Yamada *et al.*^[10] discovered fast-switching in the materials located on the GeTe- Sb_2Te_3 pseudo binary line of Ge-Sb-Te phase diagram, which has enabled the rewritable phase change optical data storage technology. On the other hand, Iwasaki *et al.*^[11] used Ag-In-Sb-Te based system for phase change optical recording successfully. The optical contrast (change in reflectivity) between the amorphous and crystalline phases enables data storage in optical recording^[1,2]. Similarly, the ability of exhibiting reversible change in resistivity has initiated the investigation of phase change random access memory (PCRAM) technology^[1,3–5]. At present, GeSbTe based ternary and AgInSbTe based quaternary systems are recognized as leading materials for optical and electronic storage media applications^[4,7]. The main requirements^[3,4] which make PCMMs a leading active layer material for both optical and electronic data storage devices are: (i) both amorphous and crystalline phases should be stable for long time

[†] Corresponding author. Ph.D.; Tel: +91 9976817141; E-mail address: kkaumaran@gmail.com (C. Rangasami)

at operating temperature; (ii) number of cycles must be $\sim 10^5$ times for optical storage; (iii) crystallization should take place at nanosecond time scales; (iv) there should be large optical contrast between the amorphous and polycrystalline states.

Binary alloys such as GeTe, SbTe, InSe and SbSe have also been investigated fairly well for optical and electronic phase change storage media applications. Of these binaries, SbTe based alloys have been suggested to be potential candidates for phase change memory device applications^[12–14]. SbTe alloys exhibit a dramatic change in reflectivity and resistivity, which are associated with transformation between amorphous and crystalline phases. In addition, SbTe alloys have operational stability in the temperature range of 300–500 K^[15]. Moreover, the thermoelectric properties of nano-structured SbTe based alloys are found to be enhanced, which can be attributed to quantum size effect and increased interface scattering of phonons. Furthermore, SbTe based alloys (Sb_2Te_3) have also been reported as suitable candidates for flash memories. This is because of the significant properties of SbTe alloys, like high endurance, non-destructive reading, direct overwriting, low-programming energy, huge-read dynamic range, fast speed, high performance, multi-state storage, and good complementary metal oxide- semiconductor logic compatibility^[16].

Detailed analysis of phase diagram of the SbTe binary system revealed that the inter-metallic compound Sb_2Te_3 exists at 60% of Te whereas the δ phases exists in a wide range of composition around 25% of Te (ASM International, 1996). For a better understanding of the physical properties of SbTe alloys, crystal structure, in general, is an essential parameter. Crystal structure of Sb_2Te_3 has been investigated by several authors. But reports on the structure of δ phases available in the literature are very scarce. Crystal structure of the compounds such as Sb_2Te , Sb_4Te_3 , Sb_8Te_3 , Sb_8Te_7 , Sb_8Te_9 , $\text{Sb}_{10}\text{Te}_6$, $\text{Sb}_{10}\text{Te}_9$ and $\text{Sb}_{14}\text{Te}_6$ ^[17–19] have been investigated fairly well. These compounds have been analyzed either by single crystal method^[20] or using high-resolution electron microscopy^[21,22]. However, on the Sb-rich side of δ phases, there have been no reports on precise determination of crystal structure. Therefore, the present work aims at investigating the crystal structure of SbTe binary alloy with composition at 12% of Te using Rietveld refinement of crystal structure and Raman spectroscopy.

2. Experimental

2.1 Synthesis of $\text{Sb}_{88}\text{Te}_{12}$

Polycrystalline $\text{Sb}_{88}\text{Te}_{12}$ was formed by melt-quench method. Briefly, 5N purity Sb and Te pieces with compositional ratio of 88:12 and total mass

Fig. 1 Schematic diagram of thermal cycle followed in melt-quench method ($T_{\text{max}}=1323$ K)

of ~ 5 g were taken in a cleaned quartz ampoule. The ampoule was then evacuated to a pressure of $\sim 5 \times 10^{-4}$ Pa and sealed, with the charge inside. The sealed ampoule was heated in a vertical tubular furnace, the temperature of which was controlled to an accuracy of 2 K. The furnace temperature was initially increased to 523 K at a rate of 4 K/min and was maintained at this temperature for 3 h in order to allow the exothermic reaction between Sb and Te to take place at a controlled rate (Champnes, 1999). Heating was continued at the same rate up to 1323 K, which is higher than the melting point of any of the constituent elements. The charge in the ampoule was allowed to react in this molten state for 60 h with intermittent shaking (2 to 5 times) in order to improve the homogeneity. Finally, the ampoule with the charge inside was quenched in water. The ingot thus obtained was polycrystalline and was black in color with shiny surface. Fig. 1 shows the block diagram of thermal cycle followed in melt-quench method.

2.2 Characterization of $\text{Sb}_{88}\text{Te}_{12}$

Powder X-ray diffraction (XRD) data of $\text{Sb}_{88}\text{Te}_{12}$ were recorded in the 2θ range 10° to 130° (step is 0.0170°) using PANalytical (model X'Pert PRO) with $\text{CuK}\alpha$ radiation at room temperature. Rietveld refinements were carried out using General Structure Analysis System (GSAS) software supported by EXPGUI graphical user interface which allows simultaneous refinement of two wavelengths ($K_{\alpha 1}$ and $K_{\alpha 2}$ with intensity ratio 0.5 in the present case). Shifted Chebyshev polynomial was used to describe the background and a Pseudo-Voigt profile function was used to model the peak shapes. The quality of fit was described by the discrepancy factors^[23] R_p , R_{wp} , R_{exp} , R_F , and χ^2 , the goodness of fit (GOF). In addition, content of the constituent elements was estimated using high resolution scanning electron microscope (HRSEM) of model FEI Quanta 200F facilitated with EDX analyzer (SUTW-SAPPHIRE with resolution 133.22).

Fig. 2 Experimental XRD pattern and the results of Rietveld refinement for $\text{Sb}_{88}\text{Te}_{12}$ (a), the insets show the data in the range 39° to 43° (b) and 80° to 130° (c), on an expanded scale. The crosses and the overlying solid line represent the experimental data and the calculated profile respectively. The short vertical markers indicate possible Bragg reflections whereas the bottom curve denotes the difference between the experimental and calculated data

2.3 Micro Raman measurements

Micro Raman measurements were carried out in backscattering geometry using Horiba Jobin Yvon, model LABRAM with 1800 grooves/mm grating (resolution = 0.3 cm^{-1}) at room temperature. An argon-ion laser with 488 nm plane polarized beam was used as the excitation source. Raman spectra were recorded with the laser beam power 0.5 mW focused to a spot size of $\sim 2 \mu\text{m}$. Measurements were made on the shiny surface of small pieces obtained from the ingot.

3. Results and Discussion

3.1 Structure analysis

Fig. 2(a) shows the experimental powder XRD pattern (symbols) of melt-quench synthesized $\text{Sb}_{88}\text{Te}_{12}$ together with the results of Rietveld refinement of crystal structure. The insets Fig. 2(b) and Fig. 2(c) show the data in the range 39° to 43° and 80° to 130° respectively, on an expanded scale. A careful inspection of the literature on crystal structure of $\text{Sb}_{88}\text{Te}_{12}$ suggests that it crystallizes in hexagonal structure^[24] and the corresponding XRD pattern consists of only a pair of peaks in the 2θ range of 39° to 43° . But the XRD pattern of $\text{Sb}_{88}\text{Te}_{12}$ consists of two pairs of peaks (Fig. 2(b)) in the same 2θ range. Presence of these peaks implies that the sample is heterogeneous and may consist of minimum of two different phases. It is important to mention here that phases (Sb and SbTe related) with A7 or distorted NaCl or hexagonal structure are expected to show a pair of peaks separately in the 2θ range 39° to 43° . Therefore, the structure analysis of $\text{Sb}_{88}\text{Te}_{12}$ is required an exhaustive preliminary investigation before

any conclusion can be drawn. More importantly, the two pairs of the peaks may be taken to indicate the presence of two phases with A7 or distorted NaCl or hexagonal structure as (104) and (110) reflections of these structures fall in this range. However, their positions and the separation between them will be determined by the composition of the system being considered. These two phases may be element Sb and any one of the phases in the system $\text{Sb}_{2n}\text{Te}_3$, where “n” is an integer. The factor that favors the above conclusion is the presence of a strong peak at around $2\theta = 28.585^\circ$ which is expected for Sb/ $\text{Sb}_{2n}\text{Te}_3$ and in fact, it is the highest intensity reflection (012) for them. Having arrived at a qualitative conclusion, as discussed above, regarding the phases present, it has been decided to confine the number of independent phases to two, to begin with. Thus, the refinements were initiated assuming two different phases, one is element Sb and the other is with general formula $\text{Sb}_{2n}\text{Te}_3$. Finally, Rietveld refinement of the crystal structure of $\text{Sb}_{88}\text{Te}_{12}$ was continued by assuming that the system consist of Sb_8Te_3 and element Sb. This assumption was made based on the peaks positions in the XRD pattern. The relevant structure parameters for Sb_8Te_3 were taken from the Ref. [18]. In the unit cell of Sb_8Te_3 (space group is $R\bar{3}m$), the atomic position 3a at (0, 0, 0) and 6c at ($2/3, 1/3, z$) are shared by Te atom. The positions 6c at ($1/3, 2/3, z$), (0, 0, z), ($1/3, 2/3, z$) and ($2/3, 1/3, z$) are occupied by Sb atoms^[18]. The crystal structure of element Sb is A7 (JCPDS-ICDD data, PDF No.85-1322) with space group $R\bar{3}m$ in which Sb atoms occupy the atomic position 6c at (0, 0, z). Site occupancies of all Wyckoff positions in the space group $R\bar{3}m$ for both Sb_8Te_3 and Sb phases were assigned as one. The refinement converged satisfactorily to $R_{\text{wp}} = 6.33\%$ (GOF is 1.191). The phase fractions of Sb_8Te_3 and Sb were found to

Table 1 Refined lattice parameters, phase fractions and discrepancy factors of $\text{Sb}_{88}\text{Te}_{12}$

Phase	Phase fraction (%)	Lattice parameters (Å)	
		<i>a</i>	<i>c</i>
Sb_8Te_3	44.44	4.27999(8)	64.01797(189)
Sb	55.56	4.31560(8)	11.25180(33)
$R_{\text{wp}}=6.33\%$, $R_{\text{p}}=4.68\%$, $R_{\text{F}}^2=4.45\%$, $R_{\text{exp}}=5.80\%$, GOF=1.191			

be 44.44% and 55.56%, respectively. The results of Rietveld refinement are shown in Fig. 2. In Fig. 2, the crosses and the overlying solid line represent the experimental data and the calculated profile respectively. The short vertical markers indicate possible Bragg reflections whereas the bottom curve denotes the difference between the experimental and calculated data. Results of refinement shows the presence of two phases as mentioned above. Refined cell parameters, phase fractions and discrepancy factors are given in Table 1. The unit cell parameters of Sb_8Te_3 and element Sb (A7) match well with those reported by Kifune *et al.*^[18] and JCPDS-ICDD data (PDF No.85-1322) respectively. While continuing the discussion on the results of Rietveld analysis, it is noteworthy to look into the crystal structure of Sb_8Te_3 in detail. There have been two views concerning the crystal structures of all possible intermetallic alloys in the SbTe system. In one^[18], a cubic close packed arrangement with chemical formula $\text{Sb}_{2n}\text{Te}_3$. In the other view^[17] a rather complex structure with the chemical formula $(\text{Sb}_2\text{Te}_3)_k(\text{Sb}_2)_m$, where “*k*” and “*m*” are integers is proposed. For instance, Sb_8Te_3 can be realized by substituting $n=4$ in the chemical formula suggested in the former model, or equivalently by letting $k=1$ and $m=3$ in that proposed in the latter model. Interestingly, the structure of Sb_8Te_3 comes out to be the same in both models^[19].

In the present work, the model proposed by Kifune *et al.*^[18] has been considered and the unit cell of Sb_8Te_3 is shown in Fig. 3. Based on this model, the structure of all physically possible alloys in the SbTe system can be generated by stacking a primary unit. This primary unit itself is composed of two different structural units, with one unit consisting of alternate layers of Sb and Te (NaCl type, characteristic of Sb_2Te_3) and the other having Sb layers alone (A7, characteristic of Sb). The atomic layer arrangement in each of this “sub-units” is cubic close packed. Kifune *et al.*^[18] defined a parameter “*M*”, which denotes the stacking period and which has its basis in the proposed chemical formula $(\text{Sb}_{2n}\text{Te}_3)$. It is written as $M=2n+3$ and gives the number of atomic layers in a unit cell, when $2n$ is multiple of three. When $2n$ is not multiple of three, *M* should be multiplied by three to get the number of layers. This requirement ensures that the unit cell is consistent with the cubic close packed arrangement. For instance, $n=3$ yields Sb_6Te_3 (Sb_2Te) with *M* given by 9 and since *M* is a multiple of three, the number of atomic layers in the unit cell is 9. On the other hand, for Sb_2Te_3 ,

Fig. 3 Unit cell of Sb_8Te_3 along with refined atomic positions, it consists of 33 layers

$n=1$ and $M=5$, which is not a multiple of three and therefore it should be multiplied by three. Hence, in this structure, which is also called 5R, the total number of atomic layers in the unit cell is 15. Similarly, $n=4$ yields Sb_8Te_3 , the alloy under consideration with *M* as 11. The structure of Sb_8Te_3 is also called 11R. The sequence of atomic planes, Te-Sb-Te-Sb-Sb-Sb-Sb-Sb-Sb-Te-Sb forms one third of the unit cell or essentially a primary unit and stacking of three such primary units constitute the unit cell of Sb_8Te_3 . Thus, there will be 33 atomic layers in the unit cell of Sb_8Te_3 . The lattice parameter *c* of a particular binary can also be evaluated using the simple expression^[18], $1.9 \times 3 \times M$, where 1.9 is the thickness of one atomic layer in Å. Note again that the factor three is used to maintain the number of layers in the unit cell to be multiples of three, when $2n$ is not a multiple of three. Using the formula given above, the lattice parameter *c* is calculated to be 62.7 Å, which is close to 63.61047(263) Å, obtained from Rietveld analysis. Further, concentration of Te (in atomic percentage) is related to *M* as $300/M$, which in the present case is 27.3. Thus, Sb_8Te_3 can be written as $\text{Sb}_{72.7}\text{Te}_{27.3}$. This non-integer value of concentration of constituents is rather unusual and several alloys in SbTe system have such composition of elements. The XRD data of Sb_8Te_3 and Sb are given in Table 2. It can be noted that only first 25 intense peaks have been given in the Table 1 to avoid cumbersome task of comprehending more than 200 peaks observed. Also,

Table 2 Powder XRD data for Sb_8Te_3 and Sb phases (the space group is $R\bar{3}m$, calculated lattice spacing (d_{cal}) and Miller indices (hkl) of selected reflections are shown)

Reflection No.	$\text{Sb}_{88}\text{Te}_{12}$			Sb		
	d_{cal} (Å)	hkl	I_{cal} (%)	d_{cal} (Å)	hkl	I_{cal} (%)
1	4.2407	0 0 15	7.6	3.7548	0 0 3	16.3
2	3.5339	0 0 18	7.1	3.5447	1 0 1	2.0
3	3.1214	1 0 $\bar{1}\bar{1}$	100.0	3.1124	1 0 $\bar{2}$	48.4
4	2.2801	1 0 22	34.5	2.2485	1 0 4	41.1
5	2.1408	1 1 0	20.3	2.1561	1 1 0	28.7
6	1.9276	0 0 33	14.1	1.9291	1 0 $\bar{5}$	13.7
7	1.9111	1 1 15	3.1	1.8774	0 0 6	19.2
8	1.8879	1 0 $\bar{29}$	2.8	1.8698	1 1 3	2.4
9	1.7654	2 0 11	13.5	1.7724	2 0 2	21.3
10	1.5607	2 0 $\bar{22}$	11.0	1.5562	2 0 $\bar{4}$	4.8
11	1.5597	1 0 37	1.5	1.4778	1 0 7	6.2
12	1.4325	1 1 33	3.0	1.4376	2 0 5	4.4
13	1.3620	2 1 $\bar{1}\bar{1}$	9.3	1.4159	1 1 6	12.2
14	1.3469	1 0 $\bar{44}$	3.5	1.3692	2 1 $\bar{2}$	10.2
15	1.2611	2 1 22	6.7	1.3175	1 0 $\bar{8}$	3.8
16	1.2473	0 0 51	1.7	1.2619	2 1 4	6.7
17	1.2360	3 0 0	3.0	1.2516	0 0 9	3.1
18	1.2161	2 1 $\bar{26}$	1.5	1.2448	3 0 0	4.7
19	1.1401	2 0 44	1.6	1.1961	2 1 $\bar{5}$	1.7
20	1.0704	2 2 0	1.8	1.0825	1 1 9	3.5
21	1.0405	3 0 $\bar{33}$	2.0	1.0611	2 1 7	1.9
22	1.0125	3 1 11	2.5	1.0375	3 0 6	4.6
23	0.9689	3 1 $\bar{22}$	1.6	1.0187	3 1 2	3.4
24	0.9358	2 2 33	2.9	0.9969	2 1 $\bar{26}$	1.9
25	0.8416	3 2 $\bar{1}\bar{1}$	2.4	0.9721	3 1 $\bar{22}$	2.8

the relative intensities of highest intense reflections of different phases are not always 100%. This is because: (1) the normalization was done according to the highest intense peak of the sample; (2) the relative intensities vary with phase fractions. In order to obtain homogeneous phase, the well grounded sample was taken through the same thermal cycle again and finally, examined with XRD measurements. The XRD pattern exhibited similar reflections as obtained in the previous pattern. This observation revealed that synthesis of $\text{Sb}_{88}\text{Te}_{12}$ using melt-quench method results in two phases, namely Sb_8Te_3 and element Sb.

3.2 Raman analysis

A typical Raman spectrum of bulk $\text{Sb}_{88}\text{Te}_{12}$ recorded at room temperature is shown in Fig. 4. In order to identify the peak positions of vibrational modes, the spectrum was deconvoluted using multiple Lorentzians. In Fig. 4, open circles, grey lines and the black line through the open circles denote respectively the experimental data, individual Lorentzians and the overall fit. Deconvolution of the spectrum yielded four peaks at 125.2, 131.2, 151.1 and 156.8 cm^{-1} . The results of Rietveld refinements have shown that $\text{Sb}_{88}\text{Te}_{12}$ consists of Sb_8Te_3 and Sb phases. Therefore, knowledge of vibrational modes of Sb_8Te_3 and Sb are essential to analyse the Raman modes of the

Fig. 4 Raman spectrum of $\text{Sb}_{88}\text{Te}_{12}$

sample without ambiguity. Raman data of Sb phase can be taken from Ref. [25]. The irreducible representation for the Raman active modes of Sb has the form, $A_{1g} + 2E_g$, which shows that there are three modes and experimentally two modes have been determined as E_g ($\sim 110 \text{ cm}^{-1}$), and A_{1g} ($\sim 151 \text{ cm}^{-1}$), with A_{1g} being the highest intensity mode. No report is available on the vibrational modes of Sb_8Te_3 . However, $\text{Sb}_{2n}\text{Te}_3$ system of alloys have the same point group (D_{3d}^5) as Sb, and hence mode characteristics should be similar to that of Sb. For instance, the zone-center modes for Sb_2Te_3 ($n=1$), can be decomposed in the irreducible form as $2A_{1g} + 2E_g$. Four modes have been identified experimentally^[26,27]: E_g modes at ~ 35 and $\sim 114 \text{ cm}^{-1}$ and A_{1g} modes at ~ 70 and $\sim 165 \text{ cm}^{-1}$. In

the limit $n \rightarrow \infty$, the concentration of Te will become negligibly small and $\text{Sb}_{2n}\text{Te}_3$ will eventually become element Sb. Importantly, it implies that the modes of Sb_8Te_3 should lie between those of Sb_2Te_3 and Sb. For instance, Sb and Sb_2Te_3 ($n=1$) have their highest intensity mode (A_{1g}) at ~ 151 and ~ 165 cm^{-1} , respectively. Therefore, the highest intensity mode of Sb_8Te_3 ($n=4$) should fall in between these two. Raman spectrum of the sample showed a strong peak at about 156 cm^{-1} , besides three other peaks. Following the above logic, the peak at 156 cm^{-1} has been assigned to A_{1g} mode of Sb_8Te_3 . The peak at 151.1 cm^{-1} is due to the A_{1g} mode of Sb. The intensity of the latter is less, as its phase fraction is low. Detailed lattice dynamics calculations are required to assign modes for all the peaks observed in the spectrum.

4. Conclusions

$\text{Sb}_{88}\text{Te}_{12}$ alloy has been synthesized by melt-quench method and analysed in detail using Rietveld refinement of crystal structure and Raman measurements. The results of Rietveld refinement have revealed that the alloy with initial composition $\text{Sb}_{88}\text{Te}_{12}$ consist of two different phases Sb_8Te_3 and Sb with 11R ($R\bar{3}m$) and A7 ($R\bar{3}m$) structures. Phase fractions of the Sb_8Te_3 and Sb phases have been determined to be 44.44% and 55.56% respectively. Raman spectroscopy has corroborated the results of Rietveld refinement by exhibiting A_{1g} modes of both Sb and Sb_8Te_3 at 151.1 and 156 cm^{-1} .

REFERENCES

- [1] M. Wuttig and N. Yamada, *Nature Mater.* **6** (2007) 824.
- [2] W. Welnic and M. Wuttig, *Mater. Today* **11** (2008) 20.
- [3] S. Raoux and M. Wuttig, *Phase change materials: Science and Application*, Springer, New York, 2009, p.1.
- [4] T. Siegrist, P. Merkelbach and M. Wuttig, *Annu. Rev. Condens. Matter Phys.* **3** (2012) 111.
- [5] M.L. Lee, L.P. Shi, Y.T. Tian, C.L. Gan and X.S. Miao, *Phys. Status Solidi A* **205** (2008) 340.
- [6] S. Raoux, R.M. Shelby, J. Jordan-Sweet, B. Munoz, M. Salinga, Y.C. Chen, Y.H. Shin, E.K. Lai and M.H. Lee, *Microelectron. Eng.* **85** (2008) 2330.
- [7] T. Matsunaga, J. Akola, S. Kohara, T. Honma, K. Kobayashi, E. Ikenaga, R.O. Jones, N. Yamada, M. Takata and R. Kojima, www.epcos.org/library/papers/pdf.2011/Oral-Papers/S4-05.pdf.
- [8] S.R. Ovshinsky, *Phys. Rev. Lett.* **21** (1968) 1450.
- [9] J. Feinleib, J. deNeufville, S.C. Moss and S.R. Ovshinsky, *Appl. Phys. Lett.* **18** (1971) 254.
- [10] N. Yamada, E. Ohno, N. Akahira, K. Nishiuchi, K. Nagata and M. Takao, *Jpn. J. Appl. Phys.* **26** (1987) 61.
- [11] Y. Nakata, T. Suenaga, M. Ejiri, S. Shida, K. Tani, N. Yiwata and H. Tashiro, *Mater. Trans.* **45** (2004) 2673.
- [12] H. Iwasaki, Y. Ide, M. Harigaya, Y. Kageyama and I. Fujimura, *Jpn. J. Appl. Phys.* **31** (1992) 461.
- [13] R.E. Simpson, P. Fons, X. Wang, A. V. Kolobov, T. Fukaya and J. Tominaga, *Appl. Phys. Lett.* **97** (2010) 161906(1).
- [14] M.H.R. Lankhorst, L. van Pieterson, M. van Schijndel, B.A.J. Jacobs and J.C.N. Rijpers, *Jpn. J. Appl. Phys.* **42** (2003) 863.
- [15] T.C. Chong, L.P. Shi, P.K. Tan, J.M. Li, H.K. Lee and X.S. Miao, *Appl. Phys. Lett.* **88** (2006) 122114.
- [16] R. Venkatasubramanian, E. Siivola, T. Colpitts and B. O'Quinn, *Nature* **413** (2001) 597.
- [17] Y. Yin, H. Sone and S. Hosaka, *J. Appl. Phys.* **102** (2007) 064503.
- [18] L.E. Shelimova, O.G. Karpinskii, M.A. Kretova, V.I. Kosyakov, V.A. Shestakov, V.S. Zemskov and F.A. Kuznetsov, *Inorg. Mater.* **36** (2000) 768.
- [19] K. Kifune, Y. Kubota, T. Matsunga and N. Yamada, *Acta Crystallogr. Sec. B* **61** (2005) 492.
- [20] P.F.P. Poudeu and M.G. Kanatzidis, *Chem. Commun.* (2005) 2672.
- [21] V. Agafonov, N. Rodier, R. Ceolin, R. Bellissent, C. Bergman and J.P. Gaspard, *Acta Cryst. C* **47** (1991) 1141.
- [22] Y. Nakata, T. Suenaga, M. Ejiri, S. Shida, K. Tani, N. Yiwata and H. Tashiro, *Mater. Trans.* **45** (2004) 2673.
- [23] R.A. Young, *The Rietveld Method* (IUCr Monograph on Crystallography, No. 5), Oxford University Press, New York, 1993, p.1.
- [24] H. Tashiro, M. Harigaya, K. Ito, M. Shinkai, K. Tani, N. Yiwata, A. Watada, N. Toyoshima, K. Makita, A. Kitano and Kenichi Kato, www.epcos.org/library/papers/pdf.2003/Tashiro.pdf
- [25] X. Wang, K. Kunc, I. Loa, U. Schwarz and K. Syassen, *Phys. Rev. B* **74** (2006) 134305.
- [26] O. Gomis, R. Vilaplana, F.J. Manjon, P.R. Hernandez, E.P. Gonzalez, A. Munoz, V. Kucek and C. Drasar, *Phys. Rev. B* **84** (2011) 174305.
- [27] K.M.F. Shahil, M.Z. Hossain, V. Goyal, and A.A. Balandin, *J. Appl. Phys.* **111** (2012) 054305.