Cooling Rate Sensitivity of RE-Containing Grain Refiner and Its Impact on the Microstructure and Mechanical Properties of A356 Alloy

Hua-Rui Zhang^{1,2} · Zhen-Bang Liu^{1,2} · Zi-Zhuo Li^{1,2} · Guo-Wei Li³ · Hu Zhang^{1,2}

Received: 30 December 2015 / Revised: 28 January 2016 / Published online: 22 March 2016
© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg 2016

Abstract The cooling rate sensitivities of AlTiB, RE and AlTiB–RE refiners were investigated using laboratory experiments and the actual industrial applications of A356 automotive wheel via low pressure die casting technology. Their impact mechanisms on the microstructure and mechanical properties of the A356 alloy were discussed. The results demonstrated that the AlTiB–RE refiner possessed most effective and synergetic refinement effects compared to the individual AlTiB or RE refiners. The AlTiB–RE refiner exhibited the least sensitivity to the cooling rate changes than the other refiners. The comprehensive properties of alloy wheel refined by the AlTiB–RE refiner were improved significantly. The tensile strength, yield strength, and elongation of wheel spoke improved by approximately 11.3%, 10.8% and 44.1%, respectively. The property difference values of the tensile strength, yield strength, and elongation in different positions of the wheel decreased from 14.8%, 31.2% and 47.7% to 8.6%, 27.1% and 30.9%, respectively.

KEY WORDS: Grain refinement; Cooling rate sensitivity; A356 alloy; Microstructure; Mechanical properties

1 Introduction

The Al–Si casting alloys, such as A356 alloys, have been widely used in the automotive, military, and aerospace industries because of their excellent castability, good corrosion resistance, and high strength to weight ratios [1, 2]. To improve the mechanical properties of these alloys, grain refinement and modification techniques by refining the

micro-constituents, namely α -Al and eutectic silicon particles, were utilized [3, 4]. The introduction of inoculating particles in the form of master alloys, such as Al–Ti–B, Al–Ti–C, and Al–B, into Al–Si alloy melts was one of the most effective ways to refine grains [5, 6].

Among the grain refiners, Al–Ti–B master alloys, particularly Al5TiB, have been most widely used in the Al–Si alloys over decades, as reported by Schneider [7]. Al5TiB contains Al₃Ti intermetallic compound and TiB₂ particles in an aluminum matrix. Based on the studies of Greer et al. [8] and Han et al. [5], the TiB₂ particles could act as heterogeneous nuclei to promote the crystallization of α -Al grains. Recently, Xu et al. [9] found that the addition of rare earth (RE) elements in the preparation process of Al–Ti–B grain refiner could decrease the size of Al₃Ti, which improved the refining efficiency of Al–Ti–B refiner. Wang et al. [10] prepared novel AlTiB–RE nanorefiners by melt-spinning in a LZK-12A-type vacuum quenching furnace using the raw materials of commercial Al–5Ti–B rods and Ce-rich mischmetal. The application of novel AlTiB–RE

Available online at <http://link.springer.com/journal/40195>

✉ Hu Zhang
zhanghu@buaa.edu.cn

¹ School of Materials Science and Engineering, Beihang University, Beijing 100191, China

² Beijing Key Laboratory for Advanced Functional Material and Thin Film Technology, Beihang University, Beijing 100191, China

³ SMX Dicastal Wheel Manufacture Company, Sanmenxia 472000, China

nanorefiners showed that the RE hindered the nucleating particles from aggregating and precipitating. This effect prolonged the fading time of refining and improved the refining efficiency [11].

Moreover, the RE elements have special physicochemical activity and might be capable of contributing to the modification of eutectic Si in Al–Si alloys, as reported by Sebaie *et al.* [12] and Li *et al.* [13]. Jiang *et al.* [14] showed that the addition of mischmetal containing La and Ce improved the morphology of eutectic Si particles compared to the unmodified A357 alloy and reduced the size of the α -Al primary phase. For A356 alloys, Tsai *et al.* [15] reported that the efficiency of modification of microstructures and the mechanical properties with the addition of 1.0 wt% La was similar to that of a commercial Sr modifier (0.01 wt%).

Although efforts have been made toward improving the refining efficiency of conventional AlTiB refiners by addition RE elements, in the case of novel AlTiB–RE or RE refiners, most of the previous research has been conducted at the laboratory scale. There is a lack of detailed investigation performed at an industrial scale. In the case of the conventional AlTiB grain refiners, one of the major problems during their actual industrial application is that the refining effects are sensitive to the cooling rates. For instance, when the Al5TiB grain refiner is applied in A356 automotive wheel by the low pressure die casting (LPDC) technology, the refining effect is met in the thin-walled regions of the wheel, such as the rims with a high cooling rate. However, the grain size in the thick walled regions, such as the wheel spokes, could be as high as 2–3 mm, and these regions possess a low cooling rate. The sensitivity of the grain refining effects to the cooling rate leads to a significant variance in the mechanical properties of the different regions of the wheel.

However, the sensitivity of the RE-containing grain refiners to the cooling rate and its mechanism have not been investigated well. In particular, the refiner's cooling rate sensitivity during an actual industrial process of casting complex-shaped products with varying wall thickness has not been reported to date. Such information is of great importance in improving the comprehensive mechanical properties of complex-shaped alloy products during an actual industrial application.

Therefore, in this work, the cooling rate sensitivity of AlTiB–RE, RE, and conventional AlTiB refiners has been investigated via designed experiments in the laboratory and actual industrial applications of the A356 alloy automotive wheel produced by the LPDC technology. The results from these three cases were compared, and the impact mechanisms on the microstructure and mechanical properties of the A356 alloy were accordingly discussed.

2 Experimental Procedure

2.1 Refining Effect

The raw material used in this study was a commercial A356 alloy with a chemical composition given in Table 1. Melting was performed in an electrical resistance furnace at (740 ± 5) °C. Three different types of the grain refiners, i.e., Al5TiB, RE, and AlTiB–RE were added to the Sr-modified A356 alloy melt. The holding time was 30 min. The RE was mischmetal and contained 60% Ce and 40% La elements. The addition of the AlTiB–RE refiner was in the form of combined use of Al5TiB and Al10RE master alloy to minimize the formation of AlSiTiRE intermetallic compounds with large size. The concentrations added were 0–0.4 wt% for RE and 0–1 wt% for Al5TiB.

To evaluate the cooling rate sensitivity of the grain refiners, the alloy melt was poured into a taper-shaped graphite mold, as shown in Fig. 1a. Using this configuration of a mold, the cooling rate decreases with the increase in the thickness of the samples. K-type thermocouples were inserted at different locations of the mold and connected to a data acquisition system to record the solidification parameters during the cooling process. The cooling curves are shown in Fig. 1b, and the average cooling rates ranged from 1.5 to 32 °C/s.

2.2 Industrial Applications

The industrial applications of the refiners were carried out in the SMX Dicastal Wheel Manufacture Company. The A356 automotive wheels with 35.56 cm (14 in.) in diameter and 11.43 cm (4.5 in.) in width were casted by the LPDC technique. The alloy wheel with a conventional concentration of 0.3 wt% Al5TiB refiner was firstly produced as a reference. AlTiB–RE with concentration of 0.3 wt% was added to the 1200-kg weighted tundish. The holding time of the refiners in tundish was about 30 min. After degassing and deslagging, the molten A356 alloy in the tundish was transferred to the electrically heated holding furnace. The injection temperature of LPDC was approximately (695 ± 5) °C. The process began with the pressurization of the furnace. The increased pressure in the furnace forced liquid aluminum up transfer tubes into the die cavities, where it was cooled and solidified by the transfer of heat from the aluminum to the die and subsequently out to the environment. After the solidification was complete, the side dies opened, and the top die was raised vertically. The wheel was ejected onto a transfer tray. Next, the die was closed, and the cycle began again. Typical cycle time is 5–6 min. Then the wheel was subjected to a T6 heat treatment. The details of the T6 treatment are listed

Table 1 Chemical composition of A356 alloys (wt%)

Si	Mg	Ti	Sr	Fe	Cu	Mn	Zn	Ga	Al
7.190	0.263	0.112	0.0146	0.111	<0.001	0.007	<0.001	0.0111	Bal.

Fig. 1 **a** Schematic of taper-shaped graphite mold and thermocouple positions; **b** Cooling curves of different sections with various diameters in the mold. The *inset* further reveals the measured average cooling rates**Table 2** Detailed conditions for the solution treatment and artificial aging during T6 treatment

Solution treatment		Artificial aging	
Temperature (°C)	Time (min)	Temperature (°C)	Time (min)
540	240	155	180

in Table 2. The concentrations of RE in final wheels were measured by an inductively coupled plasma-atomic emission spectroscopy (ICP-AES) apparatus. The samples taken from the hub, spoke, and the rim sections of the wheels were processed for microstructural and mechanical analysis (Fig. 2). The tensile samples were of a plate-type, and the gauge length and width were 30 and 6 mm, respectively. The approximate cooling rates of hub, spoke, and the rim sections calculated according to the size of secondary dendrite arm spacing were 0.26, 0.54, and 4.2 °C/s, respectively.

2.3 Microstructural Analysis

The samples were mechanically polished following standard metallographic procedures. The samples for the grain size analysis were etched using a mixture of HCl and HNO₃ (HCl:HNO₃ = 3:1) for 20–60 s. Average grain size values were obtained using a linear intercept method. Microscopic observation was performed by using an OLYMPUS-BX51 M optical microscope. The microstructure of the samples was characterized by an electron probe micro-

Fig. 2 Positions on the hub, spoke, and the rim regions from where the samples were taken

analyser (EPMA, JEOL JXA-8100). Elemental compositions were analyzed by an energy-dispersive spectrometer (EDS, Oxford INCA PentaFET-x3).

2.4 Mechanical Tests

An extensometer (INSTRON 8801) was used to perform tension tests at the room temperature under a strain rate of 2.7×10^{-4} . The cross-head speed was 1 mm/min. The strain was measured over a gauge length of 30 mm. Proof stress of 0.2% was reported as the yield stress. The hardness of the A356 alloy was measured using an HB-

Fig. 3 Typical optical micrographs of the samples without and with grain refiners at 3 °C/s: **a** without refiners; **b** 0.3 wt% AlTiB; **c** 0.3 wt% RE; **d** 0.3 wt% AlTiB–RE

3000 hardness testing machine with an indentation load of 250 kg for 15 s. At least six samples were analyzed for each of the tensile and the hardness tests.

3 Results

3.1 Refining Effect of Different Grain Refiners

The typical optical micrographs of the A356 alloy samples without any refiner addition and that of the samples containing AlTiB, RE, and AlTiB–RE grain refiners are shown in Fig. 3. The grain size of the A356 alloy that was refined after refining were added can be observed.

Figure 4 shows the variation of the average grain size with different content of the refiners under different cooling rates. The refining effect of AlTiB refiner increased with increasing AlTiB content at different cooling rates. When the alloy contained the RE refiner, it presented different refining characteristics at various cooling rates. In the case of relatively high cooling rates (17–32 °C/s), the refining effect increased with increasing RE content, as expected. In the case of 0.4 wt% RE at a cooling rate of 32 °C/s, the average grain size of the alloy decreased by 38.8% (from 273 to 167 μm). In the case of relatively low cooling rates (1.5–3 °C/s), the refining effect greatly declined and the refinement extent fluctuated between 1.8% and 7.9%.

For the AlTiB–RE refiner, refinement was much greater than the individual addition of the AlTiB refiner or the RE refiner at the same conditions. Also, the refinement level increased with increasing concentration of AlTiB–RE. The minimum grain size decreased to 119 μm by 56.4% at 32 °C/s. This finding indicated that the AlTiB and RE had synergistic refinement effects and AlTiB–RE is a highly effective grain refiner.

3.2 Cooling Rate Sensitivity of Grain Refiners

To discuss the sensitivity of different refiners to the cooling rate, the refining effects of three refiners with the same

concentrations (0.3 wt%) were compared under the same cooling conditions. Typical grain size versus cooling rate curves for the alloy samples are shown in Fig. 5a. It can be clearly observed that the cooling rate greatly affected the grain size of alloy. The average grain size decreased with increasing cooling rate.

Figure 5b shows the refining effect of different refiners as a function of the cooling rate. The refining level changes with a change in the cooling rate were almost linear for all the refiners. The cooling rate sensitivity of different refiners could be analyzed from the slopes of the lines. It can be clearly observed that the order of slopes was RE > AlTiB > AlTiB–RE, illustrating that the AlTiB–RE refiner showed the lowest sensitivity to the cooling rate among the three refiners.

Figure 6 shows the average grain sizes of different sections in the A356 alloy wheel produced by the LPDC technique with an addition of the AlTiB–RE refiner and the AlTiB refiner. When the cooling rate varied from the wheel hub to the inner rim sections, the average grain size decreased by 21.3% (from 549 to 432 μm) as the AlTiB refiner concentration increased in the alloy. The average grain size further decreased from 448 to 394 μm when the AlTiB–RE refiner was added. The extent of variation of the refining effect with the AlTiB–RE addition was only 10.6%–12.1%, while that with the addition of the AlTiB refiner was 43.2%–50.2% under the same cooling conditions. This showed that the AlTiB–RE refiner remarkably reduced the cooling rate sensitivity of the AlTiB grain refiner in an actual industrial practice.

3.3 Microstructure

Figure 7 shows the microstructure of different sections in the A356 alloy wheel with the addition of AlTiB–RE and conventional AlTiB refiners. Table 3 lists the chemical compositions of the typical phases in Fig. 7. The microstructure of the wheels consisted of α-Al dendrites, surrounded by well-modified eutectic Si particles, and Fe-based intermetallic compounds. Typical needle-shaped β-(Al₅FeSi) phase (A phase) with approximately 200 μm in

Fig. 4 Average grain size with varying refiner contents and varying cooling conditions: **a** 1.5 °C/s; **b** 3 °C/s; **c** 17 °C/s; **d** 32 °C/s

Fig. 5 **a** Typical average grain size as a function of the cooling rate for the samples without a refiner and the samples with the addition of different refiners. The addition concentration was 0.3 wt% for each refiner; **b** Refining effect of different refiners as a function of the cooling rate

length was detected in the alloy refined by AITiB, which had an adverse effect on the alloy properties. After the AITiB–RE refiner was added into the alloy, the α -Al refined with better modification of the eutectic Si. The size of β -(Al₃FeSi) phase decreased noticeably (D phase). Moreover, block-like AlSiTiRE intermetallic compounds

(B and C phases) were formed. The compounds were predominantly present in the interdendritic regions, not only in the spokes but also in the rims.

However, when the content of RE further increased to 0.16 wt%, ribbon-shaped REFeSiTiSr compounds (E phase) with a size of approximately 50 μ m were formed.

Fig. 6 Average grain sizes of different sections of the wheel made of A356 alloy with an addition of AlTiB-RE and conventional AlTiB refiners

3.4 Mechanical Properties

The mechanical properties of different sections of the A356 alloy wheel with the addition of AlTiB and AlTiB-RE refiners are shown in Fig. 8. Compared to the alloy refined by AlTiB, the properties of the alloy wheel refined by AlTiB-RE refiner significantly were improved. With an

Table 3 Chemical compositions of typical phase in Fig. 7 (at.%)

Phase	Al	Si	Mg	Sr	La	Ce	Fe	Ti
A	68.07	17.21					14.72	
B	74.25	14.51	0.83		2.01	5.88	1.28	
C	60.72	18.00		1.35	0.61	0.97	15.48	2.77
D	70.12	16.22					13.65	
E	37.09	40.06	0.97	0.60	3.46	7.75	11.07	

increase in the RE content, from 0 to 0.11 wt%, the properties gradually were improved. The tensile strength of the spoke and the inner rim were improved by 11.3% (from approximately 230–256 MPa) and by 3.7% (from approximately 270–280 MPa), respectively. The tensile strength difference between the spoke and the inner rim decreased from 14.8% to 8.6% because of the RE addition. The yield strength of the spoke and the inner rim increased from approximately 148 and 215 MPa to 164 and 225 MPa, respectively. This increase was equivalent to an increase by almost 10.8% and 4.7%, respectively. The difference between the spoke and the inner rim decreased from 31.2% to 27.1%. The elongation also increased by approximately 44.1% (spoke) and 9.2% (inner rim), and the difference between the elongation of the two sections decreased from

Fig. 7 Microstructure of different sections of the A356 alloy wheel with the addition of AlTiB and AlTiB-RE refiners: **a** spoke with the addition of the AlTiB refiner; **b** spoke with the addition of the AlTiB-0.11% RE refiner; **c** spoke with the addition of the AlTiB-0.16% RE refiner; **d** inner rim with the addition of the AlTiB refiner; **e** inner rim with the addition of the AlTiB-0.11% RE refiner; **f** a typical higher magnification of **e**

Fig. 8 Mechanical properties of the A356 alloy wheel with different refiners

47.7% to 30.9%. The hardness of the alloy wheel increased slightly.

These results suggest that the improvement levels for the wheel spokes with a low cooling rate were considerably greater than those of the other parts with a higher cooling rate. Thus, this effect decreased the difference between the properties at different positions within the wheel possessing different cooling rates.

However, the results showed that the mechanical properties became worse when the content of RE in the AlTiB–RE grain refiner reached 0.16 wt%. This trend was similar to the refining effects of AlTiB and AlTiB–RE refiners in the A356 alloy wheel (Fig. 6).

4 Discussion

From the experimental and industrial results of the A356 alloy wheel, it can be noted that the AlTiB–RE refiner had better refinement effects than the RE and the conventional AlTiB refiners. The comprehensive properties of the alloy wheel refined by the AlTiB–RE refiner, especially in the spoke, which influenced the properties of the whole wheel to the greatest extent, were significantly improved. Also, the difference between the properties at different locations

within the wheel with varying cooling rates decreased. This finding might be due to the lower cooling rate sensitivity of the AlTiB–RE grain refiner than that of the AlTiB refiner.

According to the phase diagram, the solid solubility of RE in α -Al was very low, measuring approximately 0.05 wt% at the eutectic temperature [16]. During the nucleation and growth, RE easily gathered in the front of the solid–liquid interface because of the solute redistribution. According to the report of Wang *et al.* [10], the value of constitutional supercooling parameter of RE (C_e) was much higher than that of other elements such as Ti and Fe. Thus, a strong constitutional undercooling occurred, which decreased the growth rate of the growing interface and restricted the growth of nucleation of α -Al. Next, the enriched RE adsorbed concentrated alloy elements, such as Ti, Fe and Si, resulting in the changing concentration gradient of the solid–liquid interface. The undercooling changed with the concentration gradient. Tsai *et al.* [15] showed the thermal analysis curves of A356 alloy with the addition of La during solidification. The eutectic growth temperature of A356 alloy was 577 °C. Upon adding 1.0 wt% La in the alloy, the eutectic growth temperature was lowered to 562 °C. From the cooling curves and the undercooling could be calculated [17, 18]. The results showed that the undercooling for α -Al nucleation decreased due to RE addition. Therefore, the

heterogeneous nucleation of α -Al after adding AlTiB–RE refiner could occur at a lower degree of undercooling. The extent of undercooling was proportional to the efficiency of the grain refiner in providing potent nucleating sites [19, 20]. Thus, AlTiB–RE grain refiner showed lower cooling rate sensitivity than the AlTiB alone.

In addition, the AlSiTiRE intermetallic compounds in the microstructure (Fig. 7) exhibited a high melting point and could also act as heterogeneous nucleation sites for α -Al nucleation. It consequently suppressed the growth of α -Al, which was also confirmed by Zhao *et al.* [21]. Furthermore, the composition and size of β -(Al₅FeSi) changed, which weakened the influence of β -(Al₅FeSi), contributing to the property improvement.

However, if the RE content was too high, the volume fraction and the size of the RE-containing intermetallic compounds in the alloy exceeded a certain value, the microstructure and mechanical properties of the alloy were affected because the RE-containing compounds lost the heterogeneous nucleation effect. The similar phenomenon was also identified when Er was added in A356 alloy, as shown by Shi *et al.* [22]. Especially, in the case of using Sr as a modifier, the excess RE would react with Sr to form RE–Sr containing intermetallic phase with a size of approximately 50 μ m, affecting the modification effect of eutectic Si, as evidenced by Fig. 7. Therefore, the refining effects and the corresponding properties of the alloy with the addition of AlTiB–RE presented the tendency of increase and subsequent initial decrease with increasing RE content.

5 Conclusions

1. Among three different types of the grain refiners, AlTiB–RE refiner was less sensitive to the cooling rate than the AlTiB refiner and the RE refiner. AlTiB and RE exhibited synergetic refining effects than the individual refiners of AlTiB or RE.
2. With the cooling rate variation from the wheel hub to the inner rim sections, the variation extent of refinement effect with the addition of the AlTiB–RE refiner was only 43.2%–50.2% of the alloy with the addition of the conventional AlTiB refiner.
3. In comparison with the alloy wheel with an addition of the conventional AlTiB refiner, the comprehensive properties of the alloy wheel with the addition of the AlTiB–RE refiner were improved significantly. The improvement in the tensile strength, yield strength, and elongation in the spoke with a low cooling rate was of

approximately 11.3, 10.8, and 44.1%, respectively. This improvement was considerably greater than that in the other parts of wheel with a high cooling rate. The difference between the values of the tensile strength, yield strength, and elongation at different positions of the wheel decreased from 14.8%, 31.2%, and 47.7% to 8.6%, 27.1% , and 30.9%, respectively.

Acknowledgment This work was financially supported by the National High Technology Research and Development Program (No. 2013AA031002).

References

- [1] M. Zhu, Z.Y. Jian, G.C. Yang, Y.H. Zhou, *Mater. Des.* **36**, 243 (2012)
- [2] Q. Liu, H. Zhang, Y.X. Cui, Q.C. Li, *Scr. Mater.* **25**, 371 (1991)
- [3] H.R. Sergio, E.G. Rafael, K.D. Dheerendra, H.B. Víctor, F.Z. Horacio, J.P.L. María, *Mater. Des.* **32**, 1865 (2011)
- [4] C.W. Liao, J.C. Chen, Y. Li, R. Tu, C.X. Pan, *J. Mater. Sci. Technol.* **28**, 524 (2012)
- [5] Y.F. Han, K. Li, J. Wang, D. Shu, B.D. Sun, *Mater. Sci. Eng. A* **405**, 306 (2005)
- [6] M. Nowak, L. Bolzoni, B.N. Hari, *Mater. Des.* **66**, 366 (2015)
- [7] W. Schneider, M.A. Kearns, M.J. McGarry, A.J. Whitehead, in *A Comparison of the Behaviour of AlTiB and AlTiC Grain Refiners, Light Metals*, ed. by B.J. Welch (Warrendale, PA: TMS, 1998), pp. 953–961
- [8] A.L. Greer, A.M. Bunn, A. Tronche, *Acta Mater.* **48**, 2823 (2000)
- [9] Q.Y. Xu, Y.J. Chen, T.Y. Huang, Chinese Patent ZL200610011786.2 May 2009
- [10] K. Wang, C.X. Cui, Q. Wang, S.J. Liu, C.S. Gu, *Mater. Lett.* **85**, 153 (2012)
- [11] K. Wang, C.X. Cui, Q. Wang, L.C. Zhao, Y. Hu, *J. Rare Earths* **31**, 313 (2013)
- [12] O.E. Sebaie, A.M. Samuel, F.H. Samuel, H.W. Doty, *Mater. Sci. Eng. A* **480**, 342 (2008)
- [13] J.H. Li, X.D. Wang, T.H. Ludwig, Y. Tsunekawa, L. Arnberg, J.Z. Jiang, P. Schumacher, *Acta Mater.* **84**, 153 (2015)
- [14] W.M. Jiang, Z.T. Fan, Y.C. Dai, C. Li, *Mater. Sci. Eng. A* **597**, 237 (2014)
- [15] Y.C. Tsai, C.Y. Chou, S.L. Lee, C.K. Lin, J.C. Lin, S.W. Lim, *J. Alloys Compd.* **487**, 157 (2009)
- [16] V. Raghavan, *J. Phase Equilibria Diffus.* **28**, 456 (2007)
- [17] L.Y. Zhang, Y.H. Jiang, Z. Ma, S.F. Shan, Y.Z. Jia, C.Z. Fan, W.K. Wang, *J. Mater. Process. Technol.* **207**, 107 (2008)
- [18] A. Abedi, M. Shahmiri, B.A. Esgandari, B. Nami, *J. Mater. Sci. Technol.* **29**, 971 (2013)
- [19] B.S. Murty, S.A. Kori, M. Chakraborty, *Int. Mater. Rev.* **47**, 3 (2002)
- [20] C.L. Xu, Q.C. Jiang, *Mater. Sci. Eng. A* **437**, 451 (2006)
- [21] H.L. Zhao, Y. Song, M. Li, S.K. Guan, *J. Alloys Compd.* **508**, 206 (2010)
- [22] Z.M. Shi, Q. Wang, G. Zhao, R.Y. Zhang, *Mater. Sci. Eng. A* **626**, 102 (2015)