Study on Micron Porous Copper Prepared by Physical Vacuum Dealloying

Yi-Bin Ren¹ · Yu-Xia Sun² · Ke Yang¹

Received: 30 June 2016/Revised: 8 September 2016/Published online: 31 October 2016
© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg 2016

Abstract Porous copper was prepared successfully by physical vacuum dealloying method using the CuZn alloy precursors (Cu30Zn70, Cu40Zn60 and Cu50Zn50 alloys). The micron porous copper showed a three-dimensional continuous porous structure with 1–5 μm pore size. With the increase of the Zn content in the CuZn alloy, the pore structure of the porous copper was more uniform and ordered. Temperature was the key factor for physical dealloying, and the optimized temperature was 500 °C for the CuZn alloy. The pores would fuse and disappear when the temperature was over 500 °C. Physical vacuum dealloying was an effective preparation method for porous copper, which can be used to prepare other porous metals based on the sublimation and the Kirkendall effect.

KEY WORDS: Dealloying; Sublimation; Kirkendall effect; Porous copper; Cu–Zn alloy

1 Introduction

Recently, porous metals have attracted much attention for applications such as lightweight structure, energy absorber, heat exchanger, biomaterial and catalysis. So far, various fabrication methods for porous metals have been developed [1–3], including foaming by gas bubbling, metal deposition on polyurethane foam by electroplating, powder sintering, dealloying.

Porous copper is an interesting electrode material for the electrolysis process, and the porous copper electrode was prepared by selective dissolution of aluminum from CuAl₂ alloy in NaOH solution [4]. Nakajima [1] investigated the fabrication of porous copper by unidirectional

solidification under hydrogen, and the pore diameter ranged from 5 μm up to 5 mm. The lost carbonate sintering (LSC) process was also used for manufacturing open cell copper foams [5], with a size ranged from 53 μm up to 1.5 mm.

Additionally, porous copper can be prepared by electrochemical dealloying of the CuZn alloy in many kinds of solutions [6, 7]. Porous copper prepared by dealloying was usually nanoporous copper (NPC), and several alloy systems including AlCu, CuZn, CuZr, MnCu and MgCu have been successfully developed [6–11].

Dealloying has demonstrated to be very efficient in producing three-dimensional (3D) porous metals [12, 13]. At present, the NPCs were prepared usually by selective dissolution of one metal element which was out of a binary alloy based on chemical or electrochemical principle. Recently, we have developed a novel physical dealloying method to prepare micron porous metals in vacuum environment [14–16].

Physical vacuum dealloying (PVD), or physical sublimation dealloying (PSD), is a common process by subliming one or more metal components from an alloy to form a porous metal. The precursor alloy must contain

Available online at <http://link.springer.com/journal/40195>

✉ Yi-Bin Ren
yibren@imr.ac.cn

¹ Institute of Metal Research, Chinese Academy of Sciences, Shenyang 110016, China

² Shenyang Aerospace University, Shenyang 110136, China

more than one metal element with a high vapor pressure, and at a specified temperature in vacuum environment, the matrix metal will undergo sublimation and diffusion to form voids and finally form a 3D micron porous structure with interconnected ligaments. In this study, a micron porous copper was fabricated using Cu30Zn70, Cu40Zn60 and Cu50Zn50 alloys by physical dealloying method and the microtopography and some influence factors were studied.

2 Experimental

The Cu30Zn70, Cu40Zn60 and Cu50Zn50 precursor alloys were fabricated by heating Cu powders and Zn blocks with atomic ratio of 3:7, 4:6 and 5:5 in a nitrogen atmosphere, respectively. The temperature of furnace containing Cu and Zn was raised to 900 ± 50 °C and held for 0.5 h; then the melt was cast in the graphite crucible and finally cooled down to ambient temperature. The samples with a dimension of 5 mm × 5 mm × 0.5 mm were sectioned from ingots by wire-electrode cutting, and the samples were polished with SiC papers of 1000 grit size and rinsed with absolute ethyl alcohol before physical dealloying.

The physical sublimation dealloying experiments were performed, respectively, at 500, 600 and 700 °C in dynamic high vacuum environment for 3 h, and the vacuum during experiment was kept under 10 Pa or lower. Three different samples were used for each test condition, and the measured results of the pore size distribution were average. The surface morphology, composition, and crystal structure of the physical dealloyed samples were characterized by scanning electron microscopy (SEM) equipped with energy dispersive X-ray spectroscopy (EDS) and X-ray diffraction (XRD) respectively.

3 Results

After the physical vacuum dealloying processes, colors of all the samples were changed from silver-white to red under naked eye observation. Figure 1 shows the XRD patterns of the as-prepared Cu50Zn50, Cu40Zn60 and Cu30Zn70 precursor alloys and the micron porous copper from Cu30Zn70 alloy at 500 °C. Prior to dealloying, the samples of Cu50Zn50, Cu40Zn60 and Cu30Zn70 alloys contained different single phases with diffraction peaks, respectively, corresponding to Cu_{1.05}Zn_{0.95} (JCPDS Card No. 65-9060), CuZn (JCPDS Card No. 65-6321) and Cu₅Zn₈ (JCPDS Card No. 65-3157), as shown in Fig. 1a–c, which reveals that the Cu50Zn50, Cu40Zn60 and Cu30Zn70 precursor alloys should mainly consist of Cu_{1.05}Zn_{0.95}, CuZn and Cu₅Zn₈ phases, respectively.

Fig. 1 XRD patterns of Cu50Zn50, Cu40Zn60 and Cu30Zn70 precursor alloys before (a–c), after (d) physical vacuum dealloying

After the physical vacuum dealloying, the polycrystalline pure Cu phase (JCPDS Card No. 65-9743) can be seen, as shown in Fig. 1d.

Figures 2, 3 and 4 show the surface SEM images of the Cu50Zn50, Cu40Zn60 and Cu30Zn70 alloys after physical vacuum dealloying at 500 °C, respectively. Figures 2a, 3a and 4a are the as-prepared micron porous copper, and Figs. 2b, 3b and 4b are the partial enlarged view of Figs. 2a, 3a and 4a. EDS analyses (Figs. 2c, 3c, 4c) show that almost all Zn on the surface of alloys were complete sublimated. The widths of channel and ligament of micron porous copper of Cu50Zn50 alloy are 3 ± 1 μm, and the diameter of pore is 1 ± 1 μm.

With increasing the Zn content in the alloy, the widths of the channel and ligament of the micron porous copper were reduced from Cu40Zn60 alloy of 1 ± 0.5 μm to Cu30Zn70 alloy of 0.5 ± 0.5 μm, and the pore size increased from 2 ± 1 to 5 ± 1 μm. In addition, the micron porous copper from Cu30Zn70 alloy exhibited a well-developed three-dimensional continuous porous structure, and its relative density was about 30% of bulk Cu density, which was determined by the measured mass and calculated volume, demonstrating the complete sublimation of Zn and the existence of holes in the porous copper.

4 Discussion

The method used in this study is known as physical dealloying because the process just includes two physical reactions, sublimation and diffusion, which played a dominant role during the whole process. In brief, the formation of porous structure is a result of a competition between the selective sublimation and diffusion process of the alloy components. In addition to the CuZn alloy, this

Fig. 2 SEM images and EDS analysis of Cu50Zn50 alloy after physical vacuum dealloying

Fig. 3 SEM images and EDS analysis of Cu40Zn60 alloy after physical vacuum dealloying

Fig. 4 SEM images and EDS analysis of Cu30Zn70 alloy after physical vacuum dealloying

method can be also applied for the preparation of other porous metals [14]. In the present study, this method has demonstrated its effectiveness by three CuZn alloys, and the Zn was the key element in CuZn alloy to form the micron porous copper. Firstly, Zn has a high saturated vapor pressure, for instance 1 Torr at 487 °C [17], which makes it full sublimation at high temperature in vacuum environment. Secondly, the diffusion rate of Zn is much greater than that of Cu in the CuZn alloy [18]. Therefore, Zn can be rapidly sublimated from the surface of CuZn alloy at 500 °C in vacuum environment. Thirdly, according to Kirkendall effect, a large amount of vacancies or voids can be formed in the CuZn alloy because of the differential diffusion between Cu and Zn. Therefore the pores will be formed and start from the surface of the CuZn alloys

because of their great difference in the saturated vapor pressures, then the sublimation and the differential diffusion affected mutually to trigger dealloying to form the porous copper.

The Kirkendall effect is a classical phenomenon in metallurgy, which is a consequence of different diffusivities of atoms in a diffusion couple, causing a supersaturation of lattice vacancies. This supersaturation may lead to a condensation of extra vacancies in the form of so-called Kirkendall voids, and these Kirkendall voids are generally considered as a nuisance because they deteriorate the properties of the alloy. In contrast, the Kirkendall effect has been positively used as a new fabrication route to produce porous metal. The nanotubes and hollow nanoparticles based on the Kirkendall effect have been prepared, and

Fig. 5 SEM images of Cu₃₀Zn₇₀ alloy after physical dealloying at 600 (a), at 700 °C (b)

such an effect has become an interesting synthesis route to produce nanoscale hollow structures of various material systems [19, 20]. In this study, the combined effect of the sublimation and the differential diffusion (Kirkendall effect) of Zn in the CuZn alloy is used to produce the porous copper.

In our previous study, the temperature was also the key factor for physical dealloying [15], which was not only involved in the sublimation rate, but also affected the diffusivity of Zn in the CuZn alloy. Figure 5 shows the SEM images of the Cu₃₀Zn₇₀ alloy after physical vacuum dealloying at 600 and 700 °C, respectively. With increasing the vacuum heat treatment temperature, the pores of porous copper were fused gradually and even this alloy had relative large pores at 500 °C. According to the Kirkendall effect, the diffusivity of Zn would be increased with the increase in the temperature (the intrinsic diffusivity of Zn is about 2.5 times than that of Cu at 785 °C [20]), and the Kirkendall voids should be enlarged with increasing the temperature, but in fact they partly merged together. As we know, the diffusivity of Cu was also increased with increasing the temperature, and the most lattice vacancies formed in the migration of Zn would be occupied by Cu atoms, which should be more active at higher temperature. Therefore, many small Kirkendall voids disappeared. So the physical dealloying can occur at an optimized temperature in vacuum environment for the some special alloys, and the temperature was about 500 °C for the CuZn alloy in the present study.

5 Conclusion

This study showed that the micron porous copper could be prepared by physical vacuum dealloying of the CuZn alloy. The micron porous copper showed a three-dimensional continuous porous structure with 1–5 μm pore size. With the increase of the Zn content in the CuZn alloy, the pore

structure of the porous copper becomes more even and orderly, and the temperature was the key factor for the physical dealloying process. The porous structure would be fused and disappeared when the treatment temperature was higher than the optimized temperature of 500 °C.

Acknowledgments This work was supported by the National Natural Science Foundation of China (Grant No. 31370976) and the National Basic Research Program of China (Grant No. 2012CB619101).

References

- [1]. H. Nakajima, *Prog. Mater. Sci.* **52**, 1091 (2007)
- [2]. P. Liu, B. Yu, A. Hu, K. Liang, S. Gu, *J. Mater. Sci. Technol.* **18**, 299 (2002)
- [3]. B. Li, X. Lu, *Acta Metall. Sin. (Engl. Lett.)* **27**, 338 (2014)
- [4]. A. Smith, D. Trimm, *Annu. Rev. Mater. Res.* **35**, 127 (2005)
- [5]. Y. Zhao, T. Fung, L. Zhang, *Scr. Mater.* **52**, 295 (2005)
- [6]. R. Mao, S. Liang, X. Wang, Q. Yang, B. Han, *Corros. Sci.* **60**, 231 (2012)
- [7]. Y. Lin, C. Tai, I. Sun, *J. Electrochem. Soc.* **154**, D316 (2007)
- [8]. J. Li, H. Jiang, N. Yu, C. Xu, H. Geng, *Corros. Sci.* **90**, 216 (2015)
- [9]. C. Zhao, Z. Qi, X. Wang, Z. Zhang, *Corros. Sci.* **51**, 2120 (2009)
- [10]. J. Hayes, A. Hodge, J. Biener, A. Hamza, K. Sieradzki, *J. Mater. Res.* **21**, 2611 (2006)
- [11]. H. Lu, Y. Li, F. Wang, *Scr. Mater.* **56**, 165 (2007)
- [12]. J. Erlebacher, M. Aziz, A. Karma, N. Dimitrov, K. Sieradzki, *Nature* **410**, 450 (2001)
- [13]. A. Chen, S. Shi, Y. Qiu, X. Xie, H. Ruan, J. Gu, D. Pan, *Microporous Mesoporous Mater.* **202**, 50 (2015)
- [14]. Y. Ren, Y. Sun, K. Xiao, K. Yang, *Chinese invention patent*. 201410181273.0 (2014)
- [15]. Y. Sun, Y. Ren, K. Yang, *Mater. Lett.* **165**, 1 (2016)
- [16]. Y. Sun, Y. Ren, *Vacuum* **122**, 215 (2015)
- [17]. R.E. Honig, D.A. Kramer, *RCA Rev.* **30**, 285 (1969)
- [18]. E. Kirkendall, L. Thomassen, C. Upthegrove, *Trans. AIME* **133**, 186 (1939)
- [19]. Y. Yin, R. Rioux, C. Erdonmez, S. Hughes, G. Somorjai, A. Alivisatos, *Science* **304**, 711 (2004)
- [20]. H. Fan, U. Gösele, M. Zacharias, *Small* **3**, 1660 (2007)