Correlations of Ni Contents, Formation of Reversed Austenite and Toughness for Ni-Containing Cryogenic Steels

Meng Wang¹ · Zhen-Yu Liu¹ · Cheng-Gang Li¹

Received: 23 June 2016/Revised: 13 August 2016/Published online: 8 October 2016
© The Chinese Society for Metals and Springer-Verlag Berlin Heidelberg 2016

Abstract It has been widely demonstrated that addition of Ni in low-carbon steels can effectively improve the cryogenic toughness, but the mechanism behind it has yet to be clarified. In the present work, the evolutions of microstructure and mechanical properties after quenching and tempering for Ni-containing cryogenic steels with different Ni contents (3.5–9 wt%) were investigated. The results showed that after quenching and tempering, the Ni-containing cryogenic steels were composed of tempered martensite and reversed austenite. The volume fraction of reversed austenite has increased from 0 up to 6.3% when the Ni content increases from 3.5% to 9%. The Charpy impact tests indicated that the low-temperature toughness was markedly improved with the increase in Ni content, which can be correlated with the increase in reversed austenite amount. The main contribution of reversed austenite to the toughness lies in: (1) the elimination of cementite precipitates improved the plastic deformation capacity of matrix, and (2) the crack propagation is hindered through plastic deformation.

KEY WORDS: Ni-containing cryogenic steel; Microstructure; Reversed austenite; Impact toughness; Crack propagation

1 Introduction

Ni-containing cryogenic steels have been widely used to build liquefied gas storage tanks, because these steels possess excellent toughness, high strength and ductility [1–4]. In order to ensure the safety of these tanks, the ductile-to-brittle transition temperatures (DBTTs) for Ni-containing cryogenic steels must be lower than the service temperatures by more than 20 °C to prevent abrupt brittle

fracture. The low-temperature toughness of Ni-containing cryogenic steels is mainly affected by their microstructural features such as the matrix structure, the size and distribution of cementite, and the amount of reversed austenite (γ') [5–7].

Numerous studies on the microstructure characteristics and mechanical properties of Ni-containing cryogenic steels have been conducted. Strife and Passoja [8] investigated the cryogenic fracture properties of Fe–Ni alloys containing 5.5% and 9% Ni after the quenching and tempering (QT) treatment and found that the addition of Ni could improve the cryogenic toughness. Wu et al. [5] employed a QLT treatment which consists of quenching (Q), intercritical quenching (L) and tempering (T) to produce a high-nickel steel containing 4.5% Ni and found that QLT treatment provided a better cryogenic toughness than QT treatment. Nakada et al. [9] reported that the strength and ductility could be improved by copper addition in 9% Ni steels. However, very few efforts have been focused on

Available online at <http://link.springer.com/journal/40195>

✉ Meng Wang
wmang87@126.com

✉ Zhen-Yu Liu
zylu@mail.neu.edu.cn

¹ State Key Laboratory of Rolling and Automation,
Northeastern University, Shenyang 110819, China

the effect of Ni on microstructures and low-temperature toughness during QT treatment. Therefore, in order to further optimize the designs of compositions and heat treatments for getting better properties, the mechanisms for the improvement in cryogenic toughness of low-carbon steels by addition of Ni need to be intensively clarified.

The purpose of this study was to investigate the effects of Ni addition on the low-temperature toughness of Ni-containing cryogenic steels. The toughening mechanism by Ni addition was discussed in terms of the microstructural characteristics induced by Ni elements.

2 Experimental

Steels with different Ni contents (3.5, 5, 7 and 9 wt%) were selected for this investigation. Table 1 shows the chemical compositions of the steels, which share the same compositions except Ni contents. The steels were melted in a vacuum induction furnace and cast into ingots, which were forged into plates with a size of 80 mm × 100 mm × 200 mm. The plates were homogenized at 1200 °C for 2 h and then hot-rolled to the bands with a thickness of 15 mm by using a two-high pilot rolling mill with the reduction schedule of 100 mm → 80 mm → 62 mm → 47 mm → 35 mm → holding delay → 26 mm → 19 mm → 15 mm. After finishing the rolling, the hot bands were rapidly cooled from 820 °C to the room temperature.

Heat treatments for quenching and tempering were carried out in a box-type resistance furnace. Through a lot of tests and analyses, the optimized parameters for the nickel-containing cryogenic steels were worked out. Table 2 shows the main heat treatment parameters.

Table 1 Chemical composition of Ni-containing cryogenic steels (wt%)

Alloy	C	Mn	Si	Ni
3.5Ni	0.058	0.73	0.23	3.42
5Ni	0.057	0.71	0.21	5.07
7Ni	0.062	0.72	0.17	7.11
9Ni	0.055	0.71	0.20	8.93

Table 2 Heat treatment process parameters

Alloy	Austenitizing temperature (°C)	Holding time (min)	Tempering temperature (°C)	Holding time (min)
3.5Ni	810	40	610	60
5Ni	810	40	610	60
7Ni	830	40	600	60
9Ni	830	40	600	60

The tensile testing specimens with a diameter of 8 mm and length of 40 mm were cut from the hot-rolled bands along their rolling directions. The tensile tests were conducted at room temperature with an INSTRON universal testing machine at a crosshead speed of 5 mm/min. The V-notch samples for Charpy impacting tests were machined in standard size of 10 mm × 10 mm × 55 mm, and the Charpy impact tests were performed in the temperatures range from −196 °C to −70 °C by using an INSTRON 9250HV impact tester machine. Three specimens for tensile tests and Charpy texts were used. The strength and toughness data were the average values of three measurements.

The specimens for microstructural studies were mechanically ground, polished, etched with 4% nital solution and observed via a JXA-8530F electron probe microanalyzer (EPMA). Electron backscattered diffraction (EBSD) analysis was carried out using a Zeiss Ultra-55 field emission scanning electron microscope (SEM) at an accelerating voltage of 20 kV. X-ray diffraction (XRD) analysis was carried out to determine the volume fraction of reversed austenite in a D/max2400 X-ray diffractometer. The peak intensity of $\{200\}_\gamma$, $\{220\}_\gamma$, $\{311\}_\gamma$, $\{200\}_\alpha$ and $\{211\}_\alpha$ were chosen to calculate the amount of austenite [10, 11]. The specimens for EBSD and XRD analysis were electropolished with an electrolyte consisting of 100 ml perchloric acid and 700 ml alcohol at 27 V for 35 s. A TECNAI G220 transmission electron microscopy (TEM) was used to investigate the morphology of reversed austenite and carbide, which was operated at 200 kV. Thin foils for TEM were prepared on a twin-jet electropolisher at 32 V using a solution of 8% perchloric acid and 92% anhydrous ethanol. The fracture surface of Charpy impact specimens was characterized by an FEI Quanta600 SEM.

3 Results and Discussion

3.1 Effect of Ni Content on Microstructures Evolution

Figure 1 shows SEM micrographs of the Ni-containing cryogenic steels after quenching and tempering heat treatment. Each specimen showed typical tempered

Fig. 1 SEM micrographs of **a** 3.5Ni, **b** 5Ni, **c** 7Ni, **d** 9Ni steels after quenching and tempering treatments

martensite microstructure consisting of martensite lath and cementite distributed in the matrix. The cementite presents as fine white islands that are mainly located at lath boundaries. Besides, previous studies have shown that reversed austenite is precipitated in 9Ni steel after quenching and tempering heat treatment [12, 13].

Because the reversed austenite is difficult to distinguish through SEM micrographs, we used EBSD analysis to observe its morphology and distribution; the results are shown in Fig. 2. Reversed austenite can be observed in 5Ni, 7Ni, and 9Ni steels, but not in the 3.5Ni steel. The Ni-enriched regions transform into austenite, when the tempering temperature is close to A_{c1} . The mechanism of this transformation is diffusional reversion. The alloy elements, such as C, Mn and Ni, are partitioned from the martensite matrix to the reversed austenite during the tempering process. These elements help to stabilize the reversed austenite and prevent the transformation of austenite to martensite upon cooling to ambient temperature. Most of the reversed austenite in 3.5Ni steel retransformed to fresh martensite upon cooling due to the low Ni content, thus the lack of reversed austenite in 3.5Ni steel.

Figure 2 also shows that the reversed austenite mainly located on martensite packet boundaries or prior austenite

grain. The literature suggested that the main reason for this is that these boundaries are low-energy sites for heterogeneous nucleation [14, 15]. The growth of the reversed austenite is controlled by a diffusional process rather than a shear process in this work [16, 17]. The reversed austenite formed on boundaries could more easily grow up as the diffusion along grain boundaries is more rapid. There were no significant changes in distribution or morphology as Ni content increased from 5% to 9%, but the size of the reversed austenite did increase as Ni content increased. The size distributions of the reversed austenite are shown in Fig. 2e. It can be seen that the sizes of reversed austenite are mainly concentrated on ~ 0.1 – 0.2 μm . The average sizes of reversed austenite grain of 5Ni, 7Ni and 9Ni steels measured by EBSD were 0.18, 0.22 and 0.26 μm , respectively.

However, some reversed austenite with the size smaller than 100 nm cannot detect by EBSD as its step size is 0.1 μm . XRD is used to determine the content of reversed austenite. Figure 3 shows the change in the volume fraction of the reversed austenite with the function of Ni content. It indicates that the volume fraction of the reversed austenite lineally increased with increasing Ni content.

The detailed microstructure of the tempered martensite and the reversed austenite was next further examined by

Fig. 2 EBSD analysis results of **a** 3.5Ni, **b** 5Ni, **c** 7Ni, **d** 9Ni steels (red color corresponds to fcc austenite phase), **e** the size distribution of the reversed austenite

TEM. Figure 4a shows that 3.5Ni steel was characterized by martensite lath structure and fine cementite distribute in the matrix. The cementites precipitated at lath boundaries were larger than those in the lath interiors. Some lath

boundaries were blurred due to the movement of the dislocation. The microstructure did not significantly change when Ni content increased to 5% (Fig. 4b). The corresponding selected area diffraction pattern obtained from

Fig. 3 Volume fraction of the reversed austenite as a function of Ni content

one of the precipitations (denoted by white circle) indicated that those carbides were cementites. Compared to the 3.5Ni specimens, the quantity of cementites slightly decreased once the Ni content increased to 5%. As Ni content continuously increased, the number of the cementite precipitations obviously decreased (Fig. 4e, f). It can also be seen that the blocky shape reversed austenite was formed along martensite packet boundaries in 5Ni, 7Ni and 9Ni steels (Fig. 4c–e).

The decreased quantity of cementite precipitations can be attributed to the formation of the reversed austenite. Because C, Mn and Ni alloy elements have a relative higher solubility in the austenite with face-centered cubic structure than in the martensite with body-centered cubic structure under equilibrium condition [13], during tempering process, the alloy elements will be redistributed. The EPMA line scan analyses of C, Mn and Ni element for 3.5Ni and 7Ni steel after quenching and tempering treatment are displayed in Fig. 5. Figure 5a shows that the supersaturated carbon atoms in the martensite matrix precipitated as the cementite, but the Mn and Ni contents in the cementite were lower than those in the matrix. Figure 5b shows that the C, Mn and Ni segregated into the reversed austenite during tempering. The carbon concentration in the matrix adjacent to the reversed austenite was reduced because the carbon atoms were depleted by the

reversed austenite. Consequently, very little cementite precipitations were observed in the 7Ni and 9Ni steels.

3.2 Effect of Ni Content on Strength

The tensile test results of the four test steels are shown in Fig. 6. It is found that the yield and tensile strengths increase with the increase in Ni content. In this study, the variation of the strength was mainly affected by the Ni content and the change in the microstructure. The literature suggests that Ni element could enhance the strength by solution strengthening, and the solution strengthening effect is proportional to the Ni content [18, 19]. However, Fig. 6 shows that the strength increased nonlinearly with increasing Ni content. The strength increased slowly when Ni content increased from 5% to 7%. This can be attributed to the decrease in the amount of the cementite. The cementite could inhibit the dislocation motion, thus increased the strength of matrix [20]. And the effect of precipitation strengthening increased with the increase in volume fraction of the cementite. As mentioned above, the quantity of the cementite markedly decreased once Ni content increased from 5% to 7%. This led to a significant decrease in precipitation strengthening. The mutual effects of solution strengthening and precipitate strengthening caused the slow increase in the strength when Ni content increased from 5% to 7%.

3.3 Effect of Ni Content on Impact Toughness

The variations of Charpy absorbed energy within the test temperature range for the four test steels are presented in Fig. 7a. The Charpy absorbed energies of 3.5Ni and 5Ni steels significantly decreased as test temperature decreased. The fracture mechanisms of both steels changed from ductile to brittle. By contrast, the Charpy absorbed energies of 7Ni and 9Ni steels decreased only slightly with increasing the tested temperature. Figure 7b shows that the cryogenic impact energy ($-196\text{ }^{\circ}\text{C}$) linearly increased as Ni content increased.

The total impact energy is composed of crack initiation energy and crack propagation energy [21–23]. Table 3 lists the total impact energy and corresponding crack initiation energy and crack propagation energy for the four test steels fractured at $-196\text{ }^{\circ}\text{C}$, demonstrating that as Ni content

Fig. 4 TEM micrographs of **a** 3.5Ni, **b**, **c** 5Ni, **d** 7Ni, **e** 9Ni steels after quenching and tempering treatments

Fig. 5 EPMA line scan analyses of C, Ni and Mn: **a** 3.5Ni, **b** 7Ni steel

Fig. 6 Variation of strengths and elongation with Ni content

increased, the crack propagation energy significantly increased while the crack initiation energy only increased slightly.

3.4 Toughening Mechanisms

The changes in low-temperature toughness of the test steels can be related to the variation in microstructures. Therefore, in the present study, we focused on the effect of Ni content on low-temperature toughness in terms of the variations in reversed austenite content induced by Ni elements. The correlation between the impact energy at -196°C and volume fraction of reversed austenite is presented in Fig. 8. It indicated that the low-temperature toughness increased with the increase in reversed austenite content. Previous studies have made similar observations

Fig. 7 Variations of Charpy impact energy of test steels with the function of **a** test temperature and **b** Ni content

Table 3 Percentage of total absorbed fracture energy, initiation energy and propagation energy for four test steels fractured at $-196\text{ }^{\circ}\text{C}$

Alloy	Total absorb energy (J)	Initiation energy (J)	Propagation energy (J)	Propagation to total absorb energy (%)
3.5Ni	12	7	5	41.7
5Ni	35	17.9	17.1	48.9
7Ni	133	39	94	70.7
9Ni	196	53.6	142.4	72.7

Fig. 8 Variations of Charpy impact energy with the function of the volume fraction of reversed austenite

[24, 25]. The empirical relationship between the two variables is expressed as follows:

$$E_V = 10 + 11.1V_{\gamma'} + 3V_{\gamma'}^2, \quad (1)$$

where E_V is the impact energy and $V_{\gamma'}$ is the volume fraction of reversed austenite.

The SEM fractographs of the Charpy V-notch (CVN) impact specimens fractured at $-196\text{ }^{\circ}\text{C}$ are shown in Fig. 9. The morphologies of fracture surfaces were cleavage for 3.5Ni and 5Ni specimens (Fig. 9a, b). Tear ridges were observed in the 5Ni steel. When the Ni content increased to 7%, the impact fracture morphology changed from trans-granular brittle to dimple fracture; numerous small and shallow ductile dimples were observed on the fracture surface of 7Ni specimens (Fig. 9c). Figure 9d shows many coarse ductile dimples and some voids present on the fractured surface of 9Ni specimens, the presence of which represents the substantial plastic deformation that occurs prior to the onset of fracture [26].

The secondary cracks underneath the fracture surface of impact specimens are presented in Fig. 10. Figure 10a, b demonstrates that the cracks nucleated at the interface of the matrix and cementite. Previous researches indicated that the hard cementite cannot accommodate the surrounding matrix deformation effectively and therefore

Fig. 9 SEM fractographs of Charpy impact specimens fractured at $-196\text{ }^{\circ}\text{C}$: **a** 3.5Ni, **b** 5Ni, **c** 7Ni, **d** 9Ni steels

contributes to crack initiation [19, 27]. According to Griffith theory, the presence of the cementite decreases the crack initiation energy, resulting in the decrease in toughness [28]. The deleterious effect of the cementite is increased with increasing volume fraction of the cementite [29]. Therefore, the crack initiation energy is increased with the increase in Ni content. The cracks propagate through the surrounding matrix along the cleavage plane until they are finally arrested by high-angle grain boundaries, such as prior austenite grain boundaries or martensite packet boundaries (Fig. 10a) [7, 30]. However, Fig. 10c shows that the cracks in our samples propagated through the grain boundaries without obvious deflection. This is because the cementite located at the grain boundaries weakened the grain boundary's resistance for crack

propagation [19]. Plastic deformation can hardly occur due to the decrease in crack propagation energy (Figs. 1, 4) [22]. Therefore, the 3.5Ni and 5Ni steels exhibited poor toughness. As Ni content increased, the cementite content was significantly decreased due to the clean effect of reversed austenite; the toughnesses of 7Ni and 9Ni steels were improved. We also observed a certain amount of plastic deformation around the crack tip as shown in Fig. 10d. The plastic deformation zones hindered crack propagation, which enhanced the crack propagation energy [18–20].

It should be pointed out that the reversed austenite is mechanically unstable and will transform to hard martensite due to stress concentration during the impact process; this is known as the “TRIP effect.” The

Fig. 10 SEM micrographs of the cross-sectioned area beneath the fracture surface of CVN impact specimens tested at $-196\text{ }^{\circ}\text{C}$: **a** 3.5Ni, **b**, **c** 5Ni, **d** 9Ni steels

transformation of $\gamma \rightarrow \alpha$ absorbs additional energy and enhances toughness [23, 27]. Kim and Schwartz [31], however, suggested that this transformation can only provide additional 3.3 J energy increment when the reversed austenite content is 10%. Other studies have shown that the volume expansion occurring during austenite-to-martensite transformation can relieve the

local stress concentrations around the crack tip and the crack was closed [32, 33]. As shown in Fig. 11, the crack propagation paths in our samples were only changed (Fig. 11a) or arrested (Fig. 11b, c) due to existence of the reversed austenite. As such, the reversed austenite indeed hindered crack propagation, increased crack propagation energy and yielded material with excellent toughness.

Fig. 11 EPMA map analysis results of the cross-sectioned area beneath the fracture surface of CVN impact specimens tested at $-196\text{ }^{\circ}\text{C}$ for 5Ni steel

4 Conclusions

The effect of Ni addition on the microstructures and mechanical properties of Ni-containing cryogenic steels were investigated by using four different steels of 3.5Ni, 5Ni, 7Ni and 9Ni steels. The following conclusions are drawn:

1. The tempered microstructure of Ni-containing cryogenic steels is composed of tempered martensite and a small amount of blocky reversed austenite. The volume fractions of reversed austenite increased linearly as Ni content increased, while the amount of cementite decreased.
2. The addition of Ni significantly improved the impact energy at $-196\text{ }^{\circ}\text{C}$. The improvement in toughness was attributed to the increase in reversed austenite. Reversed austenite contributed to toughness mainly by absorbing carbon from the matrix and eliminating cementite precipitations, both of which were beneficial to improving the plastic deformation capacity of the matrix. The reversed austenite can also hinder crack

propagation, leading to an increase in crack propagation energy.

Acknowledgments This work is supported by the Fundamental Research Funds for the Central Universities (No. N120807001) and the National High-tech Research and Development Program of China (863 Program) (No. 2007 AA03Z504).

References

- [1] C.K. Syn, S. Jin, J.W. Morris, *Metall. Trans. A* **7**, 1827 (1976)
- [2] Y.H. Kim, H.J. Kim, J.W. Morris, *Metall. Trans. A* **17**, 1157 (1986)
- [3] H.-M. Hyung-Seop, M.S. Lee, Kim, *Int. J. Press. Vessel Pip.* **24**, 571 (2000)
- [4] M. Lei, Y.Y. Guo, *Acta Metall. Sin. (Engl. Lett.)* **2**, 244 (1989)
- [5] S.J. Wu, G.J. Sun, Q.S. Ma, Q.Y. Shen, L. Xu, *J. Mater. Process. Technol.* **213**, 120 (2013)
- [6] J. Zhao, T. Lee, J.H. Lee, Z. Jiang, C.S. Lee, *Metall. Mater. Trans. A* **44**, 3511 (2013)
- [7] B. Hwang, C.G. Lee, S.J. Kim, *Metall. Mater. Trans. A* **42**, 717 (2010)
- [8] J.R. Strife, D.E. Passoja, *Metall. Trans. A* **11**, 1341 (1980)

- [9] N. Nakada, J. Syarif, T. Tsuchiyama, S. Takaki, *Mater. Sci. Eng. A* **374**, 137 (2004)
- [10] Z. Li, D. Wu, *ISIJ Int.* **46**, 121 (2006)
- [11] K.I. Sugimoto, N. Usui, M. Kobayashi, S.I. Hashimoto, *ISIJ Int.* **32**, 1311 (1992)
- [12] L.A. Norstrom, *Scand. J. Metall.* **5**, 41 (1976)
- [13] Y.H. Yang, Q.W. Cai, D. Tang, H.B. Wu, *Int. J. Min. Met. Mater.* **17**, 587 (2010)
- [14] D. Frear, J.W. Morris, *Metall. Trans. A* **17**, 243 (1986)
- [15] B. Fultz, J.I. Kim, Y.H. Kim, J.W. Morris, *Metall. Trans. A* **17**, 967 (1986)
- [16] Y.Y. Song, D.H. Ping, F.X. Yin, X.Y. Li, Y.Y. Li, *Mater. Sci. Eng. A* **527**, 614 (2010)
- [17] R.D.K. Misra, Z. Zhang, P.K.C. Venkatasurya, M.C. Somani, L.P. Karjalainen, *Mater. Sci. Eng. A* **527**, 7779 (2010)
- [18] B.Y. Kang, H.J. Kim, S.K. Hwang, *ISIJ Int.* **40**, 1237 (2000)
- [19] D.Y. Wu, X.L. Han, H.T. Tian, B. Liao, F.R. Xiao, *Metall. Mater. Trans. A* **46**, 73 (2015)
- [20] J. Liu, H. Yu, J. Wang, T. Zhou, C. Song, *Steel Res. Int.* **86**, 1082 (2015)
- [21] J. Kang, C. Wang, G.D. Wang, *Mater. Sci. Eng. A* **553**, 96 (2012)
- [22] S.H. Hashemi, *Int. J. Press. Vessel Pip.* **85**, 879 (2008)
- [23] Z.J. Xie, S.F. Yuan, W.H. Zhou, J.R. Yang, H. Guo, C.J. Shang, *Mater. Des.* **59**, 193 (2014)
- [24] T. Pan, J. Zhu, H. Su, C.F. Yang, *Rare Met.* **34**, 776 (2015)
- [25] J. Hu, L.X. Du, G.S. Sun, H. Xie, R.D.K. Misra, *Scr. Mater.* **104**, 87 (2015)
- [26] X.G. Tao, L.Z. Han, J.F. Gu, *Mater. Sci. Eng. A* **618**, 189 (2014)
- [27] G. Gao, H. Zhang, X. Gui, P. Luo, Z. Tan, B. Bai, *Acta Mater.* **76**, 425 (2014)
- [28] J. Chen, S. Tang, Z.Y. Liu, G.D. Wang, *Mater. Sci. Eng. A* **559**, 241 (2013)
- [29] A. Echeverria, J.M. Rodriguez-Ibabe, *Mater. Sci. Eng. A* **346**, 149 (2003)
- [30] C. Wang, M. Wang, J. Shi, W. Hui, H. Dong, *Scr. Mater.* **58**, 492 (2008)
- [31] K.J. Kim, L.H. Schwartz, *Mater. Sci. Eng.* **33**, 5 (1978)
- [32] P.D. Bilmes, M. Solari, C.I. Llorente, *Mater. Charact.* **46**, 285 (2001)
- [33] J. Hu, L.X. Du, H. Liu, G.S. Sun, H. Xie, H.L. Yi, R.D.K. Misra, *Mater. Sci. Eng. A* **647**, 144 (2015)