Fabrication, Pore Structures and Mechanical Properties of (TiB₂–Al₂O₃)/NiAl Porous Composites

Jie Wu¹ · Zhao-Tai Yang¹ · Hong-Zhi Cui¹ · Na Wei¹ · Xiao-Jie Song¹

Received: 2 July 2017 / Revised: 4 August 2017 / Published online: 18 September 2017
© The Chinese Society for Metals and Springer-Verlag GmbH Germany 2017

Abstract Open-celled porous (TiB₂–Al₂O₃)/NiAl composites were successfully fabricated by using spherical carbamide as space holders via self-propagating high-temperature synthesis (SHS). Effects of 10Al–3B₂O₃–3TiO₂ contents (0–20 wt%) on the pore structures and the quasi-static compressive behaviors of the resultant materials were investigated. The porous (TiB₂–Al₂O₃)/NiAl composites exhibit composite pore structure consisting of homogeneously distributed and interconnected millimeter pores and micropores. The millimeter pores virtually inherit the shape and size of carbamide particles, while the pore size of micropores increases with increasing the 10Al–3B₂O₃–3TiO₂ content. Depending on the volume fraction of the carbamide, the porosity of the porous materials can be easily controlled in a range of 55%–85%. When the porosity is about 72%, the compressive strengths of porous NiAl and porous (TiB₂–Al₂O₃)/NiAl composite with 15% 10Al–3B₂O₃–3TiO₂ in green compact are 19 and 32 MPa, and the corresponding strains are 2.9% and 5.7%, respectively. Furthermore, the quasi-static compressive behavior of porous (TiB₂–Al₂O₃)/NiAl composites can be estimated by Gibson–Ashby model.

KEY WORDS: Self-propagating high-temperature synthesis (SHS); Pore structure; Compressive properties; Porous (TiB₂–Al₂O₃)/NiAl

1 Introduction

Porous NiAl intermetallics have excellent characteristics of both porous ceramics and porous metals due to the mixture of metallic and covalent bonds [1, 2]. They are expected to be used in the fields of thermal insulation, catalyst carriers and high-temperature filtration for their outstanding properties, such as high melting point, low density, high specific strength, excellent oxidation and corrosion resistance [3–7]. Like bulk NiAl intermetallics, relatively low

toughness at room temperature and limited strength at high temperatures may restrict extensive applications of porous NiAl intermetallics [2, 8]. It has been explored that the mechanical properties of NiAl intermetallics can be noticeably improved by adding ceramic particles [9–12]. Xing et al. [9] found that the compressive strength and plasticity of TiB₂/NiAl composites increase linearly with the increase in TiB₂ contents (0–20 wt%). Wei et al. [10] investigated the effects of TiB₂ formation conditions on the mechanical properties of NiAl intermetallics, and the results showed that in situ formed TiB₂ has better reinforcing effect than externally added TiB₂. Michalski et al. [11] fabricated NiAl–Al₂O₃ composites by pulse plasma sintering and found that the Al₂O₃ addition can increase their hardness and fracture toughness, and the higher hardness of Al₂O₃ and crack deflection are responsible for the enhancement. Furthermore, the NiAl reinforced by fine TiC particles can significantly improve its mechanical

Available online at <http://link.springer.com/journal/40195>

✉ Jie Wu
wujie0537@163.com

¹ School of Materials Science and Engineering, Shandong University of Science and Technology, Qingdao 266590, China

properties due to grain boundary strengthening and TiC dispersion strengthening [12]. Among these ceramic particles, $\text{TiB}_2\text{-Al}_2\text{O}_3$ ceramic as a hybrid reinforcement has better enhancement effect than single TiB_2 or Al_2O_3 [13, 14], so it is conceivable that the porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites should have better mechanical performances than the porous NiAl intermetallics. Unfortunately, there is rare report about the effects of ceramic particles on the pore structures and mechanical properties of porous NiAl intermetallics, which needs further investigation.

Several technologies have been reported to prepare porous NiAl intermetallics. Dong *et al.* [6, 7] and Wu *et al.* [15, 16] successfully fabricated porous NiAl and Ni_3Al intermetallics through elemental powder reaction sintering based on Kirkendall effect, and the mechanical and corrosion behaviors of the porous intermetallics were investigated systematically [6, 7, 15, 16]. However, this method requires high vacuum and a long time of high-temperature solid-state diffusion, which has a long process flow and low efficiency. Self-propagating high-temperature synthesis (SHS) is considered as an economic technique to prepare intermetallics, ceramics and their composites [14, 17], with the advantages of low synthesis time, low energy consumption, inexpensive fabrication equipment and in situ synthesis of composite components [10, 18]. In recent years, the disadvantages of porosity formation during SHS can be regarded as a technology of producing porous materials. Kanetake *et al.* [5] fabricated porous Ni–Al intermetallics by SHS and proposed that gas released from elemental powders and initial porosity in green compact are the formation mechanisms of the pores. Morsi *et al.* [19] prepared cylindrical porous NiAl intermetallics with 60% porosity through controlling the heat generation during SHS. Hunt *et al.* [20] obtained NiAl foams using nanoparticle reactants and gasifying agent ($\text{C}_{13}\text{F}_{27}\text{COOH}$) through the chemical process of SHS. Nevertheless, the pore structures are difficult to be well controlled due to the fast speed of SHS process. Space-holder method is a very promising route of preparing open-celled porous materials [21–23]. The most outstanding technical advantage of this method is much wider range of structure parameters, thus providing more opportunities for resultant porous materials to meet the desired behaviors [21, 24]. Therefore, porous NiAl and NiAl matrix composites with adjustable pore structures can be successfully fabricated by the combination of SHS and space-holder technology.

In this work, open-celled porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites with composite pore structures were successfully fabricated by using spherical carbamide as space holders via SHS. $\text{TiB}_2\text{-Al}_2\text{O}_3$ was formed in situ by the reaction of $10\text{Al-}3\text{B}_2\text{O}_3\text{-}3\text{TiO}_2$ (in mole ratio) powders. The aim of the present study is to investigate the effects of $10\text{Al-}3\text{B}_2\text{O}_3\text{-}3\text{TiO}_2$ contents on the pore structures and the

quasi-static compressive behaviors of the porous composites. The results and analysis are expected to be useful for the development and applications of porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites.

2 Experimental

Pure Ni powder (37–45 μm , purity 99.5%), Al powder (48–75 μm , purity 99.5%), B_2O_3 powder (48–75 μm , purity 98.0%) and TiO_2 powder (37–45 μm , purity 98.0%) were used as starting materials. Spherical carbamide ($\text{CO}(\text{NH}_2)_2$, 0.6–0.9 mm) was prepared as space-holder particle. Porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites were synthesized by SHS according to the following chemical reaction.

In Eq. (1), x represents the mass percentages of $(10\text{Al} + 3\text{B}_2\text{O}_3 + 3\text{TiO}_2)$. Ni–Al powders (mole ratio is 1:1) and Al– B_2O_3 – TiO_2 powders (mole ratio is 10:3:3) were mixed in a three-dimensional blender with a rotation speed of 40 rpm and a blending time of 4 h. The mass percentages of $10\text{Al-}3\text{B}_2\text{O}_3\text{-}3\text{TiO}_2$ powders were varied from 0 to 25% with an increment of 5%. In order to control the pore structures and porosities of the composites, the aforementioned mixtures and carbamide particles with different volume fractions were blended together in a stirrer at a rotation speed of 60 rpm and a blending time of 10 min. A small amount of ethanol was added to the mixtures to avoid segregation of dissimilar particles during the blending. The well-mixed mixture was then uniaxially compressed into green compact with a pressure of 100 MPa. Subsequently, the green compact was heat-treated at 473 K for 1 h in an electric furnace to remove the carbamide particles, and then, the compact was heated to 623 K and hold for 0.5 h. Finally, the preheated compact was ignited at one end by ignition reagent (about 1 g Ti powders). Once ignited, combustion wave could self-propagate along axial direction to the other end of the compact in a very short time, and then, porous material was fabricated. The dimension of the green compact is $\Phi 25 \text{ mm} \times 30 \text{ mm}$, while the minimum and maximum dimensions of the as-synthesized samples are $\Phi 23.6 \text{ mm} \times 28.6 \text{ mm}$ and $\Phi 24.2 \text{ mm} \times 29.3 \text{ mm}$, respectively. The volume shrinkage ranges from 8.48% to 15.04%; the higher content of $10\text{Al-}3\text{B}_2\text{O}_3\text{-}3\text{TiO}_2$ powders in green compacts, the greater volume shrinkage of the products.

Phase identification of the products was carried out by X-ray diffraction (XRD, D/Max 2500PC Rigaku, Japan) analysis. The optical digital camera (Canon EOS 600D) and scanning electron microscopy (SEM, KYKY2800B)

were used to characterize the macroscopic and microscopic morphologies of the porous (TiB₂–Al₂O₃)/NiAl composites, respectively. The porosity of the resultant materials was measured with Archimedes principle in water based on the following steps [25]. The mass (M_1) of a dried porous sample was weighted in air. The mass (M_2) of the porous sample filled with the wax was weighted when it was suspended in water. Then, the porosity (P) can be calculated according to $P = 1 - M_1/(M_2 \times \rho_0)$, where ρ_0 is the corresponding theoretical density of the sample. The porosity of the sample is the average of three specimens' porosities. Quasi-static uniaxial compressive tests were performed with a loading rate of 2 mm/min on a universal material testing machine (WDW3100) at room temperature. The dimensions of all the specimens for the compressive tests were $\Phi 20 \times 20$ mm. Four specimens were tested for each sample in the compressive tests, and the compressive strength of the sample is the average of the compressive strengths of four specimens.

3 Results and Discussion

3.1 Phase Identification

Figure 1 shows the XRD patterns of products with different contents of 10Al–3B₂O₃–3TiO₂ powders in corresponding green compacts. It is observed that only the desired NiAl, TiB₂ and Al₂O₃ phases were detected. With increasing the content of 10Al–3B₂O₃–3TiO₂ powders in green compact, the peak intensities of TiB₂ and Al₂O₃ phases increase, while that of the NiAl phase decreases, suggesting that the higher 10Al–3B₂O₃–3TiO₂ content is, the more TiB₂ and Al₂O₃ phases are generated. Based on the XRD data, the

Fig. 1 XRD patterns of products with different contents of 10Al–3B₂O₃–3TiO₂ powders in corresponding green compacts

contents of NiAl, TiB₂ and Al₂O₃ in porous (TiB₂–Al₂O₃)/NiAl composites were calculated [26], which are shown in Table 1. The chemical compositions of the products were also calculated according to the phase contents in Table 1 and molecular weight of elements, as shown in Table 2. For the sample with 5% 10Al–3B₂O₃–3TiO₂, phase contents and chemical compositions were not calculated because the peak intensities of TiB₂ phase are low. The carbamide particles have no influence on the phase composition of the products, since the diffraction peak correlated with carbamide is not found in Fig. 1. Because both the melting point and decomposition temperature of carbamide are below 473 K [27], they should have been removed during the preheating process. Therefore, the reactions among the raw material powders are independent on the carbamide particles during the SHS process.

When Ni–Al and 10Al–3B₂O₃–3TiO₂ powders were mixed, all the possible reactions during SHS process can be described by the following equations:

Assuming that the amount of reactants was 1 mol, the Gibbs free energy (ΔG) for each reaction as a function of temperature was calculated, as shown in Fig. 2. Among the

Table 1 Phase compositions of the porous (TiB₂–Al₂O₃)/NiAl composites (wt%)

Sample	Phase compositions (wt%)		
	NiAl	TiB ₂	Al ₂ O ₃
(Ni–Al) + 10% (10Al–3B ₂ O ₃ –3TiO ₂)	87.7	4.4	7.9
(Ni–Al) + 15% (10Al–3B ₂ O ₃ –3TiO ₂)	82.9	6.3	10.8
(Ni–Al) + 20% (10Al–3B ₂ O ₃ –3TiO ₂)	78.2	7.3	14.5

Table 2 Chemical compositions of the porous (TiB₂–Al₂O₃)/NiAl composites (wt%)

Sample	Ni	Al	Ti	B	O
(Ni–Al) + 10% (10Al–3B ₂ O ₃ –3TiO ₂)	60.1	31.8	3.0	1.4	3.7
(Ni–Al) + 15% (10Al–3B ₂ O ₃ –3TiO ₂)	56.8	31.8	4.3	2.0	5.1
(Ni–Al) + 20% (10Al–3B ₂ O ₃ –3TiO ₂)	53.6	32.3	5.1	2.2	6.8

Fig. 2 Gibbs free energy (ΔG) as a function of temperature for the possible reactions in Ni–Al and 10Al–3B₂O₃–3TiO₂ mixed powders

above reactions, the Gibbs free energies of the reactions involved in the formation of NiAl, TiB₂ and Al₂O₃ are more negative than those of the reactions involved in other phases, such as Ni₃Al, NiTi and TiAl. It is reasonable to believe that the NiAl, TiB₂ and Al₂O₃ phases are the most possible final products according to the thermodynamic principles, which is consistent with the XRD patterns as shown in Fig. 1. Thus, the main reactions during the SHS process can be described by reactions (11) and (15).

3.2 Pore Characteristics

Figure 3 shows the typical macroscopic morphologies of porous (TiB₂–Al₂O₃)/NiAl composites. The porosities of the specimens as shown in Fig. 3a–c are about 60%, 72% and 85%, corresponding to the carbamide volume fraction of 47%, 60% and 75%, respectively. Besides the porosity, the morphology and size of pores can also be controlled also by carbamide particles. The millimeter pores with pore sizes of 0.6–0.9 mm are distributed homogeneously in porous material matrix. Compared with the morphologies of carbamide particles in Fig. 4, it is seen that both the shape and size of carbamide particles are well replicated and accordingly resulted in spherical crosssectional shape of the pores.

More detailed macroscopic and microscopic morphologies of porous (TiB₂–Al₂O₃)/NiAl composites with different 10Al–3B₂O₃–3TiO₂ contents in corresponding green compacts are shown in Figs. 5, 6 and 7. It is apparent that the porous (TiB₂–Al₂O₃)/NiAl composites exhibit composite pore structure consisting of two kinds of different pores. One is interconnected millimeter pore which originates from the removed carbamide particles. A number of small voids marked with white arrows in Fig. 5c are distributed on the pore walls. These voids are formed at the contacting points between carbamide particles [22]. The number of these voids increases with increasing the porosity, as shown in Figs. 5c and 6. These voids can form interconnected channels between the millimeter pores and guarantee an open-cellular structure of the porous materials.

The second kind of pores is micropore which is distributed on the walls and skeletons of the millimeter pores. These pores further increase the connectivity of porous (TiB₂–Al₂O₃)/NiAl composites. The content of 10Al–3B₂O₃–3TiO₂ powders has little influence on the morphology of the millimeter pores, but can significantly influence the shape and size of micropores when it is not more than 20%. In Fig. 7, it is found that the pore size of micropores increases with increasing the content of 10Al–3B₂O₃–3TiO₂ powders. The shape of micropores is nearly spherical, and the pore size is ranged from several micrometers to several tens of micrometers as the content of 10Al–3B₂O₃–3TiO₂ is between 0 and 15%. For the specimen with 20% 10Al–3B₂O₃–3TiO₂, the morphology of micropores becomes irregular, and even the long and narrow micropore over 100 micrometers was observed, which were marked by white arrows in Fig. 7e, f.

Table 3 shows the calculated adiabatic temperatures (T_{ad}) of the mixtures composed of Ni–Al and 10Al–3B₂O₃–3TiO₂ powders when they are ignited at 623 K. With the addition of 10Al–3B₂O₃–3TiO₂ powders, the T_{ad} of the mixtures increases gradually. The melting points of NiAl, Al₂O₃ and TiB₂ are 1911 K [14], 2323 K [14] and 3193 K [28], respectively, so liquid phase will appear inevitably during the SHS process. The higher the content of 10Al–3B₂O₃–3TiO₂ powders, the more the liquid phase produced. When the green compact is preheated at 473 and 623 K, porous compact is formed after the volatilization of carbamide particles. It is the key to synthesis of porous (TiB₂–Al₂O₃)/NiAl composites that pore structure of porous compact can be maintained during the SHS process, which requires controlling the amount of liquid phase and limiting the migration and solidification of the liquid phase to a narrow area.

Figure 8a shows the pore morphology of porous (TiB₂–Al₂O₃)/NiAl composite fabricated without using carbamide particles. From the figure, many traces of liquid

Fig. 3 Cross-sectional morphologies of porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composites with 15% $10\text{Al}\text{--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ and different porosities: **a** about 60%, **b** about 72%, **c** about 85%

solidification are observed, and the large pore size distribution (20–300 μm) indicates that the packing pattern of mixture powders in green compact was destroyed by the migration of liquid phase. When carbamide particles are added to green compact, the interconnected pores in porous compact are beneficial for heat volatilization, which accelerates the liquid phase solidification, so the migration of the liquid phase is limited and the pore structure of porous compact is kept if the content of $10\text{Al}\text{--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ powders is not more than 20%, as shown in Figs. 3, 5 and 6. For the sample with 25% $10\text{Al}\text{--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$, the formation of excessive liquid phase and its large migration range lead to the collapse of the pore structure in porous compact, which is shown in Fig. 8b.

As mentioned above, there are a number of micropores on pore walls and skeletons. The initial pores in green compacts and gases volatilization during SHS are the primary sources of the micropores [5, 29]. Since the green compacts were compressed with unified pressure of 100 MPa, the densities of the green compacts and initial pores are basically the same. It is reasonable that the difference in the morphology of micropores may be attributed to the volatilization of gases. The higher content of $10\text{Al}\text{--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ powders in samples, the higher the temperature and the heat, the greater the impact force generated by gases volatilization, giving rise to the increase in micropore size, and even the bigger and irregular micropores are formed when $10\text{Al}\text{--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ content reaches

Fig. 4 Morphologies of the carbamide particles

Fig. 6 SEM image of porous (TiB₂-Al₂O₃)/NiAl composite with the porosity of about 80% and the 10Al-3B₂O₃-3TiO₂ content of 15%

Fig. 5 SEM images of porous (TiB₂-Al₂O₃)/NiAl composites with porosity of about 72% and different 10Al-3B₂O₃-3TiO₂ contents in corresponding green compacts: **a** 5%, **b** 10%, **c** 15%, **d** 20%

20%, as shown in Fig. 7. After the removal of carbamide particles, porous compact provides interconnected channels for gases volatilization. Accordingly, the gases are easier to volatilize compared with the specimen fabricated without using carbamide particles. So the pore size of micropores in Fig. 7 is significantly lower than that in Fig. 8a.

Porous (TiB₂-Al₂O₃)/NiAl composites have composite pore structure consisting of homogeneously distributed millimeter pores and micropores. However, in the previous studies about porous Ni-Al intermetallics, the porous materials have single pore structure and limited pore size distribution. Porous Ni-Al intermetallics with pore sizes of

Fig. 7 SEM images of micropores of porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites with porosity of about 72% and different 10Al-3B₂O₃-3TiO₂ contents in corresponding green compacts: **a** 0, **b** 5%, **c** 10%, **d** 15%, **e**, **f** 20%

Table 3 Adiabatic temperatures (T_{ad}) of the mixtures composed of Ni-Al and 10Al-3B₂O₃-3TiO₂ powders when they are ignited at 623 K

Specimen	Adiabatic temperatures (K)
Ni-Al	2236
(Ni-Al) + 5% (10Al-3B ₂ O ₃ -3TiO ₂)	2263
(Ni-Al) + 10% (10Al-3B ₂ O ₃ -3TiO ₂)	2290
(Ni-Al) + 15% (10Al-3B ₂ O ₃ -3TiO ₂)	2317
(Ni-Al) + 20% (10Al-3B ₂ O ₃ -3TiO ₂)	2343
(Ni-Al) + 25% (10Al-3B ₂ O ₃ -3TiO ₂)	2370
10Al-3B ₂ O ₃ -3TiO ₂	2773

50–350 nm were obtained by using nanoparticle reactants via SHS [20]. Dong et al. [6, 7] fabricated porous NiAl and Ni₃Al intermetallics through reaction sintering, the pore size is ranged from 10 to 70 μm , and the morphology of the pores is similar to that of micropores in porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites. The pore structures of porous NiAl and NiAl₃ intermetallics were adjusted by the addition of 3Ti-B₄C powders during SHS process [5], and inhomogeneous millimeter pores (1–10 mm) are formed due to the greater impact force generated by gases volatilization. Compared with these results, it can be seen that space-holder technology combined with SHS provides an effective method to control the pore structure of porous materials.

Fig. 8 SEM images of pore morphologies of porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composites: **a** without carbamide particles, 15% $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$, **b** with carbamide particles, 25% $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$

3.3 Compressive Properties

When the porosity of samples is about 72%, the nominal stress–strain curves of porous NiAl and $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composite are shown in Fig. 9. It is apparent that both stress–strain curves consist of typical three regions, i.e., elastic, plateau and densification regions [30]. However, the plateau regions are not smooth but serrated, suggesting brittle fracture of pore walls after yielding deformation [23, 27], which is demonstrated in Fig. 10. The fracture mode of porous NiAl intermetallics in Fig. 10a is intergranular fracture. For porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composite with 15% $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ as shown in Fig. 10b, the fracture changes to a mode of intergranular and transgranular mixed fracture.

As mentioned above, the millimeter pore walls are not dense but have a number of micropores, which will transform to crack due to stress concentration upon loading. With the increase in strain during compressive deformation, cracks expand and brittle collapse of the pores occurs,

Fig. 9 Nominal stress–strain curves of porous NiAl and $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composite

leading to the decrease in stress. As the compression continues, collapsed pore walls start to come into contact and stress increases again until the next fracture takes place. So repeatedly, the serrated stress–strain curve appears.

In Fig. 9, the porosity of the samples is about 72%, and the compressive strengths (i.e., the peak stresses) of porous NiAl and $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composite with 15% $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ are 19 and 32 MPa, corresponding to the strains of 2.9% and 5.7%, respectively. Therefore, the stress–strain curve of the porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composite has higher compressive strength, longer elasticity region and higher plateau stress compared with that of porous NiAl intermetallics, indicating that the mechanical properties of porous NiAl intermetallics can be improved by the formation of TiB_2 and Al_2O_3 . When the porosity of porous materials is about 72%, the effect of $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ contents on the compressive strength of porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composites was investigated, as shown in Fig. 11. The higher content of $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ powders in samples, the more TiB_2 and Al_2O_3 generated, and the higher the compressive strength of porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composites when the content of $10\text{Al--}3\text{B}_2\text{O}_3\text{--}3\text{TiO}_2$ powders is not more than 15%. The increase in the compressive strength may be attributed to the following three reasons. Firstly, the microstructures of $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composites prepared by SHS have been investigated systematically in our previous papers [14, 31]. The results showed that the fine $\text{TiB}_2\text{--Al}_2\text{O}_3$ particles are mainly distributed along NiAl grain boundaries, so the NiAl grains are refined due to the dragging effect of ceramic particles on grain boundaries [14, 31], and as a result, the compressive strength of the porous materials is improved. Secondly, the fracture mode of porous $(\text{TiB}_2\text{--Al}_2\text{O}_3)/\text{NiAl}$ composites changes from intergranular fracture to mixed mode of intergranular and transgranular fractures because the NiAl grain boundaries are strengthened by $\text{TiB}_2\text{--Al}_2\text{O}_3$ particles, and

Fig. 10 Fracture morphologies of **a** porous NiAl; **b** porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composite with 15% $10\text{Al-3B}_2\text{O}_3\text{-3TiO}_2$

Fig. 11 Influence of $10\text{Al-3B}_2\text{O}_3\text{-3TiO}_2$ contents on the compressive strength of porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites with porosity of about 72%

Fig. 12 Dependence of the compressive strength on relative density for porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites with 15% $10\text{Al-3B}_2\text{O}_3\text{-3TiO}_2$

transgranular fracture consumes more energy than intergranular fracture during deformation or damage, resulting in the higher compressive strength of porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites. Thirdly, residual stress is generated in the cooling process since the elastic modulus and thermal expansion coefficient between NiAl matrix and $\text{TiB}_2\text{-Al}_2\text{O}_3$ particles are different. The interaction of the residual stress field with crack tip stress leads to the effects of crack deflection, bifurcation and pinning, which can increase the compressive strength of the specimens. However, for porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composite with 20% $10\text{Al-3B}_2\text{O}_3\text{-3TiO}_2$, greater stress concentration may be produced during compression process due to the formation of the bigger and irregular micropores (Fig. 7e, f), giving rise to the decrease in the compressive strength, as shown in Fig. 11.

Dong et al. [6, 7] have investigated the tensile strength and bending strength of porous NiAl and Ni_3Al intermetallics. Nevertheless, there is rare report about compressive strength of porous NiAl intermetallics, which is

equally important for engineering applications [22, 32]. The compressive properties of porous TiAl with similar pore structure have been investigated [22, 32]. Under the similar porosity (about 72%), the compressive strength of porous NiAl is slightly lower than that of porous TiAl, while the compressive strengths of porous $(\text{TiB}_2\text{-Al}_2\text{O}_3)/\text{NiAl}$ composites with 5–20% $10\text{Al-3B}_2\text{O}_3\text{-3TiO}_2$ are higher than that of porous TiAl.

The Gibson–Ashby model was widely used to describe the relationship between the relative stress σ/σ_0 and the relative density ρ/ρ_0 of porous materials [33]. The relationship is given by the following equations [33]:

$$\frac{\sigma}{\sigma_0} = C \left(\frac{\rho}{\rho_0} \right)^{3/2} \left[1 + \left(\frac{\rho}{\rho_0} \right)^{1/2} \right], \quad (16)$$

$$\frac{\rho}{\rho_0} = 1 - P, \quad (17)$$

where σ is the collapse stress of a porous material, σ_0 is the yield stress of the pore wall material, ρ is the density of the

porous material, ρ_0 is the density of the pore wall material, C is a constant and P is the porosity of the porous material. If Eq. (16) is applied to the porous (TiB₂–Al₂O₃)/NiAl composites, the dependence of σ versus $(\rho/\rho_0)^{3/2}[1 + (\rho/\rho_0)^{1/2}]$ should yield a straight line, which is demonstrated in Fig. 12, indicating that the compressive behavior of the porous (TiB₂–Al₂O₃)/NiAl composites can be understood by the Gibson–Ashby model.

4 Conclusions

1. Open-celled porous (TiB₂–Al₂O₃)/NiAl composites have been successfully fabricated by using spherical carbamide as space holders via SHS. The higher the content of 10Al–3B₂O₃–3TiO₂ powders in corresponding green compacts, the more TiB₂ and Al₂O₃ generated. The carbamide particles have no influence on the phase composition of the products.
2. When the content of 10Al–3B₂O₃–3TiO₂ powders is not more than 20%, the porous (TiB₂–Al₂O₃)/NiAl composites exhibit composite pore structure consisting of two kinds of different pores. One is interconnected millimeter pore which virtually inherits the shape and size of carbamide particles, and the other one is micropore which is distributed on millimeter pore walls and skeletons. Pore size of micropores increases with increasing the content of 10Al–3B₂O₃–3TiO₂ powders due to the greater impact force of gases volatilization during SHS process. By controlling the volume fraction of carbamide particles, the porosity of porous material can reach about 85%.
3. The compressive strength of porous (TiB₂–Al₂O₃)/NiAl composites can be improved compared to porous NiAl intermetallics. The possible mechanisms mainly include NiAl grain refining, transition from intergranular fracture to intergranular and transgranular mixed fracture, as well as crack deflection. Furthermore, the relationship between the compressive strength and relative density can be explained by the Gibson–Ashby model.

Acknowledgements The present work was financially supported by the Natural Science Foundation of Shandong Province (No. ZR2014EMM009) and the Public School Visiting Fund of Shandong University of Science and Technology.

References

- [1] N.S. Toloff, C.T. Liu, S.C. Deevi, *Intermetallics* **8**, 1313 (2000)
- [2] J.T. Guo, *Ordered Intermetallic Compound NiAl Alloy* (Science Press, Beijing, 2003), pp. 1–13. (in Chinese)
- [3] X.L. Shi, M. Wang, W.Z. Zhai, Z.S. Xu, Q.X. Zhang, Y. Chen, *Mater. Des.* **45**, 179 (2013)
- [4] S.Y. Zhu, Q.L. Bi, M.Y. Niu, J. Yang, W.M. Liu, *Wear* **274–275**, 423 (2012)
- [5] N. Kanetake, M. Kobashi, *Scr. Mater.* **54**, 521 (2006)
- [6] H.X. Dong, Y. Jiang, Y.H. He, M. Song, J. Zou, N.P. Xu, B.Y. Huang, C.T. Liu, P.K. Liaw, *J. Alloys Compd.* **484**, 907 (2009)
- [7] H.X. Dong, Y.H. He, Y. Jiang, L. Wu, J. Zou, N.P. Xu, B.Y. Huang, C.T. Liu, *Mater. Sci. Eng. A* **528**, 4849 (2011)
- [8] M.X. Gao, Y. Pan, F.J. Oliveira, J.L. Baptista, J.M. Vieira, *Mater. Lett.* **58**, 1761 (2004)
- [9] Z.P. Xing, J.T. Guo, Z.Q. Hu, G.Y. An, *Acta Metall. Sin. (Engl. Lett.)* **7**, 45 (1994)
- [10] N. Wei, H.Z. Cui, J. Wu, J. Wang, G.L. Wang, C. Jiang, *Acta Metall. Sin. (Engl. Lett.)* **28**, 39 (2015)
- [11] A. Michalski, J. Jaroszewicz, M. Rosiński, D. Siemiaszko, *Intermetallics* **14**, 603 (2006)
- [12] X. Zhu, T. Zhang, D. Marchant, V. Morris, *J. Eur. Ceram. Soc.* **30**, 2781 (2010)
- [13] E.M. Sharifi, F. Karimzadeh, M.H. Enayati, *Adv. Powder Technol.* **22**, 526 (2011)
- [14] X.J. Song, H.Z. Cui, L.L. Cao, P.Y. Gulyaev, *Trans. Nonferrous Met. Soc. China* **26**, 1878 (2016)
- [15] L. Wu, Y. Jiang, H.X. Dong, Y.H. He, N.P. Xu, J. Zou, B.Y. Huang, C.T. Liu, *Intermetallics* **19**, 1759 (2011)
- [16] L. Wu, Y.H. He, Y. Jiang, Y. Zeng, Y.F. Xiao, B. Nan, *Trans. Nonferrous Met. Soc. China* **24**, 3509 (2014)
- [17] H. Attar, K.G. Prashanth, L.C. Zhang, M. Calin, I.V. Okulov, S. Scudino, C. Yang, J. Eckert, *J. Mater. Sci. Technol.* **31**, 1001 (2015)
- [18] A.A. Shokati, N. Parvin, M. Shokati, *J. Alloys Compd.* **585**, 637 (2014)
- [19] K. Morsi, T. Fujii, H. McShane, M. Mclean, *Scr. Mater.* **40**, 359 (1999)
- [20] E.M. Hunt, M.L. Pantoya, R.J. Jouet, *Intermetallics* **14**, 620 (2006)
- [21] Q.Z. Wang, W.J. Liu, D.M. Lu, C.X. Cui, *Mater. Lett.* **142**, 52 (2015)
- [22] G.L. Hao, H. Wang, X.Y. Li, *Mater. Lett.* **142**, 11 (2015)
- [23] J. Wu, H.Z. Cui, L.L. Cao, Z.Z. Gu, *Trans. Nonferrous Met. Soc. China* **21**, 1750 (2011)
- [24] E. Mostafavi, A. Ataie, *J. Mater. Sci. Technol.* **31**, 798 (2015)
- [25] Y. Jiang, Y.H. He, N.P. Xu, J. Zou, B.Y. Huang, C.T. Liu, *Intermetallics* **16**, 327 (2008)
- [26] X.M. Huang, T. Xie, *Analysis Methods of Materials* (National Defense Industry Press, Beijing, 2014), pp. 56–57. (in Chinese)
- [27] G.L. Hao, F.S. Han, W.D. Li, *J. Porous Mater.* **16**, 251 (2009)
- [28] H.Z. Cui, W. Liu, L.L. Cao, Q. Song, J. Tian, F.L. Teng, J. Wang, *J. Eur. Ceram. Soc.* **35**, 3381 (2015)
- [29] M. Kobashi, N. Kanetake, *Adv. Eng. Mater.* **4**, 745 (2002)
- [30] Q.Z. Wang, C.X. Cui, S.J. Liu, L.C. Zhao, *Mater. Sci. Eng. A* **527**, 1275 (2011)
- [31] L.L. Cao, H.Z. Cui, J. Wu, H.J. Tang, *Trans. Nonferrous Met. Soc. China* **22**, 2790 (2012). (in Chinese)
- [32] G.L. Hao, Q.P. Xu, H. Wang, X.Y. Li, *Mater. Sci. Technol.* **32**, 1592 (2016)
- [33] Y. Yamada, T. Banno, Z.K. Xie, Y.C. Li, C.E. Wen, *Mater. Sci. Forum* **539–543**, 1833 (2007)