Effect of Sub- T_g Annealing on the Corrosion Resistance of the Cu–Zr Amorphous Alloys

Sang-Soo Shin¹ · Hong-Kyu Kim² · Jae-Chul Lee³ · Ik-Min Park¹

Received: 30 May 2017 / Revised: 28 June 2017 / Published online: 4 August 2017
© The Chinese Society for Metals and Springer-Verlag GmbH Germany 2017

Abstract Despite the economy of material cost and excellent toughness of Cu-based amorphous alloys, especially Cu₅₀Zr₅₀, their poor corrosion resistance to a chloride medium limits their widespread applications. In this study, corrosion tests were performed on the Cu₅₀Zr₅₀ amorphous alloy with different degrees of short-range order, which were prepared by annealing below the glass transition temperature (T_g). It was found that the corrosion resistance of amorphous alloys is improved to a significant level when the alloys were heated below T_g . Calorimetric studies showed that thermally activated relaxation process of created disorder, which occurs during sub- T_g annealing, is responsible for the improvement in the corrosion resistance. Molecular dynamics simulations performed on the Cu–Zr amorphous alloys demonstrated that the relaxation process of the alloys is associated with the formation of energetically stable icosahedra and icosahedron-like structures. Our study highlights the effects of sub- T_g annealing on the improvement in the corrosion resistance of the amorphous alloys from the viewpoint the relaxation process of the short-range orders.

KEY WORDS: Amorphous alloys; Corrosion; Annealing; Molecular dynamics; Electrochemical performance

Sang-Soo Shin and Hong-Kyu Kim have contributed equally to the present work.

Available online at <http://link.springer.com/journal/40195>

✉ Jae-Chul Lee
jcle001@korea.ac.kr

✉ Ik-Min Park
impark@pusan.ac.kr

¹ Department of Materials Science and Engineering, Pusan National University, Busan 609-735, South Korea

² Advanced Analysis Center, Korea Institute of Science and Technology, Seoul 02792, South Korea

³ Department of Materials Science and Engineering, Korea University, Seoul 136-701, South Korea

1 Introduction

Cu-based amorphous alloys, due to their low material cost compared to La-, Zr-, Pd-based counterparts, have attracted considerable interest [1]. They not only exhibit large glass forming ability (GFA) in various compositional ranges, but also possess large room-temperature plasticity and high yield strength [2–6]. Despite the aforementioned advantages, their relatively poor corrosion resistance to a chloride medium, e.g., NaCl aqueous solutions, remains a problem to be solved [7, 8].

Bulk amorphous alloys with enhanced corrosion resistance can be produced via two routes, i.e., the alloy design and thermal treatment. The principle underlying the former method is to add a minor element that promotes the formation of a passive film on the surface of the alloys [7, 9]. This method, however, has a limitation in the selection of appropriate elements. Furthermore, the addition of a minor element can often deteriorate the mechanical properties of amorphous alloys including GFA [10]. The latter method,

i.e., the thermal treatment, for enhancing the corrosion resistance of the amorphous alloys is to anneal the alloys below the glass transition temperature (hereinafter, this operation is referred to as ‘sub- T_g annealing’). It is well known that the disorder created during quenching amorphous alloys generally annihilates during sub- T_g annealing, causing the volume of icosahedral orders to increase [11]. Of various polyhedral constructing amorphous alloys, the icosahedron is the most densely packed short-range order and thus structurally and energetically most stable. Therefore, its volume fraction is known to be a typical parameter that can determine the properties such as glass forming ability, strength and plasticity [12–14]. Recently, several studies reported that the corrosion resistance of the amorphous alloys can be improved by sub- T_g annealing [15, 16]. Jiang *et al.* [15] suggested that the corrosion resistance can be enhanced by changes in the chemical orders and the formation of clusters during the annealing process. Masumoto *et al.* [16] reported that the annihilation of internal/residual stress associated with structural relaxation can improve the corrosion resistance. However, in order to understand the observed behaviors, the structural origin responsible for the improved corrosion resistance associated with sub- T_g annealing must be investigated with a consideration of atomic-scale structures.

Free volume is a typical defect structure of amorphous alloys and plays an important role in determining the properties of the amorphous alloys to similar extent as the defects such as dislocations, twins, and grain boundaries do so for crystalline alloys [17, 18]. Generally, free volumes in amorphous alloys can be evaluated quantitatively by determining atomic packing density: High atomic packing density of amorphous alloys corresponds to small free volumes. Egami *et al.* [19] and Suh and Dauskardt [20] demonstrated that sub- T_g annealing improved the mechanical properties of amorphous alloys. Sub- T_g annealing also reduces free volumes in amorphous alloys and thus lowers the potential energy of the alloy system, which in turn can improve the corrosion resistance of the alloys. This scenario on the improved corrosion resistance was tested in this study. We also elucidated the structural origin of the enhanced corrosion resistance of the alloys by analyzing the changes in the local-atomic structure (equivalently, atomic packing density and free volumes) using molecular dynamics (MD) simulations.

2 Experimental Procedure

Ingots with a chemical composition of Cu₅₀Zr₅₀ (in at.%) were prepared by arc melting appropriate amounts of Cu (99.99%) and Zr (99.7%) in a high-purity Ar (99.9999%) atmosphere. 40- μ m-thick and 15-mm-wide glassy ribbons

were prepared from the arc-molten pre-alloy using single-roller melt spinning under argon atmosphere. In order to investigate the correlation between the corrosion rate and the changes in excess free volume in amorphous alloys, the as-prepared ribbons were annealed isothermally for various time periods (0, 5, 10, 15, 20 min) below the glass transition temperature (623 K) under flowing high-purity argon atmosphere. To avoid oxidation during annealing, the glassy ribbons were sealed in a quartz tube with a vacuum of 10^{-4} Pa. The thermal stability and relative free volume changes in the ribbons were measured using differential scanning calorimetry (DSC, PerkinElmer DSC 7) at a heating rate of 40 K/min under high-purity argon atmosphere.

The as-spun and annealed Cu₅₀Zr₅₀ amorphous ribbons were examined by X-ray diffraction (XRD, Cu $K\alpha$). The detailed microstructural changes were examined using high-resolution transmission electron microscopy (HRTEM, FEI Tecnai G2, 200 kV). The samples were perforated for HRTEM observation by chemical jet thinning (Automatic twin-jet electropolisher, Fischione Instruments) using a 20 vol% solution of nitric acid in ethanol at 233 K.

The corrosion behavior of each sample was first evaluated by the immersion test. The samples were immersed into a 3.5 wt% NaCl aqueous solution, which was prepared from reagent grade chemicals and deionized water, for 48 h at room temperature. The samples subjected to corrosion tests were cleaned chemically using 20 wt% CrO₃ + 1 wt% AgNO₃ solution at 353 K for 3 min, followed by washing with distilled water and acetone. The weight losses of each sample were measured, and the corrosion rates were estimated from the weight loss:

$$\text{Corrosion rate (mm/year)} = \frac{87.6 \times \Delta W}{\rho \times A \times t},$$

where ΔW is the weight loss (g) during the immersion test, ρ is the density (g/cm³), A is the exposed area (cm²) of the sample, and t is the exposure time (h) in the solution. The surfaces of the corroded samples were observed using optical microscopy.

In order to evaluate the characteristics behaviors of electrochemical corrosion, the potentiodynamic polarization tests were carried out using a conventional three-electrode system in a 0.1 N NaCl aqueous solution at room temperature. The working, counter, and reference electrodes were the amorphous alloy, Pt, and Ag/AgCl, respectively. The area of the working electrode exposed to the solution was 1 cm². Electrochemical impedance spectroscopy (EIS) was performed in a frequency range from 100 kHz to 10 MHz with amplitude potential of $V_{\text{rms}} = 10$ mV at an open-circuit voltage using a Solartron

1260 Frequency Response Analyzer coupled to a Solartron 1287 Electrochemical Interface.

In order to explore the changes in the excess free volume during annealing in the $\text{Cu}_{50}\text{Zr}_{50}$ amorphous alloy, conventional MD simulations were performed using the embedded-atom method (EAM) potential [21, 22] as implemented in Large-scale Atomic/Molecular Massively Parallel Simulator (LAMMPS) [23]. Approximately 32,000 atoms of Cu and Zr corresponding to the stoichiometric composition of $\text{Cu}_{50}\text{Zr}_{50}$ were packed into the simulation cell with dimensions of $7.92 \times 7.92 \times 7.92$ nm and then heated to a temperature (2100 K) above the melting point of the alloy. The model alloy was relaxed for 4 ns at the same temperature to obtain randomly mixed liquid structures. This liquid was quenched to 300 K at the cooling rate of $5 \times 10^{11} \text{ K s}^{-1}$ to produce the computational amorphous alloy sample. An NPT Nosé–Hoover barostat [24] was used during the quenching process, and a periodic boundary condition (PBC) was applied to all directions to eliminate surface effects. To investigate the structural changes, i.e., changes in free volume, during annealing, the amorphous alloy was annealed for 4×10^7 steps corresponding to approximately 40 ns at 650 K which is below the sub- T_g temperature. The atomic-scale structures of the alloy were analyzed in terms of short-range orders using the weighted Voronoi tessellation technique [25].

3 Results and Discussion

Two different amorphous samples corresponding to $\text{Cu}_{50}\text{Zr}_{50}$ were used for the study: as-spun $\text{Cu}_{50}\text{Zr}_{50}$ and the $\text{Cu}_{50}\text{Zr}_{50}$ sample annealed for 20 min at 623 K (referred to as the ‘20-min-annealed sample’). Figure 1a shows the XRD patterns recorded from the as-spun and the 20-min-annealed samples. A broad halo peak, the characteristics of an amorphous structure, is evident from the XRD patterns of both samples (Fig. 1a). The HRTEM image of the 20-min-annealed sample also shows a feature-less contrast without any lattice fringes, constructing a typical amorphous structure (Fig. 1b). The electron diffraction pattern corresponding to this image (see the inset in Fig. 1b) further confirms the aforementioned result. These results support that both samples are free from crystallization.

Figure 2 shows the representative thermograms recorded from the as-spun $\text{Cu}_{50}\text{Zr}_{50}$ amorphous sample and the sample subjected to sub- T_g annealing. The DSC thermograms (Fig. 2a) showed that the amount of exothermic heat around the crystallization temperature (~ 750 K), i.e., the crystallization enthalpy, is the same for both samples, indicating that the crystallization did not occur during sub- T_g annealing. In order to investigate the change in the excess free volume after annealing, the regions

Fig. 1 **a** XRD patterns of the as-spun and the 20-min-annealed $\text{Cu}_{50}\text{Zr}_{50}$ samples, **b** HRTEM image and corresponding diffraction pattern of the 20-min-annealed $\text{Cu}_{50}\text{Zr}_{50}$ sample

corresponding to the α -relaxation were magnified (Fig. 2b). The exothermic enthalpy associated with the structural relaxation of the as-spun sample ranges from -4.70 to -5.43 J/g, whereas that of the annealed sample ranges from -0.11 to -0.34 J/g. This exothermic heat measured from the annealed samples is associated with the α -relaxation, which corresponds to the annihilation of short-range orders with loose atomic packing or excess free volume [26, 27] that was created either during quenching or subsequent deformation. This exothermic heat is proportional to the annihilation of disorder (or free volume) associated with the structural relaxation during annealing below T_g , indicating that the amorphous structures with different degrees of disorder have formed [14, 28]. Therefore, the measurement of the enthalpy associated with the α -relaxation provides a suitable means that enables the assessment of a glassy structure with different degrees of disorder. As

Fig. 2 **a** DSC thermograms recorded from the as-spun and the 20-min-annealed samples, **b** magnified view of regions in the vicinity of the glass transition temperature, showing that annealing of the samples for different time changes the exothermic heat corresponding to α -relaxation

such, the two samples in Fig. 2 display two different structures with differing degree of disorder or free volume.

To investigate the effect of sub- T_g annealing on the corrosion resistance, we selected the as-spun and the 20-min-annealed samples that exhibit the largest difference of the exothermic heat (Fig. 2). The corrosion behaviors of the samples were examined using the immersion test to relate the degree of structural disorder to the corrosion resistance. Figure 3 shows the weight loss (equivalently, the corrosion rate) of the as-spun and the annealed samples, which contain different amounts of excess free volume. In fact, the immersion test is effective in determining the corrosion rates and provides an accurate and reliable measurement. The corrosion rate of the 20-min-annealed sample is 0.2 mm/year, whereas the as-spun sample exhibited a much higher rate of 1.1 mm/year. Since the amount of excess free volume is comparatively smaller in

Fig. 3 Corrosion rates measured from the as-spun and the 20-min-annealed samples using immersion tests

the annealed sample than the as-spun sample, the improved corrosion resistance of the annealed sample is attributed to the reduced free volume.

Having identified that the corrosion resistance of the amorphous alloys depends on the amount of free volume that quantifies the structural disorder of the samples, we next observed the surface structures of the amorphous samples. Figure 4 shows the optical micrographs recorded from the surfaces of the as-spun and the annealed samples subjected to immersion tests in a 1 N NaCl aqueous solution for 48 h. Corrosion is generally accompanied by the formation of pits from the surfaces of both samples. These pits observed from both samples were formed as a result of the chemical attack of the NaCl aqueous solution, and the number density of the pits is inversely proportional to the corrosion resistance. As the number density of pits is much smaller in the 20-min-annealed sample than in the as-spun one, the corrosion resistance is higher in the annealed alloy than the as-spun one. This indicates that the annealed alloy

Fig. 4 Surface morphologies of the samples immersed in 1 N NaCl aqueous solution for 4 h at the room temperature, showing the formation of pits in **a** the as-spun sample, **b** the 20-min-annealed sample

has a more stable energy state than the as-spun one by having a smaller free volume.

Corrosion reactions including pitting are accompanied not only by chemical reactions, but also by electrochemical reactions between the alloy and the solution under an electric potential. Electrochemical corrosion behaviors of the amorphous alloys were examined by promoting the electrochemical reactions using the potentiodynamic polarization method. Potentiodynamic polarization tests were performed in a 0.1 N NaCl solution in air at room temperature, in order to measure the changes in the corrosion current (I_{corr}) and the corrosion potential (E_{corr}) in the samples with different amounts of excess free volume. Figure 5a shows the polarization curves of the as-spun and the 20-min-annealed samples. As the excess free volume reduces, the corrosion density current decreases from 0.94 to 0.19 $\mu\text{A}/\text{cm}^2$, while the corrosion potential increases from -0.17 to -0.06 V. Considering that a material with a high corrosion resistance usually has a lower anodic current density and a nobler corrosion potential [29], the results in Fig. 5a indicate that the reduced free volume

caused by sub- T_g annealing leads to an improvement in the electrochemical corrosion resistance of the amorphous alloy.

The above result was confirmed again by evaluating the corrosion penetration rate (CPR) using the corrosion current density (I_{corr}/A) measured from the potentiodynamic polarization tests. Following Faraday's law, the CPR ($\mu\text{m}/\text{year}$) can be expressed as $3.27 (M I_{\text{corr}})/(\rho A)$, where M is the atomic fraction-weighted values of the atomic weight (g/mol), I_{corr}/A is the corrosion current density (mA/cm^2) measured from the potentiodynamic polarization tests using the Tafel extrapolation method, m is the ionic valence, and ρ is the density (g/cm^3) [15, 30, 31]. The CPRs of the as-spun and the annealed samples calculated in this way are 11.2 and 2.2 $\mu\text{m}/\text{year}$, respectively. The CPRs calculated using the corrosion current density obtained from the potentiodynamic polarization tests are very different from those measured from the immersion tests; they differ by two order of magnitude. The difference of the CPRs obtained from the potentiodynamic polarization and the immersion tests probably arises because the mass loss of the samples occurred during the immersion tests is predominantly localized at the surface of the sample to form pits. Therefore, the CPRs obtained from the immersion tests are larger than those calculated from the potentiodynamic polarization tests. Nevertheless, the ratio between the CPRs of the as-spun and the annealed samples is nearly the same as that between the corrosion rates measured from the immersion tests (as-spun:annealed = 5:1). Both results in Figs. 3 and 5 consistently show that the as-spun sample is more vulnerable to corrosion than the annealed sample.

The electrochemical impedance spectra (EIS) of each alloy are represented by the Nyquist plots as shown in Fig. 5b. Both samples displayed the semicircular curves in the Nyquist diagrams. As the diameter of the semicircle is proportional to the corrosion resistance [32], the increase in the diameter of the semicircle, from 20.5 to 27.4 $\text{k}\Omega/\text{cm}^2$, again indicates that the corrosion resistance of the annealed sample increases significantly due to the reduced free volume. From this perspective, the isothermal heat treatment below T_g is an effective means of improving the corrosion resistance of amorphous alloys to both the chemical and electrochemical reactions. Combining all aforementioned results, the excess free volume is considered to be a crucial factor that determines the corrosion behavior of amorphous alloys.

To clarify the structural origin responsible for the decreased free volume associated with annealing, the atomic structure of the $\text{Cu}_{50}\text{Zr}_{50}$ amorphous alloy was resolved using conventional MD simulations. The structural changes in the amorphous alloy samples were analyzed in terms of the degree of short-range order, especially

Fig. 5 **a** Potentiodynamic polarization curves, **b** Nyquist plots of the as-spun and the 20-min-annealed samples in a 0.1 N NaCl solution at room temperature

the population/fraction of icosahedra using the weighted Voronoi tessellation method [33]. The changes in the structures of the as-cast sample and the 20-min-annealed sample were visualized by the changes in the densely packed polyhedra (icosahedra) and the remaining loosely packed polyhedra (Fig. 6). When comparing the distribution of icosahedra in the two samples in Fig. 6a, b, the annealed sample contains considerably larger numbers of icosahedra, while loosely polyhedral are abundant in the as-cast sample (see Fig. 6c, d). Considering that, of all polyhedra, icosahedra are the structure with the lowest energy state [34, 35], the annealed alloy with a large fraction of icosahedra is energetically more stable and thus can be more resistant to corrosion.

In order to quantitatively evaluate the energy state of the annealed samples, the variations of the population of icosahedra and the corresponding energy state were calculated as a function of annealing time using MD simulations (Fig. 7). The population of icosahedra in the alloy

increases linearly with annealing time (Fig. 7a). This structural change in the amorphous alloy is caused by the transformation of loosely packed structures to more densely packed structures such as icosahedra. During this relaxation process, the excess free volume with a high energy state annihilates, which lowers the potential energy of the alloy (Fig. 7b). Despite the severe spatiotemporal limitation of MD simulations, MD simulation results can explain the structural origin responsible for the improved corrosion resistance exhibited by the annealed amorphous alloys. The present analyses on the improved corrosion resistance of the annealed alloy are consistent with the previous interpretation based on the structural relaxation associated with annealing [36, 37].

The annihilation of the excess free volume associated with annealing can improve the passivity and the corrosion resistance of the amorphous alloys owing to their low energy state. This analysis agrees well with previous studies reporting that the passivity and corrosion resistance

Fig. 6 Snapshots showing changes in the population of icosahedra and other polyhedra in the $\text{Cu}_{50}\text{Zr}_{50}$ amorphous alloy during the annealing process. The distribution of icosahedra in **a** the as-spun and **b** the annealed alloy shows that the population of icosahedra is increased after annealing, whereas the population of loosely packed polyhedra is decreased in **c** the as-spun, **d** the annealed alloy

Fig. 7 Variations of **a** the population of icosahedra, **b** the potential energy of the Cu₅₀Zr₅₀ amorphous alloy calculated as function of annealing time

are improved by the elimination of the excess free volume and vacancies [15, 38, 39]. Considering that icosahedra and icosahedron-like structures are the energetically stable structures, the increase in the icosahedral population (Fig. 7a) corresponds to the increase in the activation energy barrier for disrupting the polyhedral structure via chemical reactions. The increased activation energy barrier required to disrupt the icosahedral structures in turn can improve the chemical stability of the amorphous alloys [40–44]. Therefore, sub- T_g annealing can be a useful technique to improve the corrosion resistance of amorphous alloys under simulated marine environments [45–47], which is a possible subject for a future work.

4 Conclusion

According to our experiments on the corrosion resistance of an amorphous alloy, we found that the corrosion resistance of the alloy was improved significantly after sub- T_g

annealing. Calorimetry studies showed that heating below T_g causes the partial annihilation of the excess free volume in the amorphous alloy. As was evidenced by the exothermic enthalpy generated during heating, the annihilation of free volume corresponds to the relaxation of the structure to a lower energy state, indicating that annealed structure is energetically stable. MD simulations showed that this structural state of the alloy is associated with the formation of icosahedra and icosahedron-like structures. Both experimental and simulation studies suggest that the isothermal heat treatment below sub- T_g temperature can be a feasible technique for improving the corrosion resistance of amorphous alloys without adding a passive element.

Acknowledgements This research was supported financially by the Industrial Core Technology Development Project (No. 10033222).

References

- [1] C. Dai, H. Guo, Y. Shen, Y. Li, E. Ma, J. Xu, *Scr. Mater.* **54**, 1403 (2006)
- [2] D. Xu, B. Lohwongwatana, G. Duan, W.L. Johnson, C. Garland, *Acta Mater.* **52**, 2621 (2004)
- [3] C.L. Qin, W. Zhang, K. Asami, H. Kimura, X.M. Wang, A. Inoue, *Acta Mater.* **54**, 3713 (2006)
- [4] A. Inoue, W. Zhang, T. Zhang, K. Kurosaka, *Acta Mater.* **49**, 2645 (2001)
- [5] J. Das, M.B. Tang, K.B. Kim, R. Theissmann, F. Baier, W.H. Wang, *Phys. Rev. Lett.* **94**, 205501 (2005)
- [6] O.J. Kwon, Y.C. Kim, K.B. Kim, Y.K. Lee, E. Fleury, *Met. Mater. Int.* **12**, 207 (2006)
- [7] K. Asami, C.L. Qin, T. Zhang, A. Inoue, *Mater. Sci. Eng. A* **375–377**, 235 (2004)
- [8] M.K. Tam, C.H. Shek, *Mater. Chem. Phys.* **100**, 34 (2006)
- [9] C. Qin, K. Asami, T. Zhang, W. Zhang, A. Inoue, *Mater. Trans.* **44**, 749 (2003)
- [10] M.K. Tam, S.J. Pang, C.H. Shek, *J. Non-Cryst. Solids* **353**, 3596 (2007)
- [11] N. Chen, D.V. Louzguine, S. Ranganathan, A. Inoue, *Acta Mater.* **53**, 759 (2005)
- [12] H.K. Kim, M. Lee, K.R. Lee, J.C. Lee, *Acta Mater.* **61**, 6597 (2013)
- [13] P. Murali, U. Ramamurty, *Acta Mater.* **53**, 1467 (2005)
- [14] A. Slipenyuk, J. Eckert, *Scr. Mater.* **50**, 39 (2004)
- [15] W.H. Jiang, F. Jiang, B.A. Green, F.X. Liu, P.K. Liaw, H. Choo, K.Q. Qiu, *Appl. Phys. Lett.* **91**, 041904 (2007)
- [16] Y. Masumoto, A. Inoue, A. Kawashima, K. Hashimoto, A.P. Tsai, T. Masumoto, *J. Non-Cryst. Solids* **86**, 121 (1986)
- [17] F. Spaepen, *Acta Metall.* **25**, 407 (1977)
- [18] A.S. Argon, *Acta Metall.* **27**, 47 (1979)
- [19] T. Egami, K. Maeda, V. Vitek, *Philos. Mag. A* **41**, 883 (2006)
- [20] D. Suh, R.H. Dauskardt, *J. Non-Cryst. Solids* **317**, 181 (2003)
- [21] Y.Q. Cheng, A.J. Cao, H.W. Sheng, E. Ma, *Acta Mater.* **56**, 5263 (2008)
- [22] Y.M. Kim, B.J. Lee, *J. Mater. Res.* **23**, 1095 (2008)
- [23] S. Plimpton, *J. Comput. Phys.* **117**, 1 (1995)
- [24] W.G. Hoover, *Phys. Rev. A* **34**, 2499 (1986)
- [25] F.M. Richards, *J. Mol. Biol.* **82**, 1 (1974)
- [26] K.N. Lad, *J. Non-Cryst. Solids* **404**, 55 (2014)
- [27] M.E. Launey, R. Busch, J.J. Kruzic, *Acta Mater.* **56**, 500 (2008)

- [28] K.W. Park, C.M. Lee, M. Wakeda, Y. Shibutani, M.L. Falk, J.C. Lee, *Acta Mater.* **56**, 5440 (2008)
- [29] S.L. Wang, S. Yi, *Intermetallics* **18**, 1950 (2010)
- [30] E.E. Stansbury, R.A. Buchanan, *Fundamentals of Electrochemical Corrosion* (ASM International, Materials Park, 2000), p. 146
- [31] S.F. Guo, H.J. Zhang, Z. Liu, W. Chen, S.F. Xie, *Electrochem. Commun.* **24**, 39 (2012)
- [32] X.L. Zhang, G. Chen, T. Bauer, *Intermetallics* **29**, 56 (2012)
- [33] M.I. Aoki, K. Tsumuraya, *J. Chem. Phys.* **104**, 6719 (1996)
- [34] S.Q. Wu, C.Z. Wang, S.G. Hao, Z.Z. Zhu, K.M. Ho, *Appl. Phys. Lett.* **97**, 021901 (2010)
- [35] W.X. Song, S.J. Zhao, G. Wang, *J. Chem. Phys.* **143**, 114503 (2015)
- [36] A. Aditya, H.F. Wu, H. Arora, S. Mukherjee, *JOM* (2017). doi:[10.1007/s11837-017-2384-9](https://doi.org/10.1007/s11837-017-2384-9)
- [37] K.W. Park, C.M. Lee, E. Fleury, J.C. Lee, *Scr. Mater.* **61**, 363 (2009)
- [38] N.R. Tailleart, R. Huang, T. Aburada, D.J. Horton, J.R. Scully, *Corros. Sci.* **59**, 238 (2012)
- [39] D.P. Wang, S.L. Wang, J.Q. Wang, *Corros. Sci.* **59**, 88 (2012)
- [40] P. Marcus, *Electrochim. Acta* **43**, 109 (1998)
- [41] R.S. Lillard, *Electrochem. Solid-State Lett.* **6**, B29 (2003)
- [42] R.S. Lillard, G.F. Wang, M.I. Baskes, *J. Electrochem. Soc.* **153**, B358 (2006)
- [43] X.J. Liu, X.D. Hui, H.Y. Hou, T. Liu, G.L. Chen, *Phys. Lett. A* **372**, 3313 (2008)
- [44] R. Frahm, R. Haensel, P. Rabe, *J. Phys. F Met. Phys.* **14**, 1333 (1984)
- [45] J.L. Cui, Z.D. Yao, Y.F. Cui, F.P. Cheng, T. Xiao, H.L. Sun, R.J. Tian, J.C. Sun, *Acta Metall. Sin. (Engl. Lett.)* **29**, 920 (2016)
- [46] N.W. Dai, J.X. Zhang, Q.M. Chen, X. Zhang, F.H. Cao, J.Q. Zhang, *Acta Metall. Sin. (Engl. Lett.)* **29**, 373 (2016)
- [47] H.L. Ming, S.Y. Wang, Z.M. Zhang, J.Q. Wang, E.H. Han, W. Ke, *Acta Metall. Sin. (Engl. Lett.)* **29**, 89 (2016)