Interpretation of the Habit Plane of δ Precipitates in Superalloy Inconel 718

Wen-Sheng Xu¹ · Xiao-Peng Yang² · Wen-Zheng Zhang¹

Received: 18 September 2017 / Revised: 29 November 2017 / Published online: 19 December 2017
© The Chinese Society for Metals and Springer-Verlag GmbH Germany, part of Springer Nature 2017

Abstract

A calculation method based on a combination of Δg parallelism rule, good matching site (GMS) analysis, CSL/DSCL (coincidence site lattice/displacement shift complete lattice) and the O-lattice theory has been applied to interpret the observation of the habit plane (HP) of the δ precipitates and the linear defects in the HP in an Inconel 718 superalloy. The small scattering in the HP orientation around an ideal rational plane is interpreted by the existence of a mixture of two types of steps with different heights and inclinations. These steps play a significant role to enhance the degree of matching in the HP. They are associated with secondary dislocations, with Burgers vectors of $1/6[1\ 1\ \bar{2}]_{\gamma}/1/3[0\ 0\ 1]_{\delta}$, and with a direction parallel to a near-invariant line along $[1\ \bar{1}\ 0]_{\gamma}$. The spacing of the secondary dislocations projected on the terrace plane is around 6.3 nm. The calculated dislocation structure is in good agreement with the observation.

Keywords Good matching site · Dislocation · Orientation relationship · Interfacial structure · Coincident site lattice

1 Introduction

Nickel-based Inconel 718 superalloy has a very wide range of applications in the aerospace industry as well as the oil industry due to its excellent high-temperature performance [1]. However, the mechanical properties of this alloy will become deteriorated when the alloy is employed at a temperature higher than 650 °C for a long period of time [2–6]. The phase transformation of the dispersed γ'' precipitates to large platelike δ precipitates at high temperature is considered as a dominating cause for the performance degradation [7]. A correct understanding of the morphology of δ precipitates is essential to better

control the microstructure evolution of this material during service.

Precipitation of the detrimental δ phase from the γ matrix in the Inconel 718 has been extensively investigated in numerous experimental studies [8–11]. Profuse crystallographic information has been collected from these investigations, and the obtained results are consistent with each other. The habit plane (HP) of the precipitates has been found to deviate slightly from the close-packed plane $(1\ 1\ 1)_{\gamma}$ of the matrix, which is parallel to the plane $(0\ 1\ 0)$ of the precipitates. The structure of the HP has been investigated systematically both experimentally and theoretically by Liang and Reynolds [11]. In their investigation, the alloy samples were solutionized at 1463 K for 3 h before quenching in iced brine and then isothermally aged at 1203 K for at least 50 h for precipitating plate-shaped δ from the matrix. The experimental average HP determined by a trace analysis on thirty precipitates is $(1\ 1.05\ 1.03)_{\gamma}$, and the largest deviation from this plane is 5.2 deg [11]. Two types of parallel linear defects were observed in the HP, both lying parallel to the conjugate direction of $[1\ \bar{1}\ 0]_{\gamma}/[1\ 0\ 0]_{\delta}$ [11]. Since the HP must contain $[1\ \bar{1}\ 0]_{\gamma}$, there might be a typo in the HP in [11]. Namely, the HP orientation is possibly either $(1.05\ 1.03\ 1)_{\gamma}$ or $(1.03\ 1.05\ 1)_{\gamma}$ for the interface to contain $[1\ \bar{1}\ 0]_{\gamma}$ with a

Available online at <http://link.springer.com/journal/40195>

✉ Wen-Zheng Zhang
zhangwz@tsinghua.edu.cn

Wen-Sheng Xu
xuwendsheng1990@126.com

Xiao-Peng Yang
yangxp@gmail.com

¹ Key Laboratory of Advanced Materials (MOE), School of Materials Science and Engineering, Tsinghua University, Beijing 100084, China

² Oxford Instruments Beijing Office, Beijing 100085, China

smaller experimental error. The corrected index $(1.05\ 1.03\ 1)_{\gamma}$ will be used for comparison in this study. According to Liang and Reynolds [11], two types of misfit dislocations were observed in the HP. The majority dislocations have an average spacing around 7 nm and a possible Burgers vector $1/6[1\ 1\ \bar{2}]_{\gamma}$. The authors have developed a near coincidence site (NCS) model and applied it to interpret the observed orientation relationship (OR) and HP between the δ precipitates and the γ matrix. However, their model encounters ambiguity in a trial and erroneous determination of the interfacial dislocation structures. The lattice correspondence, which is essential for calculating the structure of interfacial misfit dislocations, is ignored in the NCS model. The messages of the lattice correspondence and admissible Burgers vectors of the dislocations are buried in an NCS pattern. Their association has been explained in terms of the structure within a good matching site (GMS) cluster [12], equivalent to a localized region consisting a group of NCSs. However, NCS model claims an advantage of the model being independent of the lattice correspondence, without providing this information available in the NCS pattern.

In this work, CSL/DSCL (CSL stands for coincidence site lattice and DSCL stands for displacement shift complete lattice) and the O-lattice theory [13, 14], good matching site (GMS) analysis, and $\Delta\mathbf{g}$ parallelism calculation are combined to obtain a proper description of the dislocation structure in the HP of δ precipitates. The O-lattice theory is a powerful mathematical tool to calculate the configuration of interfacial dislocations. An essential input for the calculation is the misfit strain field. The information for specifying the misfit strain field includes the orientation relationship (OR) and the lattice parameters of the two phases, which can be taken from measurement. In addition, one also needs to specify the lattice correspondence for fit. In simple systems, such as an FCC/BCC system consisting of simple metallic phases, the Bain lattice correspondence is well established [15]. The lattice correspondence for the HP between δ precipitates and the matrix in Inconel 718 is not obvious. This system belongs a case of so-called secondary preferred state, where one-to-one lattice fitting correspondence is impossible, since the lattice parameters in this system differ significantly [14]. To define the misfit strain field, one must first specify the secondary preferred state, as a reference to a low-energy structure of “fit” between the misfit dislocations. The acquisition of this preferred state in the HP of δ precipitates can be guided according to the periodic structure within a GMS cluster [12].

While the measured OR may be taken as the input, there usually has an optimum OR within the range of experimental uncertainty of the measured OR, corresponding to a

singular interfacial structure in a preferred interface. If the observed HP has a reproducible irrational orientation, deviating slightly from a low-index plane, the HP will contain a group of steps with the nearby low-index planes being the terrace plane, i.e., $(1\ 1\ 1)_{\gamma}$ and $(0\ 1\ 0)_{\delta}$ for the δ precipitates. Since the HP contains $[1\ \bar{1}\ 0]_{\gamma}/[1\ 0\ 0]_{\delta}$ as the direction of the linear defects, the step direction must be parallel to this pair of vectors lying in both the HP and the terrace plane. In a singular interface with a small angle with respect to the terrace plane, the projected misfit displacement associated with steps must compensate the misfit between the rows in different lattices in the terrace plane [16]. Therefore, the interface geometry for the misfit compensation can be analyzed in two dimensions in terms of finding the trace of the HP on the plane normal to the steps. In the description of the 2D model, the compensation condition is similar to that described by the topological model (TM) [17] and the edge-to-edge model [18, 19] for a stepped interface. However, the interpretation of the displacement associated with the steps can be classified into two cases [20]. In case 1, there is an invariant line across the steps, such that the total misfit displacement along the invariant line is zero [21]. The vector connecting two steps along the HP trace can be decomposed into a component on the step riser and one on the terrace plane. The misfit displacement vectors associated with these two vector components must have the same values but opposite directions for the zero misfit summation. In case 2, there is a secondary dislocation associated with each step [20, 22]. Therefore, the total misfit displacement along a vector connecting the O-lattice elements in the adjacent layers of the terrace, again along the HP trace, is the Burgers vector of the secondary dislocation associated with the step crossed by the vector. The key difference between the two cases of misfit compensation is that the misfit displacement along a vector parallel to the HP trace is zero in case 1 and is nonzero in case 2. The TM model and the edge-to-edge model [18, 19] mainly deal with case 1, while the present study concerns case 2, as explain later. The small angular deviation from the rational OR is necessary to ensure the misfit compensation, when the step heights in two lattices are not exactly identical. This angle and the orientation of the HP trace for both cases can be conveniently calculated based on a $\Delta\mathbf{g}$ parallelism rule in reciprocal space, as explained in details in a review [20]. Here, a $\Delta\mathbf{g}$ vector is a vector connecting two different diffraction spots, defined by reciprocal vectors $\mathbf{g}_{\gamma}$ and $\mathbf{g}_{\delta}$, from the lattice γ and δ , respectively. Therefore, the OR to meet the misfit compensation condition can be calculated as an OR to cause a set of $\Delta\mathbf{g}$'s parallel. The direction of the parallel $\Delta\mathbf{g}$'s defines the HP normal. The edges of terrace planes defined in different lattices usually match in the determined HP, as

Table 1 Initial OR and lattice parameters of the superalloy 718

Phase	γ	δ
Compound	Ni	Ni ₃ Nb
Structure	FCC (A1)	Orthorhombic (DOa)
Space group	Fm $\bar{3}$ m (225)	Pmmn (59)
Parallel vectors	$[1\bar{1}0]_\gamma$	$[100]_\delta$
Parallel planes	$(111)_\gamma$	$(010)_\delta$
Lattice parameters (nm)	$a_\gamma = 0.3616$	$a_\delta = 0.5141$ $b_\delta = 0.4231$ $c_\delta = 0.4534$

also required by the edge-to-edge matching model. The edge-to-edge matching model emphasizes the matching between plane edges, especially the planes serving the terrace planes in two phases. However, matching between lattices in the terrace plane, i.e., the secondary preferred state in the terrace plane, is emphasized in the present study as reference of fit for determining the interfacial dislocation structure.

This study will first identify the optimum OR and corresponding HP based on the Δg parallelism rule [20, 23]. Then, a GMS pattern will be constructed to guide the selection of the constrained CSL for preferred state and hence the lattice correspondence. The interfacial dislocation structure in the HP will be determined using the O-lattice theory [13, 14]. The calculation results will be tested against the experimental results in the literature [10, 11].

2 Calculation Procedure

The initial OR and the lattice parameters adopted by Liang and Reynolds [11] are also adopted in this calculation because the fluctuation of the data in the literature is small [8–10, 24]. These data are listed in Table 1. The atomic distances along the parallel vectors $[1\bar{1}0]_\gamma$ and $[100]_\delta$ in two lattices are almost identical, with a misfit around 0.6%. This direction is regarded as a near-invariant line direction. As expected, the HP contains this good matching direction. Another direction needed to specify the orientation of the stepped HP is determined by the Δg parallelism rule, as explained below.

2.1 Determination of the OR and Preferred Interface Based on Δg Parallelism Rule

For the steps in the HP to cancel the misfit in the terrace plane, the HP must be normal to a group of parallel Δg 's. Exact parallelism of Δg 's may not be realized in a rational OR, but potential parallel Δg 's can often be estimated from the diffraction patterns measured experimentally [11]. To determine ideal OR corresponding to the geometry of exactly parallel Δg 's, we followed the method for solving a quasi-invariant line in a system consisting of cementite and austenite [23]. The analysis was mainly made in reciprocal space. Overlapped reciprocal points in the initial nominal OR with $(111)_\gamma // (010)_\delta$ and $[1\bar{1}0]_\gamma // [100]_\delta$ are shown in Fig. 1, which follows the diffraction pattern in [11]. A specific orthonormal coordinate system for the calculation of misfit deformation has been selected, such that the x -, y -, z -axes are parallel to reciprocal vectors of $(111)_\gamma$, $(11\bar{2})_\gamma$ and $(1\bar{1}0)_\gamma$ (Fig. 1). Three pairs of reciprocal spots circled

Fig. 1 According to the initial OR, the simulated diffraction patterns with zone axis: **a** $[1\bar{1}0]_\gamma // [100]_\delta$, **b** $[111]_\gamma // [010]_\delta$

Table 2 Matrices used for OR calculations

	Matrix
$\mathbf{G}_\gamma^\gamma$	$\begin{bmatrix} 1 & 1 & 1 \\ \bar{1} & \bar{1} & 1 \\ 2 & \bar{2} & 0 \end{bmatrix}$
$\mathbf{G}_\delta^\delta$	$\begin{bmatrix} 0 & 2 & 0 \\ 0 & 0 & 2 \\ 4 & 0 & 0 \end{bmatrix}$
$\mathbf{G}_\gamma$	$\begin{bmatrix} 4.7900 & 0 & 0 \\ -1.5967 & 4.5160 & 0 \\ 0 & 0 & 7.8220 \end{bmatrix}$
$\mathbf{G}_\delta$	$\begin{bmatrix} 4.7270 & 0 & 0 \\ 0 & 4.4111 & 0 \\ 0 & 0 & 7.7806 \end{bmatrix}$

in Fig. 1 have been chosen to define three non-coplanar row vectors in matrices $\mathbf{G}_\gamma^\gamma$ and $\mathbf{G}_\delta^\delta$, respectively. Here, the superscripts indicate that these vectors are described on the basis of their own lattices. These matrices are listed in Table 2. Table 2 also contains matrices $\mathbf{G}_\gamma$ and $\mathbf{G}_\delta$, with row vectors expressed in the orthonormal coordinate system in Fig. 1, corresponding to the row vectors in $\mathbf{G}_\gamma^\gamma$ and $\mathbf{G}_\delta^\delta$. The corresponding row vectors circled in Fig. 1a are connected by $\Delta\mathbf{g}$'s that are to be parallel after a particular

rotation. It can be proved with linear algebra that a group of $\Delta\mathbf{g}$'s in Fig. 1a will be all parallel to each other after this rotation. The initial deformation matrix corresponding to the initial OR is determined by: $\mathbf{A}_0 = \mathbf{G}_\delta^{-1}\mathbf{G}_\gamma$, as given in Table 3. Since all related vectors lie in the $\mathbf{x}\text{--}\mathbf{y}$ plane, normal to $[1\bar{1}0]_\gamma/[100]_\delta$ ($\mathbf{l}_2$), one can determine the rotation angle by solving a 2D problem. With an input of $\mathbf{A}_{02}$, which is a 2×2 matrix consisting of elements in the first two rows and columns in $\mathbf{A}_0$ in Table 3, the rotation angle and hence the appropriate 2×2 rotation matrix $\mathbf{R}_2$ can be solved analytically in the condition of $|\mathbf{R}_2\mathbf{A}_{02}\mathbf{I}| = 0$ [25, 26]. Here, $\mathbf{I}$ is a 2×2 unit matrix. Left multiplying the matrix $\mathbf{A}_0$ by the corresponding 3×3 rotation matrix $\mathbf{R}$, as in Table 3, one obtains the final deformation matrix $\mathbf{A} = \mathbf{R}\mathbf{A}_0$. This rotation will cause $\mathbf{A}$ to become an invariant line strain, which is a quasi-invariant line ($\mathbf{l}_1$) in the present case. The direction of $\mathbf{l}_1$, which satisfies $\mathbf{A}\mathbf{l}_1 = \mathbf{l}_1$, is the eigenvector corresponding to eigenvalue of one, as can be determined from a standard eigenproblem. The normal of HP ($\mathbf{n}$) can be determined from $\mathbf{n} = \mathbf{l}_1 \times \mathbf{l}_2$. It can also be determined as the orientation of the parallel $\Delta\mathbf{g}$'s, using $\Delta\mathbf{g}' = \mathbf{g}_\gamma' - \mathbf{g}_\gamma'\mathbf{A}^{-1}$, where $\mathbf{g}_\gamma$ is either of first two-row vectors in $\mathbf{G}_\gamma$ in Table 2.

The calculation results on the basis of γ lattice are listed in Table 3 with the matrices used in the calculation. The determined rotation angle is 0.05° (clockwise), which is negligibly small. Therefore, as illustrated in Fig. 2, the simulated diffraction pattern of the final OR is almost identical to the initial OR in Fig. 1, which agrees with the measured OR. This means that the measured OR can

Table 3 Calculated results of the OR and HP

Matrices and vectors		
Initial deformation matrix	$\mathbf{A}_0$	$\begin{bmatrix} 1.0133 & 0 & 0 \\ -0.3620 & 1.0238 & 0 \\ 0 & 0 & 1.0053 \end{bmatrix}$
Rotation matrix	$\mathbf{R}$	$\begin{bmatrix} 0.9999996 & -0.0009 & 0 \\ 0.0009 & 0.9999996 & 0 \\ 0 & 0 & 1 \end{bmatrix}$
Final deformation matrix	$\mathbf{A}$	$\begin{bmatrix} 1.0136 & -0.0009 & 0 \\ -0.3611 & 1.0238 & 0 \\ 0 & 0 & 1.0053 \end{bmatrix}$
Rotation angle	θ	$0.05^\circ(\text{clockwise})$
HP normal on lattice basis	$\mathbf{n}_\gamma'/\Delta\mathbf{g}'\text{s}$	$(1.15\ 1.15\ 1)_\gamma$

Fig. 2 Parallel $\Delta\mathbf{g}$'s and HP of the final OR in reciprocal space with zone axis $[1\bar{1}0]_\gamma/[100]_\delta$

effectively satisfy the $\Delta\mathbf{g}$ parallelism rule, as shown by a set of parallel $\Delta\mathbf{g}$'s in Fig. 2. Usually, when the sizes of the parallel $\Delta\mathbf{g}$'s are large, the determined HP belongs to case 2 [20]. The calculated HP normal to the parallel $\Delta\mathbf{g}$'s is $(1.15\ 1.15\ 1)_\gamma$, which deviates from the close-packed plane $(1\ 1\ 1)_\gamma$ by 3.77° . The measured average HP is $(1.05\ 1.03\ 1)_\gamma$, with maximum angular difference less than 5° from $(1\ 1\ 1)_\gamma$ [11]. Though the discrepancy between the calculated HP normal and the average measured value is small, a possible reason for this discrepancy will be discussed later.

2.2 Calculation of Interfacial Dislocation Structure

The O-lattice theory and an extended method for dislocation calculation [12–14, 27] have been applied to determine the interfacial dislocations. The final deformation matrix $\mathbf{A}$ for calculating the quasi-invariant line condition in Table 3 does not describe the secondary misfit strain. In order to obtain the input of secondary misfit strain field and the potential Burgers vectors of the secondary dislocations for the O-lattice calculation, we must specify the preferred state of the interface. The construction of the CSL representing the secondary preferred state is guided by examining the GMS distribution. The GMSs are constructed by interpenetrating the lattice points of both phases with the calculated OR, or simply with the initial OR since they are virtually identical. The two lattices are arranged with a lattice point from each lattice coincident at the origin $\mathbf{O}$. A GMS is defined by a pair of points from both lattices when the distance between the points is less than a selected good matching criterion [28]. The criterion for selection of GMS

Fig. 3 Distribution of GMSs in the central GMS clusters and different lattice points on different planes: **a** plane $(1\ 1\ 1)_\gamma/(0\ 1\ 0)_\delta$, **b** plane $(1\bar{1}0)_\gamma/(1\ 0\ 0)_\delta$

in the present study is based on the distance between adjacent lattice points, which must be less than 15% of the atomic distance in the matrix phase, following the value used in the structural ledge model [29] and NCS model [11]. Figure 3a, b demonstrates the distribution of GMSs on different planes. In each figure, the circle representing a GMS is centered at a δ lattice point. One can see from Fig. 3a that in the range of the figure, each lattice point from δ phase almost matches a lattice from the γ matrix in the plane $(1\ 1\ 1)_\gamma$ and $(0\ 1\ 0)_\delta$. However, the distribution of GMSs is much more sparse in the plane normal to the near-invariant line direction $[1\bar{1}0]_\gamma/[100]_\delta$, as shown in Fig. 3b. The result indicates good coincident matching in an interface parallel to $(1\ 1\ 1)_\gamma$ and $(0\ 1\ 0)_\delta$. The matching correspondence defined by GMS pairs in Fig. 3 will be used to construct a constrained CSL as the reference state for calculation of the secondary misfit.

The GMS distribution in Fig. 3a clearly suggests a secondary preferred state in the plane $(1\ 1\ 1)_\gamma$ and $(0\ 1\ 0)_\delta$, since matching between the two lattices is not in a one-to-one manner. While each lattice point in δ matches a lattice point in γ , only one out of four lattice point in γ finds a matching pattern in δ . However, the localized GMS distribution does not offer an association with the existence of the dislocations and deviation of the HP from the above parallel plane. To explore the association, we have extended the distribution of GMSs in a larger scale. Figure 4 shows the distributions of GMSs on the same planes as in Fig. 3 in a much larger scale. For the clarity of the illustration, only the GMSs and the lattice points of δ phase are

Fig. 4 Large-scale distribution of GMS clusters on different planes: **a** plane $(111)_{\gamma}/(010)_{\delta}$, **b** plane $(1\bar{1}0)_{\gamma}/(100)_{\delta}$. $x//[010]_{\delta}/[111]_{\gamma}$, $y//[001]_{\delta}/[112]_{\gamma}$, and $z//[100]_{\delta}/[1\bar{1}0]_{\gamma}$

plotted, as usual taken from the lattice with a larger unit cell. In Fig. 4a, on the plane $(111)_{\gamma}/(010)_{\delta}$, GMS clusters extend to large areas, and the spacing between the GMS clusters is also large. In Fig. 4b, the spacing is large between coplanar adjacent GMS clusters in the horizontal direction, marked by a dashed line, but the spacing is much smaller between non-coplanar adjacent GMS clusters. One will expect that an interface will contain much denser GMS clusters if it passes GMS clusters in different layers, connected by steps as marked by the solid line. The distribution of the GMS clusters in the stepped interface is shown in Fig. 5. In this figure, the GMS clusters are significantly denser in the stepped interface than the flat interface parallel to the plane $(111)_{\gamma}/(010)_{\delta}$ in Fig. 4a. This scenario is analogous to the structural ledge model applied to explaining the irrational HP in an fcc/bcc system [29]. This model shows that the interface contains a higher ratio of GMSs if the interface passes the good matching patches in different terraces, separated by structure ledges. However, in contrast to the irrational HP in the fcc/bcc system, which

belongs to the steps of case 1, the steps in present system belong to case 2, in which steps are associated with secondary dislocations, as shown later.

Having obtained the lattice correspondence for calculating the secondary misfit strain field, we need to specify the potential Burgers vectors for the secondary dislocations. They are determined on the basis of the CSL/DSCL theory [14]. By applying a small strain to lattice γ , the GMSs in Fig. 3 become constrained CSL (CCSL) points. This slight strain can be determined by the actual displacement between three nonlinearly related pairs of GMSs in the cluster containing the origin. The resulted CCSL in different planes is illustrated in Fig. 6a–c. The CCSL pattern is reserved by a relative displacement between the two lattices of δ and γ , only if the displacement vector is a lattice vector of the constrained displacement shift complete lattice (CDSCL). The small translation vectors in CDSCL are the candidates of the admissible Burgers vectors of the secondary dislocations [14]. Figure 6a, b shows, respectively, the structures of the CCSL and CDSCL in zero layer of δ lattice and the sequent layer below it. It is

Fig. 5 Configuration of GMS clusters on different terrace planes connected by steps on the stepped interface

important to note that the configurations of CCSL and CDSCL in different layers of the δ lattice are different. In Fig. 6a, each lattice point of δ phase is also a CCSL point. In Fig. 6b, where **O2** is a point located directly below the origin **O**, there is no CCSL point. In addition, the grid of CDSCL is much finer in Fig. 6b than that in Fig. 6a. Small CDSCL vectors are energetically favorable for serving the Burgers vectors of possible secondary dislocations. The difference in CDSCL vectors suggests the difference in the Burgers vectors of the dislocations in a step-free interface and stepped interface. Table 4 lists the matrices containing three column vectors representing the non-coplanar CCSL and CDSCL in different lattice coordinates. For convenience of calculation, these CCSL vectors are parallel to the selected orthonormal coordinates: $\mathbf{x} // [0\ 1\ 0]_{\delta} // [1\ 1\ 1]_{\gamma}$, $\mathbf{y} // [0\ 0\ 1]_{\delta} // [1\ 1\ 2]_{\gamma}$ and $\mathbf{z} // [100]_{\delta} // [1\bar{1}0]_{\gamma}$. When these CCSL vectors are defined in their own lattices without the constraint, they have slightly different lengths. That is why the constraint needs to apply to make a constrained CSL, i.e., CCSL. This strain defines the secondary misfit. The lengths of the three vectors can be read directly in the diagonal matrices $\mathbf{S}_{\delta}^{\text{II}}$ and $\mathbf{S}_{\gamma}^{\text{II}}$, since each of them is parallel to an axis of the orthonormal coordinates. The deviation defines the secondary misfit deformation: $\mathbf{A}^{\text{II}} = \mathbf{S}_{\delta}^{\text{II}} (\mathbf{S}_{\gamma}^{\text{II}})^{-1}$, for the unrotated OR. The determined $\mathbf{A}^{\text{II}}$ is given in Table 4. In fact, each pair of the column vectors related by $\mathbf{A}^{\text{II}}$ defines a pair of lattice points in a GMS in the center GMS cluster that contains the origin **O**, as shown in Fig. 3, since the CSL in Fig. 6 has been guided by the GMS in this cluster. Therefore, the lattice correspondence can be determined without a construction of the CSL, but the potential Burgers vectors must be determined according to the CSL/DSCL construction.

According to the CCSL and CDSCL illustrated in Fig. 6a, the available small CDSCL vectors for the possible secondary dislocations that accommodate the secondary misfit in the plane $(1\ 1\ 1)_{\gamma} // (0\ 1\ 0)_{\delta}$ are $1/2[1\ \bar{1}\ 0]_{\gamma} / 1/2[1\ 0\ 0]_{\delta}$, $1/2[1\ 0\ \bar{1}]_{\gamma} / 1/4[1\ 0\ 2]_{\delta}$, and $1/2[0\ \bar{1}\ 1]_{\gamma} / 1/4[1\ 0\ \bar{2}]_{\delta}$. With the input of these Burgers vectors and $\mathbf{A}^{\text{II}}$ in Table 4, the secondary dislocation structure in the interface parallel to $(1\ 1\ 1)_{\gamma} // (0\ 1\ 0)_{\delta}$ can be determined based on the O-lattice theory and its extension [13, 14, 27]. Corresponding to the above Burgers vectors, the determined line directions of three set of dislocations are $1/2[1\ 1\ \bar{2}]_{\gamma} / [0\ 0\ 1]_{\delta}$, $[0.75\ \bar{0}.65\ \bar{0}.11]_{\gamma} / [1\ 0\ 0.15]_{\delta}$ and $[0.65\ \bar{0}.75\ 0.11]_{\gamma} / [1\ 0\ \bar{0}.15]_{\delta}$, and with spacings of 48.3 nm, 12.6 nm, and 12.6 nm, respectively, as shown in Fig. 4a.

As illustrated in Fig. 6b, c, the shortest CDSCL vector is $1/6[1\ 1\ \bar{2}]_{\gamma} / 1/3[0\ 0\ 1]_{\delta}$ to obtain a CCSL pattern in the layer in Fig. 6b. It is the admissible Burgers vector of the secondary dislocations associated with the steps in Fig. 5. This result has been verified with the result based on the analysis of $\Delta\mathbf{g}$ characteristic triangles in reciprocal space [20, 22], showing consistency. Strictly, to calculate the spacing of the secondary dislocations associated with steps with the O-lattice formulas, one needs to add the rotation $\mathbf{R}$ in Table 3 to the secondary misfit deformation $\mathbf{A}^{\text{II}}$ in Table 4 for calculating the dislocations in the stepped interface. The determined spacing of the dislocations in the stepped interface is around 6.35 nm. Since the step height is much smaller than the projected dislocation spacing, as shown in Figs. 4 and 5, the actual dislocation spacing is close to the projected dislocation spacing without the rotation in Fig. 5. The line direction of the dislocations

Fig. 6 **a** CCSL and CDSCL on zero layer of δ phase, **b** CDSCL on the next layer, **c** CDSCL and CCSL perpendicular to the terrace plane

extends along the near-invariant line direction of $[1\bar{1}0]_\gamma/[100]_\delta$, same as their associated steps, separating the GMS clusters in different terrace planes, as illustrated in Fig. 5. To accommodate the slight misfit (0.6%) along the parallel vectors $[100]_\delta/[1\bar{1}0]_\gamma$ in the terrace plane, a set of potential dislocations with Burgers vector of $1/2[100]_\delta/1/2[1\bar{1}0]_\gamma$ are needed. Similar to those in the step-free interface, their spacing is 48.3 nm, in a direction perpendicular to the steps. However, these dislocations are not observed, probably because the misfit is very small and it is accommodated elastically. In addition, this small strain is in the range of uncertainty, since the small misfit is sensitive to the lattice parameters, which also carry a certain degree of experimental uncertainty.

3 Discussion

Different dislocation structures have been determined in the step-free and stepped interfaces. The Burgers vector of the dislocations associated with the steps is considerably smaller than those for the dislocations in the step-free interface (i.e., $1/6\langle 11\bar{2} \rangle_\gamma$ vs $1/2\langle 1\bar{1}0 \rangle_\gamma$). Though the spacing of the dislocations is also much smaller in the stepped interface, a significantly larger area of good matching implies a relatively lower misfit distortion between the dislocations. The factors decreasing interfacial energy associated with misfit deformation possibly override the effect of increasing interfacial energy due to steps. This provides one reason to explain why the orientation of

Table 4 Choice of CCSL, CDSCL, and the transformation matrix

	δ	γ
CCSL on lattice basis	$\begin{bmatrix} 0 & 0 & 1 \\ 3 & 0 & 0 \\ 0 & 1 & 0 \end{bmatrix}$	$\begin{bmatrix} 2 & 1/2 & 1 \\ 2 & 1/2 & \bar{1} \\ 2 & \bar{1} & 0 \end{bmatrix}$
CDSCL on lattice basis	$\begin{bmatrix} 0 & 0 & 1/2 \\ 1/2 & 0 & 0 \\ 0 & 1/3 & 0 \end{bmatrix}$	$\begin{bmatrix} 1/3 & 1/6 & 1/2 \\ 1/3 & 1/6 & 1/2 \\ 1/3 & 1/3 & 0 \end{bmatrix}$
CCSL on the orthonormal basis ($\mathbf{S}_\delta^{\text{II}}, \mathbf{S}_\gamma^{\text{II}}$)	$\begin{bmatrix} 1.2693 & 0 & 0 \\ 0 & 0.4534 & 0 \\ 0 & 0 & 0.5141 \end{bmatrix}$	$\begin{bmatrix} 1.2526 & 0 & 0 \\ 0 & 0.4429 & 0 \\ 0 & 0 & 0.5113 \end{bmatrix}$
Transformation matrix $\mathbf{A}^{\text{II}}$	$\begin{bmatrix} 1.0133 & 0 & 0 \\ 0 & 1.0238 & 0 \\ 0 & 0 & 1.0053 \end{bmatrix}$	

HP deviates from the atomic flat plane. This result is in principle consistent with the structure ledge model [29] in that the density of good matching zone is significantly increased by the existence of steps. As indicated in the introduction, the structure ledge model [29] dealt with case 1, but the present system belongs to case 2.

In the present study, the size and directions of available Burgers vectors play an important role in the selection of the stepped interfaces. The HP containing the periodic steps in Fig. 5 has an orientation of $(1.15 \ 1.15 \ 1)_\gamma$. The deviation angle from the terrace plane $(1 \ 1 \ 1)_\gamma$ is slightly larger compared with the measured average value of $(1.05 \ 1.03 \ 1)_\gamma$. A reason for the discrepancy is the existence of another type of steps, since two types of defects were observed [11]. The system under the present investigation is special since the GMS clusters in different layers are directly above or below the layer passing the origin (Fig. 4). Thus, the projected distance on the terrace plane between the GMS clusters of the up layer and the center cluster passing the origin is almost the same with that between the GMS clusters of the down layer and the center cluster. This situation is different from the case in the application of the structural ledge model [29], where a unique inclination of the stepped interface is determined by connecting of good matching patches in different layers. In

the present system, as illustrated in Fig. 7, fluctuation of nucleation of steps with two layers of $(0 \ 1 \ 0)_\delta$ may occur, leading a different inclination (top right) of the interface with respect to the terrace plane. For the convenience of distinction, this type of steps is referred to up-steps, and those steps leading top left inclination are called down-steps. The HP containing periodic down-steps is referred to HP_I hereafter. The orientation of the stepped interface that only contains the up-steps, called HP_II , can also be determined from the direction of another group of parallel $\mathbf{Ag}$'s, i.e., circled in Fig. 8. The interplanar spacing of planes for terraces in the two phases is almost identical, i.e., $d_{(010)\delta} = 0.4231 \text{ nm}$, $d_{(111)\gamma} = 0.4175 \text{ nm}$. If $d_{(010)\delta} = d_{(111)\gamma}$, one can prove that the parallelism of $\mathbf{Ag}$'s circled in Fig. 2 holds simultaneously with the parallelism of $\mathbf{Ag}$'s circled in Fig. 8. Similar to the method for calculation of HP_I , we can apply a slight rotation to bring exact parallelism of the circled $\mathbf{Ag}$'s in Fig. 8. The results and the input matrixes are listed in Table 5. Being defined by the parallel $\mathbf{Ag}$'s in Fig. 8, the calculated orientation of HP_II is $(1 \ 1 \ 1.31)_\gamma$, with an angular difference of 7.56° from $(1 \ 1 \ 1)_\gamma$. One can see from Fig. 6c that the smallest CDSCL vector to obtain a CCSL pattern in two layers of δ planes above the origin $\mathbf{O}'$ is again $1/6[1 \ 1 \ \bar{2}]_\gamma/1/3[0 \ 0 \ 1]_\delta$, identical to the Burgers vector associated with the down-

Fig. 7 Edge-on view of the stepped interface and its association with GMS clusters connected by up-steps. $x/[0\ 1\ 0]_{\delta}/[1\ 1\ 1]_{\gamma}$ and $y/[0\ 0\ 1]_{\delta}/[1\ 1\ 2]_{\gamma}$

Fig. 8 Another group of parallel Δg 's and the corresponding HP trace with zone axis $[1\ \bar{1}\ 0]_{\gamma}/[1\ 0\ 0]_{\delta}$

steps in HP_I . According to the misfit deformation A^{II} , δ phase expands slightly, leading to misfit displacement of a vector along of $[1\ 1\ 2]_{\gamma}/[0\ 0\ 1]_{\delta}$ with respect to γ in the direction of $1/6[1\ 1\ 2]_{\gamma}/1/3[0\ 0\ 1]_{\delta}$. It is consistent with the needed smallest CDSCL on the terraces connected by either one layer of down-step or two layers of up-step. Therefore, GMS clusters occur in these layers at the same distance from the origin. In contrast, the smallest CDSCL vector to obtain a CCSL pattern in one layer of δ planes above the origin O' is antiparallel to $1/6[1\ 1\ 2]_{\gamma}/1/3[0\ 0\ 1]_{\delta}$. The available CDSCL vector in the right direction is $1/3[1\ 1\ 2]_{\gamma}/2/3[0\ 0\ 1]_{\delta}$. Therefore, the corresponding O-lattice point or the center of the GMS

in one layer above is farther away than that on the two-layer above the origin. This is why the two-layer's up-steps is more favorable than the one-layer's ones. As can be verified by the O-lattice calculation, the up-steps in the HP_{II} are associated with secondary dislocations with Burgers vector of $1/6[1\ 1\ 2]_{\gamma}/1/3[0\ 0\ 1]_{\delta}$. As illustrated in Figs. 4b and 7, the projected spacing of secondary dislocations in the HP_{II} is similar to that in HP_I . Because of the identical Burgers vectors and similar spacing of dislocations in the two HPs, and small misfit in the step height, the energy of the HP_{II} with higher steps may not be much higher than that of HP_I . Therefore, the step structures in both types HPs can coexist in an interface.

The observations of a certain degree of scattering in the HP orientation can be explained by the existence of a mixture of two types of steps at a fluctuated ratio. This explanation agrees with the observation of two types of defects in conventional TEM images in Fig. 9a and down- and up-step structure in a high-resolution TEM image (Fig. 9b, c) [11]. The calculated direction and spacing of both types of steps agree with that of the M1 defects. The M1 defects (Fig. 9a) observed in the HPs of all precipitates are likely the down-steps. One reason is that the height of up-steps is twice as much as that of down-steps. As will be discussed later, the down-steps may be more energetically favored. Another reason is that the orientation of observed HP is close to that of HP_I containing periodic down-steps. While the direction of up-steps also agrees with that of M2 defects, the spacing is not same. The ratio of M2 defects in the observed HP is small and irregular. The effect of up-steps cancels that of down-steps on the inclination of the HP with respect to the terrace plane. Therefore, the average deviation angle (1.1°) of the observed HP is smaller than that (3.77°) of HP_I . Based on the present interpretation, the

Table 5 Results in the calculation process of HP_{II}

Matrices and vectors	
G_γ^z	$\begin{bmatrix} 1 & 1 & 1 \\ \bar{1} & \bar{1} & 1 \\ 1 & \bar{1} & 0 \end{bmatrix}$
G_δ^s	$\begin{bmatrix} 0 & 2 & 0 \\ 0 & \bar{1} & 2 \\ 2 & 0 & 0 \end{bmatrix}$
G_γ	$\begin{bmatrix} 4.7900 & 0 & 0 \\ -1.5967 & 4.5160 & 0 \\ 0 & 0 & 3.9110 \end{bmatrix}$
G_δ	$\begin{bmatrix} 4.7270 & 0 & 0 \\ -2.3640 & 4.4111 & 0 \\ 0 & 0 & 3.8903 \end{bmatrix}$
A'_0	$\begin{bmatrix} 1.0133 & 0 & 0 \\ 0.1810 & 1.0238 & 0 \\ 0 & 0 & 1.0053 \end{bmatrix}$
R	$\begin{bmatrix} 0.999998 & 0.0018 & 0 \\ -0.0018 & 0.999998 & 0 \\ 0 & 0 & 1 \end{bmatrix}$
A'	$\begin{bmatrix} 1.0136 & 0.0018 & 0 \\ 0.1792 & 1.0238 & 0 \\ 0 & 0 & 1.0053 \end{bmatrix}$
θ	-0.10°
$n_\gamma^z/\Delta g's$	$[1\ 1\ 1.31]_\gamma$

scattered HPs should be within the limitations set by the ideal angular deviation of HP_I and HP_{II} , i.e., 3.77° and 7.56° . This agrees with the observation of maximum deviation angle of 5° [11].

The Burgers vector of the down-steps is consistent with the measured Burgers vector for M1 defects, but the Burgers vector of the up-steps is inconsistent with the determined Burgers vector for M2 defects by Liang and

Fig. 9 Experimental results of the interface of δ phase: **a** contrast of two groups of steps associated with dislocations, **b** high-resolution image of the HP, **c** extended schematic diagram corresponding to **b** [11]

Reynolds [11]. Based on the flat HP in a conventional TEM image, they concluded that the M1 and M2 defects are not associated with the steps. On the other hand, their HREM micrograph of the habit plane did show atomic steps, without being associated with dislocation character. While a further high-resolution TEM study is required to verify whether these defects are associated with steps, it should be noticed that the Burgers vector of a secondary dislocation associated with a step may not be inspected as a local discontinuity of lattice planes, as a twining dislocation [30]. Continuity of lattice planes can be guided from the parallel Δg 's for each type of HP [20]. The planes defined by g connected by a Δg normal to the HP should be continuous across the interface. As expected, the plane continuity in HP_I is different from HP_{II} . In particular, the

Fig. 10 Configuration of GMS cluster under different view directions using the atomic points, **a** atomic figure of Fig. 4a, **b** atomic figure of Fig. 4b, **c** partial enlarged view of **b**. $x//[0\ 1\ 0]_{\delta}/[1\ 1\ 1]_{\gamma}$, $y//[0\ 0\ 1]_{\delta}/[1\ 1\ 2]_{\gamma}$, and $z//[1\ 0\ 0]_{\delta}/[1\ \bar{1}\ 0]_{\gamma}$

different continuities around the down- and up- steps will likely cause different local strains in relaxation. Therefore, though the Burgers vectors for the two types of steps are the same, the up-steps with a large height are probably associated with stronger local distortion and hence larger diffraction contrast. Since they may be associated with a relative higher energy, they have a less frequency of existence compared with the down-steps.

Finally, it is worth to discuss the observed steps with a single atomic layer in height as Fig. 9b. So far, the GMS, CCSL, and CDSCL constructions are based on the lattice points instead of the atoms. This is different from the NCS model which took the atomic positions into consideration [11]. The atomic positions in δ phase can be described by stacking close-packed planes in an ABAB order. After

adding the atoms, every atom in both planes is included in a GMS as shown in Fig. 10a, but the size of the GMS cluster and the arrangement of the GMS clusters in the plane $(1\ 1\ 1)_{\gamma}/(0\ 1\ 0)_{\delta}$ remain unchanged. The pattern of the edge-on GMS cluster in Fig. 10c is consistent with Fig. 16 in Ref. [11]. Due to the additional atomic layers, the steps with a single atomic layer in height are possible in the HP, as shown in Fig. 10c, in an agreement with Fig. 9c. However, as seen from Fig. 10b, unlike the down- and up-steps, these atomic steps cannot remain continuous periodically. The combination of the single-layer atomic steps to the down- and up-steps yields various heights. In order to examine the possible changes in the Burger vectors after adding atoms, modified CCSL and CDSCL have been constructed based on the atomic positions, as shown in

Fig. 11 Based on atomic points: **a** CCSL and CDSCL on zero atomic layer of δ phase, **b** CDSCL on the next atomic layer, **c** CDSCL and CCSL perpendicular to the terrace plane

Fig. 11. If the interface is parallel to the terrace plane $(1\ 1\ 1)_\gamma // (0\ 1\ 0)_\delta$, the available Burgers vectors for the possible secondary dislocations, as illustrated in Fig. 11a, remain to be $1/2[1\ 0\ 0]_\delta / 1/2[1\ \bar{1}\ 0]_\gamma$, $1/4[1\ 0\ 2]_\delta / 1/2[1\ 0\ \bar{1}]_\gamma$, and $1/4[1\ 0\ \bar{2}]_\delta / 1/2[0\ \bar{1}\ 1]_\gamma$. As illustrated in Fig. 11b, c, the change by adding or reducing one atomic layer in step height can be observed and the Burgers vectors of the dislocations associated with either down- or up-steps remain to be $1/6[1\ 1\ \bar{2}]_\gamma / 1/3[0\ 0\ 1]_\delta$. This result indicates that the analysis based on lattice points is effective for investigation of the dislocation structure in the HP, though the steps may have different heights according to the atomic structures.

While the results in Ref. [11] are rich and stimulating to the present study, interpretation of experimental results in the present approach is different from the previous work. A major difference is the methods for determining the dislocation structure. Misfit dislocations were inserted into interfaces in the NCS model [11], which was unable to determine the proper Burgers vectors and configurations of dislocations. In the present analysis, the secondary dislocations locate between the GMS clusters, as also determined from the O-lattice calculations. The Burgers vectors were determined from the CSL/DSCL analysis, which is combined with the GMS and O-lattice study in a systematic manner.

4 Conclusions

The Δg parallelism rule, the GMS analysis, and the secondary O-lattice model are combined to interpret the OR and to determine the interfacial dislocation structure in the HP of the δ precipitates in superalloy 718. The following conclusions were obtained:

1. The orientations of stepped HPs are calculated utilizing the Δg parallelism rule. The calculated orientations of two types of HPs are $HP_I (1.15\ 1.15\ 1)_\gamma$ and $HP_{II} (1\ 1\ 1.31)_\gamma$, with a negligible rotation from measured rational OR. These HPs contain steps arranged in different inclination directions. The height of the up-steps in HP_{II} is defined by double layers of $(0\ 1\ 0)_\delta$, while that of the down-steps of HP_I is defined by a single layer of $(0\ 1\ 0)_\delta$. The observed HP is interpreted by containing denser GMS clusters separated by a mixture of two types of steps. In addition, the Burgers vector of the dislocations between the GMS clusters is much smaller compared with that in the step-free interface. This structure can account for the orientation and its scattering of the observed HP.

2. A CSL/DSCL/O-lattice model has been applied for calculating the interfacial dislocation structure, with the input data obtained based on the GMS construction and Δg analysis. The Burgers vector of the secondary dislocation associated with both types of steps is $1/6[1\ 1\ 2]_\gamma/1/3[0\ 0\ 1]_\delta$. Their direction is $[1\ \bar{1}\ 0]_\gamma$, and their projected spacing onto the terrace plane is around 6.3 nm. The calculated spacing and Burgers vector of the secondary dislocations associated with steps agree with the experimental observations of the major defects. Their association with the steps agrees with the measured average orientation of the HP, but the one-to-one association needs further experimental verification.

Acknowledgements This work was financially supported by the National Natural Science Foundation of China (Grant No. 51671111) and the National Key Research and Development Program of China (Grant No. 2016YFB0701304). The authors wish to express thanks to Mr. Zhipeng Sun and Jinyu Zhang for their helpful discussions.

References

- [1]. J.H. Du, X.D. Lü, J.L. Qu, Q. Deng, J.Y. Zhuang, Z.Y. Zhong, *Acta Metall. Sin. (Engl. Lett.)* **19**, 418 (2006)
- [2]. J.F. Barker, E.W. Ross, J.F. Radavich, *JOM* **22**, 31 (1970)
- [3]. L. Liu, C. Zhai, C. Lu, W. Ding, A. Hirose, K.F. Kobayashi, J. Mater. Sci. Technol. **47**, 355 (2005)
- [4]. J.H. Du, X.D. Lu, Q. Deng, J.L. Qu, J.Y. Zhuang, Z.Y. Zhong, *Mat. Sci. Eng. A* **452**, 584 (2007)
- [5]. L.C.M. Valle, L.S. Araujo, S.B. Gabriel, J. Dille, L.H. de Almeida, *J. Mater. Eng. Perform.* **22**, 1512 (2013)
- [6]. Z.S. Yu, J.X. Zhang, Y. Yuan, R.C. Zhou, H.J. Zhang, H.Z. Wang, *Mater. Sci. Eng. A* **634**, 55 (2015)
- [7]. I. Kirman, D.H. Warrington, *Metall. Mater. Trans. B* **1**, 2667 (1970)
- [8]. I. Kirman, *J. Iron Steel Inst.* **207**, 1612 (1969)
- [9]. Y.G. Nakagawa, G.C. Weatherly, *Mater. Sci. Eng.* **10**, 223 (1972)
- [10]. M. Sundaraman, P. Mukhopadhyay, S. Banerjee, *Metall. Mater. Trans. A* **19**, 453 (1988)
- [11]. Q. Liang, W.T. Reynolds, *Metall. Mater. Trans. A* **29**, 2059 (1998)
- [12]. W.Z. Zhang, *Metall. Mater. Trans. A* **44**, 4513 (2013)
- [13]. W. Bollmann, *Crystal Defects and Crystalline Interfaces* (Springer, Berlin, 1970)
- [14]. W. Bollmann, *Crystal Lattices, Interfaces, Matrices* (Bollmann, Geneva, 1982)
- [15]. C.M. Wayman, *Introduction to the Crystallography of Martensitic Transformations* (Macmillan, New York, 1964)
- [16]. W.Z. Zhang, Z.P. Sun, J.Y. Zhang, Z.Z. Shi, H. Shi, *J. Mater. Sci.* **53**, 4253 (2017)
- [17]. R.C. Pond, S. Celotto, J.P. Hirth, *Acta Mater.* **51**, 5385 (2003)
- [18]. M.X. Zhang, P.M. Kelly, *Acta Mater.* **46**, 4617 (1998)
- [19]. P. Kelly, M.X. Zhang, *Mater. Forum* **23**, 41 (1999)
- [20]. W.Z. Zhang, G.C. Weatherly, *Prog. Mater. Sci.* **50**, 181 (2005)
- [21]. U. Dahmen, *Acta Metall.* **30**, 63 (1982)
- [22]. F. Ye, W.Z. Zhang, *Acta Mater.* **50**, 2761 (2002)
- [23]. W.Z. Zhang, F. Ye, C. Zhang, Y. Qi, H.S. Fang, *Acta Mater.* **48**, 2209 (2000)
- [24]. C.T. Sims, N.S. Stoloff, W.C. Hagel, *Superalloys II* (Wiley-Interscience, New York, 1987)
- [25]. S.Q. Xiao, J.M. Howe, *Acta Mater.* **48**, 3253 (2000)
- [26]. J. Wu, W.Z. Zhang, X.F. Gu, *Acta Mater.* **57**, 635 (2009)
- [27]. W.Z. Zhang, *Appl. Phys. Lett.* **86**, 121919 (2005)
- [28]. X.P. Yang, W.Z. Zhang, *Sci. China Technol. Sci.* **55**, 1343 (2012)
- [29]. J.M. Rigsbee, H.I. Aaronson, *Acta Metall.* **27**, 351 (1979)
- [30]. J.W. Christian, *The Theory of Transformations in Metals and Alloys* (Elsevier Science, Oxford, 2002)