Effect of Mo Addition on Corrosion Behavior of High-Entropy Alloys CoCrFeNiMo_x in Aqueous Environments

Xu-Liang Shang¹ · Zhi-Jun Wang¹ · Qing-Feng Wu¹ · Jin-Cheng Wang¹ · Jun-Jie Li¹ · Jia-Kang Yu¹

Received: 7 June 2018 / Revised: 31 July 2018 / Published online: 5 September 2018
© The Chinese Society for Metals and Springer-Verlag GmbH Germany, part of Springer Nature 2018

Abstract

The corrosion behavior of CoCrFeNiMo_x alloys was investigated in aqueous environments, NaCl and H₂SO₄ solutions, respectively, to simulate typical neutral and acidic conditions. The cyclic polarization curves in NaCl and the potentiodynamic curves in H₂SO₄ clearly reveal the beneficial effects of Mo and the detrimental effect of σ -phase on the corrosion resistance. The X-ray photoelectron spectroscopy results of CoCrFeNiMo_x alloys in H₂SO₄ solution indicate that Cr and Mo predominate the corroded surface of the alloys, where Mo primarily exists in the form of MoO₃.

Keywords High-entropy alloys · Corrosion · σ -phase · Molybdenum

1 Introduction

Conventional alloys are based on a single principal element such as iron, nickel, aluminum. Differently, Cantor et al. [1] and Yeh et al. [2] proposed the concept of high-entropy alloys (HEAs), which consist of several principal components instead a base of single component. The investigation of HEAs promotes researches from the corner to the center in the phase diagram and tremendously enriches the category of the modern alloy systems. HEAs are inclined to form solid solution phases with simple crystal structures [3–5] and have been considered to have better corrosion resistance.

Shi et al. [6] and Qiu et al. [7] summarized the researches of corrosion-resistant HEAs, including the corrosion-resistant property of HEAs in various aqueous environments. Compared with conventional alloys, some HEAs possess better corrosion resistance, which is attributed to the simple phase composition and uniform element distribution [8–10]. CoCrFeNi was demonstrated to have good corrosion resistance because of the single face-centered cubic (fcc) structure and the dominant effect of Cr [11–13].

The effects of Co, Fe and Ni on the corrosion resistance were also revealed [14]. Moreover, the effects of typical elements on the corrosion resistance of CoCrFeNi-based HEAs were investigated widely, such as Al, B, Cu, Ni, W, Nb [15–22].

As to the effect of Mo on the corrosion behavior of HEAs, Chou et al. [23, 24] and Shang et al. [16] investigated the Co_{1.5}CrFeNi_{1.5}Ti_{0.5}Mo_x and CoCrFeNi(W_{1-x}Mo_x) alloys and showed the beneficial effect of Mo. Additionally, the beneficial effect of Mo addition on the corrosion behavior of conventional alloys, such as stainless steel (SS) [25–30], Ni–Cr–Mo [31, 32] and Ni–Cr–Mo–Fe alloys [33], has been widely investigated. However, the corrosion resistance mechanisms of Mo are different in different systems. Sugimoto and Sawada [30] concluded that in austenitic stainless steel the formation of a Mo⁶⁺-rich passive film in chromium oxyhydroxide network reduced the corrosion current density in the active region. Hashimoto et al. [28] proposed that the corrosion in active region was retarded by forming and retaining molybdenum oxyhydroxide or molybdates (MoO₄²⁻). Furthermore, MoO₄²⁻ was detected in passive films of the Mo-bearing alloys in acidic solutions [34–38], whereas, according to the Pourbaix diagrams [39], MoO₃ was recognized as the only compound formed in 0.5 mol/L H₂SO₄. Wanklyn [27] reported that MoO₂ formed directly at the typical potentials in crevices. Yang et al. [40] and Hashimoto et al. [41] proposed that a protective film of MoO₂ formed. Furthermore, MoO₂ was demonstrated to be the only

Available online at <http://link.springer.com/journal/40195>

✉ Zhi-Jun Wang
zhjwang@nwpu.edu.cn

¹ State Key Laboratory of Solidification Processing, Northwestern Polytechnical University, Xi'an 710072, China

stable compound in such environment, according to Pourbaix diagram [39]. However, Habazaki et al. [42] investigated the potentiostatic polarization curves and corresponding dissolution curves for molybdenum metal in 6 mol/L HCl and the results showed that Mo existed in the form of MoO_2 in the passive region and formed HMoO_4^- at higher potential. Other theories were also proposed, such as enrichment of Mo in the metallic state in the alloy layer just below the passive film [43, 44], enrichment of Cr in the oxide layer by selective dissolution of Mo [42, 44], thickening of the passive film and stabilization of the Cr oxides with the presence of Mo^{6+} [45, 46] forming an amorphous oxide film with a glassy structure [47]. In CoCrFeNi-based HEAs, the effect of Mo addition on the corrosion behavior and its mechanism are still unknown.

For CoCrFeNiMo_x alloys, the microstructure and mechanical properties have been confirmed by Shun et al. [48] and Liu et al. [49]. In this work, considering the service environment, the corrosion behavior of CoCrFeNiMo_x ($x = 0.1\text{--}0.5$) in aqueous environments is investigated. NaCl and H₂SO₄ solutions are used to simulate typical neutral and acidic conditions, respectively. The matrix of CoCrFeNiMo_x alloys possesses single fcc structure. The secondary (Cr, Mo)-rich σ -phase appears when $x = 0.3$ and increases with the addition of Mo content.

2 Experimental

2.1 Materials Preparation

Elements Co, Cr, Fe, Ni and Mo with purity of more than 99.95 wt% were used as raw materials. The CoCrFeNiMo_x ($x = 0.1\text{--}0.5$) are 5-component alloys, and the atomic ratio is as follows: Co:Cr:Fe:Ni:Mo = 1:1:1:1: x . The alloys were melted with electromagnetic stirring five times to ensure the homogeneity and then solidified in a water-cooled copper hearth. The samples were cut into pieces of 2 mm in thickness and 10 mm in diameter. All the specimens were mechanically grounded with a suite of 240#, 800# and 1500# SiC grit papers orderly and then cleaned with ultrasound and ultrapure water to ensure the cleanness of the sample surface. Finally, the test specimen was cold-mounted with the flat specimen holder kit to give an exposed surface area of 0.5 cm². All curves are normalized to 1 cm² during the data processing. The electrochemical results are reproducible after these processing processes and the curves were measured at least three times to ensure the reproducibility.

2.2 Electrochemical Measurement

The electrochemical measurements of CoCrFeNiMo_x were taken in 3.5 wt% NaCl and 0.5 mol/L H₂SO₄ solutions to simulate the neutral and acidic environments independently at ambient temperature ($\sim 25^\circ\text{C}$). The electrochemical properties were tested with a typical three-electrode cell. The cell is made up of the specimen as the working electrode (WE), Pt plate (2 cm $\times$ 2 cm) as a counter electrode (CE) and a reference electrode (RE). The saturated calomel reference electrode (SCE) and mercurous sulfate electrode (K₂SO₄) were chosen as the RE, respectively, in 3.5 wt% NaCl and 0.5 mol/L H₂SO₄ solutions to alleviate the liquid junction potential. The SCE is 0.242 V higher than the standard hydrogen electrode (SHE), and the mercurous sulfate electrode (K₂SO₄) is 0.652 V higher than SHE. Additionally, the distance between WE and CE was set as 20 mm; the distance between WE and RE, and the distance between RE and CE are both 24 mm to further guarantee the accuracy.

The electrochemical workstation of Princeton Applied Research (PARSTAT 4000) is used for electrochemical tests. Cyclic polarization curves were obtained in 3.5 wt% NaCl with a scan rate of 1 mV/s from an initial potential of -0.5 V to a final potential of 1.5 V versus the open-circuit potential (OCP), where the potential reversed and returned to the initial potential. Similarly, a potentiodynamic polarization technique was employed at a scan rate of 1 mV/s from the initial potential of $-0.5 V_{\text{OCP}}$ to the final potential of $1.5 V_{\text{OCP}}$ in 0.5 mol/L H₂SO₄. A series of electrochemical parameters for the corrosion properties were measured: corrosion potential (E_{corr}), primary passivation potential (E_{pp}), breakdown potential (E_{b}) and width of passive region between E_{b} and E_{pp} (ΔE). For cyclic polarization test, other parameters are confirmed to evaluate the corrosion resistance: protection potential (E_{prot}), repassivation potential (E_{rp}), invariable anodic current in the passive region (i_{pass}) and corrosion current density (i_{corr}) [24]. The electrochemical impedance spectroscopy (EIS) measurement at OCP was used to analyze the mechanism of corrosion in a frequency range of 0.01–100,000 Hz and a sinusoidal potential amplitude of 10 mV. Furthermore, in order to reveal the mechanism of passivation, the chronoamperometry test was performed on three independent samples with the same composition of CoCrFeNiMo_{0.4}. The samples were potentiostatically polarized for 1 h in 0.5 mol/L H₂SO₄ with the potential of -550 mV, -100 mV and 350 mV, respectively. Before the electrochemical tests, all the specimens were immersed in the prepared test solutions for 12 h and the OCP was recorded for 30 min to reach a steady-state potential.

2.3 Surface Characterization

After the electrochemical measurements, the corroded surfaces were observed by scanning electron microscopy (SEM) equipped with energy-disperse spectroscopy (EDS). The X-ray photoelectron spectroscopy (XPS) was used to analyze the compositions of passive film and the valence states of elements after the chronoamperometry test. The detected area is approximately $300 \times 700 \mu\text{m}^2$, and the detected depth is of nanometer scale near the surface. XPS analyses were performed with a Kratos Axis Ultra DLD using monochromatic AlK_α (1486.6 eV) radiation, and the XPS spectra were rectified for charging by taking the C 1s spectrum for adventitious C at a binding energy of 284.8 eV. Survey spectra were recorded, followed by high-resolution XPS spectra for Co 2p, Cr 2p, Fe 2p, Ni 2p, Mo 3d regions.

3 Results

3.1 Corrosion Behavior of CoCrFeNiMo_x in NaCl Solution

The cyclic polarization technique was used to evaluate the corrosion of CoCrFeNiMo_x ($x = 0.1$ – 0.5) alloys in 3.5 wt% NaCl solution, as shown in Fig. 1. The positive hysteresis, i.e., reversed current density exceeds the forward current density, indicates the appearance of pitting corrosion and

pit propagation. In the potential range between E_{prot} and E_{b} , new pits will not initiate, but old ones will grow up [50]. Table 1 shows the electrochemical parameters of the CoCrFeNiMo_x alloys after cyclic polarization in 3.5 wt% NaCl solution. For single fcc solution CoCrFeNiMo_{0.1} and CoCrFeNiMo_{0.2}, with the addition of Mo, the values of i_{corr} and i_{pass} decreased exponentially and the E_{prot} was observed (Fig. 1b). CoCrFeNiMo_{0.2} shows much better corrosion resistance than CoCrFeNiMo_{0.1}. In CoCrFeNiMo_{0.3}, the corrosion resistance decreased dramatically with much higher i_{corr} and i_{pass} than in CoCrFeNiMo_{0.2}.

Figure 2 shows the SEM images of CoCrFeNiMo_x alloys after cyclic polarization in 3.5 wt% NaCl. The CoCrFeNiMo_x alloys possess typical structure of dendrite. The surface corrosion of all specimens indicates that Cl[−] ion severely attacked the surfaces of the alloys during polarization. The major type of corrosion is galvanic corrosion. Differently, galvanic corrosion occurred at the junctions of dendrites for CoCrFeNiMo_{0.1} and CoCrFeNiMo_{0.2}. For CoCrFeNiMo_x ($x = 0.3$ – 0.5), corrosion appeared at both the junctions of dendrites and the interfaces of σ -phase and matrix. Furthermore, considering the initiation and growth of pitting in SS [51–53], the corrosion type at lower potential is general corrosion, and pitting corrosion dominates at higher potential, especially in transpassive region. In order to confirm the corrosion type more precisely, Fig. 3 shows the images of laser confocal microscope (LSCM) for two specimens: one with

Fig. 1 Cyclic polarization curves of CoCrFeNiMo_x alloys in 3.5 wt% NaCl solution: **a** $x = 0.1$; **b** $x = 0.2$; **c** $x = 0.3$; **d** $x = 0.4$; **e** $x = 0.5$

Table 1 Electrochemical parameters of CoCrFeNiMo_x alloys in 3.5 wt% NaCl solution

Designation	E_{corr} (mV vs. RE)	i_{corr} ($\mu\text{A}/\text{cm}^2$)	E_{pp} (mV vs. RE)	i_{pass} ($\mu\text{A}/\text{cm}^2$)	E_b (mV vs. RE)	E_{prot} (mV vs. RE)	E_{rp} (mV vs. RE)	ΔE (mV)
Mo _{0.1}	− 263	0.381	− 134	38	949	−	− 182	1083
Mo _{0.2}	− 131	0.072	− 28	16	941	747	184	969
Mo _{0.3}	− 257	0.766	− 181	50	955	11	− 178	1136
Mo _{0.4}	− 261	0.082	− 261	16	948	695	237	1209
Mo _{0.5}	− 261	0.738	− 100	24	965	370	63	1065

Fig. 2 SEM images of CoCrFeNiMo_x alloys in 3.5 wt% NaCl solution: **a** $x = 0.1$; **b** $x = 0.2$; **c** $x = 0.3$; **d** $x = 0.4$; **e** $x = 0.5$; **b'**–**e'** high magnification of Fig. 2**b**–**e**, respectively

precipitated σ -phase (CoCrFeNiMo_{0.3}) and the other without precipitated σ -phase (CoCrFeNiMo_{0.1}). The colors represent the height of different locations, and the area in red is higher than the area in blue. Accordingly, pitting corrosion and galvanic corrosion were observed. CoCrFeNiMo_{0.3} corroded much more badly. The cracks on the surface of CoCrFeNiMo_{0.3} are caused by the breakdown of passive film. According to the former works of Shun et al. [48] and Liu et al. [49], the interdendritic phase of CoCrFeNiMo_x is Cr- and Mo-rich phase and the dendrite is a Cr- and Mo-depleted phase. Therefore, galvanic corrosion occurred at the junctions of dendrites. With the addition of Mo, (Cr, Mo)-rich σ -phase appeared inside the interdendrite and acted as the cathode. Therefore, galvanic corrosion for CoCrFeNiMo_x ($x = 0.3$ – 0.5) that occurred at the junctions of dendrites as well as the interfaces around σ -phase is caused by element segregations along with the low anode/cathode surface area. Additionally, pitting corrosion may have occurred at the sites with defect [53], such as grain boundary, areas with element segregation, shrinkage porosity and cavity.

The EDS maps of CoCrFeNiMo_{0.5} after cyclic polarization in 3.5 wt% NaCl (Fig. 4) indicate that Co, Fe and Ni gathered together in dendrites and Mo accumulated in interdendrites and σ -phase, which is in accordance with the work of Shun et al. [48]. The cracks observed on the surface of CoCrFeNiMo_{0.5} are Cr- and O-depleted areas, indicating that Cr played the dominant role in sustaining the completeness of passivation and preventing further corrosion. This conclusion was also demonstrated by our previous work [54].

EIS analysis was performed to investigate the corrosion and passivation processes that occurred on the surface. Figure 5a, b shows the effect of Mo content on the Nyquist and Bode plots of CoCrFeNiMo_x alloys in 3.5 wt% NaCl solution at OCP with a sinusoidal potential amplitude of 10 mV, running from 100 kHz to 10 mHz at room temperature. The Nyquist plots show unfinished semicircles with center depressed below the x-axis, which is due to the charge transfer process in the electrode–electrolyte interface and is related to changes in the passive film property [55, 56]. CoCrFeNiMo_{0.2} possesses the highest charge

Fig. 3 LSCM images of CoCrFeNiMo_x alloys after cyclic polarization in 3.5 wt% NaCl solution: **a** CoCrFeNiMo_{0.1}, corrosion morphology; **b** CoCrFeNiMo_{0.1}, topographic map; **c** CoCrFeNiMo_{0.3}, corrosion morphology; **d** CoCrFeNiMo_{0.3}, topographic map

transfer resistance (R_{ct}) and the best corrosion resistance accordingly. However, the Nyquist plots for CoCrFeNiMo_{0.4} and CoCrFeNiMo_{0.5} in low frequency show Warburg impedance. Figure 5c, d gives the corresponding equivalent electrical circuit, where R_s is solution resistance, R_{ct} is the resistance of oxides, C_{dl} corresponds to the capacitance of the oxide layer, and W corresponds to the Warburg impedance [20]. Figure 5c shows the equivalent electrical circuit for CoCrFeNiMo_{0.2} and CoCrFeNiMo_{0.3}, indicating that the corrosion behavior was dominated by electrochemistry. Figure 5d shows the equivalent electrical circuit for CoCrFeNiMo_{0.4} and CoCrFeNiMo_{0.5}, indicating that the corrosion behavior was controlled by diffusion as well as electrochemistry [20, 57, 58].

3.2 Corrosion Behavior of CoCrFeNiMo_x in H₂SO₄ Solution

Figure 6 plots the potentiodynamic polarization curves of CoCrFeNiMo_x in 0.5 mol/L H₂SO₄ solution. The potentiodynamic curves of CoCrFeNiMo_x alloys change directly from the Tafel region into the stable passive region, without showing an active-passive region (Fig. 6b), indicating that the passive film is formed spontaneously [19]. The corresponding electrochemical parameters are given in Table 2. CoCrFeNiMo_{0.2} showed better corrosion resistance with smaller i_{corr} (2.926 $\mu\text{A}/\text{cm}^2$) and i_{pass} (9 $\mu\text{A}/\text{cm}^2$) than CoCrFeNiMo_{0.1} with i_{corr} (9.666 $\mu\text{A}/\text{cm}^2$) and i_{pass} (30 $\mu\text{A}/\text{cm}^2$). For CoCrFeNiMo_{0.3}, σ -phase occurred and the corrosion resistance of the alloy decreased abruptly. With the further addition of Mo, σ -phase precipitated more and the corrosion resistance of CoCrFeNiMo_{0.4} behaved better than CoCrFeNiMo_{0.3}.

Fig. 4 EDS maps of CoCrFeNiMo_{0.5} after cyclic polarization in 3.5 wt% NaCl for different elements

CoCrFeNiMo_{0.5} possessed the highest Mo content and the most precipitated σ -phase, and the corrosion resistance decreased a little, compared with CoCrFeNiMo_{0.4}. Therefore, Mo has a beneficial effect on enhancing the corrosion resistance of CoCrFeNiMo_x alloys in H₂SO₄ solution.

Additionally, some interesting phenomena should also be noted from the polarization curves in Fig. 6a, b. The curves have similar passive region width (ΔE) and trend in passive region, indicating that the passive films may possess analogous structure. The difference of i_{pass} may be caused by the thickness, compactness, solubility of passive film and so on. With the addition of Mo, the E_{corr} for the alloys shifted up.

Figure 7 displays the SEM images of CoCrFeNiMo_x after potentiodynamic polarization in 0.5 mol/L H₂SO₄ solution. Figure 8 shows the LSCM images of CoCrFeNiMo_{0.1} and CoCrFeNiMo_{0.5}. The major corrosion types of CoCrFeNiMo_{0.1} and CoCrFeNiMo_{0.2} without the σ -phase precipitation are pitting corrosion and galvanic

corrosion at the interdendrites, as shown in Fig. 8a, b. Intergranular corrosion is observed in Fig. 8a. When σ -phase appeared, the major corrosion type of CoCrFeNiMo_x ($x = 0.3$ – 0.5) turns into galvanic corrosion at the interfaces around σ -phase, as shown in Fig. 8c, d.

In order to investigate the mechanism of passivation for the CoCrFeNiMo_x alloys in 0.5 mol/L H₂SO₄ solution, the chronoamperometry technique was performed for 1 h at different potentials in passive region, respectively, and -550 , -100 and 350 mV versus RE were chosen, as shown in Fig. 7. Furthermore, considering the similarity of the passive films for the alloys and CoCrFeNiMo_{0.4} showed the best corrosion resistance, we chose CoCrFeNiMo_{0.4} as the representative of the alloys and investigated the passive film. Table 3 and Fig. 9 give the cationic fraction analyzed by XPS for CoCrFeNiMo_{0.4} potentiostatically polarized for 1 h in 0.5 mol/L H₂SO₄ solution at about 25 °C. Cr and Mo are the main elements on the surface and restrain the corrosion that occurred in passive region. Furthermore, the

Fig. 5 **a** Bode, **b** Nyquist plots of CoCrFeNiMo_x alloys in the 3.5 wt% NaCl solution after different amounts of Mo addition; **c**, **d** corresponding equivalent electrical circuits (Z : impedance; Z_{re} : real part of impedance; and Z_{im} : imaginary part of impedance)

Fig. 6 **a** Potentiodynamic polarization curves of CoCrFeNiMo_x alloys in 0.5 mol/L H₂SO₄ solution, **b** magnification of curves around corrosion potential E_{corr}

fractions of Ni and Co decreased gradually with the increase in potential. The variation of fractions for these elements with the potential may be attributed to the oxidation and dissolution of which at different potentials.

The high-resolution spectra of Co $2p_{3/2}$, Cr $2p_{3/2}$, Fe $2p_{3/2}$, Ni $2p_{3/2}$ and Mo $3d_{5/2}$ indicate the oxidation state and the other with relatively lower energy of lower oxidation state or metallic state. Co $2p_{3/2}$ showed two binding energy components near 778.0 eV and 780.6 eV, which may

represent Co and CoO [59, 60]. Cr $2p_{3/2}$ spectra showed two binding energy components at approximately 574.0 eV and 576.6 eV, which correspond to Cr and Cr₂O₃, respectively [61, 62]. Fe $2p_{3/2}$ spectra exhibited two binding energy components at approximately 706.9 eV and 710.4 eV, which may be attributed to the appearance of Fe and Fe₂O₃, respectively [63, 64]. Ni $2p_{3/2}$ showed two binding energy components at approximately 852.5 eV and 854.7 eV, which may be corresponding to Ni and NiO

Table 2 Electrochemical parameters of CoCrFeNiMo_x alloys in 0.5 mol/L H₂SO₄ solution

Designation	E_{corr} (mV vs. RE)	i_{corr} ($\mu\text{A}/\text{cm}^2$)	E_{pp} (mV vs. RE)	i_{pass} ($\mu\text{A}/\text{cm}^2$)	E_b (mV vs. RE)	ΔE (mV)
Mo _{0.1}	− 688	9.666	− 638	30	469	1107
Mo _{0.2}	− 682	2.926	− 661	9	460	1121
Mo _{0.3}	− 694	8.626	− 656	30	453	1109
Mo _{0.4}	− 663	0.712	− 576	6	462	1038
Mo _{0.5}	− 632	1.526	− 536	12	450	986

Fig. 7 SEM images of CoCrFeNiMo_x alloys in 0.5 mol/L H₂SO₄ solution: **a** $x = 0.1$; **b** $x = 0.2$; **c** $x = 0.3$; **d** $x = 0.4$; **e** $x = 0.5$; (**c'**–**e'**) high magnification of Fig. 7**c**–**e**, respectively

[65, 66]. Mo $3d_{5/2}$ showed three binding energy components. The binding energy components at approximately 227.6 eV, 228.6 eV and 232.4 eV represent typical Mo, MoO₂ and MoO₃, respectively [31, 67–69]. Accordingly, the oxidation state of Co, Cr, Fe, Ni and Mo in the passive film for CoCrFeNiMo_x alloys exists in the form of Co²⁺, Cr³⁺, Fe³⁺, Ni²⁺, Mo⁴⁺ and Mo⁶⁺. Furthermore, we calculate the ratios for the main elements with different oxidation states, as listed in Table 4. The results show that the oxidation state of elements Cr, Fe and Mo plays a leading role than their metallic state. The elements Co and Ni existed mainly in the metallic state. What is more, the fraction of oxidation state for each element increased with the increase in potential, especially when the potential was loaded from − 100 to 350 mV. For element Mo, Mo⁶⁺ takes the major part and we can conclude that Mo⁶⁺ plays a main part in retarding the corrosion, rather than Mo⁴⁺.

4 Discussion

It has been reported that the addition of Cr and Mo greatly affects the corrosion resistance of nickel alloys and SS [26, 29, 30, 35, 40], especially for Ni–Cr–Fe–Mo stainless steel. The synthetic effect of Cr and Mo contents on pitting corrosion usually can be evaluated qualitatively by pitting resistance equivalent (PRE), which is generally defined as follows [70, 71]:

$$\text{PRE} = M_{\text{Cr}} + 3.3M_{\text{Mo}}, \quad (1)$$

where M_{Cr} and M_{Mo} are the mass fraction of Cr and Mo, respectively. Accordingly, the higher PRE predicts the better corrosion resistance of alloys. Here, the PRE values for single fcc solid solution CoCrFeNiMo_{0.1} and CoCrFeNiMo_{0.2} are 36 and 47, respectively. Therefore, CoCrFeNiMo_{0.2} was considered to possess better pitting corrosion resistance than CoCrFeNiMo_{0.1}. With the further addition of Mo, although the PRE values of CoCrFeNiMo_x ($x = 0.3$ – 0.5) increased gradually and even reached 77 for CoCrFeNiMo_{0.5}, the corrosion resistance of it was not

Fig. 8 LSCM images of CoCrFeNiMo_x alloys after potentiodynamic polarization in 0.5 mol/L H₂SO₄ solution: **a** CoCrFeNiMo_{0.1}, corrosion morphology; **b** CoCrFeNiMo_{0.1}, topographic map; **c** CoCrFeNiMo_{0.5}, corrosion morphology; **d** CoCrFeNiMo_{0.5}, topographic map

Table 3 Cationic fractions analyzed by XPS for CoCrFeNiMo_{0.4} potentiostatically polarized for 1 h in 0.5 mol/L H₂SO₄ solution

Potential (mV vs. RE)	Co	Cr	Fe	Ni	Mo
– 550	8.52	44.89	8.14	6.42	32.03
– 100	8.02	35.82	11.73	6.79	37.65
350	6.18	52.24	8.44	5.27	27.87

enhanced continually. This is caused by the influence of σ -precipitation inside interdendrites. The secondary σ -phase was a (Cr, Mo)-rich phase and was demonstrated to be detrimental to corrosion resistance in SS for causing a (Cr, Mo)-depleted region and a stressed region around it [72–77]. The corrosion preference of (Cr, Mo)-depleted phase could be primarily caused by galvanic coupling of (Cr, Mo)-depleted phase and (Cr, Mo)-rich phase, where (Cr, Mo)-rich phase acted as cathode and the other acted as

Fig. 9 Analytical results of XPS for CoCrFeNiMo_{0.4} potentiostatically polarized for 1 h in 0.5 mol/L H₂SO₄

Table 4 Summary of ratios for main elements with different oxidation states detected by XPS

Voltage (mV vs. RE)	Co ²⁺ /Co ⁰	Cr ³⁺ /Cr ⁰	Fe ³⁺ /Fe ⁰	Ni ²⁺ /Ni ⁰	Mo ⁶⁺ : Mo ⁴⁺ : Mo ⁰
– 550	0.34	5.38	2.94	0	47.61: 16.59: 35.80
– 100	0.37	6.90	1.60	0.10	48.93: 17.11: 33.96
350	1.33	14.46	5.46	0.46	61.29: 15.54: 23.17

anode. The difference of potential for cathode and anode afforded a driving force for the dissolution of (Cr, Mo)-depleted phase. Therefore, galvanic corrosion that occurred around σ -phase dominated the corrosion process. Compared with the corrosion behavior of CoCrFeNiMo_{0.2}, the corrosion resistance of CoCrFeNiMo_{0.3} decreased rapidly, which was caused by the σ -phase precipitation. Considering the σ -phase for CoCrFeNiMo_x ($x = 0.3$ – 0.5) possessed different forms and volume fractions, the effect of σ -phase should be discussed further.

With the further addition of Mo, the volume fraction of σ -phase increased and σ -phase exhibited different shapes with separated spot, continuous line and connected bulk. When the precipitated σ -phase in different alloys possesses the same volume fraction, the spot-like σ -phase is most harmful to corrosion resistance in the most brittle areas, followed by the continuous line-like and the connected bulk σ -phase. Additionally, the bulk σ -phase is lamellar and the primary phase within it is considered to be corroded badly. Based on the above analyses, we can conclude that the corrosion behavior of CoCrFeNiMo_x ($x = 0.1$ – 0.5) in 3.5 wt% NaCl and 0.5 mol/L H₂SO₄ solutions depends on the combined effect of beneficial Mo and detrimental σ -phase.

5 Conclusions

1. Mo possesses a beneficial effect on the corrosion resistance of CoCrFeNiMo_x alloys, while σ -phase is detrimental in 3.5 wt% NaCl and 0.5 mol/L H₂SO₄. Therefore, the further work focusing on alleviating or eliminating the σ -phase could further improve the corrosion resistance.
2. CoCrFeNiMo_{0.2} or CoCrFeNiMo_{0.4} showed the best corrosion resistance, indicating that the best proportion of Mo and σ -phase.
3. The XPS results of CoCrFeNiMo_x alloys in H₂SO₄ solution indicate that Cr and Mo play the leading role in corrosion resistance, where Mo primarily exists in the form of MoO₃.

Acknowledgement The work was supported financially by the National Natural Science Foundation of China (Nos. 51471133 and 51771149).

References

- [1] B. Cantor, I. Chang, P. Knight, A. Vincent, *Mater. Sci. Eng. A* **375**, 213 (2004)
- [2] J.W. Yeh, S.K. Chen, S.J. Lin, J.Y. Gan, T.S. Chin, T.T. Shun, C.H. Tsau, S.Y. Chang, *Adv. Eng. Mater.* **6**, 299 (2004)
- [3] M.C. Gao, J.W. Yeh, P.K. Liaw, Y. Zhang, *High-Entropy Alloys: Fundamentals and Applications* (Springer, Berlin, 2016)
- [4] M.H. Tsai, J.W. Yeh, *Mater. Res. Lett.* **2**, 107 (2014)
- [5] W. Zhang, P.K. Liaw, Y. Zhang, *Sci. China Mater.* **61**, 2 (2018)
- [6] Y. Shi, B. Yang, P.K. Liaw, *Metals* **7**, 43 (2017)
- [7] Y. Qiu, S. Thomas, M. Gibson, H.L. Fraser, N. Birbilis, *N.P.J. Mater. Degradation* **1**, 15 (2017)
- [8] M.J. Yao, K.G. Pradeep, C.C. Tasan, D. Raabe, *Scr. Mater.* **72**, 5 (2014)
- [9] M.S. Lucas, G.B. Wilks, L. Mauger, J.A. Muñoz, O.N. Senkov, E. Michel, J. Horwath, S.L. Semiatin, M.B. Stone, D.L. Abernathy, E. Karapetrova, *Appl. Phys. Lett.* **100**, 251907 (2012)
- [10] F. He, Z. Wang, Q. Wu, S. Niu, J. Li, J. Wang, C. Liu, *Scr. Mater.* **131**, 42 (2017)
- [11] Z. Wu, H. Bei, F. Otto, G.M. Pharr, E.P. George, *Intermetallics* **46**, 131 (2014)
- [12] F. He, Z. Wang, Q. Wu, J. Li, J. Wang, C. Liu, *Scr. Mater.* **126**, 15 (2017)
- [13] X. Shang, Z. Wang, F. He, J. Wang, J. Li, J. Yu, *Sci. China Technol. Soc.* **61**, 189 (2018)
- [14] H. Yang, X. Shang, L. Wang, Z. Wang, J. Wang, X. Lin, *Acta Metall. Sin.* **54**, 905 (2018). (in Chinese)
- [15] X.W. Qiu, C.G. Liu, *J. Alloys Compd.* **553**, 216 (2013)
- [16] C. Shang, E. Axinte, J. Sun, X. Li, P. Li, J. Du, P. Qiao, Y. Wang, *Mater. Des.* **117**, 193 (2017)
- [17] Y.J. Hsu, W.C. Chiang, J.K. Wu, *Mater. Chem. Phys.* **92**, 112 (2005)
- [18] J.B. Cheng, X.B. Liang, B.S. Xu, *Surf. Coat. Technol.* **240**, 184 (2014)
- [19] Y. Shi, B. Yang, X. Xie, J. Brechtel, K.A. Dahmen, P.K. Liaw, *Corros. Sci.* **119**, 33 (2017)
- [20] C. Lee, Y. Chen, C. Hsu, J. Yeh, H. Shih, *J. Electrochem. Soc.* **154**, C424 (2007)
- [21] Y.X. Liu, C.Q. Cheng, J.L. Shang, W. Rui, L. Peng, Z. Jie, *Trans. Nonferrous Met. Soc.* **25**, 1341 (2015)
- [22] J. Cheng, D. Liu, X. Liang, B. Xu, *Acta Metall. Sin. (Engl. Lett.)* **27**, 1031 (2014)
- [23] Y.L. Chou, Y.C. Wang, J.W. Yeh, H.C. Shih, *Corros. Sci.* **52**, 3481 (2010)
- [24] Y. Chou, J. Yeh, H. Shih, *Corros. Sci.* **52**, 2571 (2010)
- [25] A. Pardo, M.C. Merino, A.E. Coy, F. Viejo, R. Arrabal, E. Matykina, *Corros. Sci.* **50**, 1796 (2008)
- [26] M. Ameer, A. Fekry, F.E. Heikal, *Electrochim. Acta* **50**, 43 (2004)
- [27] J. Wanklyn, *Corros. Sci.* **21**, 211 (1981)
- [28] K. Hashimoto, K. Asami, K. Teramoto, *Corros. Sci.* **19**, 3 (1979)
- [29] K. Sugimoto, Y. Sawada, *Corros. Sci.* **17**, 425 (1977)
- [30] K. Sugimoto, Y. Sawada, *Corrosion* **32**, 347 (1976)
- [31] A. Mishra, S. Ramamurthy, M. Biesinger, D. Shoesmith, *Electrochim. Acta* **100**, 118 (2013)

- [32] J. Hayes, J. Gray, A. Szmodis, C. Orme, *Corrosion* **62**, 491 (2006)
- [33] A. Tomio, M. Sagara, T. Doi, H. Amaya, N. Otsuka, T. Kudo, *Corros. Sci.* **98**, 391 (2015)
- [34] Y. Lu, C. Clayton, *J. Electrochem. Soc.* **132**, 2517 (1985)
- [35] A. Brooks, C. Clayton, K. Doss, Y. Lu, *J. Electrochem. Soc.* **133**, 2459 (1986)
- [36] C. Clayton, Y. Lu, *J. Electrochem. Soc.* **133**, 2465 (1986)
- [37] C. Clayton, Y. Lu, *Corros. Sci.* **29**, 881 (1989)
- [38] Y. Lu, C. Clayton, A. Brooks, *Corros. Sci.* **29**, 863 (1989)
- [39] M. Pourbaix, J.A. Franklin, *Atlas of Electrochemical Equilibria in Aqueous Solutions*, 2nd edn. (NACE International, Houston, 1974)
- [40] W. Yang, R.C. Ni, H.Z. Hua, A. Pourbaix, *Corros. Sci.* **24**, 691 (1984)
- [41] K. Hashimoto, K. Asami, A. Kawashima, H. Habazaki, E. Akiyama, *Corros. Sci.* **49**, 42 (2007)
- [42] H. Habazaki, A. Kawashima, K. Asami, K. Hashimoto, *Corros. Sci.* **33**, 225 (1992)
- [43] Z. Szklarska-Smialowska, *Pitting Corrosion of Metals* (NACE, Houston, 1986)
- [44] M.W. Tan, E. Akiyama, A. Kawashima, K. Asami, K. Hashimoto, *Corros. Sci.* **37**, 1289 (1995)
- [45] C. Leygraf, G. Hultquist, I. Olefjord, B.O. Elfström, V. Knyazheva, A. Plaskeyev, Y.M. Kolotyrkin, *Corros. Sci.* **19**, 343 (1979)
- [46] A. Irhzo, Y. Segui, N. Bui, F. Dabosi, *Corrosion* **42**, 141 (1986)
- [47] T. Wijesinghe, D.J. Blackwood, *Corros. Sci.* **50**, 23 (2008)
- [48] T.T. Shun, L.Y. Chang, M.H. Shiu, *Mater. Charact.* **70**, 63 (2012)
- [49] W. Liu, Z. Lu, J. He, J. Luan, Z. Wang, B. Liu, Y. Liu, M. Chen, C. Liu, *Acta Mater.* **116**, 332 (2016)
- [50] B. Wilde, *Corrosion* **28**, 283 (1972)
- [51] K. Ogura, T. Ohama, *Corrosion* **40**, 47 (1984)
- [52] G. Frankel, *J. Electrochem. Soc.* **145**, 2186 (1998)
- [53] W. Tian, N. Du, S. Li, S. Chen, Q. Wu, *Corros. Sci.* **85**, 372 (2014)
- [54] X. Shang, Z. Wang, F. He, J. Wang, J. Li, J. Yu, *Sci. China Technol. Sci.* **61**, 2 (2017)
- [55] P. Bommersbach, C. Alemany-Dumont, J.P. Millet, B. Normand, *Electrochim. Acta* **51**, 1076 (2005)
- [56] L. Liu, Y. Li, F. Wang, *Electrochim. Acta* **52**, 7193 (2007)
- [57] A.S. Hamdy, E. Shenawy, T. Bitar, *Int. J. Electrochem. Soc.* **1**, 171 (2006)
- [58] A. Pardo, M.C. Merino, A.E. Coy, F. Viejo, R. Arrabal, E. Matykina, *Corros. Sci.* **50**, 780 (2008)
- [59] N. McIntyre, M. Cook, *Anal. Chem.* **47**, 2208 (1975)
- [60] T. Chuang, C. Brundle, D. Rice, *Surf. Sci.* **59**, 413 (1976)
- [61] G.C. Allen, P.M. Tucker, P.K. Wild, *J. Chem. Soc.* **74**, 1126 (1978)
- [62] J. Leiro, E. Minni, *Philos. Mag. B* **49**, L61 (1984)
- [63] C.E. Myers, H.F. Franzen, J.W. Anderegg, *Inorg. Chem.* **24**, 1822 (1985)
- [64] V. Nefedov, Y.V. Salyn, G. Leonhardt, R. Scheibe, *J. Electron Spectrosc. Relat. Phenom.* **10**, 121 (1977)
- [65] C. Wagner, W. Rigg, L. Davis, J. Moulder, G. Muilenberg, *Handbook of X-ray Photoelectron Spectroscopy* (Perkin-Elmer Corporation, Eden Prairie, 1979)
- [66] C.P. Li, A. Proctor, D.M. Hercules, *Appl. Spectrosc.* **38**, 880 (1984)
- [67] M.C. Biesinger, B.P. Payne, A.P. Grosvenor, L.W. Lau, A.R. Gerson, R. Smart, *Appl. Surf. Sci.* **257**, 2717 (2011)
- [68] D. Zingg, L.E. Makovsky, R. Tischer, F.R. Brown, D.M. Hercules, *J. Phys. Chem.* **84**, 2898 (1980)
- [69] H. Yao, R. Baird, H. Gandhi, *J. Catal.* **84**, 8 (1983)
- [70] J. Simmons, *Mater. Sci. Eng. A* **207**, 159 (1996)
- [71] J.O. Nilsson, *Mater. Sci. Technol.* **8**, 685 (1992)
- [72] D.Y. Kobayashi, S. Wolyne, *Mater. Res.* **2**, 239 (1999)
- [73] X.H. Zhao, Z.Q. Bai, Y.R. Feng, A.Q. Fu, *Appl. Mech. Mater.* **184**, 1038 (2002)
- [74] J. Michalska, M. Sozańska, *Mater. Charact.* **56**, 355 (2006)
- [75] H.M. Ezuber, A. Houd, F. Shawesh, *Desalination* **207**, 268 (2007)
- [76] J. Xu, C. Zhuo, J. Tao, S. Jiang, *Appl. Surf. Sci.* **255**, 2688 (2008)
- [77] K. Adhe, V. Kain, K. Madangopal, H. Gadiyar, *J. Mater. Eng. Perform.* **5**, 500 (1996)