Tribological Characterization of Commercial Pure Titanium Processed by Multi-Directional Forging

I. Ansarian¹ · M. H. Shaeri¹ · M. Ebrahimi² · P. Minárik³

Received: 28 October 2018 / Revised: 26 November 2018 / Published online: 20 February 2019
© The Chinese Society for Metals (CSM) and Springer-Verlag GmbH Germany, part of Springer Nature 2019

Abstract

This work discusses tribological properties of commercial pure (CP) titanium processed by multi-directional forging (MDF) up to six passes at room temperature and 220 °C. For this purpose, wear test was conducted by dry sliding pin-on-disk method on the initial and ultrafine grained samples using different stress magnitudes of 1, 1.5 and 2 MPa. The results showed that wear resistance of CP titanium increases after the first pass of MDF in comparison with the initial condition, irrespective of the applied normal stress. For example, the average wear rate of MDFed samples was decreased about 30% and 24%, after first pass at room temperature and 220 °C, respectively. However, average wear rate of the samples processed by six MDF passes was reduced about 40% at lower normal loads; it was increased about 9% at higher ones as compared to the initial condition. It was also found that the dominated wear mechanisms were abrasive and delaminated at the lower stresses, while the delamination mechanism was intensified and a slight adhesion was observed during the higher applied normal loads.

Keywords Multi-directional forging · Commercial pure titanium · Tribological behavior · Wear mechanisms

1 Introduction

Severe plastic deformation (SPD) methods have proved their capability and potential as a suitable technique for production of bulk ultrafine grain (UFG), and even, nanostructure (NS) metals and alloys [1–5]. Some of the prominent SPD methods which have been well developed include equal channel angular pressing (ECAP) [6, 7], equal channel forward extrusion [8], high-pressure torsion (HPT) [9], planar twist extrusion (PTE) [10], constrained groove pressing (CGP) [11], accumulative roll bonding (ARB) [12], cryorolling [13], multi-directional forging (MDF) [14], etc. It is

generally accepted that materials with refined grain structure can be prepared by imposing shear stress through SPD methods, during which the density of dislocations significantly increases. Moreover, the resulting structure is almost free of porosities and impurities, and the material does not suffer from the dimensional change [15–17].

Multi-directional forging is categorized among the relatively new SPD methods. Nevertheless, till now, a lot of different pure metals and alloys have been processed by this technique with perspective results. Through this two-side closed forging technique, the rectangular sample with different aspect ratios is pressed from three directions. Additionally, the sample can be rotated 90° around the central forging axis after each pass of the process to intersect the shear bands at three dimensions. This results in extreme grain refinement and homogenization of the final microstructure. It should be noted that this method can be performed at various temperatures, strains (by considering the sample dimensions) and strain rates. Accordingly, the controllable amount of the induced strain during each pass and the repeatability of the process are the main advantages of MDF method. Furthermore, the attained structure after consecutive passes of MDF is more homogenous in comparison with some SPD methods due to the multi-axial nature of this technique. Moreover, low ductile materials could be

Available online at <http://link.springer.com/journal/40195>

✉ M. H. Shaeri
shaeri@ENG.ikiu.ac.ir

¹ Department of Materials Science and Engineering, Imam Khomeini International University (IKIU), P.O. Box 34148-96818, Qazvin, Iran

² Department of Mechanical Engineering, Faculty of Engineering, University of Maragheh, P.O. Box 55136-533, Maragheh, Iran

³ Department of Physics of Materials, Faculty of Mathematics and Physics, Charles University, Prague, Czech Republic

processed by this technique due to the compressive nature of the induced strain [18, 19].

Although improved mechanical properties of the ultrafine grain materials have been well demonstrated, there are limited studies on their tribological behavior. In fact, the wear resistance of UFG materials is of crucial importance especially for structural applications, because surface degradation is one of the main reasons of failure in case of components which are in contact during motion [20, 21]. As known, one of the motives for the application of SPD-processed pure titanium is its potential as a biomaterial. Improving strength and fatigue properties of pure titanium through different SPD methods makes it a suitable candidate for implant materials by considering its good corrosion resistance and biocompatibility. It is needed to mention that if the wear resistance of implant would be low, the abrasive particles may lead to loss of exact bio-metal contact and occurrence of toxic reactions in the surrounding live tissues; therefore, investigation of wear resistance is unavoidable [22].

The effect of some SPD methods on wear properties of commercial pure (CP) titanium has been investigated in limited researches. Purcek et al. [23] reported that by reducing the grain size of CP titanium to 300 nm via the ECAP process at 300 °C, despite the improvement of mechanical properties, no significant improvement was observed in slip wear resistance. On the other hand, the studies by Wang et al. [24] and La et al. [25] showed that by applying the HPT process at RT and eight passes of ECAP process at 450 °C, wear resistance improved. In general, there are scattered results about the wear resistance of UFG pure titanium. Also, despite the simplicity, low cost and more potential for industrial application of MDF process in comparison with those of many SPD methods [14], the effect of this process on the wear properties of CP titanium has not been studied. For this aim, grade 2 CP titanium was processed through MDF process up to six passes at both room and 220 °C temperatures. Afterward, wear rate of initial material and MDF-processed CP titanium at different conditions was measured. Moreover, the surface morphology of worn surfaces and abrasive particles was investigated by scanning electron microscope (SEM).

2 Experimental

The MDF die used in this study was manufactured from tool steel AISI/SAE H13 and was heat treated in order to obtain the hardness of 52 HRC. The used BT1 titanium (grade 2) has a nominal composition of 99.27 Ti, 0.372 Al, 0.201 Fe, 0.079 Mn, 0.043 Cr and 0.029 V (wt%). The as-received material was in rolled condition. The samples were machined to the rectangular shape with dimension of

10 mm × 10 mm × 15 mm. Prior to the MDF process, all samples were annealed at 800 °C for 1 h and were cooled in furnace. For MDF operation, a hydraulic press was applied with a 100 t capacity and a ram speed of 1.6 mm/s was used. MDF process was performed at room temperature (RT) and 220 °C up to six passes. Molykote 1000 solid lubricant paste with composition of grease, graphite, calcium fluoride and copper metal powder was employed in order to decrease the friction between the surfaces of the sample and die.

For microstructural investigations and grain size measurements of the as-received and MDFed samples, SEM of Zeiss Auriga Compact equipped with electron backscatter diffraction (EBSD) camera was used at an accelerating voltage of 15 kV and a beam current of 10 nA. The raw data were analyzed by OIM TSL7 software. Tensile and shear strengths of samples were documented by Zwick/Roell Z100 universal testing machine at room temperature with the strain rate of 10^{-3} s^{-1} . At least three measurements were conducted for each sample in order to increase reliability. The hardness of samples was measured by Vickers microhardness testing method using HVS-1000A microhardness device. It should be noted that the test was performed with the load of 500 grams and dwell time of 15 s in accordance with ASTM E-384 standard.

Furthermore, wear behavior of samples was measured by pin-on-disk method using TR-20 DUCOM device according to ASTM G99 standard and with the humidity of about 20%. The device was equipped with a non-contact transducer in order to determine the friction coefficient in dry condition. For all tests, the total sliding distance was chosen to be 1000 m with the sliding speed of 0.2 m s^{-1} at room temperature. Also, the applied normal forces were selected to be 20, 30 and 40 N, which are equivalent to normal pressures of about 1, 1.5 and 2 MPa, respectively. To prepare the required wear testing pins, cylinders with the diameter of 5 mm and height of 7.5 mm were fabricated using the implementation of wire cutting and milling machines. In addition, 100Cr6 steel material was utilized for preparation of counterface disks with the height of 7 mm and diameter of 50 mm. Afterward, they were heat treated to obtain the hardness of about 63 HRC. Finally, the magnetic grinding machine was used to attain abrasive disks with optimal surface smoothness and similar surface roughness.

The weight loss of samples was measured through a digital balance with a precision of 0.1 mg. In order to calculate dynamic friction coefficient between the titanium and steel, wear parameters including normal load, linear speed, frequency, etc. were adjusted; after that, applied normal load and linear speed were inserted to CDT25 software to record the variation of friction coefficient within the sliding distance. For a better understanding of wear mechanism, the surface morphology of worn samples was investigated by SEM MIRA3-TESCAN equipped with energy-dispersive

spectrometer (EDS). It is worth mentioning that EDS was used in order to analyze the chemical composition of worn surface and particles. Additionally, the worn particles which play an important role in the analysis of wear behavior were collected after each test. Finally, SEM with secondary and backscatter electrons sensors was applied to determine dimensions, morphology and the chemical composition of gold-coated aforementioned worn particles.

3 Results and Discussion

3.1 Microstructure Observations

Figure 1 shows EBSD maps of the CP titanium before and after the six passes of MDF process at both room temperature and 220 °C. It was observed from Fig. 1a that the annealed sample has relatively spherical and equiaxed grains with the average grain size of about 44 μm . According to Fig. 1b, c, the microstructures were significantly refined with resulting average grain sizes of 390 nm and 430 nm after six passes of MDF process at room and 220 °C temperatures, respectively. The main reason for the considerable decrease in grain size is the increment of dislocations density and consequently low-angle grain boundary (LAGB) during the first step of MDF process. The aforementioned sub-grains are subsequently transformed to high-angle grain boundaries

(HAGBs) by increasing the amount of the plastic strain during higher pass numbers. Eventually, the grain boundaries become stabilized, and ultrafine grain structure is formed [26, 27].

3.2 Mechanical Properties

Mechanical properties of the investigated samples have been listed in Table 1. The results indicate that the utilization of six-pass MDF process, irrespective of the operating temperature, leads to the improvement of hardness magnitude, tensile yield strength and shear yield strength due to the increment of dislocations density and formation of the UFG structure which are clearly observed in Fig. 1. As demonstrated, the mechanical properties of MDFed samples are improved more considerable by processing at room temperature than the temperature of 220 °C. It can also be mentioned that the obtained mechanical properties at both temperatures become closer to each other by increasing the pass numbers due to the microstructural homogenization and formation of UFG structure.

3.3 Wear Behavior

Figure 2 shows wear rate of CP titanium processed up to six passes of MDF at both temperatures, when the normal pressures of 1, 1.5 and 2 MPa were applied. It was observed

Fig. 1 EBSD maps of CP titanium after **a** annealing, **b** six passes at room temperature, **c** six passes at 220 °C (ND normal direction, TD transverse direction)

Table 1 Mechanical properties of CP titanium before and after MDF process up to six passes at both room temperature (RT) and 220 °C

Condition	Vickers hardness (HV)	Shear yield strength (MPa)	Tensile yield strength (MPa)
As-received	136 ± 7.27	207 ± 14	228 ± 17.15
One pass at RT	209 ± 4.71	393 ± 11.8	433 ± 24.3
One pass at 220 °C	183 ± 10.71	290 ± 3.5	335 ± 7.5
Three passes at RT	246 ± 4.71	450 ± 1.0	560 ± 35.2
Three passes at 220 °C	225 ± 12.8	406 ± 5.0	450 ± 37.41
Six passes at RT	268 ± 16.53	497 ± 13	615 ± 21.6
Six passes at 220 °C	235 ± 9.14	450 ± 2.0	593 ± 12.5

Fig. 2 Variation of wear rate versus pass number of MDF-processed CP titanium at room and high temperatures in applied normal stresses of **a** 1 MPa, **b** 1.5 MPa, **c** 2 MPa

that the first pass of MDF leads to improvement of wear resistance as compared to the initial sample for all applied normal loads at both room and high temperatures. The origin of this improvement may be described by Archard relation:

$$Q = V/L = KF/H, \quad (1)$$

where Q , V , L , F and H represent wear rate, wear volume, total sliding distance, applied normal load and hardness magnitude, and K represents the Archard coefficient (wear coefficient) with the magnitude of lower than 1, which depends on the surface condition [11].

Based on Eq. (1), wear resistance (Q^{-1}) is proportional to the hardness of sample. In other words, wear resistance of CP titanium is improved by application of MDF process due to the increment of the hardness magnitude. It is worth mentioning that irrespective of the applied normal loads, average wear resistance of the material was increased by 30% and 24% after the first pass of MDF at room and 220 °C temperatures, respectively.

As shown in Fig. 2a, MDF process has a positive effect on wear resistance of CP titanium regardless the processing temperature, when the normal stress of 1 MPa is applied. Six passes of MDF lead to ~40% increment of wear resistance in comparison with the annealed condition. Although wear resistance of the material was improved after the first pass in higher applied normal loads, it subsequently deteriorated

in samples with higher pass number. As can be seen, for the normal stress of 1.5 MPa, a limited improvement in wear resistance can be observed with increasing MDF passes from 3 to 6 (specially in processed samples at high temperature), while in case of 2 MPa normal stress, the wear resistance was reduced by increasing the pass number up to six passes. It should be also noted that at higher applied normal loads, the reduction in wear resistance by increment of pass number is more profound in processed samples at high temperature. Although hardness and strength were dramatically improved after the third and sixth MDF pass, wear resistance of the aforementioned cases did not reflect this improvement for the normal stresses of 1.5 MPa and 2 MPa. This may be mainly attributed to the active wear mechanisms. Titanium is one of the most reactive materials. It easily reacts with oxygen and transforms to rutile (TiO_2). It seems that the surface oxide layer on titanium plays a prominent role in wear behavior of coarse grain (CG) and UFG titanium, and possibly, otherwise positive effect of UFG structure can be negative for wear resistance [20]. It should be noted that the rate of weight loss is sharply intensified, and the wear mechanism is transformed from mild to severe condition, by increasing the applied pressure to the magnitudes higher than 2 MPa. This phenomenon may be the result of temperature rise due to the load increment of the worn surface sublayers; hence, making the formed

tribological layer unsteady. This layer has a ceramic nature, because it is gradually produced by oxidation and reaction of two surfaces. If the tribological layer is destroyed, it can be formed again by the oxidation and chemical reactions of uncovered surfaces. It means that the applied normal stress of 2 MPa is beyond the limit of mild wear, additionally, the sample with the UFG structure (six MDF passes) may be more prone to form oxides on its surface; therefore, higher weight loss occurs due to the unsteady nature of the tribological layer [23, 28]. Titanium oxide films have been observed to form more readily on deformed surfaces in comparison with the annealed ones, because formation of oxides in UFG condition stems from higher reactivity of the surface due to the higher surface fraction of grain boundaries and non-equilibrium grain boundaries [29–32].

Figure 3a–d shows variation of the friction coefficient versus sliding distance for different investigated samples. As shown in Fig. 3d, the total sliding distance could be divided into two regions. The first one is called running-in region in where the magnitude of friction coefficient quickly increases with adding sliding distance until it reaches a steady state region. The reason of the mentioned increase can be explained by the increment of the real contact surface, the creation of three-body wear condition results from the occurrence of wear particles between the pin and disk and the formation of the scratches [33–37]. It seems that the overall friction force could be related to two sources: the adhesion force which is related to the asperities between the real surfaces of layers and deformation force which is required for scratching the soft surface using both abrasive particles and the asperities of the harder surface. By reaching the 200 m sliding distance, the running-in region (first zone) is finished and the second region starts. Also, the period of running-in depends on the initial surface roughness, so that increasing the initial surface roughness results in a longer running-in period [33]. In the steady state region, the tribological layer is formed due to the oxidation and interaction of surfaces, and if it is damaged due to the unsteady conditions, it could be formed again and has a capability to self-healing. It can be said that the mean friction coefficient magnitude remains constant if the wear mechanism is constant. The observed increment of amplitude fluctuation of the friction coefficient versus sliding distance is an indication of adhesion and severe scratching. One example of this event is shown in Fig. 3c with the oval box. In fact, the tribological layer is fragmented and formed again, which leads to the rise and fall of the friction coefficient [28].

Furthermore, irrespective of the MDF pass number and processing temperature, the mean friction coefficient of the investigated material remains relatively constant in the range of 0.49–0.62 (see Fig. 3e, f). Comparable results have been reported earlier for titanium. Wang et al. [24] showed that the dynamic friction coefficient of titanium is ~0.6 and grain

refinement of the material does not have the considerable effect on it, while wear mechanism of CG and UFG titanium was different from each other. Likewise, it was reported by La et al. [25] that the friction coefficient of titanium is in the range of 0.45–0.60 and the UFG structure does not have any sizeable effect.

Wear mechanism and consequently sample wear rate are changed due to the increment of the applied normal load. For instance, at the six-pass room-temperature MDFed sample, the amount of wear rate is increased about 37% and 32% by increasing the applied normal stress from 1 to 1.5 MPa and from 1.5 to 2 MPa, respectively, while the mean friction coefficient is still constant. It is mainly due to this fact that the friction coefficient is strongly depended on the shear strength of interface, which is located between the pin and disk [28]. This relation is represented as follows:

$$\mu = \frac{1}{\sqrt{(\tau_0/\tau_i)^2 - 1}}, \quad (2)$$

where μ , τ_0 and τ_i are friction coefficient, shear yield strength of the bulk material and shear yield strength of interface, respectively.

This equation indicates that friction coefficient has an ascending relation with the shear stress of interface. It is generally accepted that the shear strength of interface is lower than the bulk material, because the interface (the tribological layer in this work) is mainly formed by oxides with ceramic nature. Nevertheless, with increasing normal load, there is a local increment of temperature at the tribological layer and consequently the shear strength of interface is reduced. Hence, the magnitude of friction coefficient is almost the same, irrespective of the applied normal loads [28].

Figure 4 shows the results of SEM images of worn surface at the initial annealed condition and after six MDF passes (room temperature and 220 °C), when the normal stress of 1 MPa was applied. In addition, EDS point analysis of selected regions is added to this figure. Accordingly, it is clear that wear resistance of CP titanium is improved after the six passes of MDF process, which was shown in Fig. 2a. As shown in Fig. 4a for the annealed CP titanium, there are some deep craters shown with oval boxes. The rectangular box of Fig. 4a is an indication of delamination on the surface of the sample. This mechanism has also been reported in the work of La et al. [25] on the wear behavior of CG and UFG titanium and observed in many samples of this study, as well. During delamination mechanism, some cracks are nucleated at the subsurface regions and grown parallel with the surface. They are created at regions of subsurface which undergoes plastic deformation. It should be noted that most delamination of titanium sample is related to the tribological layer. This phenomenon occurs in the tribological layer

Fig. 3 Variation of friction coefficient vs. sliding distance of CP titanium during MDF process up to six passes with applied normal stresses of 1 MPa **a**, **b**, 2 MPa **c**, **d** operating at room temperature **a**,

c, 220 °C **b**, **d**, mean friction coefficients of samples before and after MDF process at room temperature **e**, 220 °C **f**

during the mild wear. Additionally, regions 1 and 2 in Fig. 4a shown by the arrows are the glossy areas. These areas can be an indication of adhesive wear which is slightly occurred. It can be caused by the low shear strength of the annealed sample's subsurface that has lost the ability to hold the tribological layer in these regions [25, 28]. According to Shamsipur et al. [38] abrasive and adhesive wear, was also occurred in

the as-received CG titanium sample. In addition, La et al. stated that adhesion and delamination wear mechanism were observed in worn surface of CG Ti [25].

The arrows in the lower rectangular box of Fig. 4b which is related to the six-pass high-temperature sample show that the tribological layer is being delaminated. Two upper rectangular boxes are also indicative of abrasive wear

Fig. 4 SEM images of worn surfaces during applied normal stress of 1 MPa for **a** initial condition, **b** six passes at 220 °C, **c** six passes at room temperature, **d** EDS analysis of points A–C in **c**

mechanism in which the scratches are slightly deep in small one. Additionally, single arrows (outside of the rectangular boxes) illustrate the grooves which are possibly formed due to the roughness of contact surfaces and maybe the presence of particles. These particles which have been separated from the tribological layer, and could not get out among the surfaces, are trapped between two surfaces. Consequently, they create some scratches and grooves on the sample's surface, since they are hard enough due to the ceramic nature [23]. Also, the hard debris particles are generated by delamination mechanism or by the asperities of mating surfaces [38, 39]. These debris may affect the wear properties in two different ways: (1) they may get locked between the sliding surfaces and propagate the three-body abrasive wear, consequently enhanced the wear rate, and (2) these particles form a protective transfer layer on the sliding surface in a way that no scratch can be seen on it [39].

In Fig. 4c which is related to the six-pass MDFed titanium at room temperature, the arrows in the lower rectangular box are an indication of tribological layer's delamination. Also, the upper rectangular box shows abrasive wear mechanism. The arrow representing region 1 shows that the abraded particles are fragmented due to the delamination process. It can be found from the chemical analysis of the

specified points in Fig. 4d that wear is still limited to the tribological layer due to the presence of considerable amount of oxygen concentration in EDS analysis of different points. It can also be said that the wear process is controlled by the tribological layer.

Based on the results of the point analysis and surface morphology in Fig. 4 can be deduced that wear resistance of UFG CP titanium is better than the CG counterpart when the normal stress of 1 MPa is applied. According to Fig. 4b, c, wear mechanism and surface morphology of the six-pass CP titanium are relatively similar at both room and 220 °C temperatures at this applied normal stress. In other words, temperature of MDF process has no sizeable effect on morphology and wear behavior of these two aforementioned samples. It is related to this fact that grain size, hardness magnitude and strength of the deformed CP titanium after undergoing six passes at both room and 220 °C temperatures are close to each other. Eventually, UFG fabrication of titanium leads to the improvement of the surface morphology at normal stress of 1 MPa, in which more homogeneous grooves and craters with less depth are achieved. Hence, the craters and grooves are limited to the tribological layer, and the wear process becomes more controllable. Similarly, Wang et al. [24] reported that by applying the HPT process

and formation of UFG structures in pure titanium, wear properties were improved due to formation of more uniform grooves, and accordingly UFG Ti showed lower wear rate compared to that of CG Ti.

Figure 5 shows results of SEM analysis of worn surface of the initial annealed sample and six-pass MDFed samples at room temperature and 220 °C temperatures, when the normal stress of 2 MPa was applied. In addition, EDS points analysis of selected regions is added to this figure. According to Fig. 5a, secondary electron image has clearly

illustrated the roughness of the surface in which the deep craters and grooves are observed. Some of them are exhibited by arrows. Severe delamination occurred in this sample can be an indication of weak wear resistance of the annealed CP titanium. Additionally, the tribological layer seems to be highly unstable; therefore, fragmentation and crushing of debris and their smearing with the layer are subsequently occurred. Unsteadiness of the tribological layer can be caused by the increment of the normal pressure beyond the critical value (a little higher than 2 MPa) and the lower shear

Fig. 5 SEM images of worn surface during applied normal stress of 2 MPa for **a** initial condition, **b** six passes at 220 °C, **c** six passes at room temperature, EDS analysis of points A and B in **d**, **e**

strength of the annealed titanium. These lead to the temperature rise and easy flow of the subsurface. The particles smeared with the surface can be possibly inhibited due to the unstable surface layer and the friction of surfaces; consequently, wear resistance of the annealed sample is reduced by initiation of the severe wear regime [23, 28].

The secondary electron image of Fig. 5b shows a wide and delaminated shape fragmentation. This is due to the high magnitude of the applied normal stress which leads to the flow of subsurface and more unsteadiness of the tribological layer compared to the low force magnitude. It should be mentioned that the wear of six passes at 220 °C CP titanium is still restricted to the tribological layer, because the chemical analysis of the specified points shows that although the oxygen is reduced, the tribological layer still exists in metal surface. By considering the rectangular box of Fig. 5c, it is found that there are some glossy regions which are an indication of adhesive wear. It is clear that the tribological layer is removed from these regions, and the weight percent of elements in Fig. 5e confirms this event. According to this figure, it can be noted that the oxygen amount of point B is lower than 5%, while there is about 95% titanium. By regarding that the chemical analysis of this region is relatively metallic, it can be concluded that the fragmentation has been occurred from the titanium pin. Consequently, the tribological layer is unsteady through applying normal stress of 2 MPa; therefore, more wear rate is obtained for the UFG CP titanium as compared to the annealed condition. Furthermore, the wear rate of six-pass CP titanium at RT is more than the corresponding sample at 220 °C, as a result of slight adhesive wear in Fig. 5c. This matter is in good agreement with the achieved results of Fig. 2c.

Figure 6 shows SEM images of worn particles at the initial annealed condition and after six MDF passes at room temperature and 220 °C, when the normal stress of 2 MPa was applied. In addition, EDS point analysis of selected regions is added to this figure. As shown in Fig. 6a, the particles in annealed sample are coarse with the delaminated shape which is an indication of severe delamination mechanism. It is in suitable coincidence with relatively deep and long shape craters on the worn surface of Fig. 5a. According to chemical analysis of specified points in Fig. 6d, weight percent of region A indicates that the oxygen amount is highly reduced and the weight percent of iron and titanium is increased that might be due to the sticking of iron to the titanium. Also, the weight percent of region C in which the oxygen value is decreased, and the titanium magnitude is higher than 93%, represents that a part of these particles is fragmented from the titanium itself. This relates to the lower shear strength of the annealed sample, and presumably, it may cause sticking the steel disk to the titanium, and the occurrence of slight adhesive wear. In fact, the nature of particle is almost metallic in this region.

The planar shape of particles at the worn surface of six-pass MDFed sample at the temperature of 220 °C is clearly similar to the craters of the worn surface in Fig. 5b, indicating a delamination wear mechanism [28]. Additionally, the existence of aligned grooves in Fig. 6b is associated with the abrasive wear mechanism of the tribological layer. As can be observed for the UFG structure of titanium during the normal stress of 2 MPa, the abrasive particles of Fig. 6b, c are larger than the particles in Fig. 6a for the annealed condition [32]. This result is in acceptable agreement with the reduction in wear resistance of six-pass MDFed sample in comparison with the annealed sample (Fig. 2c). According to Fig. 6c, it is obvious that particles are very coarse, porous and weak. In other words, the compaction of sample's particles is lost with increasing applied normal stress. This leads to the stability reduction of the tribological layer which is separated so fast. The weight percent of region A shows that the oxygen amount is dramatically decreased, and the particles are relatively metallic. So, the coarse particles with the metallic nature can be an indication of severe wear regime. Additionally, the occurrence of slight adhesive wear mechanism at the worn surface of Fig. 5c is confirmed by the obtained chemical analysis, discussed before.

Finally, SEM images of worn particles during the applied normal load of 20 N for the annealed condition and six-pass MDFed sample at both room temperature and 220 °C are shown in Fig. 7. The particles of this figure are in planar shape, since the delamination mechanism is taken place at the worn surface of the corresponding samples in Fig. 4. Moreover, it is clear that the particle size of Fig. 6 is coarser than the counterpart in Fig. 7. As expected, the size of particles is enlarged by increasing the applied normal stress from 1 to 2 MPa. It is also found that the annealed sample has somewhat bigger particles than the UFG one at the normal stress of 1 MPa which is in accordance with the deeper craters in worn surface of the annealed titanium. These results are in suitable agreement with the wear resistance improvement of produced UFG CP titanium compared to the initial one (Fig. 2a).

4 Conclusions

- (1) Microstructure analysis showed that coarse grained structure of CP titanium is transformed to ultrafine grained one by applying six passes of MDF process at both room temperature and 220 °C. Accordingly, the average grain size is changed from 43 µm to 390 nm and 430 nm for room temperature and 220 °C, respectively. Furthermore, this process leads to the considerable enhancement of mechanical properties of CP titanium, including the hardness, shear and tensile strengths.

Fig. 6 SEM images of abrasive particles during applied normal stress of 2 MPa for **a** initial condition, **b** six passes at 220 °C, **c** six passes at room temperature, EDS analysis of **d** points A–C in **a**, **e** points A and B in **c**

- (2) Analysis of tribological behavior showed that the average wear rate of six-pass deformed samples decreases about 40% and 9% during applied normal stresses of 1 and 2 MPa, respectively, as compared to the annealed sample. Also, the average wear rate of one-pass MDFed samples at room temperature and 220 °C is about 30% and 24% lower than that of annealed titanium sample, respectively, in all applied normal stresses (1, 1.5, 2 MPa). Totally, it can be stated that UFG CP titanium produced by six passes of MDF process is suitable for tribological applications at lower normal stresses; while at higher applied normal stresses, one-pass MDFed CP titanium is more appropriate.
- (3) MDF processing temperature had no considerable effect on the microstructure and mechanical properties of six-pass MDFed samples. Therefore, no significant difference was observed in wear resistance and its mechanisms for six-pass MDFed samples at both room temperature and 220 °C. However, the sample processed by one MDF pass at room temperature exhibited slightly better wear resistance (about 6%) for all applied normal stresses, when compared to its 220 °C counterpart.
- (4) The dynamic friction coefficient of titanium at both CG and UFG structures is in the range of 0.49–0.62. In other words, grain refinement and increment of applied

Fig. 7 SEM images of abrasive particles during applied normal stress of 1 MPa for **a** initial condition, **b** six passes at 220 °C, **c** six passes at room temperature

normal stress have not significant effect on the friction coefficient magnitude.

- (5) Evolution of surface morphology and wear particles produced during the applied stress of 1 MPa showed that wear mechanism is transformed from severe delamination, intense abrasive and poor adhesive mechanisms for the annealed condition to delamination and slight abrasive mechanism for the case of UFG sample (limited to the tribological layer). On the other hand, wear mechanism of the annealed and UFG samples is relatively similar to each other if 2 MPa stress is applied. It means that they experience severe delamination, abrasive and poor adhesive mechanisms.

Acknowledgements This work was supported financially by the Iran National Science Foundation (No. 94809610) and the Czech Science Foundation Project (No. GB14-36566G).

References

- [1] I. Ansarian, M. Shaeri, *Trans. Nonferrous Met. Soc. China* **27**, 1928 (2017)
- [2] M.H. Shaeri, M.T. Salehi, S.H. Seyyedein, M.R. Abutalebi, J.K. Park, *Mater. Des.* **57**, 250 (2014)
- [3] F. Djavanroodi, A.S. Zolfaghari, M. Ebrahimi, K. Nikbin, *Acta Metall. Sin. (Engl. Lett.)* **27**, 95 (2014)
- [4] L. Du, S. Yao, J. Hu, H. Lan, H. Xie, G. Wang, *Acta Metall. Sin. (Engl. Lett.)* **27**, 508 (2014)
- [5] R.G. Guan, D. Tie, *Acta Metall. Sin. (Engl. Lett.)* **30**, 409 (2017)
- [6] M.H. Shaeri, M.T. Salehi, S.H. Seyyedein, M.R. Abutalebi, J.K. Park, *J. Alloys Compd.* **579**, 350 (2013)
- [7] M.H. Shaeri, F. Djavanroodi, S. Ahmadi, M. Seddighi, M.T. Salehi, S.H. Seyyedein, *J. Strain Anal. Mater. Des.* **48**, 512 (2013)
- [8] M. Ebrahimi, H. Gholipour, F. Djavanroodi, *Mater. Sci. Eng. A* **650**, 1 (2016)
- [9] M. Farvizi, M.R. Akbarpour, E.Y. Yoon, H.S. Kim, *Met. Mater. Int.* **21**, 891 (2015)
- [10] M. Ebrahimi, M. Shamsborhan, *J. Alloys Compd.* **705**, 28 (2017)
- [11] M. Ebrahimi, S. Attarilar, F. Djavanroodi, C. Gode, H.S. Kim, *Mater. Des.* **63**, 531 (2014)
- [12] A. Fattah-alhosseini, S.O. Gashti, *Acta Metall. Sin. (Engl. Lett.)* **28**, 1222 (2015)
- [13] A. Joshi, K.K. Yogesha, R. Jayaganthan, *Mater. Charact.* **127**, 253 (2017)
- [14] I. Ansarian, M.H. Shaeri, M. Ebrahimi, P. Minárik, K. Bartha, *J. Alloys Compd.* **876**, 83 (2019)
- [15] J. Liu, A.S. Khan, L. Takacs, C.S. Meredith, *Int. J. Plasticity* **64**, 151 (2015)
- [16] A. Esmaili, M.H. Shaeri, M.T. Noghani, A. Razaghian, *J. Alloys Compd.* **757**, 324 (2018)
- [17] M. Chegini, M.H. Shaeri, *Mater. Charact.* **140**, 147 (2018)
- [18] L. Tang, C. Liu, Z. Chen, D. Ji, H. Xiao, *Mater. Des.* **50**, 587 (2013)
- [19] A. Kundu, R. Kapoor, R. Tewari, J.K. Chakravarty, *Scr. Mater.* **58**, 235 (2008)
- [20] N. Gao, C.T. Wang, R.J. Wood, T.G. Langdon, *J. Mater. Sci.* **47**, 4779 (2012)
- [21] N. Gao, C.T. Wang, R.J. Wood, T.G. Langdon, *Mater. Sci. Forum* **667**, 1095 (2011)
- [22] C.T. Wang, N. Gao, M.G. Gee, R.J. Wood, T.G. Langdon, *J. Mater. Sci.* **48**, 4742 (2013)
- [23] G. Purcek, O. Saray, O. Kul, I. Karaman, G.G. Yapici, M. Haouaoui, H.J. Maier, *Mater. Sci. Eng. A* **517**, 97 (2009)
- [24] C.T. Wang, N. Gao, M.G. Gee, R.J. Wood, T.G. Langdon, *Wear* **280**, 28 (2012)
- [25] P. La, J. Ma, Y.T. Zhu, J. Yang, W. Liu, Q. Xue, R.Z. Valiev, *Acta Mater.* **53**, 5167 (2005)
- [26] C.S. Meredith, A.S. Khan, *J. Mater. Proc. Technol.* **219**, 257 (2015)
- [27] A. Fattah-Alhosseini, M.K. Keshavarz, Y. Mazaheri, A.R. Ansari, M. Karimi, *Mater. Sci. Eng. A* **693**, 164 (2017)
- [28] I.M. Hutchings, P. Shipway, *Tribology: Friction and Wear of Engineering Materials*, 2nd edn. (Tribology, Cambridge, 2016), pp. 47–166
- [29] K.D. Ralston, N. Birbilis, *Corrosion* **66**, 075005 (2010)
- [30] S. Dan, J.H. Jiang, P.H. Lin, D.H. Yang, *Trans. Nonferrous Met. Soc. China* **19**, 1065 (2009)

- [31] A. Balakrishnan, B.C. Lee, T.N. Kim, B.B. Panigrahi, Trends Biomater. Artif. Organs **22**, 58 (2008)
- [32] A. Balyanov, J. Kutnyakova, N.A. Amirkhanova, V.V. Stolyarov, R.Z. Valiev, X.Z. Liao, Y.H. Zhao, Y.B. Jiang, H.F. Xu, T.C. Lowe, Y.T. Zhu, Scr. Mater. **51**, 225 (2004)
- [33] S.A. Miab, B. Avishan, S. Yazdani, Acta Metall. Sin. (Engl. Lett.) **29**, 587 (2016)
- [34] B.Y. Qian, W. Miao, M. Qiu, F. Gao, D.H. Hu, J.F. Sun, R.Z. Wu, B. Krit, S. Betsofen, Acta Metall. Sin. (Engl. Lett.) (2018). <https://doi.org/10.1007/s40195-018-0845-y>
- [35] J.L. Wang, W. Yang, D.P. Xu, X.F. Yao, Acta Metall. Sin. (Engl. Lett.) **30**, 1109 (2017)
- [36] T.G. Wang, Y. Dong, B.A. Gebrekidan, Y.M. Liu, Q.X. Fan, K.H. Kim, Acta Metall. Sin. (Engl. Lett.) **30**, 688 (2017)
- [37] R.S. Bajwa, Z. Khan, V. Bakolas, W. Braun, Acta Metall. Sin. (Engl. Lett.) **29**, 8 (2016)
- [38] A. Shamsipur, S.F. Kashani-Bozorg, A. Zarei-Hanzaki, Acta Metall. Sin. (Engl. Lett.) **30**, 550 (2017)
- [39] M. Fellah, L. Aissani, M.A. Samad, A. Iost, T.M. Zine, A. Montagne, C. Nouveau, Acta Metall. Sin. (Engl. Lett.) **30**, 1089 (2017)