Element Segregation and Solidification Behavior of a Nb, Ti, Al Co-Strengthened Superalloy ЭK151

Yuan-Guo Tan^{1,2} · Fang Liu¹ · An-Wen Zhang^{1,2} · Da-Wei Han¹ · Xiao-Yu Yao^{1,2} · Wei-Wei Zhang^{1,2} · Wen-Ru Sun¹

Received: 16 January 2019 / Revised: 28 February 2019 / Published online: 9 April 2019
© The Chinese Society for Metals (CSM) and Springer-Verlag GmbH Germany, part of Springer Nature 2019

Abstract

The as-cast microstructure, element segregation and solidification behavior of a multi-alloyed superalloy ЭK151 have been investigated. The results show that the severe element segregation leads to the complicated precipitations at the inter-dendritic region, including η -Ni₃(Ti, Nb), eutectic ($\gamma + \gamma'$) and Laves, which shows the characteristics of both Ti, Al-strengthened and Nb-strengthened alloys. Differential thermal analysis, heating and quenching tests reveal the solidification sequence as follows: Liquids $\rightarrow \gamma$ matrix $\rightarrow$ (Nb, Ti)C $\rightarrow \eta$ -Ni₃(Ti, Nb) $\rightarrow$ eutectic ($\gamma + \gamma'$) $\rightarrow$ Laves. The melting points are between 1250 and 1260 °C for (Nb, Ti)C, between 1200 and 1210 °C for η phase, between 1180 and 1190 °C for eutectic ($\gamma + \gamma'$) and Laves. γ' initially precipitates from matrix at 1150 °C and achieves the maximum precipitation at 1130 °C. According to the microstructure evolution captured during solidification and composition analysis by an energy dispersive spectrometer and electron probe microanalyzer, (Nb, Ti)/Al ratio is put forward to explain the formation of η -Ni₃(Ti, Nb) and eutectic ($\gamma + \gamma'$). The solidification of γ matrix increased the Nb, Ti concentration in the residual liquids, so the high (Nb, Ti)/Al ratio would result in the formation of η -Ni₃(Ti, Nb); the precipitation of the phase consumed Nb and Ti and decreased the (Nb, Ti)/Al ratio in the liquid, which led to the precipitation of eutectic ($\gamma + \gamma'$). Laves formed by the sides of η -Ni₃(Ti, Nb) and in front of the eutectic ($\gamma + \gamma'$) after Al, Ti were further depleted by the two phases and Cr, Co, Mo were rejected to liquids.

Keywords Superalloy · ЭK151 · Solidification · Eutectic ($\gamma + \gamma'$) · η -Ni₃(Ti, Nb) · Laves

1 Introduction

ЭK151 is an advanced wrought superalloy developed by Russia [1]. It is precipitation-strengthened by intermetallic compound γ' [2] and possesses outstanding high-temperature strength, superior fatigue and creep resistance [3], and hot corrosion and oxidation resistance [4]. Thus, the alloy is applied as the gas turbine components of Russian fifth-generation fighter jets with a high service temperature ranging from 750 to 800 °C [5].

The superior mechanical properties of ЭK151 alloy come from the high content of solution-strengthened and

precipitation-strengthened elements. The weight proportion of solution-strengthened elements Mo, W, Cr, Co, V reaches 34%, and that of precipitation-strengthened elements Al, Ti, Nb reaches 10%, which is maximum among all of the difficult-to-forge superalloys [3]. However, the element segregation of a superalloy with a highly alloyed degree is extremely serious, resulting in various inter-dendritic precipitations. For instance, the high content of Al and Ti in alloy U720Li causes the formation of coarse eutectic ($\gamma + \gamma'$) [6]; the high content of Nb in alloy In718 leads to the large amounts of Laves at inter-dendritic region [7]. And alloy ЭK151 with a higher amount of Al, Ti and Nb will possess more complicated precipitations. The precipitations not only are hardly eliminated in the process of homogenization, but also become the cracking sites [8–10] during forging and rolling as well as sharply damage the mechanical properties of ЭK151 alloy. Thus, it is important to ascertain the element segregation and solidification behavior of the as-cast alloy ЭK151, which is the necessary information for eliminating the detrimental phases and optimizing strengthening effects of some elements in the subsequent process [11].

Available online at <http://link.springer.com/journal/40195>

✉ Wen-Ru Sun
wrsun@imr.ac.cn

¹ Institute of Metal Research, Chinese Academy of Sciences, Shenyang 110016, China

² University of Science and Technology of China, Hefei 230026, China

There are two main methods to capture the microstructure evolution during solidification process. One is through in situ observation. Miao et al. had employed the confocal scanning laser microscope (CSLM) to continuously observe the solidification process [12, 13]. However, they only captured the morphology change of dendrites but missed the phase transformation due to the limitation of resolution of the CSLM. The other way to investigate the solidification behavior is the high-temperature freezing method. Specimens will be heated in a certain range of temperature and then quenched into water to keep the high-temperature state. This method allows researchers to adopt scanning electron microscope (SEM), energy dispersive spectrometer (EDS) and transmission electron microscope (TEM) to further analyze the phase transformation and element segregation behavior during heating and quenching [14].

Russian adopted the cast-and-wrought method to manufacture the difficult-to-deformation alloy [15], by which the elements segregation can be eliminated. Thereby, investigating the solidification behavior, element segregation and microstructure of highly alloyed superalloy such as ЭК151 will help to develop a deep insight into the design, process and application of analogous superalloys [16, 17].

2 Experimental

The material used in the present work is a 6 kg ЭК151 ingot produced by vacuum induction melting, and the analyzed composition of the ingot is given in Table 1.

The samples with size of 10 mm × 10 mm × 10 mm were cut from the edge, half radius and center of the ingot by electron discharge machine (EDM), manually grinded to 2000 grit and polished to get a mirror surface, subsequently etched in a solution of 5 g CuCl₂ + 100 ml HCl + 100 ml CH₃CH₂OH for 1.5 min. The dendritic morphology and inter-dendritic precipitations were observed by optical microscope (OM) and SEM. Elemental analysis was performed using electron probe microanalysis (EPMA) and EDS. Crystal structures of the inter-dendritic precipitations were determined by TEM, and the specimens for TEM were prepared by cutting the samples to slices with thickness of 500 μm, then mechanically grinded to 60 μm thickness and punched to circular slices with radius of 3 mm. The twin-jet electro-polishing was performed in a solution of 10% HClO₄ + 90% CH₃CH₂OH at −20 °C and 24 V.

The solidification process of the alloy was characterized by differential thermal analysis (DTA), cylindrical samples

with size of Φ3 mm × 2 mm, heated at 10 °C/min in pure Ar atmosphere in the temperature ranging from 900 to 1400 °C.

The incipient melting temperatures (IMTs) of minor precipitations are difficult to be detected by DTA, so the “heating and quenching” tests were conducted to further investigate the solidification process. The samples with the size of 10 mm × 10 mm × 10 mm were soaked at a given temperature for 10 min and then quenched in water. The heating temperature is in the range from 1100 to 1250 °C with 10 °C intervals. The microstructures of quenched samples were observed by SEM and TEM.

3 Results

3.1 As-Cast Microstructure

Figure 1a shows the microstructure of marginal sample of the as-cast alloy ЭК151, the dendritic cores are fine, and the inter-dendritic regions merely take up a little part, so the element segregation is relatively slight, while as the samples are cut from the part closer to the center of the ingot, the inter-dendritic area is enlarged and even partially distributes in block as shown in Fig. 1b, c.

Figure 2 shows a higher-resolution microstructure of samples cut from half radius of the ingot. Four kinds of phases with different sizes were observed and marked as Phases A, B, C and D. Phase A is in lath-like shape with width of 3–5 μm and length of 20–30 μm, crossed the inter-dendritic region. Phase B with size of 5–10 μm is in rosette shape, similar to the eutectic (γ + γ′) in most superalloys. Phase C with size of 3–5 μm is in blocky shape. Phase D, which has the same size with Phase C, is in irregular shape. The square γ′ in inter-dendritic region is shown in Fig. 2b.

The chemical compositions of inter-dendritic matrix and four phases are listed in Table 2. By comparing the composition of matrix and phases, it is found that lath-like Phase A was rich in Nb, Ti, and poor in Cr, Mo, Co, and the Ni/(Nb, Ti) ratio is 3.79. According to its characteristics of chemistry and morphology, this phase is inferred as η-Ni₃(Ti, Nb) [18]. The rosette-shape Phase B might be the eutectic (γ + γ′) [10], as it is enriched in Al, Ti and shortage of Cr, Mo, Co. By contrast, Cr, Mo, Co and Nb are segregated in Phase C, which is similar to Laves [7, 19, 20] in terms of chemical composition. It is worth noting that the compositions of Phase A, B and C are complementary and they are always accompanying with each other. Phase D is extremely rich

Table 1 Chemistry (wt%) of ЭК151 alloy

C	Cr	Co	W	Mo	Al	Nb	Ti	V	B	Ni
0.06	10.86	14.93	2.93	4.41	3.62	3.26	2.73	0.59	0.003	Bal.

Fig. 1 As-cast microstructures of 9K151 alloy at the edge **a**, half radius **b**, center **c** of the ingot

Fig. 2 As-cast microstructures of 9K151 alloy: **a** phases precipitated in inter-dendritic region; **b** γ' phases precipitated in inter-dendritic region

Table 2 Compositions of the matrix and precipitates precipitated in the inter-dendritic region measured by EPMA (at.%)

Element	V	Cr	Co	Ni	W	Nb	Mo	Ti	Al
Matrix	0.68	12.36	15.28	54.15	0.41	2.79	2.78	4.60	6.97
Phase A	0.45	4.65	13.38	58.39	0.34	7.30	1.11	8.61	6.76
Phase B	0.43	6.37	12.30	58.89	0.26	3.28	1.38	6.84	9.30
Phase C	0.60	20.94	19.67	33.40	0.68	9.92	8.20	3.21	3.07
Phase D	1.02	1.02	0.97	3.49	1.11	59.65	3.88	28.89	0.53

in Nb and Ti, but depleted in the rest elements, so it is supposed to be (Nb, Ti)C [19].

Figure 3a shows the TEM bright-field image and selected area diffraction pattern of a lath-like phase. The crystal structure of the phase is hexagonal with parameters of $a=0.5161$ nm and $c=0.8557$ nm, and it is enriched in Nb and Ti measured by TEM-EDS. Obviously, the lath-like phase is Phase A marked in Fig. 2 and it is determined to be the η -Ni₃(Ti, Ni) [6]. Figure 3b shows the bright-field image and selected area electron diffraction (SAED) pattern of a phase with lamellar morphology. The crystal structure of the phase is face-centered cubic with parameters

of $a=0.3780$ nm, which is consistent with the structural characteristic of γ and γ' [21]. Thus, the rosette-like Phase B with lamellar morphology is determined to be eutectic ($\gamma+\gamma'$), and the lamellar structure is formed by the alternate precipitation of γ and γ' . Figure 3c shows the TEM image and SAED pattern of a blocky phase, and according to the morphology and size, the phase should be the Phase C. According to EPMA, the chemical composition of Phase C is similar to Laves in alloy In718, especially in terms of feature atom ratio. The (Fe, Ni)/(Cr, Mo, Nb, Ti) ratio is 1.30 for the Laves in alloy In718 [11], while the (Co, Ni)/(Cr, Mo, Nb, Ti) ratio is 1.28 for Phase C, suggesting that Phase C

Fig. 3 TEM images and the corresponding selected area diffraction patterns of the precipitates in the as-cast ЭK151 alloy: **a** η phase at $[242]$ zone axis; **b** eutectic ($\gamma+\gamma'$) at $[112]$ zone axis; **c** Laves phase at $[0001]$ zone axis; **d** MC-carbide at $[112]$ zone axis

is likely to be Laves. SAED pattern further shows that the crystal structure of Phase C is hexagonal, with parameters of $a=0.4901$ nm and $c=0.7840$ nm, consistent with the crystal structure of MgZn_2 -type Laves [22]. Thus, Phase C is inferred as C14-type Laves. Figure 3d presents a phase with irregular morphology and rich in Nb, Ti. The SAED pattern shows that the phase is face-centered cubic MC with parameters of $a=0.4426$ nm. Thus, Phase D is determined to be (Nb, Ti)C.

3.2 Element Segregation

In order to evaluate the element segregation degree, the composition of dendrite core and γ matrix at the inter-dendritic

region is detected by EPMA, and the partition coefficients, k , (defined as the element proportion ratio of dendrite core to inter-dendritic region) are given in Table 3. For W and V, $k > 1$, the two elements are absorbed into γ matrix during solidification. By contrast, for Nb, Ti and Mo, $k < 1$, they are rejected to the residual liquids in the solidification process and it is worth noting that the k value of Nb and Ti is merely 0.36 and 0.53, indicating that the two elements have a severe segregation tendency to inter-dendritic area and significant influence on the final precipitations. For other elements, including Cr, Co, Ni, Al, $k \approx 1$, they distribute uniformly between dendritic and inter-dendritic area.

To further analyze the element segregation in inter-dendritic region, the influence of inter-dendritic precipitations

Table 3 Distribution and partition coefficients of the elements in the as-cast ЭK151 alloy (EPMA results, wt%)

Element	V	Cr	Co	Ni	W	Nb	Mo	Ti	Al
Inter-dendrites	0.64	11.22	15.56	55.69	1.54	3.63	4.38	3.67	3.54
Dendrites	0.77	12.06	17.04	56.79	2.86	1.30	3.67	1.95	3.55
k	1.20	1.07	1.10	1.02	1.86	0.36	0.84	0.53	1.00

needs to be taken into consideration. As shown in Fig. 4, the element Nb is enriched in η and Laves and not depleted in eutectic ($\gamma + \gamma'$), so the element is segregated in the inter-dendritic area during the whole solidification process, whereas Ti and Al are enriched in η and eutectic ($\gamma + \gamma'$), respectively, but depleted in Laves, which means the two elements are mainly consumed by the formation of η and eutectic ($\gamma + \gamma'$). In comparison, the elements Cr, Co, Mo are enriched in Laves but depleted in η and eutectic ($\gamma + \gamma'$), indicating that these elements are in favor of the formation of Laves but rejected by the formation of η and eutectic ($\gamma + \gamma'$).

3.3 Solidification Behavior

Figure 5 shows the heating DTA curve, and there are four endothermic peaks on the curve, marked as PC-1, PC-2, P-C3 and P-C4, respectively. The γ dendritic core is the main components of the alloy and precipitates firstly during the solidification, so the largest endothermic peak, PC-1, is related to the melting of γ matrix. The second peak, PC-2, is located between 1260 and 1270 °C. In most cases, the incipient temperature of MC is quite high, which means the P-C2 might be corresponded to the melting of MC. However, the phase transitions corresponded to P-C3, located

Fig. 4 Element distribution in the inter-dendritic region of the as-cast 3K151 alloy

Fig. 5 Heating DTA curve of 9K151 alloy

at about 1180 °C, and P-C4, at 1120 °C are unclear. And the incipient melting temperatures (IMTs) of inter-dendritic phases including (Nb, Ti)C, η -Ni₃(Ti, Nb), eutectic ($\gamma + \gamma'$) and Laves could not be detected only from the curve.

In order to determine the IMTs and capture the phases evolution of (Nb, Ti)C, η -Ni₃(Ti, Nb), eutectic ($\gamma + \gamma'$), and

Laves, the as-cast samples were soaked from 1100 to 1250 °C with 10 °C intervals for 10 min and quenched in water, and then, the quenched microstructures were observed.

No melted pools were observed when the alloy was soaked in the range of 1110 and 1180 °C, but some white particles were found in the inter-dendritic areas. With the increment of soaking temperature, the white particles (Fig. 6a) increased noticeably, reaching the maximum precipitation at 1130 °C (Fig. 6b); then, the number of which declined remarkably at 1150 °C as shown in Fig. 6c. When the temperature rose to 1170 °C, few particles could be found in the inter-dendritic area (Fig. 6d). Therefore, the white-particle phase precipitated from the matrix at about 1150 °C and reached the maximum precipitation at 1130 °C, corresponding to the P-C4 in the heating curve.

The morphology of white particles is shown in Fig. 7a, b, respectively. According to the SAED pattern and TEM-EDS results in Fig. 7c, d, the particles, enriched in Ni, Al, Ti elements, are face-centered cubic structure with the parameter of $a = 0.3761$ nm, which should be the γ' phase, but the γ' precipitating at 1130 or 1150 °C is in irregular shape, which is markedly different to the γ' at original state in terms of morphology.

Fig. 6 Microstructures of as-cast 9K151 superalloy soaked at 1110 °C a, 1130 °C b, 1150 °C c, 1170 °C d

Fig. 7 Images and the corresponding SAED patterns of the white particles in the alloy soaked at 1130 °C: **a** SEM image of white particles; **b** TEM image of white particles; **c** corresponding SAED patterns at [011] axis zone of particles; **d** TEM-EDS of the particles

Melting pools were observed only when the heating temperature exceeded 1180 °C. Figure 8a, b is the SEM images of the alloy soaked in 1190 °C. In Fig. 8a, lath-like η has no obvious difference in comparison with that of as-cast state, and around the phase, the incipient melting took place. In the melting region, the eutectic phase [7] is rich in Nb, Cr, Co, Mo, detected to be Laves according to the SEM-EDS analysis (Fig. 8c); the morphology changed moderately and was typically formed by fast solidification of quenching. At the edge of the melting pool, the eutectic ($\gamma + \gamma'$) rich in Ti and Al is detected by SEM-EDS in Fig. 8d. The lamellar morphology of the phase, shown in Fig. 8b, changed obviously comparing with the original state, and the size decreased sharply to about only 1–2 μm . Therefore, it is supposed to be the chilled microstructure of eutectic ($\gamma + \gamma'$). The incipient melting temperatures (IMTs) of eutectic Laves and ($\gamma + \gamma'$) are both between 1180 and 1190 °C corresponding to the P-C3 in the DTA heating curve.

After alloy was soaked and quenched at 1200 °C, the lath-like η phase still existed, and the morphology did not change comparing to that in as-cast state shown in Fig. 9a. The chemical composition is detected by SEM-EDS as shown in Fig. 9c. When the temperature increased to 1210 °C, the

lath-like η phase appeared in the as-cast microstructure was hardly found in the heated and quenched microstructure. Some short-rod phases were found in the melting pool as shown in Fig. 9b. The phase is rich in Nb and Ti shown in Fig. 9d, which indicates that it is the chilling morphology of η phase. Thus, the IMT of η -Ni₃(Ti, Nb) is between 1200 and 1210 °C. The quantity of η phase is relatively low so that the endothermic peak of η precipitation is not reflected in the DTA curve.

When the alloy was soaked in a higher temperature of 1250 °C, the melting pools were enlarged as shown in Fig. 10a and the microstructure of the melting pool is shown in Fig. 10b. Only NbC phase existed outside the melting pools, measured by SEM-EDS as shown in Fig. 10c. Thus, the IMT of NbC phase is above 1250 °C related to the P-C2 between 1260 and 1270 °C in the DTA curve.

4 Discussion

It was found in previous researches that in high Ti alloying alloys, like GH696 (similar to Russian alloy ЭП33), the segregation of Ti will lead to the precipitation of η [23]; in

Fig. 8 Microstructures of η phase and chilled morphology of eutectic Laves **a** and chilled morphology of eutectic ($\gamma + \gamma'$) **b**, **c** EDS spectrum of the eutectic Laves, **d** EDS spectrum of eutectic ($\gamma + \gamma'$)

high Nb alloying alloys, such as In718, the Laves would be the main inter-dendritic precipitation because of the segregation of Nb [7]. In an Al and Ti co-strengthened alloy, like U720Li, it will form both eutectic ($\gamma + \gamma'$) and η at inter-dendritic region [6], while in alloy GH742 (similar to Russian alloy ЭП742) with a high content of Nb, Ti and moderate content of Al, eutectic ($\gamma + \gamma'$) and Laves would form [24]. Alloy ЭК151 with a high content of Al, Ti and Nb, possesses three mainly precipitations at inter-dendritic region, including eutectic ($\gamma + \gamma'$), η and Laves, showing the characteristics of both high Al, Ti alloying alloys and high Nb alloying alloys. And it can be inferred that the formation of eutectic ($\gamma + \gamma'$), η and Laves is the result of the segregation of Al, Ti and Nb during solidification.

To further illustrate the relationship between microstructure and element segregation, the results of the as-cast microstructure observation, dendritic segregation and solidification behavior were analyzed, and it is found that the microstructure evolution during solidification process is mainly induced by Nb, Ti segregation. With the solidification of γ matrix, Nb, Ti, Mo are segregated in the residual liquids, in which Nb and Ti exhibit a strong positive segregation, resulting in the precipitation of (Nb, Ti)C. The amounts of the phase are relatively low, so the segregation degrees of Nb and Ti in liquids are generally not influenced by the

formation of (Nb, Ti)C, although it will absorb Nb, Ti during precipitation.

In the previous work, some researchers put forward that the Ti/Al ratio is a crucial factor influencing the formation of eutectic ($\gamma + \gamma'$) or η [25, 26]. It is found that when the Ti/Al ratio in the liquids is higher than a criterion value about 2 [27], η phase is tended to form, while when the Ti/Al ratio decreases below the key point, eutectic ($\gamma + \gamma'$) will precipitate [27–29]. However, the result of this work is inconsistent with the previous results. The Ti/Al ratio of η is only 1.27, much lower than the criterion value in GH2135, even lower than the Ti/Al ratio (1.89) of eutectic ($\gamma + \gamma'$) in alloy U720Li [25, 26]. In the case, eutectic ($\gamma + \gamma'$) should theoretically precipitate prior to the η phase. However, η phase precipitates prior to eutectic ($\gamma + \gamma'$) in our alloy due to the high content of Nb. It is worth noting that in this alloy, Nb is largely enriched in η phase, and according to periodic laws of chemical elements, Nb has similar chemical properties and atom size with Ti, which indicates that Nb might be able to substitute the site of Ti in the crystal structure to some degree, so in this study, we counted (Nb, Ti)/Al ratio. The (Nb, Ti)/Al ratio of η phase is 2.35, and that of eutectic ($\gamma + \gamma'$) is merely 1.20. Combining the element segregation behavior, the phase transformation mechanism can be explained more appropriately: the segregation of Ti,

Fig. 9 Microstructures of η phase and chilled morphology of eutectic Laves soaked at 1210 °C **a** and chilled morphology of η phase soaked at 1200 °C **b**, **c** EDS spectrum of the η phase soaked at 1210 °C, **d** EDS spectrum of η phase at 1200 °C

Fig. 10 Microstructures of as-cast 9K151 superalloy soaked at 1250 °C for 10 min and then quenched in water for melting pools **a** and MC-carbide **b**, **c** EDS spectrum of the MC-carbide

Nb in residual liquids firstly promotes the precipitation of η , and with the formation of η , the contents of Ti, Nb are partially consumed. Thus, the eutectic ($\gamma + \gamma'$) starts to form. As shown in Figs. 2a, 6d, some tiny eutectic ($\gamma + \gamma'$) are formed at one ends of the η phase, indicating that when lath-like η phase is growing, and the contents of Ti and Nb in front of the phase are consumed, leading to the formation of eutectic ($\gamma + \gamma'$).

As the η phase and eutectic ($\gamma + \gamma'$) precipitate, the elements of Cr, Co and Mo are rejected into the residual liquids, promoting the precipitation of Laves. Figure 2a shows that Laves are distributed at two sides of η phase. Because the precipitation temperature of η phase is much higher than that of Laves, the elements of Cr, Co, Mo originally rejected to the liquids in front of the η are diffused to the sides of the phase. The precipitation temperatures of eutectic ($\gamma + \gamma'$) and Laves are much closer, so Laves directly precipitate in front of eutectic ($\gamma + \gamma'$), as the Cr, Co, Mo are rejected to the residual liquids.

The precipitation of η , eutectic ($\gamma + \gamma'$) and Laves phase has reduced the incipient melting temperature of the alloy [14, 30], which will narrow down the thermal process window. Otherwise, the important strengthening elements like Al, Ti, Nb, Mo, Cr, Co of alloy ЭК151 severely segregate in inter-dendritic phases causing a negative effect on mechanical properties. Some researchers revealed that the eutectic ($\gamma + \gamma'$) and Laves phase would be the source of crack initiation cite [31–33] during cogging in U720Li and In718, respectively, and η phase is also detrimental to the property of materials because of its distribution in the grain [34]. Therefore, it is necessary to eliminate those phases, which could help the strengthening elements exit in a proper form and play their strengthening role.

5 Conclusions

- (1) The co-addition of Al, Ti and Nb renders the ЭК151 alloy the characteristics of both the high Al, Ti alloying alloys in which η -Ni₃(Ti, Nb) and eutectic ($\gamma + \gamma'$) are precipitated, and the high Nb alloying alloys in which the Laves phase is precipitated.
- (2) The solidification sequence of the ЭК151 alloy is as followings: γ matrix at 1340 °C, NbC at 1262 °C, η -Ni₃(Ti, Nb) between 1200 and 1210 °C, eutectic ($\gamma + \gamma'$) and Laves between 1180 and 1190 °C.
- (3) The precipitation of η or eutectic ($\gamma + \gamma'$) is largely corresponding to the ratio of (Nb, Ti)/Al in high Nb alloying alloy, for that Nb might be able to partially substitute the site of Ti in η phase.
- (4) The η , eutectic ($\gamma + \gamma'$) and Laves phases are precipitated as a result of composition evolution. The solidification of η will absorb the Ti, Nb, causing the decrease of (Nb,

Ti)/Al ratio in the liquid, which leads to the precipitation of eutectic ($\gamma + \gamma'$). As eutectic ($\gamma + \gamma'$) precipitate, Ti, Al will be further consumed and Cr, Co, Mo will be rejected to the residual liquid. Thus, the final liquid is mainly constituted by Nb, Cr, Co, Mo, so Laves is formed at the end of solidification.

References

- [1] E.B. Chabina, B.S. Lomberg, E.V. Filonova, S.V. Ovsepyan, M.M. Bakradze, *Trudy VIAM* **9**, 3 (2015)
- [2] M.M. Bakradze, S.V. Ovsepyan, S.A. Shugaev, M.N. Letnikov, *Trudy VIAM* **9**, 1 (2013)
- [3] Z.N. Bi, J.L. Qu, J.H. Du, X.Y. Peng, C.S. Yi, X.L. Peng, *J. Iron Steel Res. Int.* **23**, 263 (2011)
- [4] M.M. Bakradze, B.S. Lomberg, S.A. Sidorov, M.V. Bubnov, *Trudy VIAM* **6**, 2 (2017)
- [5] Z.N. Bi, J.L. Qu, J.H. Du, X.Y. Peng, C.S. Yi, X.L. Peng, *Rare Metal Mater. Eng.* **42**, 919 (2013)
- [6] G.D. Zhao, L.X. Yu, F. Qi, F. Liu, W.R. Sun, Z.Q. Hu, *Acta Metall. Sin. (Engl. Lett.)* **29**, 518 (2016)
- [7] Z.J. Miao, A.D. Shan, Y.B. Wu, J. Lu, Y. Hu, J.L. Liu, H.W. Song, *Trans. Nonferrous Met. Soc. China* **22**, 318 (2012)
- [8] H.W. Zhang, X.Z. Qin, X.W. Li, L.Z. Zhou, *Mater. Sci. Eng. A* **711**, 303 (2018)
- [9] H.W. Zhang, X.Z. Qin, X.W. Li, L.Z. Zhou, *Acta Metall. Sin. (Engl. Lett.)* **53**, 684 (2017)
- [10] L.T. Chang, H. Jin, W.R. Sun, *J. Alloys Compd.* **653**, 266 (2015)
- [11] A.W. Zhang, Y. Yang, S. Zhang, D. Zhang, W.H. Zhang, D.W. Han, F. Qi, Y.G. Tan, X. Xin, W.R. Sun, *Acta Metall. Sin. (Engl. Lett.)* (2018). <https://doi.org/10.1007/s40195-018-0834-1>
- [12] L. Wang, J.X. Dong, Y.L. Tian, *J. Univ. Sci. Technol. Beijing Miner. Metall. Mater.* **15**, 594 (2008)
- [13] Z.J. Miao, A.D. Shan, W. Wang, L.U. Jun, X.U. Wen-Liang, H.W. Song, *Trans. Nonferrous Met. Soc. China* **21**, 236 (2011)
- [14] B.L. Sheng, X.W. Wei, *Acta Metall. Sin. (Engl. Lett.)* **16**, 335 (2003)
- [15] Z. Li, G.Q. Zhang, Z.H. Zhang, S.F. Tian, *Acta Metall. Sin. (Engl. Lett.)* **17**, 205 (2004)
- [16] J. Hou, F.F. Han, X.X. Ye, B. Leng, M. Liu, Y.L. Liu, X.T. Zhou, *Acta Metall. Sin. (Engl. Lett.)* **32**, 401 (2019)
- [17] D.H. Kim, *Acta Metall. Sin. (Engl. Lett.)* **18**, 33 (2005)
- [18] S.S. Seo, I.S. Kim, J.H. Lee, C.Y. Jo, H. Miyahara, K. Ogi, *Trans. A-Phys. Metall. Mater. Sci.* **38**, 883 (2007)
- [19] J.J. Ruan, N. Ueshima, K. Oikawa, *J. Alloys Compd.* **737**, 83 (2018)
- [20] Y.F. Guo, M.Y. Sun, B. Xu, D.Z. Li, *J. Mater. Process. Technol.* **249**, 202 (2017)
- [21] G.D. Zhao, G.L. Yang, F. Liu, *Acta Metall. Sin. (Engl. Lett.)* **30**, 887 (2017)
- [22] E.V. Melnik, *Dopovidi Akademii Nauk Ukrainskoi Rsr Seriya a-Fiziko-Matematichni Ta Technichni Nauki* **10**, 949 (1974)
- [23] Y.C. Wang, G.L. Wu, C.H. Zhao, J. Dong, T. Yu, *J. Iron Steel Res. Int.* **23**, 64 (2011)
- [24] X.L. Pan, W.R. Sun, Z. Li, S.L. Yang, S.R. Guo, H.C. Yang, Z.Q. Hu, *Rare Metal Mater. Eng.* **39**, 55 (2010)
- [25] S.H. Chen, M.J. Zhao, L.J. Rong, *Acta Metall. Sin.* **48**, 1335 (2012)
- [26] C.Y. Cui, Y.F. Gu, D.H. Ping, H. Harada, T. Fukuda, *Mater. Sci. Eng. A* **485**, 651 (2008)

- [27] J. Guo, *Material Science and Engineering for Superalloys* (Science Press, Beijing, 2008)
- [28] H. Li, H. Song, W. Liu, *Metall. Mater. Trans. A* **2**, 915 (2019)
- [29] T. Hara, S. Kobayashi, T. Ueno, K. Oikawa, *J. Cryst. Growth* **506**, 91 (2019)
- [30] D.W. Han, F. Liu, B. Zhang, W.R. Sun, *Acta Metall. Sin. (Engl. Lett.)* **31**, 1224 (2018)
- [31] L.X. Yu, W.R. Sun, Z.B. Zhang, W.H. Zhang, F. Liu, X. Xin, F. Qi, D. Jia, Z.Q. Hu, *Mater. Res. Innov.* **19**, 68 (2015)
- [32] M. Yamamoto, A. Nitta, T. Ogata, *J. Soc. Mater. Sci. Jpn.* **50**, 510 (2001)
- [33] C.Y. Jo, N. Jones, S.J. Choe, D. Knowles, *Met. Mater. Int.* **4**, 1017 (1998)
- [34] R. Bao, Y.I. Jian-Hong, Y.D. Peng, H.Z. Zhang, L.I. Ai-Kun, *Trans. Nonferrous Met. Soc. China* **22**, 853 (2012)