Effect of Alloyed Mo on Mechanical Properties, Biocorrosion and Cytocompatibility of As-Cast Mg–Zn–Y–Mn Alloys

Longlong Zhang^{1,2} · Yatong Zhang^{1,2} · Jinshan Zhang^{1,2} · Rui Zhao^{1,2} · Jiaxin Zhang^{1,2} · Chunxiang Xu^{1,2}

Received: 3 September 2019 / Revised: 15 October 2019 / Published online: 7 January 2020
© The Chinese Society for Metals (CSM) and Springer-Verlag GmbH Germany, part of Springer Nature 2020

Abstract

The influences of Mo contents on mechanical properties, biocorrosion and cytocompatibility of as-cast Mg–6Zn–8.16Y–2.02Mn–*x*Mo (*x* = 0.0, 0.1, 0.3, 0.5, 0.7 wt%) alloys were firstly investigated. Appropriate amount of Mo was conducive to grain refinement and the formation of long-period stacking ordered structure with continuous distribution, which was advantageous to mechanical properties and corrosion resistance. Mg–6Zn–8.16Y–2.02Mn–0.3Mo exhibited the ultimate tensile strength of 265.0 MPa, elongation of 13.5% and the lowest weight loss rate in Hank's solution. Moreover, the cell toxicity cultured in 25% extract was evaluated and the alloy with 0.3 wt% Mo exhibited the best cytocompatibility. Thus, the alloy was expected to become a novel biodegradable implant material.

Keywords Magnesium alloy · Mo · Corrosion · Cytocompatibility · Mechanical properties

1 Introduction

Magnesium alloys have received more and more attention as implant biomaterials owing to the low price, excellent mechanical properties, good biocompatibility and biodegradability [1–3]. Nevertheless, there are several long-standing challenges in practical applications, such as the express katabolism of mechanical integrity in human body, the collapse of alloys caused by excessive corrosion rates and localized corrosion [4–6]. Consequently, it is urgent to develop new magnesium alloys with excellent mechanical properties and low corrosion rate [7].

Mg–Zn–Y alloys with long-period stacking ordered (LPSO) structures have been the research hotspot due to their outstanding mechanical properties and corrosion resistance [8–12]. Generally, the increase in the volume fraction of LPSO phase is usually at the expense of high RE, which undoubtedly increases production costs. Thus, a

major issue is reducing the cost of magnesium alloys containing rare earth. It is necessary to modify the alloy composition by adding alloying elements into magnesium alloys [13–19]. For instance, Mn addition refined the grain size of Mg–Zn–Y alloy and enhanced mechanical properties and corrosion resistance [16–18]. As reported by Zhang et al. [19] as-cast Mg–Zn–Y–Mn–Cd with LPSO structure exhibited the outstanding UTS (247 MPa) and elongation (16.5%). Regarding corrosion behaviors of Mg alloys, numerous studies had also reported that alloying elements played a critical role in the corrosion of Mg alloys owing to the changes in microstructure, such as grain size and secondary phases or intermetallic compounds [20–22]. LPSO phase accelerated corrosion and acted as local cathode [23, 24]. However, some researches had reported that LPSO phase played a positive role. The corrosion resistance of Mg alloys with LPSO structure was better than that of free-LPSO structure [25]. The corrosion behaviors of Mg–Zn–Y alloys greatly depended on the distribution and volume fraction of LPSO phase, and continuously distributed LPSO phase can be corrosion barriers [26, 27]. In addition, Mg–Zn–Y alloy was promising to be a biodegradable material [28].

Reportedly, Mo not only had an important impact on various physiological activities in the human body, but also had a specific detoxification effect [29, 30]. It was proved that Mo addition was conducive to grain refinement, enhancing mechanical properties and corrosion

Available online at <http://link.springer.com/journal/40195>.

✉ Jinshan Zhang
jinshansx@tom.com

¹ College of Materials Science and Engineering, Taiyuan University of Technology, Taiyuan 030024, China

² Shanxi Key Laboratory of Advanced Magnesium-based Materials, Taiyuan 030024, China

resistance of the steel, aluminum alloy and magnesium alloy [31–35]. The corrosion resistance of AZ91D alloy substrate was improved by the coating containing Mo, and it was proved that Mo could act as a pitting corrosion inhibitor [35]. However, there were several researches about the impact of Mo on magnesium alloys with LPSO. In the present study, the microstructure, mechanical properties, biocorrosion resistance and cytocompatibility of Mg–6Zn–8.16Y–2.02Mn alloys with different Mo contents were systematically studied to develop a novel degradable biomaterial.

2 Experimental

2.1 Material Preparation and Microstructural Analysis

Ingots of Mg–6Zn–8.16Y–2.02Mn–*x*Mo alloys were processed under the protection of high-purity argon by combining pure Mg, Zn, Y, Mn and Mo in an electric resistance furnace at 1023 K, and cast into a preheated permanent mold (473 K) to obtain cylindrical bars with 20 mm diameter. The nominal chemical compositions of alloys are listed in Table 1. The microstructure of alloys was characterized by optical microscopy (OM) and scanning electron microscopy (SEM, TESCAN-MIRA3) equipped with energy-dispersive spectroscopy (EDS). The constituent phases of as-cast alloys were measured by X-ray diffraction (XRD). To determine the grain size, three concentric circles on the samples were examined by virtue of an optical microscope and are sufficiently long to traverse at least 50 intercepts. The grain size was measured by

nano-measurer software and measured at least 100 grains per sample for average. Subsequently, the area fractions of phases were measured by IPWIN60 software. All specimens for microstructural characterization were cut from the same positions on the bars, grinded through 3000 grit SiC paper and polished, and then etched using 4.0 vol.% nital (4.0% HNO₃ in ethanol).

2.2 Tensile Test

Tensile specimens with a gauge dimension of 18 mm × 4 mm × 2 mm were performed using a DNS100 electronic-versal material test machine with a crosshead speed of 0.2 mm/min at room temperature.

2.3 Corrosion Test

The corrosion behaviors of alloys were investigated using immersion test (weight loss experiment and the hydrogen evolution experiment) and electrochemical measurement in Hank's solution at 37 °C according to ASTM standard [1]. The corrosive media was Hank's solution with a composition (g/L): NaCl 8.00, KCl 0.40, MgSO₄·7H₂O 0.20, CaCl₂·2H₂O 0.185, NaHCO₃ 0.35, Na₂HPO₄ 0.0477, KH₂PO₄ 0.06, and C₆H₆O₆ (D-glucose) 1.00 [18].

The electrochemical test was conducted with a workstation (standard three-electrode glass cell): the counter electrode (platinum sheet), reference electrode (saturated calomel electrode) and working electrode (the samples with an exposed area of 1 cm²). The open circuit potential (OCP) test was performed for 50 min to make sure the stable potential. The electrochemical impedance spectroscopy (EIS) was performed in the frequency range from 100 kHz to 0.01 Hz. by using a 10 mV sinusoidal potential at open circuit potential (OCP). The EIS spectra were fitted using ZSimp Win 3.10 software. Potentiodynamic polarization curves were obtained at a scan rate of 0.5 mV s^{−1} and were analyzed by CView software.

The samples with Φ 20 mm × 10 mm for immersion test were polished with 3000 grit SiC paper and then cleaned with acetone followed by alcohol in an ultrasonic cleaner. After immersion, the corrosion products were removed by boiling solution (200 g/L CrO₃ + 10 g/L AgNO₃), and then cleaned using alcohol, dried with warm flowing air and weighed. The corrosion surface morphologies of the alloys were characterized by SEM–EDS. The average corrosion

Table 1 Nominal chemical composition of the-cast Mg–Y–Zn–Mn–Mo alloys

Designation	Nominal compositions (wt%)				
	Mg	Y	Zn	Mn	Mo
Alloy A	Bal.	8.16	6.00	2.02	0.00
Alloy B	Bal.	8.16	6.00	2.02	0.10
Alloy C	Bal.	8.16	6.00	2.02	0.30
Alloy D	Bal.	8.16	6.00	2.02	0.50
Alloy E	Bal.	8.16	6.00	2.02	0.70

rate P_W and P_{AH} (mm/y) based on the weight loss and hydrogen evolution test, respectively, were calculated using the following formulas [28]:

$$P_W = 2.10(W - W_0)/A_1 t_1, \quad (1)$$

$$P_{AH} = 2.006V_h/A_2 t_2, \quad (2)$$

where W and W_0 (mg) are the weight before immersion and after removal of corrosion products, respectively; t_1 is the immersion time (d); A_1 (cm²) is the area exposed to the solution; V_h (mL) is the evolved hydrogen volume for t_2 (d) time; and A_2 (cm²) is the area exposed to the Hank's solution. All measurements mentioned above are repeated at least three times to ensure the repeatability.

2.4 Cell Cytocompatibility

The mouse fibroblasts L929 cells were used for cytocompatibility evaluation. The cell toxicity cultured in Mg alloys extracts was evaluated by methyl thiazolyl diphenyl-tetrazolium bromide (MTT) test [36]. Cells were cultured in Dulbecco's modified Eagle's medium (DMEM) containing 10% fetal bovine serum (FBS) at 37 °C, 5% CO₂ in thermostatic cultivation box. L929 cells were completely adhered to the TC flask bottom and were detached with 0.5% trypsin. The

detached cells were prepared into 1×10^5 cells/mL suspensions which were added to 96-well plate for 100 μ L cells/well and cultured for 24 h to allow cells attachment. This extraction ratio was designated as 100% extract. The medium was less concentrated extract prepared by diluting the 100% extract into 25% extract solution. After incubated for 1, 2 and 3 days, 10 μ L MTT was added to each well and followed incubated at 37 °C for 4 h. Then the medium was discarded and replaced by 150 μ L dimethyl sulfoxide (DMSO) in each well and kept in a shaker for 15 min. The absorbance was determined by SpectraMax 190 with a wavelength of 550 nm. All tests mentioned above shall be conducted at least three times. The cell morphology was characterized by inverted fluorescence microscopy (LEICA, DMI3000B).

3 Results

3.1 Microstructural Evolution

Figure 1 shows the OM images of as-cast Mg–6Zn–8.16Y–2.02Mn– x Mo alloys. Combined with XRD (Fig. 2), the alloys mainly included α -Mg matrix, 18R-LPSO phase (Mg₁₂YZn) and W phase (Mg₃Zn₃Y₂). When Mo content increased from 0.0 to 0.3 wt%, α -Mg grain became finer and more homogeneous and showed

Fig. 1 Optical micrographs of as-cast alloys: (a) Alloy A, (b) Alloy B, (c) Alloy C, (d) Alloy D, (e) Alloy E, (f) volume fraction of each phase and average grain size

Fig. 2 XRD patterns of as-cast Mg-6Zn-8.16Y-2.02Mn alloys with different Mo additions

a trend of the transition from columnar dendrites to equiaxial dendrites. The volume fraction of 18R-LPSO phase increased, while that of W phase reduced with the increase in Mo content. However, the microstructure was deteriorated with more Mo. The volume fraction of 18R-LPSO phase and average grain size in Alloy C were measured to be 24.0% and 22.0 μm , respectively (Fig. 1f). The SEM images and EDS spectra of the alloys as shown in Fig. 3 revealed that the block-like phase and the fish-like phase were 18R-LPSO phase and W phase, respectively. This was consistent with the previous reports [15, 16, 19]. Furthermore, LPSO phase in Alloy C increased and partially formed a continuous network, which can be consistent with the result shown in Fig. 1. Figure 4 shows EDS maps of Alloy C. 18R-LPSO phase and W phase had large amounts of Mg, Y and Zn. The mostly Mo was distributed at the grain boundaries. That was positive to grain refinement. This was discussed in subsequent Sect. 4.1.

Fig. 3 SEM images of as-cast alloys: (a) Alloy A, (b) Alloy B, (c) Alloy C, (d) Alloy D, (e) Alloy E, and EDS analysis results of (f) point A, (g) point B

Fig. 4 (a) SEM micrograph of the Mg-6Zn-8.16Y-2.02Mn-0.3Mo alloy, (b–f) EDS maps

3.2 Mechanical Properties of Mg-6Zn-8.16Y-2.02Mn- x Mo Alloys

The UTS and elongation of as-cast Mg-6Zn-8.16Y-2.02Mn- x Mo alloys are presented in Fig. 5. It was indicated that the variation of Mo content had a significant impact on mechanical properties of the alloys. As Mo content increased to 0.3 wt%, the UTS and ductility of the Alloy C were enhanced to 265.0 MPa and 13.5%, respectively, which were 51.4% and 132.8% higher than those of free-Mo alloy. With the further addition, they were decreased slightly. The alloy with 0.3 wt% Mo exhibited the excellent comprehensive mechanical properties.

Fig. 5 Comparison of the UTS and elongation of as-cast Mg-6Zn-8.16Y-2.02Mn- x Mo alloys

Fig. 6 Immersion tests of Mg-6Zn-8.16Y-2.02Mn- x Mo alloys in Hank's solution (a) hydrogen evolution, (b) the average corrosion rate

3.3 Biocorrosion Behavior of Mg-6Zn-8.16Y-2.02Mn- x Mo Alloys

3.3.1 Immersion Test

Figure 6 shows hydrogen evolution and weight loss results of Mg-6Zn-8.16Y-2.02Mn- x Mo alloys immersed in Hank's solution. As seen from Fig. 6a, when Mo addition was less than 0.3 wt%, the volume of hydrogen was decreased with the increase in Mo at the same time. However, it was increased with the further addition. The alloys with Mo released less volume of hydrogen than that of Mo-free alloy. Especially, the volume of hydrogen evolution of the Alloy C (2.87 mL/cm²) was decreased by 72.7% compared to that of Alloy A (10.51 mL/cm²) at the time of 120 h immersion. Moreover, the average corrosion rates of alloys, P_{AH} and P_W , are shown in Fig. 6b. It was seen that P_{AH} and P_W presented the same rank. The Alloy C showed the lowest weight loss rate ($P_W = 1.34$ mm/y), fell by 72.3% compared to that of the Alloy A (4.83 mm/y). Besides, the value of P_W was larger than P_{AH} because of some hydrogen dissolving into Mg matrix during immersion and the experimental and method errors [37].

The corrosion surfaces of the alloys with different Mo contents immersed in Hank's solution are shown in Fig. 7. The corrosion surface of Alloy C (Fig. 7c) was relatively uniform. Some corrosion areas in alloys except Alloy C

seemed to be only slight corrosion, while most areas underwent severe corrosion (Fig. 7a-e). Figure 8 shows SEM micrographs of as-cast alloys immersed in Hank's solution after removing corrosion products. Table 2 shows the results from the EDX analysis of Alloy C in the points of a, b as shown in Fig. 8e. It was observed from Alloy A immersed for 3 h, the α -Mg matrix and the areas near the W phase were corroded severely, whereas α -Mg matrix farther from the grain boundary and the areas near the 18R-LPSO phase were corroded slightly (Fig. 8a). After immersed for 6 h, as shown in Fig. 8b, the corrosion of Alloy A became more serious. 18R-LPSO phase was corroded and few could be found. W phase was broken off easily because of the hollowed-out structure. While the corrosion pits of the alloy with 0.3 wt% Mo were shallower, the morphology of 18R-LPSO phase had little change (Figs. 8e and f).

3.3.2 Electrochemical Measurement

The potentiodynamic polarization curves of Mg-6Zn-8.16Y-2.02Mn- x Mo alloys in Hank's solution are shown in Fig. 9. The major parameters calculated by the method of Tafel extrapolation are shown in Table 3. In the case of cathodic kinetics, the cathodic current density decreased in the order of Alloy A > Alloy E > Alloy D > Alloy B > Alloy C, which was consistent with that of the hydrogen evaluation rate (Fig. 6a). The corrosion

Fig. 7 Morphologies of corrosion product formed on the surface of (a) Alloy A, (b) Alloy B, (c) Alloy C, (d) Alloy D, (e) Alloy E immersed in Hank's solution for 3 h

currents, i_{corr} for Alloy A, Alloy B, Alloy C, Alloy D and Alloy E, were 12.2×10^{-5} , 7.29×10^{-5} , 1.58×10^{-5} , 8.86×10^{-5} and 9.54×10^{-5} A/cm², respectively. The i_{corr} of Alloy C was lowest, indicating the best corrosion resistance.

The electrochemical impedance spectra (EIS) of Mg–6Zn–8.16Y–2.02Mn– x Mo alloys are shown in Fig. 10. Figure 10a shows Nyquist diagram and electrochemical equivalent circuit (EEC) model. The fitting results are listed in Table 4. It was obvious that Nyquist plots of all alloys had the similar shapes, which were consisted of the large capacitance loop in the high frequency range and an inductance loop in low frequency range. The high frequency capacitance loop was caused by the electric double layer at the interface of Mg substrate and solution. The inductive loop may be attributed to the existence of relaxation processes of adsorbed species on the electrode surface [38, 39]. The diameters of capacitance loop decreased in the order: Alloy C > Alloy B > Alloy D > Alloy E > Alloy A, implying the corrosion rate of Alloy C was minimum. There were two peaks which can be seen from the phase angle plots (Fig. 10b), indicating two time constants were existed and the improvement in the corrosion protection was likely due

to the formation of a compact protective coating [34]. The results corresponded to two capacitive loops in Fig. 10a. Additionally, log $|Z|$ -log f curves at low frequency range illustrated that Alloy C showed the biggest $|Z|$ value, which was agreement with the largest capacitive semi-circle. Seen from the equivalent circuit model (Fig. 10a), R_s and R_{ct} represent the solution resistance and charge transfer resistance, respectively. Q_{dl} is a constant phase element and represents electric double layer at the interface between Mg substrate and electrolyte solution. Y_{dl} and n_{dl} are used to define Q_{dl} . The value of n_{dl} was between 0.8 and 1.0, indicating that the electric double-layer capacitance on the substrate surface was close to the ideal capacitance. Y_{dl} can reflect roughness of the electrical double layer [40]. L is inductive impedance resistance; R_L is the film resistance in local corrosion region. In general, the total resistance (R_t) is higher, the dissolution rate of Mg substrate is lower, and it is commonly used to evaluate the corrosion resistance of alloys [40]. Based on the EEC, R_t can be defined as the sum of resistance values of R_{ct} and R_L in parallel and R_s . The value of R_t for Alloy C ($\sim 261.54 \Omega \text{cm}^2$) is greater than that of Alloy A ($\sim 116.32 \Omega \text{cm}^2$), indicated a superior corrosion resistance for Alloy C.

Fig. 8 SEM micrographs of alloys immersed in Hank's solution after removing corrosion products (**a, b**) Alloy A, (**c, d**) Alloy B, (**e, f**) Alloy C, (**g, h**) Alloy D, (**i, j**) Alloy E

Table 2 EDS analysis result of Alloy C from Fig. 8e (at.%)

Area	Phase	Mg	Zn	Y	Mo	Mn
a	α -Mg	98.6	0.8	0.6	–	–
b	18R-LPSO	88.7	5.7	5.6	–	–
c	W phase	64.2	23.6	12.1	0.1	–

Fig. 9 Potentiodynamic polarization curves of Mg-6Zn-8.16Y-2.02Mn-xMo alloys**Table 3** Typical parameter values from the polarization curves of Mg-Zn-Y-Mn-Mo alloys

Alloy	i_{corr} (A/cm ²)	E_{corr} /V versus SCE	Corrosion rate (mm/y)
Alloy A	12.2×10^{-5}	-1.51	2.70
Alloy B	7.29×10^{-5}	-1.49	1.61
Alloy C	1.58×10^{-5}	-1.44	0.36
Alloy D	8.86×10^{-5}	-1.45	1.96
Alloy E	9.54×10^{-5}	-1.48	2.11

3.4 Cellular Compatibility of Mg-6Zn-8.16Y-2.02Mn-xMo Alloys

Figure 11 shows the morphologies of L929 cells cultured in 25% extract of Mg-6Zn-8.16Y-2.02Mn-xMo alloys for 1 day, 2 days and 3 days, respectively. It was discovered that the cell morphology of Mg-6Zn-8.16Y-2.02Mn with different Mo contents was very similar after cultured 1 day. After 2 days of culture, the cells were spreading, growing and reproducing available. However, after 3 days, the morphologies of cells in the extracts of Alloy A, Alloy B and Alloy C exhibited flattened spindle shapes, while cells in D and Alloy E had only a small amount of cell spreading.

Figure 12 shows the relative cell viability of as-cast Mg-6Zn-8.16Y-2.02Mn-xMo alloys in the 25% extracts for different time. According to ISO 10993-5 [36], the cell viability of a material was higher than 75%, indicating not or slightly cytotoxic. After cultured for 1 day, the relative cell viability of the five alloys cultured in 25% extracts was much higher than 75% and that of Alloy A was lower than the others. After 2 days of culture, the relative cell viability of the alloys was still non-toxic and the value was higher than that for 1 day. However, after culturing for 3 days, relative cell viabilities of Alloy A, Alloy B and Alloy C increased, especially that of Alloys C increased to 129.5%. But that of Alloy D and Alloy E decreased drastically, indicating slightly toxic. Overall, the alloy with 0.3 wt% Mo content

Fig. 10 Electrochemical impedance spectra of Mg-6Zn-8.16Y-2.02Mn-xMo alloys in Hank's solution **a** Nyquist diagram, compatible Equivalent circuit and **b** Bode spectra

Table 4 Parameters of the alloys obtained from electrochemical impedance spectra

Alloy	R_s (Ω cm ²)	Y_{dl} (μ Ω^{-1} cm ⁻² s ⁿ)	n_{dl}	R_{ct} (Ω cm ²)	L (H cm ⁻²)	R_L (Ω cm ²)
Alloy A	5.16	58.37	0.84	209.2	805	237.2
Alloy B	6.18	21.96	0.91	323.1	1077	440.9
Alloy C	4.74	19.84	0.95	374.9	1409	815.2
Alloy D	5.88	33.78	0.87	301.8	1247	704.8
Alloy E	4.99	32.68	0.89	259.5	1102	215.4

showed a better cytocompatibility than others. The results are basically consistent with those of morphology discussed in Fig. 11.

4 Discussion

4.1 Influence of Mo Microalloying on Microstructure

The alloy C obtained the finest grain size (22.0 μ m), and the volume fraction of 18R-LPSO phase increased to 24.0%. It was well known that the heterogeneous nucleation can efficiently promote the formation of homogeneous, fine and equiaxed grains in metal ingots. On the one hand, because it was basically insoluble in magnesium matrix, Mo was mainly distributed along the grain boundaries during solidification process (as shown in Fig. 4). Mo segregation induced broader constitutional supercooling (CS) at solidification interface, resulting in promoting nucleation and preventing the further growth of grains. On the other hand, Mo had body-centered cubic (BCC) lattice which was distinctly different from Mg (simple hexagonal close-packed, HCP). Nevertheless, the atomic arrangement was similar and the atomic spacing was also very close between (0002) Mg and (110) Mo, so the interfacial tension was smaller and was conducive to promote the nucleation [41]. According to the edge-to-edge matching theory [42], an epitaxial relationship had been predicted as (0002) Mg $\parallel$ (100) Mo, [11–20] Mg $\parallel$ [010] Mo and the lattice misfit was less than 2% between (0002) Mg and (110) Mo, which reduced the critical undercooling for nucleation and enhanced the heterogeneous nucleation rate.

Moreover, the second phases (18R-LPSO + W phase) were also influenced by Mo addition. Mo was conducive to the formation of 18R-LPSO phase while suppresses W phase. The electronegativity of Mo (2.16) is larger, compared with those of Mg (1.31), Y (1.22), Zn (1.65) and Mn (1.55). It is known that LPSO/ α -Mg interface has the largest

difference potential and shows the lowest negative potential [43]. Thus, Mo atoms are easily diffused to the LPSO/ α -Mg interface during solidification owing to the opposite attraction. The greater electronegativity difference leads to forming more LPSO phase [19]. Mo atoms can promote the formation of phase LPSO phase.

4.2 Influence of Mo Microalloying on Mechanical Properties

The optimal mechanical properties can be ascribed to the grain refinement and second-phase strengthening [44, 45]. The grain refinement is conducive to enhance strength of the alloys based on Hall–Petch formula. Moreover, LPSO phase could improve mechanical strength [43]. As known, 18R-LPSO phase, as a strengthening and toughening phase, could effectively prevent the movement of dislocation and result in the strengthening effect, while W phase, as a hard and brittle phase, is not conducive to the deformation [15]. It can be seen from Fig. 1 that the alloying Mo can promote the formation of 18R-LPSO phase with continuous network while inhibit W phase. So the alloy with Mo addition possesses the optimal mechanical properties.

4.3 Influence of Mo Microalloying on Biocorrosion Resistance

The Mo can improve the corrosion resistance of Mg–6Zn–8.16Y–2.02Mn alloy which can be ascribed to reasons as followed. Firstly, grain refinement had an advance to corrosion resistance of the metal. As a rule, the more grain boundaries, the finer grain was easier to form a protective oxide film due to higher energy at the grain boundaries, improving corrosion resistance [21, 46]. Secondly, the continuous 18R-LPSO phase can be a barrier at the interface of substrate and eutectic phase (W phase) to postpone the substrate corrosion [26, 27, 47]. Thirdly, the electronegativity of Mo was greater than that of other

Fig. 11 Optical images of L929 cells that cultured in Mg–6Zn–8.16Y–2.02Mn–*x*Mo extraction mediums for 1 day, 2 days and 3 days

Fig. 12 Relative growth rate of cells for Mg–6Zn–8.16Y–2.02Mn–xMo alloys cultured in 25% extract solution for 1 day, 2 days and 3 days

elements. The addition of Mo changed the electrochemical state of the metal matrix since the atoms in the metal crystal were bonded together by metallic bonds, making the electrons in the metal crystal more difficult to lose. And standard electrode potential of Mo was higher (Mg: -2.36 , Zn: -0.76 , Y: -2.37 , Mn: -1.180 , Mo: -0.20 V), resulting in the stability of the grain boundary. Mo addition enhanced corrosion resistance of intergranular and the α -Mg matrix. The schematic diagrams of corrosion mechanisms of as-cast Mg–6Zn–8.16Y–2.02Mn–xMo alloys are presented in Fig. 13. When dipped in Hank's solution, the corrosion of the alloy often began from micro-galvanic couple regions. Usually, second phases or impurities acted as the cathodic and Mg matrix as anodic [28]. For Mg–6Zn–8.16Y–2.02Mn alloy, the discontinuous 18R-LPSO and W phase began to peel off during corrosion. However, the continuous

Fig. 13 Schematic diagrams of corrosion mechanisms of as-cast Mg–6Zn–8.16Y–2.02Mn–xMo alloys

18R-LPSO phase in Alloy C can be a barrier to postpone the corrosion, which was in line with the reports in previous studies [26, 27]. Consequently, grain refinement, 18R-LPSO structure with continuous distribution and Mo addition were liable for the notable amelioration in corrosion resistance of the alloy.

4.4 Influence of Mo on the Cellular Compatibility

Mo was an essential trace element and had low toxicity [29, 34]. Furthermore, Y element in Mg alloys showed moderate toxicity to bone- and vascular-related cells. Zn and Mn had been shown to play both catalytic and structural roles in enzymes, and human requirement was estimated at 15 and 4 mg/d, respectively [48]. But excess Mn and Zn largely reduced the cell viability of L929 cells in vitro study [49]. The Mg intake was about 300–400 mg/d, and redundant magnesium cations can be excreted by urine [50]. The cell viability of L929 cells on the extracts of as-cast Mg–6Zn–8.16Y–2.02Mn with Mo increased gradually with the decrease in the corrosion rate. For one thing, Alloy C with 0.3 wt% Mo addition had the lowest corrosion rate (1.34 mm/y). The proliferation of the cells was promoted, and the cell viability was gradually increased because of the low concentration of metal ions in the extract. For another, evolution during the degradation of magnesium alloys brought about alkalization of solution. The gas pockets can cause separation between tissues and tissue layers. The local alkalization can break physiological reaction balances and may even bring out an alkaline poisoning effect depended on the pH [51]. Finally, it is known that the biocompatibility of Mo was uncertain [30]. For all alloys, the volume of hydrogen was increased in the order as Alloy C < Alloy B < Alloy D < Alloy E < Alloy A, just as shown in Fig. 6. However, Alloy D and Alloy E had poor cytocompatibility which may be ascribed to that the superfluous Mo ion was added. In a word, metal ions concentration, alkaline and hydrogen must be considered for the design of the final implant materials.

5 Conclusions

- (1) Mg–Zn–Y–Mn–Mo alloys were comprised of α -Mg matrix, 18R-LPSO phase and W phase. With the increase in Mo addition until 0.3 wt%, the grain size of α -Mg phase became fine and the volume fraction of 18R-LPSO phase was increased. The opposite phenomenon appears with more Mo addition.
- (2) The alloy with 0.3 wt% Mo obtained finest grains and largest volume fraction of 18R-LPSO phase with continuous distribution. And the alloy exhibited the most excellent UTS of 265 MPa and elongation of 13.5%,

respectively, which were 51.4%, 132.8% higher than that of Mo-free alloy.

- (3) The alloys with Mo had a better corrosion resistance than that of the Mo-free alloy. Adding 0.3 wt% Mo, the P_W (1.34 mm/y) and I_{corr} (1.5813×10^{-5} A/cm²) was acquired in alloy due to grain refinement and continuous distribution of 18R-LPSO phase.
- (4) Mg–6Zn–8.16Y–2.02Mn with 0.3 wt% Mo obtained good cytocompatibility in 25% extract solution, while those with more Mo were not conducive to cell survival. That may be due to the need for an adaptation of the cells for survival, and Mo at a certain concentration was beneficial to cells.

Acknowledgements This research was financially supported by the National Natural Science Foundation of China (Nos. 51474153 and 51574175).

References

- [1] F. Witte, J. Fischer, J. Nellesen, H.A. Crostack, V. Kaese, A. Pisch, F. Beckmann, H. Windhagen, *Biomaterials* **27**, 1013 (2006)
- [2] H.G. Liu, F.Y. Cao, G.L. Song, D.J. Zheng, Z.M. Shi, M.S. Dargusch, A. Atrens, *J. Mater. Sci. Technol.* **35**, 2003 (2019)
- [3] F. Witte, *Acta Biomater.* **6**, 1680 (2010)
- [4] S.X. Zhang, X.N. Zhang, C.L. Zhao, J.A. Li, Y. Song, C.Y. Xie, H.R. Tao, Y. Zhang, Y.H. He, Y. Jiang, Y.J. Bian, *Acta Biomater.* **6**, 626 (2010)
- [5] X.B. Zhang, Y.J. Wu, Y.J. Xue, Z.Z. Wang, L. Yang, *Mater. Lett.* **86**, 42 (2012)
- [6] Y. Jang, B. Collins, J. Sankar, Y. Yun, *Acta Biomater.* **9**, 8761 (2013)
- [7] J.F. Wang, Y.Y. Wei, S.F. Guo, S. Huang, X.E. Zhou, F.S. Pan, *Mater. Lett.* **81**, 112 (2012)
- [8] H. Liu, H. Huang, J.P. Sun, C. Wang, J. Bai, A.B. Ma, X.H. Chen, *Acta Metall. Sin. (Engl. Lett.)* **32**, 269 (2019)
- [9] K. Yang, J.S. Zhang, X.M. Zong, W. Liu, C.X. Xu, *Acta Metall. Sin. (Engl. Lett.)* **30**, 464 (2017)
- [10] L.Z. Liu, X.H. Chen, J.F. Wang, L.Y. Qiao, S.Y. Gao, K. Song, C.Y. Zhao, X.F. Liu, D. Zhao, F.S. Pan, *J. Mater. Sci. Technol.* **35**, 1074 (2019)
- [11] X.M. Zong, D. Wang, W. Liu, K.B. Nie, C.X. Xu, J.S. Zhang, *Acta Metall. Sin. (Engl. Lett.)* **29**, 32 (2016)
- [12] J.Q. Hao, J.S. Zhang, C.X. Xu, Y.T. Zhang, *Mater. Sci. Eng. A* **735**, 99 (2018)
- [13] J. Zhu, X.H. Chen, L. Wang, W.Y. Wang, Z.K. Liu, J.X. Liu, X.D. Hui, *J. Alloys Compd.* **703**, 508 (2017)
- [14] Y.H. Ali, D. Qiu, B. Jiang, F.S. Pan, M.X. Zhang, *J. Alloy. Compd.* **619**, 639 (2015)
- [15] J. Wang, J.S. Zhang, X.M. Zong, Z.Y. You, K.B. Nie, *Mater. Sci. Eng. A* **648**, 37 (2015)
- [16] D. Li, J.S. Zhang, Z.P. Que, C.X. Xu, X.F. Niu, *Mater. Lett.* **109**, 46 (2013)
- [17] F.G. Qi, D.F. Zhang, X.H. Zhang, X.X. Xu, *Mater. Sci. Eng. A* **593**, 70 (2014)
- [18] D.H. Cho, B.W. Lee, J.Y. Park, K.M. Cho, I.M. Park, *J. Alloys Compd.* **695**, 1166 (2017)

- [19] Y.G. Zhang, W.L.J.S. Zhang, W.Z.Q.Q. Ma, X.M. Zong, C.X. Xu, *Mater. Sci. Eng. A* **748**, 294 (2019)
- [20] R.C. Zeng, L.Y. Cui, W. Ke, *Acta Metall. Sin.* **54**, 1215 (2018)
- [21] R.C. Zeng, W.C. Qi, H.Z. Cui, F. Zhang, S.Q. Li, E.H. Han, *Corros. Sci.* **96**, 23 (2015)
- [22] Z.Y. Ding, L.Y. Cui, R.C. Zeng, Y.B. Zhao, S.K. Guan, D.K. Xu, C.G. Lin, *J. Mater. Sci. Technol.* **34**, 1550 (2018)
- [23] X. Zhao, L.L. Shi, J. Xu, *Mater. Sci. Eng. C* **33**, 3627 (2013)
- [24] S. Izumi, M. Yamasaki, Y. Kawamura, *Corros. Sci.* **51**, 395 (2009)
- [25] X.B. Zhang, Q. Wang, F.B. Chen, Y.J. Wu, Z.Z. Wang, Q. Wang, *Mater. Lett.* **138**, 212 (2015)
- [26] J.S. Zhang, J.D. Xu, W.L. Cheng, C.J. Chen, J.J. Kang, *J. Mater. Sci. Technol.* **28**, 1157 (2012)
- [27] P. Cheng, Y.H. Zhao, R.P. Lu, H. Hou, *J. Alloys Compd.* **764**, 226 (2018)
- [28] X.M. Zong, J.S. Zhang, W. Liu, Y.T. Zhang, Z.Y. You, C.X. Xu, *Adv. Eng. Mater.* **20**, 1800017 (2018)
- [29] J. Liu, L.X. Yang, C.Y. Zhang, B. Zhang, F.H. Wang, *J. Alloys Compd.* **782**, 648 (2019)
- [30] World Health Organization, *Trace Elements in Human Nutrition and Health*, 1996
- [31] A.R. Farkoosh, X.G. Chen, M. Pekguleryuz, *Mater. Sci. Eng. A* **620**, 181 (2015)
- [32] S.K. Shaha, F. Czerwinski, W. Kasprzak, J. Friedmann, D.L. Chen, *Mater. Sci. Eng. A* **684**, 726 (2017)
- [33] S.C. Zhang, H.B. Li, Z.H. Jiang, B.B. Zhang, Z.X. Li, J.X. Wu, H.C. Zhu, *Mater. Char.* (2019)
- [34] M.H. Kazimierzak, J. Morgiel, Z. Swiatek, J.M. Vega, G.L. Eva, *Corros. Sci.* **135**, 107 (2018)
- [35] A.D.F. López, I.L. Lehr, S.B. Saidman, *J. Alloys Compd.* **702**, 338 (2017)
- [36] International Standard ISO 10993–5: Biological evaluation of medical devices—Part 5: Tests for in vitro cytotoxicity, 2009
- [37] N.I.Z. Abidin, A.D. Atrens, D. Martin, A. Atrens, *Corros. Sci.* **53**, 3542 (2011)
- [38] G. Song, A. Atrens, D.S.T. Jonh, X. Wu, J. Nairn, *Corros. Sci.* **39**, 1981 (1997)
- [39] Q. Qu, S.L. Li, L. Li, L.M. Zuo, X. Ran, Y. Qu, B.L. Zhu, *Corros. Sci.* **118**, 12 (2017)
- [40] Z. Wang, C. Chen, J. Jiu, S. Nagao, M. Nogi, H. Koga, H. Zhang, G. Zhang, K. Suganuma, *J. Alloy. Compd.* **716**, 231 (2017)
- [41] D. Qiu, M.X. Zhang, *J. Alloy. Compd.* **586**, 39 (2014)
- [42] M.X. Zhang, P.M. Kelly, *Acta Mater.* **53**, 1073 (2005)
- [43] C.Q. Li, D.K. Xu, Z.R. Zeng, B.J. Wang, L.Y. Sheng, X.B. Chen, E.H. Han, *Mater. Des.* **121**, 430 (2017)
- [44] R.G. Li, R.L. Xin, Q. Liu, A. Chapuis, S.F. Liu, G.Y. Fu, L. Zong, *Mater. Des.* **114**, 450 (2017)
- [45] N. Tahreen, D.F. Zhang, F.S. Pan, X.Q. Jiang, D.Y. Li, D.L. Chen, *J. Mater. Sci. Technol.* **34**, 1110 (2018)
- [46] K. Chen, J.W. Dai, X.B. Zhang, *Corros. Rev.* **33**, 101 (2015)
- [47] X.B. Zhang, Z.X. Ba, Z.Z. Wang, Y.J. Wu, Y.J. Xue, *Mater. Lett.* **163**, 250 (2016)
- [48] Y.F. Zheng, X.N. Gu, F. Witte, *Mater. Sci. Eng., R* **77**, 1 (2014)
- [49] J. Cheng, B. Liu, Y.H. Wu, Y.F. Zheng, *J. Mater. Sci. Technol.* **29**, 619 (2013)
- [50] J. Vormann, A.M. Mol, *Adv. Mater. Res.* **24**, 27 (2003)
- [51] G.L. Song, *Corros. Sci.* **49**, 1696 (2007)