Microstructure and Mechanical Properties of Cu Matrix Composites Reinforced by TiB₂/TiN Ceramic Reinforcements

Jinwei Yin¹ · Peilong Zhou^{1,2} · Hanqin Liang¹ · Dongxu Yao¹ · Yongfeng Xia¹ · Kaihui Zuo¹ · YuPing Zeng¹

Received: 27 February 2020 / Revised: 1 April 2020 / Accepted: 22 April 2020 / Published online: 9 July 2020
© The Chinese Society for Metals (CSM) and Springer-Verlag GmbH Germany, part of Springer Nature 2020

Abstract

Cu matrix composites reinforced by TiB₂/TiN ceramic reinforcements (Cu/TBN composites) were prepared by hot pressing method. Prior to the hot pressing, Cu/TiB₂/TiN composite powders (CTBN powders), which were used as the starting materials of Cu/TBN composites, were fabricated by self-propagating high-temperature synthesis method. The CTBN particles were found to be in a special core–shell structure with a Cu–Ti alloy core and a TiB₂/TiN ceramic shell. The test results presented obvious improvements in mechanical properties. The highest ultimate tensile strength reached up to 297 MPa, 77 MPa higher than that of Cu. And the highest hardness reached up to 70.7 HRF, 15.7 HRF higher than that of Cu. A comparative study indicated that the core–shell structured particles could bring about more obvious strengthening effect than the traditional irregularly shaped particles, which was due to the improved Cu/ceramics interfacial bonding, the linkage strengthening effect of both TiB₂ and TiN, and higher load bearing ability of the core–shell structured reinforcements.

Keywords Cu matrix composite · Microstructure · Mechanical property · Self-propagating high-temperature synthesis (SHS)

1 Introduction

Copper alloy is widely applied in machinery fields because of its relatively high thermal and electrical conductivity, low cost and ease of fabrication. However, as modern machines develop toward higher speeds and higher power densities, it requires better wear resistance and mechanical properties of Cu alloys considering the high reliability and long service life. Cu matrix composites reinforced by ceramic reinforcements (CMMCs) have been proved to have superior wear resistance and mechanical properties [1–4], thus have been interesting to researchers in recent years. Titanium nitride (TiN) and titanium diboride (TiB₂) are potential

reinforcements because of their outstanding mechanical properties, low densities, high melting temperature and good wear resistance. Moreover, both the two kinds of ceramics have high electrical and thermal conductivity [5], which makes them the good candidates of reinforcements in CMMCs due to their wide application in electronic parts and heat-conducting components. Titanium nitride exhibits low friction coefficient in air and in liquid because of the formation of titanium dioxide layers [6], which is quite beneficial to the improvement of wear resistance.

The traditional CMMCs are mostly reinforced by ex situ reinforcements such as SiC [7, 8], Si₃N₄ [9, 10], B₄C [4] et al., in other words, the ceramic reinforcements and Cu powders are separately prepared prior to the preparation of CMMCs. Although the ex situ routes have been successfully applied to prepare kinds of metal matrix composites (MMCs), it has several drawbacks, including poor reinforcements/matrix interfacial bonding and agglomeration of ceramics. Compared with the ex situ composites, the in situ composites have more advantages, such as thermodynamically stability of in situ formed ceramics, strong interfacial-bonding between matrix and reinforcements, uniform distribution of the ceramic particles, and good mechanical properties of composites.

Available online at <http://link.springer.com/journal/40195>.

✉ YuPing Zeng
yuping-zeng@mail.sic.ac.cn

¹ State Key Laboratory of High Performance Ceramics and Superfine Microstructure, Shanghai Institute of Ceramics, Chinese Academy of Sciences, Shanghai 200050, China

² Center of Materials Science and Optoelectronics Engineering, University of Chinese Academy of Sciences, Beijing 100049, China

Both TiB_2 and TiN can be formed via the in-situ processes in MMCs [11–14]. Chen et al. [15] prepared the Cu matrix composites using TiB_2/TiN as the reinforcements and h-BN as the solid lubrications. According to their work, both wear resistance and hardness of the composites were improved. But the XRD patterns indicated that the amount of TiB_2 generated was fairly small. Zhang et al. [16] prepared TiB_2/TiN ceramics by the reaction between h-BN and TiH_2 with the sintering temperature ranging from 1000 to 1600 °C. They pointed that the TiN was formed at 1000 °C, but the TiB_2 was not detected until the temperature was up to 1600 °C. The reaction between Ti and BN was suggested to be the following:

where the B (amor) stands for amorphous boron.

In the work of Chen et al. [15], the sintering temperature was ranging from 780 to 970 °C, which was not sufficient to generate enough amount of TiB_2 . According to the work of Zhang et al. [16], to achieve the complete reaction between Ti and BN, the sintering temperature should be higher than 1600 °C. However, when the temperature is above 1600 °C, Cu has already been already in liquid state (the melting point of Cu is 1080 °C). A new problem comes up: the TiB_2/TiN reinforcements may float up to the upper surface of the liquid Cu due to the large disparity of the densities, which results in the nonuniform distribution of reinforcements in the matrix.

In this work, the self-propagating high-temperature synthesis (SHS) method was applied to prepare CTBN powders. During the SHS process, the combustion temperature was more than 2000 °C, which was sufficient for the generation of TiB_2 . Since the high temperature lasted quite a short time, the TiB_2/TiN ceramics were adhered to the instantaneously appeared Cu droplets, and had no time to float up, thus the distribution of ceramics was uniform. Then, the powders were the mixed with additional Cu powders to fabricate Cu matrix composites by hot pressing. Microstructure and mechanical properties of the composites were researched to evaluate the strengthening effect.

2 Experimental

2.1 Preparation of CTBN Powders

Cu, Ti and BN were used as the starting raw powders, characteristics listed in Table 1. These reactants, composition listed in Table 2, were ball milled in absolute ethanol for 24 h. Then, the resulting slurries were dried at 60 °C for

Table 1 Characteristics of raw powder

Powder	Grain size, d_{50} (μm)	Purity (%)
Cu	20.7	≥ 99.5
Ti	5.6	≥ 99.99
BN	0.16	≥ 99.5

Table 2 Composition of the raw materials for the SHS process

Products	Composition of the raw materials		
	Cu (g)	Ti (g)	BN (g)
A-CTBN	0	143.6	49.6
B-CTBN	143.6	143.6	44.6
C-CTBN	143.6	143.6	49.6
D-CTBN	143.6	143.6	54.6
E-CTBN	143.6	143.6	59.6

3 h to remove ethanol followed by pulverizing and passing through a 100 mesh sieve. After that, the mixtures were put in a BN-coated graphite crucible. A tungsten heating coil was used to ignite the reaction of titanium powders and BN powders. The combustion reaction process proceeds in the SHS furnace using Ar as the protective atmosphere. After the reactions, the samples were removed from the combustion synthesis vessel. The products were pulverized and passed through a 100 mesh sieve to obtain uniform and refined powders. The produced powders in Table 2 are labeled as A-CTBN, B-CTBN, C-CTBN, D-CTBN and E-CTBN, respectively.

2.2 Preparation of Cu/TBN Composites

The C-CTBN powders fabricated by SHS process were selected as the reinforcement phases to prepare the Cu/TBN composites, because BN and Ti in this group can completely react with each other according to stoichiometric ratio. Additional Cu powders mixed with the C-CTBN powders were ball milled by planetary ball milling for 3 h to form the uniform mixtures. After that, the mixtures were dried at 60 °C for 3 h to remove ethanol followed by pulverizing and passing through a 100 mesh sieve. The resulting powder mixtures were hot pressed in a graphite die under a uniaxial load of 25 MPa in vacuum. The composites were sintered at two different sintering temperatures (1000 °C and 1030 °C) for 2 h.

X-ray diffraction (XRD, D8 discover, Bruker, Germany) was applied to analyze the phase composition of the powders and the composites. Scanning electron microscopy (SEM, JSM-6390, JEOL, Japan) was applied to characterize

microstructures of CTBN powders and fractured surfaces of Cu/TBN composites.

Densities of composites were measured using Archimedes method in deionized water as an immersion medium. Theoretical density of composites was calculated by the following equation:

$$\rho_{th} = \rho_{TBN} V_{TBN} + \rho_{Cu} V_{Cu}, \quad (3)$$

where ρ_{th} , ρ_{TBN} and ρ_{Cu} were the theoretical density of composites, TiB₂/TiN ceramics and Cu matrix, respectively; V_{TBN} , V_{Cu} were the volume fraction of TiB₂/TiN ceramics and Cu matrix. All the TiB₂/TiN content mentioned in this work represented the mass fraction of only TiB₂/TiN in the Cu/TBN composites, and the share of Cu in CTBN powders was included in the Cu matrix. The relative density (R) was achieved by the following equation:

$$R = \rho_{ar} / \rho_{th}, \quad (4)$$

where ρ_{ar} was experimental density achieved by Archimedes method.

Tensile strength was measured using a universal testing machine (Instron-5566, Instron, USA) with a tensile rate set at 3 mm/min. Each final value of tensile strength tests was the average of six measurements. Hardness tests were conducted on polished samples using Rockwell hardness tester (Wilson-2000, Instron, USA), and the load of 60 kg was applied by the spherical indenter of 1.58 mm in diameter.

3 Results and Discussion

3.1 Compositions of the CTBN Composite Powders

The XRD patterns of the CTBN powders are presented in Fig. 1. Compositions of the raw materials are listed in Table 2. Since TiB₂ and TiN peaks can be found in all the groups, it confirms that the TiB₂ and TiN phases have been successfully formed via the reaction between Ti and BN during the SHS process. The inexistence of BN in the B-CTBN patterns indicates that the BN is completely exhausted by the reaction with Ti to convert into TiB₂ and TiN. Although the amounts of BN and Ti in A-CTBN and C-CTBN are coincide with the reaction stoichiometric ratio, BN peaks still can be found in both patterns, which means that the reaction is incomplete and residual Ti may diffuse into the Cu particles to form Cu/Ti alloy. In D-CTBN and E-CTBN, the BN is excessive for the reaction with Ti, and the peaks of BN can be still detected.

Fig. 1 XRD patterns of the CTBN powders: (a) A-CTBN, (b) B-CTBN, (c) C-CTBN, (d) D-CTBN, (e) E-CTBN

Fig. 2 Microstructure of C-CTBN powder, and EDS mapping results of Cu, Ti, B and N

Fig. 3 Typical hexagon clubbed structure of TiB_2 particle

3.2 Microstructures

Figure 2 shows the micrograph of the C-CTBN powders. According to the energy disperse spectroscopy (EDS) mapping tests, the smooth background labeled “a” in Fig. 2 is detected to be Cu, and is covered by various small particles. The small spherical particles labeled “b” in diameter of dozens of nanometers are mostly TiN, which can be proved by the EDS mapping tests (Ti) and (N). The spherical particles labeled “c”, a bit larger than “b”, are BN according to the EDS mapping tests (B) and (N). The large particles embedded into the Cu metal should be TiB_2 , which coincide with the EDS mapping tests (Ti) and (B). The TiB_2 particles generated during the SHS process are hexagon and clubbed particles as shown in Fig. 3, which is partly buried into the Cu matrix. According to the research by Yang et al. [17] and Xinghong et al. [18], the clubbed structured TiB_2 with high aspect ratio was very effective to improve the mechanical properties and wear resistance of composites.

3.3 Densification

Figure 4 shows the change of relative densities of Cu/TBN composites with different TiB_2/TiN contents. Densities of the composites in both groups present a steady decrease with TiB_2/TiN content increasing from 0 to 4 wt%. Obviously, the ceramic reinforcements are the major factors inhibiting densification of the composites. Although the ceramics are partly embedded into the Cu particles during the SHS process, plenty surfaces of ceramics are exposed. These exposed particles can weaken mass transfer by pinning effect thus to block the connection between Cu particles. And the relatively poor wettability between Cu matrix and ceramics can further enhance the inhibition [19, 20]. As a result, the

Fig. 4 Relative densities of Cu/TBN composites with different TBN contents: filled square: 1000 °C for 2 h; filled circle: 1030 °C for 2 h

relative density decreases with the TiB_2/TiN content increasing. Comparing the two different sintering programs, higher sintering temperature is proved to be helpful to promote the densification.

3.4 Mechanical Properties

The hardness of composites, as shown in Fig. 5a, is markedly affected by the TiB_2/TiN content. As the TiB_2/TiN content increases from 0 to 4 wt%, the hardness in both groups presents a continuous increase accordingly, which is mostly due to the increasing geometric share of the TiB_2/TiN ceramics [21]. Both TiB_2 and TiN have the extremely high hardness over 30 GPa, as a result, the higher TiB_2/TiN content, the higher hardness of composites. Moreover, the results indicate that higher sintering temperature at 1030 °C is also helpful to obtain higher hardness probably due to better densification.

Figure 5b shows the effect of TiB_2/TiN content on the ultimate tensile strength (UTS) of composites sintered at both 1000 °C and 1030 °C. It can be seen that the UTS increases as the TiB_2/TiN content increases from 0 to 2 wt%, and reaches the highest value at 2 wt% (291 MPa for 1000 °C and 297 MPa for 1030 °C). Although the UTS of both groups basically has the same change tendency, the value at 1030 °C is higher than that at 1000 °C, which can be attributed to the improved Cu/ceramics interfacial bonding strength and better densification at higher sintering temperature. The stress–strain curves of Cu/TBN composites are shown in Fig. 5c, d. It can be seen that the strain is decreased with the TiB_2/TiN content increasing whether the sintering temperature is 1000 °C or 1030 °C, and the stress–strain behavior of composites sintered at 1000 °C and 1030 °C shows little difference.

Fig. 5 Hardness **a** and UTS **b** of Cu/TBN composites: filled square: 1000 °C for 2 h; filled circle: 1030 °C for 2 h. And stress–strain curves of Cu/TBN composites sintered at 1000 °C **c**, 1030 °C **d**

3.5 Strengthening Mechanisms

Figure 6a–d shows the polished surface of the Cu/TBN composites with different contents of TiB₂/TiN. The offwhite areas are detected to be Cu matrix, and the dark gray areas are the C-CTBN particles fabricated during the SHS process. As the TiB₂/TiN content increases from 1 to 4%, the dark gray areas cover an increasing proportion. The C-CTBN particles distributed in the matrix are core–shell structured with a TiB₂/TiN shell and a Cu/Ti alloy core (Fig. 6e). As Fig. 6a–d shows, the C-CTBN particles are randomly distributed in the Cu matrix. Besides the large composite particles, some small particles are also observed to be scattered in the Cu matrix. These small particles are probably resulted from the rupture of the large CTBN particles during the ball milling process. No aggregation of the C-CTBN particles can be found in the composites.

The reinforcements of TiB₂ and TiN in the composites have a significant effect on the microstructure of the

composites. In the composites, a quite high thermal mismatch exists between the Cu matrix and the TiB₂/TiN ceramic particles. Thus, during the cooling process after sintering, dislocations formed at the interfaces between Cu and ceramics (including both TiB₂, TiN and residual BN) due to the thermal mismatch [22, 23]. In this manner, thermally induced dislocations result in the “dislocation strengthening” in the Cu matrix. Considering more interface existing around smaller reinforcement particles for dislocation to take place, a decreased particle size brings about the increased effect of dislocation strengthening [24], thus the TiN particles in the size of about 50 nm are more effective in strengthening Cu matrix in the dislocation strengthening manner than the micro-sized TiB₂ particles.

Apart from the dislocation strengthening, load transfer from Cu matrix to reinforcements is also an important strengthening mechanism in the Cu/TBN composites. However, the irregular ceramic particles with low aspect ratio are commonly considered not efficient in load transfer [17,

Fig. 6 Distribution of C-CTBN particles in the Cu/TBN composites with different TBN contents: **a** 1%, **b** 2%, **c** 3%, **d** 4%; **e** core-shell structure of C-CTBN composite particles

18, 25]. In this case, the short clubbed TiB_2 particles with higher aspect ratio have an advantage over the TiN particles. As a result, the strengthening effect can be considered as the combined action of both the spherical TiN particles in dislocation strengthening mechanisms and the short clubbed TiB_2 particles in load transfer mechanism.

The core-shell structure, in which a Cu-Ti alloy core is uniformly covered by a TiB_2/TiN ceramic shell, is quite an interesting microstructure, which has a different structure with the traditional reinforcements. To evaluate the effect of the core-shell structure on the mechanical properties of Cu/TBN composites, a comparative study has been made. Three different kinds of specimens are selected to make the

comparison: (a) Cu without any ceramics reinforcements, (b) Cu matrix composites reinforced by A-CTBN, and (c) Cu matrix composites reinforced by C-CTBN. And the TiB_2/TiN content in both (b) and (c) is 2 wt%. Their stress-strain curves are shown in Fig. 7. Cu without any ceramics has the largest strain but the lowest UTS. Composites (c) have the highest UTS and the lowest strain, although both (b) and (c) have the same TiB_2/TiN contents.

It is commonly accepted that the increase in particle size means the decrease in work hardening and the accelerated damage in the form of particle cracking. As a result, the general view expects that the smaller the particles, the higher the composites strength [26, 27]. According to this view,

Fig. 7 Comparison of stress–strain curves: (a) Cu without any ceramics reinforcements, (b) Cu matrix composites reinforced by A-CTBN, (c) Cu matrix composites reinforced by C-CTBN

Fig. 8 TBN/Cu interfacial structure

composites (c) should have a lower UTS than (b) because the C-CTBN particle has a much larger size ($d_{50} = 22 \mu\text{m}$) than the TiB₂ (length $\leq 1 \mu\text{m}$, diameter $\leq 0.5 \mu\text{m}$) and TiN ($d_{50} = 20 \text{ nm}$) in A-CTBN, but the test results are obviously opposite. The abnormal results can be attributed to the improved Cu/ceramics interfacial bonding and the special core–shell structure.

The improved TBN/Cu interfacial bonding is an important factor of the improvement of UTS. Figure 8 shows the TBN/Cu interfacial structure. The Cu/TiB₂ interface in the rectangular box is very tight with almost no gaps. This

interface is due to TiB₂ buried in molten Cu during SHS process. For the TiB₂ not buried in molten Cu, the TiB₂ surface is partly exposed to pores (labeled “A”), and partly forms a weak interface bonding with Cu matrix (labeled “B”) due to interface diffusion and it is difficult to have a high interface bonding strength. For group (b), the Cu/ceramics interfacial bonding is mainly formed by interfacial diffusion, therefore, the interfacial bonding strength is relatively weak, and the interfaces can be easily cracked, thus it is hard to obtain good strengthening effect. However, in the case of group (c), Cu is instantaneously molten during the SHS process, thus the TBN/Cu interfacial wetting is much optimized. It can be observed from Figs. 2, 3 and 8 that some of the TiB₂ particles have already firmly buried into the Cu matrix after the SHS process. These buried particles are hard to be pulled out during the fracture process, which is beneficial to the improvement of tensile strength.

Load transfer mechanism can be described as following [24]: the load is transferred from the weaker matrix, across the matrix/reinforcement interface, to the typically stiffer reinforcement when the composites are under an applied load, and the strengthening take place by the reinforcement “carrying” much of the applied load. The stress transferred to the particles is gradually accumulated to the maximum in middle part of the particles. If the stress is accumulated to be higher than the fracture strength of the ceramic particles, the particle fracture happens. However, due to the low aspect ratio of particulate materials and low ceramics/metal interfacial bonding strength, load transfer is not efficient, and the stress accumulated on the particles is far below the fracture strength of the ceramics. As a result, it is usually the ceramics/metal interfaces debonding rather than the particles crack. In other words, the strengthening potential is not explored sufficiently. But it is quite different for the core–shell particles. On one side, the load can be transferred to the TiB₂/TiN ceramics like the case in the particle reinforced composites; on the other side, it can be further transferred from the TiB₂/TiN ceramics shells to the Cu–Ti alloy inner cores. Since plenty of ceramic particles, especially the clubbed TiB₂ particles, are firmly buried into the Cu matrix, the core–shell structure can act as a unit. The load transferred to the Cu–Ti alloy core can be accumulated to quite high level without rupture because the alloy can tolerate a certain strain to release the stress concentration. The load bared by the core–shell particles is summation of both TiB₂/TiN ceramic particles and the Cu–Ti alloy core, thus the UTS of composites is obviously elevated.

Although the UTS is increased due to the strengthening effect of the TiB₂/TiN ceramics, the elongation of the Cu/TBN composites is decreased as shown in Fig. 7. As mentioned above, the TiB₂/TiN ceramics mostly exist around Cu/Ti alloy cores, so these regions present more brittleness than plasticity. During the tensile process, despite the

deformation of Cu/Ti alloy cores can endure some strain to release the stress concentration, the brittle regions cannot deform as large as the Cu matrix, so these regions are usually fractured former than the Cu matrix. As a result, higher reinforcement content means more sources of the cracks in the brittle regions, and the elongation of the composites is decreased accordingly.

The fractured micrographs of the tensile samples for the pure Cu and Cu/TBN composites with 2 wt% TiB_2/TiN have been examined using SEM as shown in Fig. 9. The fractured morphology of Cu is mostly ductile morphology of dimples. However, in the Cu/TBN composites as shown in Fig. 8c, the ductile morphology is not as obvious as it in the Cu, and plenty of micro-ceramic particles appear on the fractured surface, which is the typical feature of brittle fracture. Despite this, some ductile features in the form of dimples are also observed due to the localized deformation on the fractured surface (Fig. 8d). It can be concluded that the fracture of Cu/TBN composites is a complex process of both brittle fracture and ductile fracture, which is similar with some other MMCs [28, 29].

The fracture process can be described as follows. The discontinuous crack is accumulated ahead of the continuous crack tip, which results in the micro-crack extension. The crack propagates when these micro-cracks are connected by

micro-void coalescence, which explains the dimpled appearance of the fracture surface [30]. However, due to the different thermal expansions of the TiB_2/TiN ceramics and Cu matrix during the cooling process after sintering, it can bring about the tensile triaxial stress state around the ceramic particles. Once the crack propagates to these areas, it can be deflected around the TiB_2/TiN particles [31]. Hence then, it is hard to generate the long path cracks, and the dimples in Cu/TBN composites only exist in micro-area.

4 Conclusion

The Cu/TBN composites with improved tensile strength and hardness were prepared using CTBN particles as the reinforcements. The strengthening effect was considered as the combined action of both the spherical TiN particles in dislocation strengthening mechanisms and the short clubbed TiB_2 particles in load transfer mechanisms. Moreover, the CTBN particles exhibited better strengthening effect than the traditional ceramic particles, which was mainly attributed to the special core-shell structure and the enhanced interfacial bonding strength. The highest UTS and hardness reached up to 297 MPa and 70.7 HRF, respectively. The fracture of Cu/

Fig. 9 Fractured surface micrographs of specimens: **a, b** Cu; **c, d** Cu/TBN composites (Cu/C-CTBN) with 2 wt% TiB_2/TiN ceramics. All specimens were sintered at 1030 °C for 2 h

TBN composites was a complex process of both brittle fracture in the macroscale and ductile fracture in the microscale.

Acknowledgements This work was financially supported by the National Key R&D Program of China (No. 2018YFF01013605), the National Natural Science Foundation of China (No. 51501215), the Youth Innovation Promotion Association CAS (No. 2019254), the Science Foundation for Youth Scholar of State Key Laboratory of High Performance Ceramics and Superfine Microstructures (No. SKL201701), the State Key Laboratory of New Ceramic and Fine Processing Tsinghua University (No. KF201806).

References

- [1] M. Guo, K. Shen, M. Wang, *Acta Mater.* **57**, 4568 (2009)
- [2] S. Sharma, T. Nanda, O.P. Pandey, *Ceram. Int.* **44**, 104 (2018)
- [3] P. Zhang, J. Jie, H. Li, T. Wang, T. Li, *J. Mater. Sci.* **50**, 3320 (2015)
- [4] B.-W. Ahn, J.-H. Kim, K. Hamad, S.-B. Jung, *J. Alloys Compd.* **693**, 688 (2017)
- [5] A. Jha, S.J. Yoon, *J. Mater. Sci.* **34**, 307 (1999)
- [6] T. Aizawa, T. Akhadejdamrong, C. Iwamoto, Y. Ikuhara, A. Mitsuo, *J. Am. Ceram. Soc.* **85**, 21 (2002)
- [7] Y. Zhan, G. Zhang, *J. Mater. Sci.* **40**, 223 (2005)
- [8] D.M. Jarzabek, M. Milczarek, T. Wojciechowski, C. Dziekonski, M. Chmielewski, *Ceram. Int.* **43**, 5283 (2017)
- [9] J. Yin, D. Yao, Y. Xia, K. Zuo, Y. Zeng, *J. Alloys Compd.* **615**, 983 (2014)
- [10] C. Zhang, J. Yin, D. Yao, K. Zuo, Y. Xia, H. Liang, Y. Zeng, *Compos. Part A Appl. Sci. Manuf.* **102**, 145 (2017)
- [11] J. Li, F. Li, K. Hu, Y. Zhou, *J. Alloys Compd.* **334**, 253 (2002)
- [12] J.H. Shim, J.S. Byun, Y. Whan Cho, *Scr. Mater.* **47**, 493 (2002)
- [13] M. Kitiwan, A. Ito, T. Goto, *J. Eur. Ceram. Soc.* **34**, 197 (2014)
- [14] C.L. Yeh, C.H. Chiang, *Ceram. Int.* **41**, 11287 (2015)
- [15] B. Chen, Q. Bi, J. Yang, Y. Xia, J. Hao, *Mater. Sci. Eng. A* **491**, 315 (2008)
- [16] G.J. Zhang, Z.Z. Jin, X.M. Yue, *J. Am. Ceram. Soc.* **78**, 2831 (1995)
- [17] Y.F. Yang, H.Y. Wang, Y.H. Liang, R.Y. Zhao, Q.C. Jiang, *Mater. Sci. Eng. A* **445–446**, 398 (2007)
- [18] Z. Xinghong, Z. Chuncheng, Q. Wei, H. Xiaodong, V.L. Kvanin, *Compos. Sci. Technol.* **62**, 2037 (2002)
- [19] S. Cho, K. Kikuchi, T. Miyazaki, K. Takagi, A. Kawasaki, T. Tsukada, *Scr. Mater.* **63**, 375 (2010)
- [20] Y. Zhang, H.L. Zhang, J.H. Wu, X.T. Wang, *Scr. Mater.* **65**, 1097 (2011)
- [21] Y.A. Lu, J.F. Yang, W.Z. Lu, R.Z. Liu, G.J. Qiao, C.G. Bao, *Mater. Sci. Eng. A* **527**, 6289 (2010)
- [22] J.N. Wei, Z.B. Li, F.S. Han, *Phys. Status Solidi A* **191**, 125 (2002)
- [23] W.D. Fei, M. Hu, C.K. Yao, *Mater. Chem. Phys.* **77**, 882 (2003)
- [24] N. Chawla, Y.L. Shen, *Adv. Eng. Mater.* **3**, 357 (2001)
- [25] N. Xu, Y.P. Zong, F.Z. Hang, L. Zuo, *Acta Metall. Sin. (in Chinese)* **43**, 863 (2007)
- [26] S.V. Kamat, A.D. Rollett, J.P. Hirth, *Scr. Metall. Mater.* **25**, 27 (1991)
- [27] M.T. Kiser, F.W. Zok, D.S. Wilkinson, *Acta Mater.* **44**, 3465 (1996)
- [28] P. Jin, X.B. Lv, Q.Z. Wang, Z.Y. Ma, Y. Liu, S. Li, *Acta Metall. Sin. (in Chinese)* **47**, 298 (2011)
- [29] Q.K. Cai, C.L. He, M.J. Zhao, J. Bi, C.S. Liu, *Acta Metall. Sin. (in Chinese)* **39**, 865 (2003)
- [30] Y. Flom, R.J. Arsenault, *Acta Metall.* **37**, 2413 (1989)
- [31] L. Cao, C.P. Jiang, Z.K. Yao, T.Q. Lei, *Acta Metall. Sin. (in Chinese)* **25**, 113 (1989)