Effect of LiTFSI and LiFSI on Cycling Performance of Lithium Metal Batteries Using Thermoplastic Polyurethane/Halloysite Nanotubes Solid Electrolyte

Zhichuan Shen^{1,2} · Jiawei Zhong^{1,2} · Wenhao Xie^{1,2} · Jinbiao Chen^{1,2} · Xi Ke^{1,2} · Jianmin Ma³ · Zhicong Shi^{1,2}

Received: 16 October 2020 / Revised: 7 November 2020 / Accepted: 18 November 2020 / Published online: 11 February 2021
© The Chinese Society for Metals (CSM) and Springer-Verlag GmbH Germany, part of Springer Nature 2021

Abstract

All-solid-state lithium batteries (ASSLB) are promising candidates for next-generation energy storage devices. Nevertheless, the large-scale commercial application of high energy density ASSLB with the polymer electrolyte still faces challenges. In this study, a thin solid polymer composite electrolyte (SPCE) is prepared through a facile and cost-effective strategy with an infiltration of thermoplastic polyurethane (TPU), lithium salt (LiTFSI or LiFSI), and halloysite nanotubes (HNTs) in a porous framework of polyethylene separator (PE) (TPU–HNTs–LiTFSI–PE or TPU–HNTs–LiFSI–PE). The composition, electrochemical performance, and especially the effect of anions (TFSI[−] and FSI[−]) on cycling performance are investigated. The results reveal that the flexible TPU–HNTs–LiTFSI–PE and TPU–HNTs–LiFSI–PE with a thickness of 34 μm exhibit wide electrochemical windows of 4.9 and 5.1 V (vs. Li⁺/Li) at 60 °C, respectively. Reduction in FSI[−] tends to form more LiF and sulfur compounds at the interface between TPU–HNTs–LiFSI–PE and Li metal anode, thus enhancing the interfacial stability. As a result, cell composed of TPU–HNTs–LiFSI–PE exhibits a smaller increase in interfacial resistance of solid electrolyte interphase (SEI) with a distinct decrease in charge-transfer resistance during cycling. Li/Li symmetric cell with TPU–HNTs–LiFSI–PE could keep its stable overpotential profile for nearly 1300 h with a low hysteresis of approximately 39 mV at a current density of 0.1 mA cm^{−2}, while a sudden voltage rise with internal cell impedance-surge signals was observed within 600 h for cell composed of TPU–HNTs–LiTFSI–PE. The initial capacities of NCM/TPU–HNTs–LiTFSI–PE/Li and NCM/TPU–HNTs–LiFSI–PE/Li cells were 149 and 114 mAh g^{−1}, with capacity retention rates of 83.52% and 89.99% after 300 cycles at 0.5 C, respectively. This study provides a valuable guideline for designing flexible SPCE, which shows great application prospect in the practice of ASSLB.

Keywords Solid polymer composite electrolyte · Lithium metal anode · Thermoplastic polyurethane · Halloysite nanotubes · Cycling performance

1 Introduction

To date, the rapid energy expansion has urged researchers to develop advance energy storage devices [1]. Although Lithium ion batteries (LIBs) are considered as one of the attractive rechargeable batteries, they cannot satisfy the ever-increasing electric storage demands [2]. Thus, the development of batteries with high gravimetric and volumetric energy and power density has stimulated the intense research interest in recent years [3]. Lithium metal batteries (LMBs) are quite indispensable for the next-generation energy storage devices owing to the high theoretical capacity of lithium metal anode (3860 mAh g^{−1}) [4]. However, safety concerns such as short circuit and explosion arising from Li dendrite growth regarding the application of high-energy LMBs are

Available online at <http://link.springer.com/journal/40195>

✉ Xi Ke
kexi@gdut.edu.cn

✉ Zhicong Shi
zhicong@gdut.edu.cn

¹ School of Materials and Energy, Guangdong University of Technology, Guangzhou 510006, China

² Guangdong Engineering Technology Research Center for New Energy Materials and Devices, Guangzhou 510006, China

³ School of Physics and Electronics, Hunan University, Changsha 410082, China

ever-growing because of the employ of highly volatile and flammable organic liquid electrolytes [5]. Thus, the long-term durability of LMBs will be limited by the use of liquid electrolytes. In comparison with liquid electrolytes, LMBs with solid-state electrolyte (SSE) will be safer and possess longer cycle life with much more excellent thermal stability and wider electrochemical windows [6]. Therefore, SSE is considered as a potentially beneficial substitute for the present organic liquid electrolytes.

SSE can be generally divided into two categories: inorganic solid electrolyte (ISE) and solid polymer electrolyte (SPE) [7]. Unlike ISE that is brittle with poor interface contact, SPE is highly flexible which can fit in any battery shape in addition to their improved safety and stability [8]. Recently, thermoplastic polyurethane (TPU) has been investigated as a promising polymer electrolyte for LMBs [9]. For example, Liu et al. [10] designed a comb-like cationic TPU electrolyte with dimensional stability at room temperature. TPU contains a two-phase microstructure which is composed of hard and soft segments [11]. The hard part provides mechanical strength and thermal stability, while the soft part affords the transportation path for Li^+ , which ultimately provides the polymer chains with property of ion transmission [12]. Ibrahim et al. [13] constructed a castor oil-based polyurethane electrolyte which demonstrated a maximum ionic conductivity (σ) of $1.42 \times 10^{-6} \text{ S cm}^{-1}$ at 25 °C. However, the actual application of TPU in LMBs is restricted by the relatively poor electrochemical performance, and TPU-based SPE obtains little attention in battery research. In fact, this issue can be addressed by introducing nanoscale inorganic fillers into TPU molecular chains.

Numerous nano-fillers with unique nanostructures have been employed including TiO_2 nanorods, lithium montmorillonite sheets, and $\text{g-C}_3\text{N}_4$ nanosheets, etc. [14]. The addition of nano-fillers is able to sharply reduce the crystallization of polymer matrix and distribute the Li^+ well [15]. Among them, halloysite nanotubes (HNTs) are of particular interest because of their tubular geometric features consisting of bilayers of alumina octahedral and silica tetrahedral sheets [16]. The external silica surface of HNTs has a similar structure to SiO_2 , whereas the internal alumina core behaves similarly to gibbsite. Thus, zeta potential of HNTs can be roughly described by a positive inner surface with a negatively charged outer layer. Such oppositely charged surfaces guarantee selective association of charged substances, meaning that negatively charged anions will be preferably accommodated on the inner surface, whereas positively charged Li^+ ions tend to be adsorbed on the silica surface [17]. Moreover, the space charge effect will reduce the migration barrier of Li^+ and improve the ionic conductivity [18].

When combined with TPU, the lone-pair electrons in the C=O units of TPU interact with Li^+ adsorbed on the outside surface of HNTs, enabling the TPU chains to conform regularly to HNTs. Such interaction among HNTs, lithium salt, and TPU results in the formation of ordered 3D channels, which will facilitate the dissociation of lithium salt and Li^+ transport. In this way, TPU, HNTs, and lithium salt together form the main part of solid polymer composite electrolytes (SPCE).

Considering the further practical application, polyethylene (PE) separator was selected as the support for the above-mentioned TPU-based electrolyte, which can also effectively reduce its thickness. Such thin SPCE shows advantages in alleviating the resistance and improving battery performance via reducing Li^+ diffusion distance, which may consequently make ionic conductivity no longer be the bottleneck for the application of SPCE [19]. In addition, on the one hand, LiTFSI and LiFSI have been reported to enable stable cycling for LIBs [20]. On the other hand, it was found that anions of lithium salt play important roles in governing the electrochemical performance [21]. Nevertheless, deep understanding of the effect of LiTFSI or LiFSI on TPU-based composite electrolyte in ASSLB is lacked. Therefore, in this study, we will mainly focus on revealing the effects of LiTFSI and LiFSI on electrochemical performance in TPU-based electrolytes.

Herein, a composite of TPU polymer, HNTs and lithium salt in the porous framework of PE separator was prepared by a facile and cost-effective strategy to obtain a thin and flexible SPCE for LMBs (Scheme 1). The composition and electrochemical performance of the two types of electrolyte were analyzed with a series of characterization tests. The flexible TPU–HNTs–LiTFSI–PE and TPU–HNTs–LiFSI–PE with a thickness of 34 μm exhibited wide electrochemical windows of 4.9 and 5.1 V (vs. Li^+/Li) at 60 °C, respectively. Reduction in FSI^- tends to afford more LiF and sulfur compounds at the interface between

Scheme 1 Schematic illustration of the fabrication process of SPCE

TPU–HNTs–LiFSI–PE and Li metal anode, thus enhancing the interfacial stability. Based on this, TPU–HNTs–LiFSI–PE exhibits a smaller increase in interfacial resistance of SEI with a distinct decrease in charge-transfer resistance than that of TPU–HNTs–LiTFSI–PE during cycling. Li/Li symmetric cell with TPU–HNTs–LiFSI–PE could keep its stable overpotential profile for nearly 1300 h with a low hysteresis of approximately 39 mV at a current density of 0.1 mA cm^{-2} . The initial capacities of NCM/TPU–HNTs–LiTFSI–PE/Li and NCM/TPU–HNTs–LiFSI–PE/Li cells were 149 and 114 mAh g^{-1} , with capacity retention rates of 83.52% and 89.99% after 300 cycles at 0.5 C, respectively. This flexible SPCE provides a valuable guideline for cosmically commercial application of ASSLB.

2 Experimental

2.1 Chemicals

Lithium bis(trifluoromethylsulfonyl)imide (LiTFSI), and lithium bis(fluorosulfonyl)imide (LiFSI) were all obtained from Guangzhou Tinci Materials Technology Co., Ltd. $\text{LiNi}_{0.8}\text{Co}_{0.1}\text{Mn}_{0.1}$ powders were purchased from Canrd Company. Halloysite nanotubes (HNTs) with a diameter of 80 nm and a length of 500 nm were obtained from JIHENG Materials Co., Ltd. Thermoplastic polyurethane (TPU) was provided by BASF Corporation. PE separators with a thickness of 12 μm were obtained from Hebei Gellec New Energy Science & technology Co., Ltd. Acetone was obtained from Tianjin Damao Chemical Reagents. All chemicals were used without further purification.

2.2 Synthesis

2.2.1 Preparation of Solid-State Polymer Composite Electrolytes (TPU–HNTs–LiTFSI–PE and TPU–HNTs–LiFSI–PE)

Typically, about 1.50 g of TPU, 0.30 g of HNTs, 0.50 g of LiTFSI and 10.00 mL of acetone were added into a flask and completely dissolved at 30 °C with continuous stirring for 6 h (mass ratio of TPU/HNTs/LiTFSI = 15:3:5). Then, the solution was infiltrated into a PE separator by a coating method and subsequent solvent evaporation. The TPU–HNTs–LiTFSI–PE and TPU–HNTs–LiFSI–PE electrolytes were finally dried at 80 °C under vacuum for 12 h before further utilization. The TPU–HNTs–LiFSI–PE was composed of TPU, HNTs, LiFSI and PE separator, while

TPU–HNTs–LiTFSI–PE contained the components of TPU, HNTs, LiTFSI and PE separator. Each of the above SPCE had an areal loading capacity of about 4.43 mg cm^{-2} .

2.2.2 Preparation of $\text{LiNi}_{0.8}\text{Co}_{0.1}\text{Mn}_{0.1}$ (NCM) Cathodes

The NCM cathodes were prepared using a typical N-methylpyrrolidone (NMP) slurry coating method with $\text{LiNi}_{0.8}\text{Co}_{0.1}\text{Mn}_{0.1}$, conductive carbon black and PVDF binder with a mass ratio of 8:1:1 on carbon-coated aluminum foils. The areal loading capacity of NCM was about 2 mg cm^{-2} .

2.3 Materials Characterization

Gold particles were sprayed onto the surface of SPCE under N_2 atmosphere, and surface morphology of samples was characterized using an S4800 scanning electron microscope (SEM, Hitachi, Tokyo, Japan). The composition of the particles was analyzed by a Spectrum 100 Fourier infrared spectrometer (Perkin-Elmer, Waltham, MA, USA) using the KBr squash technique. X-ray photoelectron spectroscopy (XPS) was performed using an ESCALAB 250Xi spectrometer (Thermo Fisher Scientific, Waltham, MA, USA, Al K_{α} , $h\nu = 1486.6 \text{ eV}$) under vacuum ($2 \times 10^{-7} \text{ Pa}$).

2.4 Electrochemical Measurements

The symmetric cells (SS/SPCE/SS, CR2032-type coin) were used to measure ionic conductivities (σ) of SPCE in a frequency range of 10^6 – 10^{-1} Hz from 30 to 90 °C by an electrochemical workstation (ZIVE SP1, Shanghai Anzinc). σ was given by the following equation:

$$\sigma = \frac{l}{R_b S}, \quad (1)$$

where l is the thickness of the SPCE, S is the geometric area of the blocking stainless steel electrodes, and R_b is the resistance of electrolytes.

The lithium ion transference number (t_{Li^+}) of the electrolyte films was determined in symmetric cells (Li/SPCE/Li, CR2032-type coin). A constant polarization voltage of 10 mV was applied to cells, and current densities were measured from an initial value to a steady-state value after 3000 s. AC impedance spectra of the films before and after polarization were obtained in a frequency range from 10^5 to 10^{-1} Hz . t_{Li^+} was calculated as follows:

$$t_{\text{Li}}^+ = \frac{I_s(V - I_0 R_0)}{I_0(V - I_s R_s)}, \quad (2)$$

where I_0 is the initial current density, I_s is the steady-state current density, R_0 is the resistance before polarization, R_s is the resistance of electrolytes after polarization, and $V = 10$ mV.

The linear sweep voltammograms (LSV) measurements were carried out in a potential window of 3.0–6.0 V with a scan rate of 10 mV s^{-1} for Li|SPCE|SS cells (CR2032-type coin). Cyclic voltammetry (CV) measurements were performed to evaluate the electrochemical stability of SPCE from 3.0 to 4.5 V at a scan rate of 0.1 mV s^{-1} for NCM|SPCE|Li cells (CR2032-type coin).

The stability of SPCE with Li metal anode was tested in Li|SPCE|Li cells at a current density of 0.1 mA cm^{-2} with an areal capacity of 0.1 mAh cm^{-2} at 60°C using a battery test system (LANHE CT2001A, Wuhan Land Electronic Co., Ltd.). The long cycling performance and galvanostatic charge–discharge profiles of NCM|SPCE|Li cells were also tested on a Land battery test system. In the above cells, the areal loading capacities of NCM and SPCE were about 2 mg cm^{-2} and 4.43 mg cm^{-2} , respectively. The density of Li metal was 0.534 g cm^{-3} .

3 Results and Discussion

SEM was employed to characterize the morphologies of PE separator and SPCE. The results show that the PE separator was highly porous with a pore size ranging from 529 to 647 nm (Fig. 1a, b). After infiltration of electrolyte,

pores of PE separator disappeared, indicating that the pores were filled with TPU–HNTs–LiTFSI which could act as Li^+ -conductive path [22]. Moreover, the wrinkles appeared in Fig. 1c, d reveal that the surface of PE separator was also covered by electrolyte, which may improve the interfacial adhesion between SPCE and electrode, effectively decreasing their interfacial resistance [23]. In Fig. 1e, f, the thickness of this transparency SPCE determined by a micrometer was about $34 \mu\text{m}$, which is slightly thicker than that in the report by Cui et al. [24].

FTIR was carried out to compare the compositions of different materials and reveal the interactions between lithium salt and the electrolyte (Fig. 2a–c). For PE, the bands located from 2949 to 2838 cm^{-1} were attributed to the vibrations of $-\text{CH}_3$ and $-\text{CH}_2$. The infiltration of TPU–HNTs–LiTFSI or TPU–HNTs–LiFSI–PE not only brought the reduction in both absorbance and quantity for the above characteristic peaks, but also introduced the $\text{Ar}-\text{COO}-$ (1723 cm^{-1}) and $-\text{CONH}-$ (1532 cm^{-1}) peaks to the separator, which was in accordance with the SEM results (Fig. 1c, d). Characteristic peaks of $-\text{SO}_2-$ and $-\text{CF}_3$ structure appeared at 1331 cm^{-1} , 1240 cm^{-1} , 1200 cm^{-1} , and 1141 cm^{-1} in the LiTFSI spectrum, which were absent in the spectrum of TPU–HNTs–LiTFSI–PE, thus indicating successful introduction of lithium salt. In comparison with LiFSI, the peaks located at 1385 cm^{-1} , 1223 cm^{-1} , and 1185 cm^{-1} belonged to $-\text{SO}_2-$ structure were observed in the spectral line of TPU–HNTs–LiFSI–PE, which confirmed the successful introduction of LiFSI. Moreover, by carefully investigating the bands in the region of 1100 – 1800 cm^{-1} , the peak locations of $-\text{SO}_2-$ and $-\text{CF}_3$ for TPU–HNTs–LiTFSI–PE took a red shift to 1330 cm^{-1} , 1225 cm^{-1} , 1188 cm^{-1} , and 1137 cm^{-1} , respectively, confirming that the electrolyte

Fig. 1 SEM images under different magnifications of **a, b** PE separator, **c, d** SPCE and **e, f** digital photographs of flexible SPCE with a thickness of $34 \mu\text{m}$

Fig. 2 FTIR spectra of **a** LiFSI and LiTFSI, **b** HNTs, TPU, and PE at 4000–500 cm^{-1} , **c** TPU-HNTs-LiFSI-PE, TPU-HNTs-LiTFSI-PE, and TPU at 1800–700 cm^{-1} . XPS spectra on C 1s of **d** TPU-HNTs-PE, **e** TPU-HNTs-LiTFSI-PE, and **f** TPU-HNTs-LiFSI-PE

Table 1 Binding energy of C 1s of TPU-HNTs-PE, TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE in the XPS spectra in Fig. 2

Material	BE (eV)				
	C-C	C-O	C=O	CF ₃	Li
TPU-HNTs-PE	284.75	286.16	288.69	–	–
TPU-HNTs-LiTFSI-PE	284.78	286.25	288.89	292.44	56.58
TPU-HNTs-LiFSI-PE	284.81	286.33	289.12	–	55.85

causes LiTFSI to dissociate. For TPU-HNTs-LiFSI-PE, the same red shift for characteristic peaks of $-\text{SO}_2-$ was also displayed, revealing the dissociation of LiFSI in TPU.

For investigating the chemical change in the materials, the XPS analysis was performed for the SPCE (Fig. 2d–f). According to a previous report [25], the electron transfer from one atom to another would cause a positive shift of binding energy (BE). In the TPU-HNTs-LiTFSI-PE system, BE values of both C–O and C=O peaks positively shifted when compared with the TPU-HNTs-PE (Table 1) because of electron transfer. In comparison with TPU-HNTs-LiTFSI-PE, TPU-HNTs-LiFSI-PE manifested a larger positive shift of C–O and C=O peaks, indicating that the interaction between TPU-HNTs-PE and LiFSI was stronger than that with LiTFSI. FTIR spectroscopy together

with XPS analysis proved the successful combination of lithium salt and TPU-HNTs-PE.

Figure 3a, b shows the EIS and Arrhenius plots of the TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE in the temperature range from 30 to 90 °C. The ionic conductivity at 30 and 60 °C of TPU-HNTs-LiTFSI-PE were 1.69×10^{-6} and $1.87 \times 10^{-5} \text{ S cm}^{-1}$, respectively, which were higher than those of TPU-HNTs-LiFSI-PE ($3.17 \times 10^{-7} \text{ S cm}^{-1}$ at 30 °C and $4.97 \times 10^{-6} \text{ S cm}^{-1}$ at 60 °C). A higher ionic conductivity implies a faster ionic mobility, which is advantageous to achieve improved charge–discharge capacity for batteries.

The t_{Li}^+ of solid-state electrolyte was employed as an important parameter to evaluate the cycling stability of lithium ion batteries (LIBs) (Fig. 3c, d). t_{Li}^+ for the TPU-HNTs-LiTFSI-PE system was 0.48 at 60 °C, slightly higher than that of most liquid electrolytes (0.1–0.4) [26], while TPU-HNTs-LiFSI-PE showed a lower value ($t_{\text{Li}}^+ = 0.24$) at the same temperature. The large t_{Li}^+ was favorable to reduce concentration polarization and had a positive effect on the performance of batteries, as the low t_{Li}^+ would easily cause concentration gradients in electrolytes and generate cell polarization that leads to a premature failure of cells [27, 28].

The reversibility of lithium plating/stripping of Li|TPU-HNTs-LiTFSI-PE|Li and

Fig. 3 **a** EIS curves of TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE at 30–90 °C. **b** Temperature-dependent ionic conductivity for TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE. **c, d** Chronoamperometry profiles and AC impedance spectra of lithium symmetric cell with TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE before and after polarization

Li/TPU-HNTs-LiFSI-PE/Li cells was also evaluated at 60 °C (Fig. 4a). For the Li/TPU-HNTs-LiTFSI-PE/Li cell, a gradual increase in voltage hysteresis over time and a sudden voltage rise with internal cell impedance-surge signals were observed within 600 h. In contrast, Li metal anode of the Li/TPU-HNTs-LiFSI-PE/Li cell could keep stable overpotential profiles throughout the whole cycling process for nearly 1300 h with a low voltage hysteresis of about 39 mV at a current density of 0.1 mA cm^{-2} , which was indicative of a smaller resistance and a decreased polarization of the SEI film. According to the above analysis, a low t_{Li}^+ may induce the growth of Li dendrite and raise safety issues, suggesting that TPU-HNTs-LiTFSI-PE may promote a properly uniform Li plating/stripping and suppress lithium dendrite growth [29]. However, our experimental results were inconsistent with this conclusion. Thus, an unstable interface between lithium metal anode and TPU-HNTs-LiTFSI-PE was the most probable control factor for the irregular overpotential

changes, which indicated that there was a continuous reaction on lithium metal anode during cycling [30]. Correspondingly, the changes of overpotential obtained for Li/TPU-HNTs-LiFSI-PE/Li at a constant current density reflected the cycling stability [31–33]. Therefore, the LiFSI exhibited a stronger protection capability for Li metal anodes during Li plating/stripping process, suggesting that its SEI film was comparatively stable over repeating cycles [34].

Nyquist plots and the corresponding fitting results of Li/SPCE/Li cells after different cycles were applied to provide further evidence of the interface variation (Fig. 4b, c). Unlike the liquid symmetric cells which only exhibited one semicircle with a low-frequency tail, both of the Li/TPU-HNTs-LiTFSI-PE/Li and Li/TPU-HNTs-LiFSI-PE/Li systems displayed two semicircles and a tail. The first semicircle in higher frequency range corresponded to the interfacial resistance between SPCE and Li metal anode (R_{sf}), and the second semicircle

Fig. 4 **a** Voltage profiles of Lithium symmetric cells using TPU-HNTs-LiTFSI-PE or TPU-HNTs-LiFSI-PE at a current density of 0.1 mA cm^{-2} with a restricted specific capacity of 0.1 mAh cm^{-2} at 60°C . **b** EIS curves, **c** R_{sf} and R_{ct} variation of lithium symmetric cells using TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE after 100, 200, 300, 400, and 500 h

in the lower frequency range was indicative of the resistance of Li^+ flux transferred from SPCE to Li metal anode (R_{ct}) [35–40]. The appearance of the second semicircle further suggested that TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE membrane adhered tightly to the

surface of Li metal anode, which could act as an artificial SEI layer [41].

At first, Li|TPU-HNTs-LiTFSI-PE|Li showed smaller R_{sf} (111.00Ω) and R_{ct} (49.63Ω) than those of Li|TPU-HNTs-LiFSI-PE|Li ($R_{sf} = 192.80 \Omega$, $R_{ct} = 61.58$

Fig. 5 XPS spectra of **a, b** C 1s, **c, d** F 1s, and **e, f** S 2p on the surface of lithium metal anode after cycling of lithium symmetric cells using TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE

Table 2 Binding energy of C 1s, F 1s, and S 2p on lithium metal anode after cycling of lithium symmetric cells using TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE

Material	BE (eV)							
	C 1s			F 1s		S 2p		
	C-C-O	C-O-CO ₂ -Li	Li ₂ CO ₃	CF ₃	LiF	R-SO ₃	-SO ₂ -	Li _x SO _y
TPU-HNTs-LiTFSI-PE	284.75	286.33	289.66	688.45	684.56	—	168.59	—
TPU-HNTs-LiFSI-PE	284.81	286.27	288.96	687.39	684.51	170.48	169.31	166.46

Ω), which were related to the ionic conductivity as discussed before. During 500 h, the semicircle at high frequency range for Li metal anode in TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE electrolytes kept expanding owing to the continuous Li dendrite growth, while the same trend of semicircle at middle frequency range represented a partial blockage of Li metal anode surface by dead Li [42, 43]. Compared to TPU-HNTs-LiTFSI-PE, TPU-HNTs-LiFSI-PE exhibited a more stable variation of R_{sf} and R_{ct} during cycling, which indicated a better interfacial stability.

XPS was employed to further analyze the element valence on the surface of Li metal anodes after cycling (Fig. 5 and Table 2). In Fig. 5a, b, the peaks located from 284 to 289 eV,

assigned to C-C-O, C-O-CO₂-Li, and Li₂CO₃, respectively, were generated from the reduction in TPU and lithium salt [36]. In comparison with TPU-HNTs-LiTFSI-PE, the higher peak area ratio of Li₂CO₃/C-C-O revealed that TPU-HNTs-LiTFSI-PE contained a higher content of Li₂CO₃. In the F 1s spectra (Fig. 5c, d), peaks of LiF and CF₃ observed in TPU-HNTs-LiFSI-PE (684.51 and 687.39 eV) were much higher than those of TPU-HNTs-LiTFSI-PE (684.56 and 688.45 eV). A recent report pointed out that the formation of a functionalized SEI membrane with a layer of LiF not only retarded the electron transfer by three orders of magnitude, but also avoided the undesirable lithium deposition on the top surface and ameliorated Li migration [44]. Thus, the presence of a LiF-rich compact SEI film was

Fig. 6 CV curves of **a** NCM/TPU-HNTs-LiFSI-PE/Li and **b** NCM/TPU-HNTs-LiTFSI-PE/Li batteries at 3.0–4.5 V. **c** LSV curves of NCM/TPU-HNTs-LiFSI-PE/Li and NCM/TPU-HNTs-LiTFSI-PE/Li batteries at 3.0–6.0 V. **d** Initial charge-discharge curves of NCM/TPU-HNTs-LiFSI-PE/Li and NCM/TPU-HNTs-LiTFSI-PE/Li batteries at 60 °C. Cycling performance of **e** NCM/TPU-HNTs-LiFSI-PE/Li and **f** NCM/TPU-HNTs-LiTFSI-PE/Li batteries at 60 °C. Voltage profiles of **g** NCM/TPU-HNTs-LiFSI-PE/Li and **h** NCM/TPU-HNTs-LiTFSI-PE/Li batteries at 60 °C

vital to the long-term stable plating/stripping cycling of the highly reactive lithium metal anode, which would effectively retard the side reactions between the deposited lithium and the TPU based electrolyte [45]. It could be tentatively suggested that because of the high population of FSI⁻ and their reactivity against reduction, splitting F by cleavage of S–F bond resulted in a thermodynamically stable LiF more easily, which precipitated on the Li metal anode surface [46]. Therefore, the reduction in FSI⁻ tended to afford more LiF at the interface between TPU–HNTs–LiFSI–PE and Li metal anode.

In addition, LiF with a large band gap of 13.6 eV would effectively block the electron migration but provided poor ionic conductivity ($\approx 10^{-31}$ S cm⁻¹) when formed on the anode surface [47, 48]. On the contrary, Li₂CO₃ possessed higher ionic conductivity ($\approx 10^{-8}$ S cm⁻¹) yet may generate electronic leakage [48, 49]. Any individual component could not fleetly transport Li⁺ from TPU-based electrolyte to Li metal anode alone. However, the interfaces between LiF and Li₂CO₃ would facilitate space charge accumulation, enhance Li⁺ migration, and reduce electron tunneling, ultimately leading to a low electronic conductivity of the interface layer, which could explain the reason why TPU–HNTs–LiTFSI–PE exhibited a smaller R_{ct} than that of TPU–HNTs–LiFSI–PE in 300 h [48, 50].

For S 2p (Fig. 5e, f), the BE peaks of TPU–HNTs–LiFSI–PE located at 166.46, 169.31 and 170.48 eV belonged to Li_xSO_y, SO₂CF₃, and R–SO₃, respectively, which were generated from broken fragment of –SO₂F group in FSI⁻, while TPU–HNTs–LiTFSI–PE showed only a small peak of SO₂CF₃ at 168.59 eV [46]. Abundant LiF and sulfur compounds would be conducive for the interfacial stability between SPCE and Li metal anode. It is the above composition differences that were responsible for the distinct cycling behaviors observed.

CV curves of NCM|TPU–HNTs–LiTFSI–PE|Li and NCM|TPU–HNTs–LiFSI–PE|Li at 3.0–4.5 V (versus Li/Li⁺) are shown in Fig. 6a, b. A distinct difference between the first and subsequent cycles was demonstrated for both samples, which resulted from the formation of SEI layer on NCM surface during the charging process. All samples have prominent redox peaks due to oxidation/reduction of Ni²⁺/Ni⁴⁺ and Co³⁺/Co⁴⁺ corresponding to Li⁺ extracting/embedding process [51]. The three pairs of oxidation and reduction peaks on their second and third cycles are originated from three-phase transitions of NCM during the charge–discharge process. In comparison with TPU–HNTs–LiFSI–PE, the smaller overlaps of TPU–HNTs–LiTFSI–PE represented the improvement of electrochemical reversibility [52]. It was worth noting that there were significant differences in

oxidation–reduction potentials during the first cycle, which is different from that of a recent research [53]. The potential difference of TPU–HNTs–LiFSI–PE is larger than that of TPU–HNTs–LiTFSI–PE on account of the poorer ionic conductivity.

LSV was applied to investigate electrochemical stability of the electrolyte and obtain the appropriate cut-off voltage for the following cycling test. As shown in Fig. 6c, the electrochemical decomposition potentials of TPU–HNTs–LiTFSI–PE and TPU–HNTs–LiFSI–PE at 60 °C were about 4.9 and 5.1 V, respectively. As aforementioned, due to a stronger protection capability for Li metal anodes offered by LiFSI, a stable SEI film between lithium metal anode and TPU–HNTs–LiFSI–PE was constructed, thus, the TPU–HNTs–LiFSI–PE exhibited a broader voltage window than TPU–HNTs–LiTFSI–PE. Besides, a weak Faraday current of above SPCE also appeared between 4.3 V and the decomposition potential. For safe application, 4.3 V was chosen as the cut-off voltage for cycling measurements of NCM|SPCE|Li. The above degradation voltages were higher than those of PEO based systems (3.8 V), revealing the high electrochemical stability with metallic lithium [54].

For evaluating electrochemical performance of SPCE in ASSLB, NCM|TPU–HNTs–LiTFSI–PE|Li and NCM|TPU–HNTs–LiFSI–PE|Li cells were assembled and measured at 60 °C. The corresponding initial charge–discharge curves in Fig. 6d manifested that the initial coulombic efficiency and discharge specific capacity of TPU–HNTs–LiTFSI–PE were 87.93% and 180.51 mAh g⁻¹, respectively, which are higher than those of TPU–HNTs–LiFSI–PE (78.59% and 148.53 mAh g⁻¹), meaning that TFSI⁻ was beneficial to the reduction of Li⁺ loss in the first cycle. Furthermore, at a cut off voltage of 4.3 V, the above samples exhibited a small increase in specific capacity during the primary few cycles, which was attributed to the activation of NCM, as confirmed by the CV curves. After 300 cycles, the discharge capacities of NCM|TPU–HNTs–LiTFSI–PE|Li and NCM|TPU–HNTs–LiFSI–PE|Li were separately 125.58 and 102.59 mAh g⁻¹, corresponding to capacity retention rates of 83.52% and 89.99%, respectively (Fig. 6e–h). Apparently, the application of LiTFSI had a positive effect on the improvement of specific capacity, but the ability on mitigation of capacity attenuation was worse than that of LiFSI.

For the purpose of understanding the distinction of cycling behaviors of TPU–HNTs–LiTFSI–PE and TPU–HNTs–LiFSI–PE, the impedance spectra of above cells recorded after 100th, 200th, and 300th cycle at a rate of 0.5 C were compared, and the results are shown in Fig. 7. EIS curves of both TPU–HNTs–LiTFSI–PE and

Fig. 7 **a** EIS curves of NCM|TPU-HNTs-LiTFSI-PE|Li and NCM|TPU-HNTs-LiFSI-PE|Li batteries after 100, 200, and 300 cycles. **b** R_{sf} and R_{ct} variation of NCM|TPU-HNTs-LiTFSI-PE|Li and NCM|TPU-HNTs-LiFSI-PE|Li batteries after 100, 200, and 300 cycles

TPU-HNTs-LiFSI-PE presented a high-frequency semi-circle, an intermediate-frequency semi-circle, and a low-frequency tail. These three components could be ascribed to the resistances arising from the SEI layer (R_{sf}), the charge-transfer resistance (R_{ct}) at the electrode/electrolyte interface, and the impedance associated with the Li^+ diffusion process in the active materials [55]. Additionally, the EIS curves were fitted with equivalent circuit models by Zview software, in which R_s was related to the bulk resistance of the cell [56]. Figure 7a shows the variation of fitted resistance of TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE. It is obvious that both the initial R_{sf} and R_{ct} of TPU-HNTs-LiTFSI-PE showed a smaller value than those of TPU-HNTs-LiFSI-PE, which was indicative of the significant influence of anions.

Cycling at 60 °C made the initial R_{sf} and R_{ct} of TPU-HNTs-LiTFSI-PE increase from 57.86 Ω and 136.50 Ω to 85.71 Ω and 276.10 Ω , respectively, while those of TPU-HNTs-LiFSI-PE increased separately

from 97.22 Ω and 168.40 Ω to 143.70 Ω and 386.20 Ω . TPU-HNTs-LiTFSI-PE exhibited a smaller variation of R_{sf} and R_{ct} after 100 cycles than TPU-HNTs-LiFSI-PE. Such increase in R_{sf} and R_{ct} reflected a higher activation demand of TPU-HNTs-LiTFSI-PE in the early stage (Fig. 7b). In the range of 100th–300th cycle, R_{sf} and R_{ct} of TPU-HNTs-LiTFSI-PE kept a small variation, while R_{sf} of TPU-HNTs-LiFSI-PE showed insignificant change but R_{ct} displayed a distinct decrease. Notably, after 100th cycle, a new low frequency semi-circle appeared in both the impedance spectra of TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE, which might be ascribed to the charge-transfer resistance (R_n) caused by Li dendrite growth. The R_n values from 100 to 300th cycle of TPU-HNTs-LiFSI-PE were much smaller than those of TPU-HNTs-LiTFSI-PE, explaining the better capacity retention rate of TPU-HNTs-LiFSI-PE at 60 °C in the previous analysis. Therefore, it is suggested that the

Fig. 8 XPS spectra of **a, b** C 1s, **c, d** F 1s, and **e, f** S 2p on the surface of lithium metal anode of NCM/TPU-HNTs-LiTFSI-PE/Li and NCM/TPU-HNTs-LiFSI-PE/Li batteries after cycling

Table 3 Binding energy of C 1s, F 1s, and S 2p on the surface of lithium metal anode in cycled NCM/TPU-HNTs-LiTFSI-PE/Li and NCM/TPU-HNTs-LiFSI-PE/Li batteries

Material	BE (eV)							
	C 1s				F 1s		S 2p	
	C-C-O	-CO ₂ -Li	Li ₂ CO ₃	CF ₃	CF ₃	LiF	R-SO ₃	SO ₂ CF ₃
TPU-HNTs-LiTFSI-PE	284.79	286.23	288.84	292.41	688.41	—	169.72	168.52
TPU-HNTs-LiFSI-PE	284.80	286.34	289.09	—	687.49	684.81	170.73	169.55

application of LiFSI in this system is more beneficial to support the Li⁺ free intercalation/deintercalation.

The XPS spectra of Li metal anode after cycling were collected to testify the chemical state and composition of the electrode-electrolyte interface (Fig. 8 and Table 3). In C 1s spectra (Fig. 8a, b), the peaks located from 284–289 eV belonged to C-C-O, C-O-CO₂-Li, and Li₂CO₃, respectively, which were derived from the reduction reaction between TPU and lithium salt [36]. In contrast with TPU-HNTs-LiTFSI-PE, the CF₃ peak at 292.41 eV of TPU-HNTs-LiTFSI-PE was generated from the decomposition of TFSI[−] [57]. For F 1s (Fig. 8c, d), LiF and CF₃ peaks appeared in TPU-HNTs-LiFSI-PE were located at 684.51

and 687.39 eV, respectively, while TPU-HNTs-LiTFSI-PE only manifested a CF₃ peak at 687.49 eV. From the spectra of S 2p (Fig. 8e, f), peaks belonged to SO₂CF₃, and R-SO₃ were observed in both the spectra of TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE. Clearly, component content of Li₂CO₃, LiF, and sulfur substances of TPU-HNTs-LiFSI-PE were more than those of TPU-HNTs-LiTFSI-PE. As discussed above, abundant LiF and sulfur compounds would enhance the stability of interface between SPCE and Li metal anode, while Li₂CO₃ and LiF would together accelerate the Li⁺ transport at interface. As a result, TPU-HNTs-LiFSI-PE performed a more stable cycling behavior of the full cell than TPU-HNTs-LiTFSI-PE.

Fig. 9 a, b Rate performance and c, d voltage profiles of NCM/TPU-HNTs-LiTFSI-PE/Li and NCM/TPU-HNTs-LiFSI-PE/Li batteries at various current densities at 60 °C

Rate performance of TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE were also investigated at 60 °C from 3.0 to 4.3 V (Fig. 9). Compared to TPU-HNTs-LiFSI-PE, TPU-HNTs-LiTFSI-PE presented a higher discharge specific capacity whether at low or high rates, which could be attributed to the higher Li^+ conductance and the lower R_{sf} .

4 Conclusion

In summary, TPU composited with HNTs containing lithium salt (LiTFSI or LiFSI) was infiltrated onto the PE separator to fabricate SPCE via a facile one-step solvent evaporation process. We demonstrated that the cycling behaviors of TPU-HNTs-LiTFSI-PE and TPU-HNTs-LiFSI-PE were highly dependent on the anions of LiTFSI and LiFSI. The FSI^- in TPU-HNTs-LiFSI-PE significantly suppressed the increase in cell resistance by offering more LiF and sulfur compounds. Such composition provided by the solid-state

electrolyte-separator system enhanced the interfacial stability with lithium metal anode and demonstrated higher tolerance against capacity degradation. Benefiting from this, TPU-HNTs-LiFSI-PE exhibited superior stable cycling performances for nearly 1300 h in lithium symmetric cell. Noticeably, NCM/TPU-HNTs-LiFSI-PE/Li full cell could effectively cycle at 0.5 C at 60 °C and keeps an excellent capacity retention rate of 89.99% after 300 cycles. It is suggested that the interface composition between Li metal anode and SPCE played a key role in regulating the cycling performance of Li/SPCE/Li and NCM/SPCE/Li systems. The possible explanations for the influence of interface on cycling performance were also proposed. These results provide valuable information for the design of flexible SPCE, which would be significative for the development of ASSLB.

Acknowledgements This research was financially supported by the National Natural Science Foundation of China (No. 21673051) and the Department of Science and Technology of Guangdong Province, China (No. 2019A050510043).

References

- [1] X. Liu, W. Yang, Z. Liu, H. Fan, W. Zheng, *Acta Metall. Sin. Engl. Lett.* (2020). <https://doi.org/10.1007/s40195-020-01160-7>
- [2] X. He, Y. Zhang, L. Yang, J. Zhao, H. Li, Y. Gao, B. Wang, X. Guo, *Acta Metall. Sin. Engl. Lett.* (2020). <https://doi.org/10.1007/s40195-020-01104-1>
- [3] B. Ding, Z. Cai, Z. Ahsan, Y. Ma, S. Zhang, G. Song, C. Yuan, W. Yang, C. Wen, *Acta Metall. Sin. Engl. Lett.* (2020). <https://doi.org/10.1007/s40195-020-01095-z>
- [4] J.R. Nair, L. Imholt, G. Brunklaus, M. Winter, *Electrochem. Soc. Interface* **28**, 55 (2019)
- [5] J. Liang, J. Luo, Q. Sun, X. Yang, R. Li, X. Sun, *Energy Storage Mater.* **21**, 308 (2019)
- [6] S. Tan, X. Zeng, Q. Ma, X. Wu, Y. Guo, *Electrochem. Energy Rev.* **1**, 113 (2018)
- [7] A. Manthiram, X. Yu, S. Wang, *Nat. Rev. Mater.* **2**, 16103 (2017)
- [8] M. Dirican, C. Yan, P. Zhu, X. Zhang, *Mater. Sci. Eng. R* **136**, 27 (2019)
- [9] C. Tao, M. Gao, B. Yin, B. Li, Y. Huang, G. Xu, J. Bao, *Electrochim. Acta* **257**, 31 (2017)
- [10] L. Liu, X. Wu, T. Li, J. Power Sour. **249**, 397 (2014)
- [11] K. Ramanjaneyulu, N. Bar, M.S. Arif Sher Shah, S.V. Manorama, P. Basak, *J. Power Sour.* **217**, 29 (2012)
- [12] T. Wen, Y. Du, M. Digar, *Eur. Polym. J.* **38**, 1039 (2002)
- [13] S. Ibrahim, A. Ahmad, N. Mohamed, *Polymers* **7**, 747 (2015)
- [14] S. Qian, H. Chen, Z. Wu, D. Li, X. Liu, Y. Tang, S. Zhang, *Batteries Supercaps* (2020). <https://doi.org/10.1002/batt.202000149>
- [15] C. Zhao, X. Zhang, X. Cheng, R. Zhang, R. Xu, P. Chen, H. Peng, J. Huang, Q. Zhang, *Proc. Natl. Acad. Sci.* **114**, 11069 (2017)
- [16] Q. Zhu, X. Wang, J.D. Miller, A.C.S. Appl. Mater. Interfaces **11**, 8954 (2019)
- [17] J. Tully, R. Yendluri, Y. Lvov, *Biomacromol* **17**, 615 (2016)
- [18] J. Gao, Q. Shao, J. Chen, *J. Energy Chem.* **46**, 237 (2020)
- [19] J. Wan, J. Xie, X. Kong, Z. Liu, K. Liu, F. Shi, A. Pei, H. Chen, W. Chen, J. Chen, X. Zhang, L. Zong, J. Wang, L. Chen, J. Qin, Y. Cui, *Nat. Nanotechnol.* **14**, 705 (2019)
- [20] G.G. Eshetu, T. Diemant, S. Grugeon, R.J. Behm, S. Laruelle, M. Armand, S. Passerini, A.C.S. Appl. Mater. Interfaces **8**, 16087 (2016)
- [21] R. Cao, J. Chen, K.S. Han, W. Xu, D. Mei, P. Bhattacharya, M.H. Engelhard, K.T. Mueller, J. Liu, J. Zhang, *Adv. Funct. Mater.* **26**, 3059 (2016)
- [22] J. Wu, Z. Rao, Z. Cheng, L. Yuan, Z. Li, Y. Huang, *Adv. Energy Mater.* **9**, 1902767 (2019)
- [23] Q. Ma, X.X. Zeng, J. Yue, Y.X. Yin, T.T. Zuo, J.Y. Liang, Q. Deng, X.W. Wu, Y.G. Guo, *Adv. Energy Mater.* **9**, 1803854 (2019)
- [24] J. Wu, L. Yuan, W. Zhang, Z. Li, X. Xie, Y. Huang, *Energy Environ. Sci.* (2020). <https://doi.org/10.1039/D0EE02241A>
- [25] Z. Shen, H. Wen, H. Zhou, L. Hao, H. Chen, X. Zhou, *Mater. Sci. Eng. C* **105**, 110073 (2019)
- [26] H.G. Buss, S.Y. Chan, N.A. Lynd, B.D. McCloskey, *ACS Energy Lett.* **2**, 481 (2017)
- [27] Y. Zhang, W. Lu, L. Cong, J. Liu, L. Sun, A. Mauger, C.M. Julien, H. Xie, J. Liu, *J. Power Sour.* **420**, 63 (2019)
- [28] S. Tang, Q. Lan, L. Xu, J. Liang, P. Lou, C. Liu, L. Mai, Y. Cao, S. Cheng, *Nano Energy* **71**, 104600 (2020)
- [29] C. Ma, K. Dai, H. Hou, X. Ji, L. Chen, D.G. Ivey, W. Wei, *Adv. Sci.* **5**, 1700996 (2018)
- [30] S. Xiong, Y. Diao, X. Hong, Y. Chen, K. Xie, *J. Electroanal. Chem.* **719**, 122 (2014)
- [31] G.H. Lane, A.S. Best, D.R. MacFarlane, M. Forsyth, A.F. Hollenkamp, *Electrochim. Acta* **55**, 2210 (2010)
- [32] G.H. Lane, P.M. Bayley, B.R. Clare, A.S. Best, D.R. MacFarlane, M. Forsyth, A.F. Hollenkamp, *J. Phys. Chem. C* **114**, 21775 (2010)
- [33] S. Xiong, K. Xie, Y. Diao, X. Hong, *J. Power Sour.* **236**, 181 (2013)
- [34] G. Wang, C. Chen, Y. Chen, X. Kang, C. Yang, F. Wang, Y. Liu, X. Xiong, *Angew. Chem. Int. Ed.* **59**, 2055 (2020)
- [35] K. Chen, R. Pathak, A. Gurung, E.A. Adhamash, B. Bahrami, Q. He, H. Qiao, A.L. Smirnova, J.J. Wu, Q. Qiao, Y. Zhou, *Energy Storage Mater.* **18**, 389 (2019)
- [36] N.W. Li, Y.X. Yin, C.P. Yang, Y.G. Guo, *Adv. Mater.* **28**, 1853 (2016)
- [37] Y. Liu, D. Lin, P.Y. Yuen, K. Liu, J. Xie, R.H. Dauskardt, Y. Cui, *Adv. Mater.* **29**, 1605531 (2017)
- [38] S. Choudhury, L.A. Archer, *Adv. Electron. Mater.* **2**, 1500246 (2016)
- [39] E. Cha, M.D. Patel, J. Park, J. Hwang, V. Prasad, K. Cho, W. Choi, *Nat. Nanotechnol.* **13**, 337 (2018)
- [40] A.M. Gaikwad, B.V. Khau, G. Davies, B. Hertzberg, D.A. Steingart, A.C. Arias, *Adv. Energy Mater.* **5**, 1401389 (2015)
- [41] R. Pathak, K. Chen, A. Gurung, K.M. Reza, B. Bahrami, J. Pokharel, A. Baniya, W. He, F. Wu, Y. Zhou, K. Xu, Q.Q. Qiao, *Nat. Commun.* **11**, 93 (2020)
- [42] G. Wan, F. Guo, H. Li, Y. Cao, X. Ai, J. Qian, Y. Li, H. Yang, A.C.S. Appl. Mater. Interfaces **10**, 593 (2018)
- [43] J. Yamaki, K.H. Shin-ichi Tobishima, K. Saito, M.A. Yasue Nemoto, *J. Power Sour.* **74**, 219 (1998)
- [44] M. Wang, Z. Peng, W. Luo, F. Ren, Z. Li, Q. Zhang, H. He, C. Ouyang, D. Wang, *Adv. Energy Mater.* **9**, 1802912 (2019)
- [45] G. Yang, Y. Li, S. Liu, S. Zhang, Z. Wang, L. Chen, *Energy Storage Mater.* **23**, 350 (2019)
- [46] X. Fan, L. Chen, X. Ji, T. Deng, S. Hou, J. Chen, J. Zheng, F. Wang, J. Jiang, K. Xu, C. Wang, *Chemical* **4**, 174 (2018)
- [47] L. Suo, W. Xue, M. Gobet, S.G. Greenbaum, C. Wang, Y. Chen, W. Yang, Y. Li, J. Li, *Proc. Natl. Acad. Sci. USA* **115**, 1156 (2018)
- [48] Q. Zhang, J. Pan, P. Lu, Z. Liu, M.W. Verbrugge, B.W. Sheldon, Y.T. Cheng, Y. Qi, X. Xiao, *Nano Lett.* **16**, 2011 (2016)
- [49] Z. Liu, Y. Qi, Y.X. Lin, L. Chen, P. Lu, L.Q. Chen, *J. Electrochem. Soc.* **163**, A592 (2016)
- [50] X. Zhang, S. Wang, C. Xue, C. Xin, Y. Lin, Y. Shen, L. Li, C.W. Nan, *Adv. Mater.* **31**, 1806082 (2019)
- [51] P. Zhou, Z. Zhang, H. Meng, Y. Lu, J. Cao, F. Cheng, Z. Tao, J. Chen, *Nanoscale* **8**, 19263 (2016)
- [52] S. Yang, Q. Fan, Z. Shi, L. Liu, J. Liu, X. Ke, J. Liu, C. Hong, Y. Yang, Z. Guo, A.C.S. Appl. Mater. Interfaces **11**, 36742 (2019)
- [53] L. Liu, X. Wang, C. Yang, P. Han, L. Zhang, L. Gao, Z. Wu, B. Liu, R. Liu, *Acta Metall. Sin. Engl. Lett.* (2020). <https://doi.org/10.1007/s40195-020-01142-9>
- [54] P. Han, Y. Zhu, J. Liu, *J. Power Sour.* **284**, 459 (2015)
- [55] L. Zhang, G. Liang, G. Peng, F. Zou, Y. Huang, M.C. Croft, A. Ignatov, *J. Phys. Chem. C* **116**, 12401 (2012)
- [56] J. Zheng, W.H. Kan, A. Manthiram, A.C.S. Appl. Mater. Interfaces **7**, 6926 (2015)
- [57] D. Yoo, S. Yang, Y.S. Yun, J.H. Choi, D. Yoo, K.J. Kim, J.W. Choi, *Adv. Energy Mater.* **8**, 1802365 (2018)